THE MEASUREMENT OF SOLID-LIQUID INTERFACIAL ENERGY IN
COLLOIDAL SUSPENSIONS USING GRAIN BOUNDARY GROOVES

by

RICHARD B. ROGERS

Submitted in partial fulfillment of the requirements

For the degree of Doctor of Philosophy

Dissertation Advisors: Prof. K.P.D. Lagerlöf
Prof. B.J. Ackerson

Department of Materials Science and Engineering

CASE WESTERN RESERVE UNIVERSITY

May, 2006

* We also certify that written approval has been obtained for any proprietary material contained therein.

To the praise of Jesus Christ, the Master Materials Engineer

In the beginning was the Word, and the Word was with God, and the Word was God. He was with God in the beginning. Through him all things were made; without him nothing was made that has been made.

John 1: 1-3, NIV (New International Version)

TABLE OF CONTENTS

Chapter 1	Introduction	1
1.1	Research Goal	1
1.2	Motivation	1
1.3	Approach	5
1.4	Dissertation Overview	6

Part I: *In-situ* Crystallography of Ordered Colloids using Optical Microscopy

Chapter 2	Parallel-Beam Technique	8
2.1	Introduction	8
2.2	Background	10
2.2.1	Technique Overview	10
2.2.2	Analysis Procedure	12
2.3	Experimental Procedure	18
2.3.1	Samples	18
2.3.2	Experimental Equipment	18
2.3.3	Calibration	20
2.3.4	Image Processing and Data Analysis	21
2.4	Results	21
2.5	Discussion	26
2.5.1	Real Space	26
2.5.2	Reciprocal Space	30
2.6	Summary and Conclusions	43
Chapter 3	Divergent-Beam Technique	45
3.1	Introduction	45
3.2	Background	46
3.2.1	Technique Overview	46
3.2.2	Analysis Procedure	50
3.3	Experimental Procedure	55
3.3.1	Sample	55
3.3.2	Experimental Equipment	55
3.3.3	Image Processing and Data Analysis	55
3.4	Results	57
3.5	Discussion	62
3.6	Conclusions	75
Chapter 4	Comparison of Techniques	76

Part II: Grain Boundary Groove Techniques Applied to Colloids in a Gravitational Field

Chapter 5	Theory	80
5.1	Introduction	80
5.1.1	Literature Review	80
5.1.1.1	Grain Boundary Groove Techniques	80
5.1.1.2	Hard Sphere Colloids	95

5.2	Isotropic Theory for Colloids in a Gravitational Field	107
5.2.1	Development and Solution of General Equation for Interface Shape.....	107
5.2.2	Application to Hard Sphere Colloids in a Gravitational Field.....	113
5.2.2.1	General Expressions for $\Pi(\phi)$ and $y(\phi)$	114
5.2.2.2	$y_r(\phi)$ and $\phi(y_r)$ for the Fluid Phase	116
5.2.2.3	$y_r(\phi)$ and $\phi(y_r)$ for the Solid Phase	118
5.2.2.4	$\Delta\Pi_r(y_r)$ and $f_r(y_r)$	119
5.2.2.5	Equation for the Interface Shape.....	122
5.3	Summary and Conclusions	130
Chapter 6	Experiments.....	132
6.1	Introduction.....	132
6.2	Experimental Procedure.....	132
6.2.1	Experimental Equipment	132
6.2.2	Samples	137
6.2.2.1	Particle Size Characterization.....	138
6.2.2.2	Particle and Fluid Density Characterization	139
6.2.2.3	Sample Preparation	140
6.2.3	Image Processing	142
6.3	Results.....	145
6.3.1	Interface Cross Sections.....	147
6.3.2	Grain Boundary Grooves	148
6.3.3	Grain Tips	156
6.4	Discussion.....	165
6.4.1	Interface Cross Sections.....	165
6.4.2	Grain Boundary Grooves	166
6.4.2.1	Groove Stability	167
6.4.2.2	Crystal Orientation.....	169
6.4.2.3	Analysis using Isotropic Theory	173
6.4.2.4	Analysis using the Capillarity Vector Approach	182
6.4.2.5	Interfacial Energy Anisotropy.....	185
6.4.3	Grain Tips	186
6.4.3.1	Tip Stability	188
6.4.3.2	Tip Orientation.....	191
6.4.3.3	Analysis using Isotropic Theory	193
6.4.3.4	Interfacial Energy Anisotropy.....	200
6.4.4	Comparison with Literature Results	200
6.5	Summary and Conclusions	206
Chapter 7	Concluding Remarks	210
7.1	Summary and Conclusions	210
7.2	Future Work.....	213
References		216

LIST OF TABLES

Table 1. Comparison of data from real space and reciprocal space measurements.	34
Table 2. Angular relationships for various divergent-beam geometries.....	51
Table 3. Summary of published values of γ_{rl} for hard spheres.	106
Table 4. Density data	140
Table 5. Grain boundary tilt and contact angle measurements.....	175
Table 6. Model parameters.	176
Table 7. Results of fitting to isotropic models.....	177
Table 8. Isotropic fit results after evaluation of parameters..	181
Table 9. Values for γ_{rl} from Arbel-Cahn approach..	184
Table 10. Results of fitting C204b grain tip data to isotropic models.	195
Table 11. Summary of values of γ_{rl} for hard spheres.....	205

LIST OF FIGURES

Fig. 1. Geometry of the Ewald sphere construction.....	13
Fig. 2. Micrographs of crystallite studied in Chapter 2.	23
Fig. 3. OFT images of crystallite shown in Fig. 2	25
Fig. 4. Geometry of tilted close-packed planes.....	28
Fig. 5. Stereographic projection of crystal orientation	35
Fig. 6. Indexed OFT data	38
Fig. 7. Kossel lines in parallel-beam image.....	42
Fig. 8. Laue cone geometry.....	49
Fig. 9. Comparison of Kossel patterns from $\sin\psi$ and $\tan\psi$ scaling relationships.....	49
Fig. 10. Geometry of divergent-beam patterns for a Kossel pair.....	53
Fig. 11. Geometry of divergent-beam patterns for a single Kossel cone.....	54
Fig. 12. Divergent-beam image with swab in front focal plane of the condenser blocking a portion of the scattering.....	58
Fig. 13. Comparison of divergent-beam imaging modes.....	59
Fig. 14. Examples of divergent-beam patterns seen in colloidal crystals formed from $1/2\mu\text{m}$ -diameter spheres	60
Fig. 15. Divergent-beam pattern from same crystal examined using parallel-beam technique at two different camera exposures.....	61
Fig. 16. Divergent-beam image from Fig. 14a showing examples of Kossel lines used in analysis.....	70
Fig. 17. Reciprocal lattice data extracted from Fig. 16.....	71

Fig. 18. Indexed Kossel lines corresponding to Fig. 14b.....	72
Fig. 19. Indexed Kossel lines corresponding to Fig. 15.....	73
Fig. 20. Stereographic projection of the orientation of the crystallite in Fig.2.....	74
Fig. 21. Interface geometry.....	83
Fig. 22. Family of interface curves.....	85
Fig. 23. Geometry of the Arbel-Cahn method.....	91
Fig. 24. Phase diagram for monodisperse hard spheres in 1-g.....	98
Fig. 25. Published values of γ_{rl}	107
Fig. 26. Modified interface geometry.....	108
Fig. 27. Volume fraction vs. reduced height for a hard sphere liquid.....	117
Fig. 28. Volume fraction vs. reduced height for the hard sphere solid and fluid phases.....	119
Fig. 29. Comparison of 10-term and linear approximations of $\Delta\Pi_r(y_r)$ given by Eqs. 5.74 and 5.75.....	121
Fig. 30. Comparison of 10-term and linear approximations of $f(y_r)$ given by Eqs. 5.76 and 5.77.....	122
Fig. 31. Interface curves for $\gamma_{rl} = 10$	127
Fig. 32. Orthogonal separation of the linear and polynomial cases vs. y_r for $\gamma_{rl} = 10$..	128
Fig. 33. Maximum separation between interface curves vs. γ_{rl} for the polynomial and linear cases.....	128
Fig. 34. The ratio of γ_{lin} to γ_{poly} vs. γ_{rl}	130
Fig. 35. Microscope mounted in rotation fixture.....	133
Fig. 36. Experiment geometry.....	133
Fig. 37. Comparison of single and frame-averaged DIC images.....	143
Fig. 38. DIC image from center of a z-stack used to examine interface cross-section..	147

Fig. 39. Interface cross-section.	148
Fig. 40. Darkfield image showing entire height of cell.	150
Fig. 41. Darkfield image of a portion of the crystalline region in a sample..	150
Fig. 42. Darkfield images of the GBGs analyzed in this work.	151
Fig. 43. DIC image of GBG 206c-1.....	152
Fig. 44. DIC image of GBG 206c-2.....	153
Fig. 45. DIC image of GBG 206c-3.....	154
Fig. 46. Divergent-beam images of the GBGs shown in Fig. 43-Fig. 45	155
Fig. 47. A GBG with a noticeably asymmetric interface shape between sides	156
Fig. 48. Darkfield images of grain tips 7 weeks after initiating experiment	159
Fig. 49. Time series of C204b grain tip	159
Fig. 50. Time series of C204b at LHS epoxy plug	160
Fig. 51. Time series of two grain boundaries in C204b.....	160
Fig. 52. Length of C204b crystalline region vs. time	161
Fig. 53. Grain boundary groove positions over time.	161
Fig. 54. High magnification DIC mosaic of C204b tip.....	162
Fig. 55. Projections of 3-D data from C204b grain tip.	163
Fig. 56. Oblique darkfield image of C206e grain tip.	164
Fig. 57. DIC image of C206e grain tip..	164
Fig. 58. Divergent-beam images of two grain tips.....	165
Fig. 59. Indexed Kossel lines from C206c-3 RHS.....	171
Fig. 60. Stereographic projection of GBG crystal orientations..	172
Fig. 61. Isotropic model fits to GBG C206c-3 LHS data..	179

Fig. 62. Stereographic projection of grain tip orientations..	193
Fig. 63. Fits of C204b tip interface data to isotropic models.....	195
Fig. 64. C204b grain tip data and selected isotropic model fits.....	197
Fig. 65. Comparison with published values of γ_{rl}	206

The Measurement of Solid-Liquid Interfacial Energy in Colloidal Suspensions using Grain Boundary Grooves

Abstract

by

RICHARD B. ROGERS

Interfacial energy is a fundamental physiochemical property of any multi-phase system. Among the most direct approaches for determining solid-liquid interfacial energy are techniques based on measuring the shape of grain boundary grooves in specimens subjected to a linear temperature gradient. We have adapted several of these techniques to crystallizing colloids in a gravitational field. Such colloids exhibit an order-disorder phase transition and are important not only as self-assembling precursors to photonic crystals, but also as physical models of the melting-freezing phase transition in atomic and molecular systems. We have also developed and tested parallel-beam and divergent-beam techniques for determining the orientation and lattice parameters of randomly oriented single colloidal crystals *in situ* using optical microscopy. We tested our grain boundary groove and crystallography techniques using suspensions of sterically stabilized poly-(methyl methacrylate) (PMMA) spheres, which have been shown to closely approximate the hard sphere potential. Isotropic model fits to grain boundary groove data were inconsistent, but we obtained $\gamma_{110} = (0.58 \pm 0.05)k_B T/\sigma^2$ using a capillary vector approach, which is suitable for both isotropic and anisotropic surface energies. Kinks observed in groove profiles suggest a minimum anisotropy parameter of $\epsilon_6 = 0.029$ for hard spheres. We also observed grain tips at the termination of the solid

phase in each sample, resulting from a slight side-to-side tilt of our samples with respect to gravity. These grain tips offer significantly more interface height and accessible crystallographic orientations compared to typical grain boundary grooves, suggesting their potential use for interfacial energy measurements in both colloidal and atomic/molecular systems. Initial tests of our crystallography techniques suggest that they are suitable for extracting lattice parameters to within about 1% and orientation data to within about 2° . The value of our interfacial energy measurement using the capillary vector model is in close agreement with the majority of published experimental and computer simulation values for hard spheres, indicating the validity of our grain boundary groove technique adaptations to colloidal systems in a gravitational field.

Acknowledgements

Many people have contributed to the success of this work. I would like to thank:

- my advisors, Peter Lagerlof and Bruce Ackerson, for their guidance and encouragement.
- Andy Hollingsworth, Ron Ottewill and his group at Bristol, and Andrew Scofield for synthesizing and characterizing the particles used in our experiments; and Bill Russel, Paul Chaikin, Dave Weitz, and Phil Segre for providing the particles to us.
- Carl Fritz for designing the microscope rotation fixture; and Carl and the NASA Glenn Fabrication Shop for building it.
- Walt Turner for assistance in fabricating some of the early sample cells.
- Daan Frenkel, Peter Voorhees, and many of my NASA colleagues for helpful conversations.
- Bill Meyer for help in learning *Mathematica*.
- Richard Czentorycki and John Jindra for help with illustrations.
- Kim Soboslay for help with formatting, proofing, and format conversions.
- my employer, the NASA Glenn Research Center, for funding my Ph.D. program.
- the NASA Glenn Strategic Research Fund for funding much of the experimental hardware.
- my NASA supervisor, Bhim Singh, for allowing me to spend a generous portion of my workdays on this project for a number of years.

Chapter 1

Introduction

1.1 Research Goal

The central goal of this research project is to develop a technique to measure the absolute interfacial energy of colloidal liquid-colloidal crystal interfaces in crystallizing colloids by adapting existing grain boundary groove (GBG) techniques to colloidal systems. We will test our approach experimentally using monodisperse hard spheres. A secondary and supporting goal is to develop techniques to determine the orientation of single colloidal crystals whose orientations are not restricted to alignment with symmetry axes with respect to the observation frame of reference.

1.2 Motivation

Colloidal crystals are currently being studied for two separate, but interrelated, reasons. First, colloidal crystals are of scientific and technological interest as photonic band gap materials in which photons are manipulated in ways similar to that of electrons in semiconductor materials.[1-3] Secondly, colloidal crystals are an excellent physical model to study fundamental aspects of thermodynamic phase transitions. [4, 5]

Photonic crystals are an emerging class of engineering materials with the potential for extensive technological application. A photonic crystal is a material in which the dielectric constant of the medium is modulated periodically on a length scale comparable

to electromagnetic wavelengths of interest, often in the visible or near-visible regimes. [1-3] This variation in dielectric constant can lead to photonic band gaps, which are analogous to electronic band gaps in metals and semiconductors. Photonic band gaps are ranges of optical frequencies in which propagation of electromagnetic energy is forbidden in a range of directions for partial band gaps, or in any direction for complete band gaps. The technology of fabricating useful 1-D photonic crystals in the form of multilayer films is well-established. However, the fabrication of 2-D and 3-D photonic structures is in its infancy and the topic of vigorous research. Photonic structures in these higher dimensions have even greater potential for technological applications. For example, defects in 2-D and 3-D photonic structures could produce miniature resonators, waveguides, and mirrors for integrated optical circuits. [3]

One route to fabricating photonic crystals is to employ self-assembling colloidal systems to create the desired photonic microstructure. Photonic behavior can be enhanced by infiltrating materials into the interstices of colloidal crystals [6-8], infiltrating materials then dissolving the original particles to form inverse structures [9-12], or by substituting the original particles with other materials [13]. High index contrast are desired for photonic band gap materials [3]. However, in any of these approaches, the use of index-matched precursors allows characterization of the structure and orientation of the precursor crystal that is not possible in the final photonic crystal.

Physical models have a rich history in materials science. Two notable examples are bubble rafts, which were used to explore the concepts of dislocations and grain boundaries [14], and the organic analogs, which are used in solidification science [15]. Model colloids that exhibit thermodynamic phase transitions are an emerging class of

physical models with tremendous potential in materials science. For example, suspensions of monodisperse hard spheres undergo a liquid-solid phase transition as a function of particle volume fraction in analogy to the freezing-melting phase transition in atomic and molecular systems. [16]

Model colloids can be viewed as a cross between bubble rafts and the organic analogs. With colloids, it is possible to make observations at the individual particle level, as with bubble rafts. At the same time, phenomena of interest in colloidal systems are thermodynamically driven, as are the organic analogs. If the spheres in a colloidal suspension are greater than about $0.25\mu\text{m}$ in diameter, they can be individually resolved using optical microscopy. Furthermore, if the index of refraction of the spheres closely matches that of the suspending fluid, imaging is possible in the bulk of a colloidal sample. In addition to their accessible length scale, movement in colloidal systems occurs on a convenient time scale. The motion of colloidal spheres over distances comparable to their size is slow enough to be followed by both the human eye and standard video equipment. This is in great contrast to the movement of individual atoms, whose characteristic vibrations are on the order of 10^{13} Hz in a typical atomic solid. [17] Following such rapid atomic movement is well beyond current or foreseeable capabilities. The accessible length and time scales of colloidal models allow researchers to observe phase transitions not only on the macroscopic length scale [18-20], but also at the particle level. [20-22] Microstructural defects such as vacancies, dislocations, and phase boundaries, can also be studied macroscopically [20, 23, 24] and in 3-D at the particle length scale [20, 25]. In contrast, the study of atomic systems using high-resolution transmission electron microscopy (TEM) is typically limited to the observation

of columns of atoms. There are some situations where individual atoms can be identified in TEM images [26], but this is currently the exception rather than the rule. In general, there is no equivalent technique that allows the observation of individual atoms in the interior of atomic crystals. [27] Both phase transitions and microstructural defects are central topics in materials science. In fact, the emphasis on studying materials on the microstructural length scale is one aspect of the field that distinguishes materials science from the related fields of chemistry, physics, and structural engineering. [28] Colloidal models offer a means to observe the *mechanisms* of change on a relative time scale that is often inaccessible in atomic systems. Their thermodynamic nature combined with accessible time and length scales make colloidal systems a very promising, but as yet underutilized, physical model in mainstream materials science research.

The dominance of interfacial properties is one of the distinguishing characteristics of a colloidal system. [29] Therefore, detailed knowledge of the interfacial energy is important in both photonic crystal fabrication and physical modeling. Many theoretical predictions have been made for the solid-liquid interfacial energy in a hard sphere system [30-42], but only three values based on experimental measurements have been published to date [21, 43, 44]. The range of published values for interfacial energy is reasonable compared to similar ranges for atomic and molecular materials but there is significant disparity regarding several aspects of the variation of interfacial energy with crystallographic orientation. Also, the experiment-based predictions all relied on classical nucleation theory (CNT), which is considered to be an indirect method [45]. The approach used in the present work is the first measurement by what is considered a direct method [45].

There are many way to increase the complexity and richness of the thermodynamic phase behavior in a colloidal system such as modifying the interparticle potential [46-48], combining monodisperse distributions of several sizes of particles [49, 50], adding nonadsorbing polymer [51, 52], or by using non-spherical particles [53-57]. However, the hard sphere model is the most fundamental system in this class of physical models, and is therefore the logical starting place for application to materials science questions. We expect that the techniques developed in this work will be useful for measuring the solid-liquid interfacial energy in more complex colloidal systems as well.

1.3 Approach

The approach taken in this work is to measure the free energy of the colloidal liquid-colloidal crystal interface by studying grain boundary grooves. The corresponding approach with traditional materials is to place a specimen in a well-characterized linear temperature gradient and record the liquid-solid interface shape [58, 59]. For a given temperature gradient and entropy of fusion, there is a family of interface shapes that varies with interfacial energy. By fitting the experimentally observed interface shape to a theoretical form, the interfacial energy can be determined. For colloids, we use earth's gravitational field to produce an osmotic pressure gradient rather than a temperature gradient and adapt the equations accordingly. The interface shape is recorded using an optical microscope that has been oriented with the optical axis perpendicular to the g -vector (see Fig. 35, p.133). This approach is used to measure the interfacial energy in a model system of sterically stabilized poly-(methyl methacrylate) (PMMA) spheres, which has been shown to closely approximate the hard sphere potential [60].

In order to assess the dependence of interfacial energy on crystallographic orientation, we also develop two complementary Fourier-space techniques to determine the orientation of individual colloidal crystals *in situ* on the microscope stage. The first is a parallel-beam approach, and the second is a divergent-beam approach.

1.4 Dissertation Overview

This dissertation is divided into two parts. In Part I, we develop two complementary techniques for performing *in-situ* crystallography of ordered colloids using optical microscopy since this capability is required in Part II. Chapter 2 develops a parallel-beam technique, and Chapter 3 develops a divergent-beam technique. Experiments using hard sphere colloids are described in both Chapter 2 and Chapter 3 for the respective techniques. The two techniques are compared in Chapter 4.

Part II is devoted to adapting existing GBG techniques for measuring the solid-liquid interfacial energy of atomic and molecular systems in a temperature gradient to colloidal suspensions in a gravitational field. Required theory is developed in Chapter 5, and the adaptations are tested with hard sphere experiments in Chapter 6. Lastly, Chapter 7 summarizes the entire dissertation and gives suggestions for future work.

Part I:

In-situ Crystallography of Ordered Colloids using Optical
Microscopy

Chapter 2

Parallel-beam Technique

2.1 Introduction

Techniques for determining the structure and orientation of atomic and molecular crystals are well established. X-ray and electron diffraction techniques are the main techniques used for such measurements at the atomic scale. However, a rapidly growing field of research is the study of colloidal crystals in which equivalent techniques are not nearly as well developed. A colloidal crystal consists of colloidal-scale particles ($\sim 10\text{nm}$ to $10\mu\text{m}$) arranged with 3-D periodicity. This chapter describes a reciprocal space approach for obtaining orientation and structure data from individual colloidal crystals using optical microscopy in specimens where the particle index of refraction closely matches that of the suspending fluid. This approach facilitates these reciprocal space measurements in the same instrument used for real-space imaging with minimal instrument reconfiguration and no change to the sample-instrument interface.

The structure of colloidal crystals has been primarily investigated by means of powder diffraction techniques using visible-wavelength lasers [50, 61, 62]. This technique requires a relatively large sample with many small crystallites. However, it is often desired to know the orientation of individual crystal grains. For example, during studies of photonic band gap crystals, large crystals of known orientation are often desired, and powder diffraction techniques are not useful. Our motivation for developing

this technique was the need to determine the orientation of individual colloidal crystals in the study of the interfacial energy between a colloidal liquid and colloidal crystal.

Saunders studied the reciprocal lattice of opals, which are naturally forming colloidal crystals, using a Laue-type experimental setup using visible light [63]. This apparatus produced both qualitative and quantitative results. However, this approach does not allow real-space imaging of the sample in the same apparatus. Other researchers have probed the reciprocal lattice of colloidal crystals using parallel-beam techniques (see e.g., refs. [64, 65]), but these observations have been limited to simple cases where the direct beam is aligned to a direction of high symmetry in the crystal.

Real-space imaging via 2-D optical microscopy has been used in several cases to determine the structure of colloidal crystals. However, these studies also have been limited to very specific orientations of a crystal with respect to the microscope focal plane [66, 67]. It is conceivable that 3-D confocal microscopy could be used to determine both the structure and the orientation of individual colloidal crystals since the centroid of each particle can be determined [21, 68, 69], and hence the reciprocal lattice can be determined from digital Fourier transform calculations. However, there are many situations where the fluorescent labeling requirements, effect of dye on interparticle potential, photobleaching limitations, large datasets, and/or costly equipment associated with confocal microscopy are undesirable.

The technique discussed in this chapter can be used to study colloidal crystals of any random orientation and allows real-space and reciprocal space data to be gathered in the same instrument. It can be combined with confocal or conventional microscopy contrast techniques such as Zernike phase contrast or Nomarski differential interference

contrast [70] to provide orientation and structure data to complement real-space imaging at the individual particle level. The technique described in this chapter is based on reconstructing a portion of a crystal's reciprocal lattice from data obtained via an optical microscope using a parallel incident beam. It can be applied to closely index-matched colloidal crystals whose lattice parameters are roughly on the same length scale as optical wavelengths.

2.2 Background

2.2.1 Technique Overview

Even though a colloidal crystal can be imaged in real-space, its reciprocal lattice is still the natural choice for determining structure and orientation because every point in a crystal's reciprocal lattice describes the orientation and spacing of the corresponding crystal plane. This is evident in the standard use of both reciprocal space and real space techniques in TEM [26]. In an optical microscope, a moveable Bertrand lens or equivalent optics allows easy switching between reciprocal space and real space. A primary difference between using TEM with atomic and molecular crystals and optical microscopy with colloidal crystals is the relative length scale of the crystal lattice versus the probe wavelength. Diffraction from crystal planes follows Bragg's law where each Bragg spot represents a point in the reciprocal lattice [71]. In TEM, the ratio of plane spacings to electron wavelength is typically such that Bragg angles are very small (typically $<1^\circ$), and it is a good approximation that diffracting planes lie in a zone axis defined by the beam direction. In contrast, colloidal crystals that can be imaged using

optical microscopy typically scatter light over a wide range of angles similar to conventional x-ray Laue experiments.

Optical microscopy differs from both TEM and x-ray Laue techniques in that it is not practical in a conventional optical microscope to manipulate the orientation of the sample with respect to the direct beam. However, it is relatively easy to manipulate the direct beam in an optical microscope while leaving the sample fixed with respect to the microscope's optical axis. A consequence of this difference is that the detector (human eye or camera) in the colloidal crystal/optical microscope experiment is not always perpendicular to the beam direction. This results in geometric distortions in the projection of symmetry elements onto the focal plane, so visual alignment and simple measurement techniques such as those typically employed in TEM are not useful. It would be possible to use x-ray Laue techniques such as the Leonhardt chart for forward scattering in conjunction with a Wulff net to produce a stereographic projection. However, an easier and more useful approach is possible due to the ability for interactive positioning of the direct beam using quasi-monochromatic light in the optical microscope.

The proposed technique is based on a standard optical microscope in the transmitted light mode. After a colloidal crystal of interest is located within a sample and isolated by stopping down the field diaphragm, an optical Fourier transform (OFT) image is formed by inserting a Bertrand lens or equivalent optics into the beam path. The sample is then illuminated with a collimated beam formed by placing a pinhole in one position of the turret condenser. When the microscope is properly adjusted for Koehler illumination, translating the pinhole in the front focal plane of the condenser results in

varying the angle of incidence of the beam with respect to the optical axis of the microscope. This is due to the Fourier transform relationship between the illumination beam path and imaging beam path [72]. This translation can be produced without modifying the microscope within the range of the turret condenser rotation arc and the built-in adjustments for centering condenser elements such as phase rings. Full access to the range of incident angles up to the numerical aperture (NA) limit of the condenser would be possible with custom modifications to the condenser.

The steps used to obtain the needed information are as follows. First, the scattering image is viewed through the eyepieces or via a color video camera using white light to find illumination angles that produce Bragg scattering features. Next, a narrow band pass interference filter is placed in the illumination path to produce quasi-monochromatic light. An image is then recorded of the scattering pattern, which in the case of a perfect crystal would consist of a collection of isolated spots. This procedure can be repeated as needed at different wavelengths and various illumination angles to gather data from which a portion of the reciprocal lattice can be reconstructed.

2.2.2 Analysis Procedure

For simplicity in outlining the procedure for extracting quantitative data from experimental images, we will concentrate on features which give rise to distinct Bragg spots in reciprocal space. This procedure is easily extended to any type feature in reciprocal space, such as Bragg rods. There are two conditions required to produce Bragg scattering. The first is described by Bragg's law, which in the context of colloidal crystals is

$$2.1 \quad \lambda_0 = 2nd_{hkl} \sin \theta_B$$

where λ_0 is the wavelength of light in a vacuum, n is the index of refraction of the suspending medium, d_{hkl} is the spacing of the (hkl) planes, and θ_B is the angle between (hkl) and the diffracted beam. The second condition is that the angle of incidence must equal the angle of scattering with respect to the (hkl) plane.

The geometry for satisfying Bragg's law can be visualized using the Ewald sphere construction shown in Fig. 1, which depicts a diametral plane of the sphere.

Fig. 1. Geometry of the Ewald sphere construction.

The incident beam is described by the vector S_0 and the diffracted beam is represented by the vector S which makes an angle $2\theta_B$ with S_0 . The origin of the real-

space lattice is at point C located at the center of the sphere and the origin of the reciprocal lattice is at point O where the incident beam exits the sphere. The Bragg conditions are met for plane (hkl) when a vector in the reciprocal lattice lies on the surface of the Ewald sphere [71], such as point P_{hkl} . Such a reciprocal lattice vector is defined as

$$2.2 \quad \sigma = S - S_0$$

The radius of the Ewald sphere depicted in Fig. 1 equals n/λ_0 . Note that this is similar to the typical Ewald sphere for wavelength-specific x-ray techniques such as powder diffraction rather than assigning it a value of unity as is customary for x-ray Laue scattering. It is easiest to visualize the proposed technique by imagining that the incident beam and the Ewald sphere pivot about the reciprocal lattice origin, which is what physically happens in such experiments. This is in contrast to most electron and x-ray diffraction experiments where the crystal (and hence the reciprocal lattice) is rotated, whereas the incident beam remains fixed.

All data needed to describe S and S_0 can be derived from experimental images and knowledge of the wavelength of light used to produce the image. In an OFT image obtained via optical microscopy, the position of any feature is related to scattering angle by

$$2.3 \quad r = L \sin \psi$$

where r is the radial distance of the Bragg spot from the center of the image, L is a proportionality constant, and $\psi = 2\theta_B$. Note that r scales with $\sin \psi$ rather than $\tan \psi$, as in x-ray diffraction, because optical microscopes are designed to meet the Abbe sine condition in order to minimize aberrations [73, 74]. The center of the image is defined as

the point at which a beam parallel to the optical axis forms an image. The constant L is determined experimentally and is analogous to the camera length in TEM. The angle ψ corresponds to the angle between the optical axis and the scattering vector.

A series of coordinate transformations and vector algebra are used to reduce raw image data to reciprocal lattice vectors. First, the origin of the coordinate system is translated to coincide with the image of a beam traveling along the optical axis of the microscope, which corresponds to a scattering angle of zero. Bragg scattering features in an experimental OFT image are described in Cartesian coordinates (x, y) using the image processing convention of placing the origin in the upper left corner of the image with the x-axis horizontal and the y-axis vertical. The x-y plane is parallel to the exit pupil of the microscope objective, which is being imaged in this technique. It is advantageous to anticipate a third axis parallel to the optical axis of the microscope and pointing in the direction that the light travels. However, this results in a left-handed frame of reference, so the coordinate axis translation is combined with a mirror about the x-axis to produce a right-handed system with the origin lying on the optical axis:

$$\begin{aligned} x' &= x - x_{OA} \\ y' &= y_{OA} - y \end{aligned}$$

where the subscript OA designates the optical axis in the image. Data points are then transformed to 3-D scattering vectors in spherical coordinates given by:

$$\psi = \sin^{-1}\left(\frac{r}{L}\right)$$

$$\begin{aligned}
2.5 \quad \varepsilon &= \sin^{-1}\left(\frac{y'}{r}\right) & \text{for } y' \geq 0 \\
\varepsilon &= -\sin^{-1}\left(\frac{y'}{r}\right) & \text{for } y' < 0 \\
\rho &= \frac{n}{\lambda_0}
\end{aligned}$$

where $r = \sqrt{x'^2 + y'^2}$. The first spherical coordinate, ψ , is described above and follows from Eq. 2.3. The second spherical coordinate, ε , defines the angular position of the Bragg spot in the image plane with respect to the Cartesian x-axis. The third spherical coordinate ρ gives the distance of the data point from the origin and is equal to the radius of the Ewald sphere since all data points lie on the surface of this sphere.

Next, the scattering vectors are transformed to reciprocal lattice Cartesian coordinates where:

$$\begin{aligned}
x_R &= \rho \sin \psi \cos \varepsilon \\
2.6 \quad y_R &= \rho \sin \psi \sin \varepsilon \\
z_R &= \rho \cos \psi
\end{aligned}$$

Finally, the reciprocal lattice vector σ is obtained from $\mathbf{S}_0$ and $\mathbf{S}$ in Cartesian coordinates via Eq. 2.2.

If the crystal structure is known, then reciprocal lattice data can be used to determine lattice parameters and to determine crystal orientation. In general, the basis vectors can be determined from three σ 's which are not all co-planar if the indices of each σ can be determined. Let

$$2.7 \quad A = \begin{pmatrix} h_1 & k_1 & l_1 \\ h_2 & k_2 & l_2 \\ h_3 & k_3 & l_3 \end{pmatrix}$$

$$2.8 \quad x = \begin{pmatrix} a_1^*_x & a_1^*_y & a_1^*_z \\ a_2^*_x & a_2^*_y & a_2^*_z \\ a_3^*_x & a_3^*_y & a_3^*_z \end{pmatrix}$$

$$2.9 \quad B = \begin{pmatrix} \sigma_{1x} & \sigma_{1y} & \sigma_{1z} \\ \sigma_{2x} & \sigma_{2y} & \sigma_{2z} \\ \sigma_{3x} & \sigma_{3y} & \sigma_{3z} \end{pmatrix}$$

where h, k, l are plane indices, the subscripts $1, 2, 3$ refer to the three experimentally determined reciprocal lattice vectors, and the subscripts x, y, z refer to Cartesian vector components. The reciprocal lattice vector matrix B can be represented as a product of the index matrix, A and the reciprocal lattice basis vector matrix, x :

$$2.10 \quad Ax = B$$

Matrix B is known from experimental data, and it is possible to deduce matrix A from knowledge of plane spacings and the relationships between planes of a known crystal structure. What is sought in this procedure is matrix x . From elementary linear algebra,

$$2.11 \quad x = A^{-1}B$$

where A^{-1} is the inverse of A .

For an unknown crystal structure, conventional reciprocal lattice methods can be employed to deduce the crystal structure and then the reciprocal lattice basis vectors [71].

2.3 Experimental Procedure

2.3.1 Samples

The colloidal suspension consisted of $(1.15 \pm 0.01)\mu\text{m}$ diameter PMMA spheres sterically stabilized with short PHSA chains grafted to the surface and suspended in an index-matching solution of decahydronaphthalene and tetrahydronaphthalene. This system closely approximates a hard sphere potential [60] in which crystallization occurs as a function of volume fraction [16]. The volume fraction of the bulk suspension was manipulated to fall within the coexistence region identified by gravity-induced separation of colloidal crystal and colloidal liquid phases. The volume fraction was determined to be 0.513 ± 0.005 via the lever rule from a linear regression of interface height in a cylindrical vial extrapolated to time zero [75]. After homogenizing the bulk sample using a vortex mixer, we filled a flat microcapillary cell (Vitrocom) with nominal internal dimensions of 0.1mm x 2mm x 50mm via capillary action by dipping the end of the cell into the suspension. Both ends were then sealed with epoxy and the cell was mounted to a standard 25mm x 75mm microscope slide using optical epoxy. The sample was allowed to crystallize with the small dimension of the cell parallel to the gravity vector.

2.3.2 Experimental Equipment

An upright biological microscope (Zeiss Axioskop) in the transmitted light mode with a standard 100W tungsten halogen lamp was used. A high resolution 3-chip CCD video camera (Optronics DEI-750) was used to acquire images which in turn were digitized and stored on a PC for post processing. Image analysis was performed using

Image-Pro Plus software (Media Cybernetics) with numerical data exported to a spreadsheet for calculations.

Real-space images were gathered in the normal fashion in the phase contrast and DIC imaging modes. For OFT imaging, two equivalent setups were used. The first simply used the standard Bertrand lens. In the second method, the camera was coupled to the microscope via a breadboard optical train (Linos) which performed the OFT and provided an accessible conjugate plane to insert a mask to block the direct beam when necessary. The focal lengths of the lenses were maximized within the limit of practicality to minimize aberrations, and the combination of focal lengths was chosen to match the size of the exit pupil of the microscope objective to the size of the camera imaging array. The beam block consisted of an appropriately sized dot of flat black paint on a round microscope coverslip. The beam block could be manually positioned to correspond to the moveable direct beam.

One position of the 1.4 NA oil condenser was outfitted with a 270 μ m diameter pinhole made by piercing a folded sheet of aluminum foil with an ordinary straight pin. This produced a nearly collimated beam having a half angle beam divergence of 3/4°. An oil immersion 63x/1.4NA phase contrast objective was used. The half-cone angle of rays that can be detected with this objective is theoretically 68° about the optical axis, though we measured it to be ~63°. The position of the optical axis in the OFT images was determined by finding the geometric center of the annular phase contrast ring. This result was checked against the center of the bright spot produced when the condenser was completely removed from the microscope producing a collimated beam along the optical axis. These two results agreed to within 1/3°.

When the microscope was adjusted for Koehler illumination, translation of the pinhole in the front focal plane of the condenser corresponds to varying the angle of a collimated beam of light incident on the sample from below. The position of the pinhole was manipulated by a combination of manually rotating the condenser turret and manipulating the centering adjustments for the turret position of the pinhole. This procedure allowed access to a 9° wide arc across the exit pupil of the objective that included the optical axis and corresponded to about 11% of the area of the full aperture. This limited range was more than adequate for the experiment described below.

Interference notch filters with 10nm full width half maximum (FWHM) transmission bands were used to produce quasi-monochromatic light for quantitative measurements. The intensity vs. wavelength curves for the filters were highly symmetric about their peak wavelengths.

2.3.3 Calibration

Real-space images were calibrated by using a traceable test target (Richardson Technologies, Inc.) to establish an absolute scale for each microscope objective. The objective used for OFT imaging was also calibrated for the OFT breadboard optics using a transmission diffraction grating. The relationship for light scattered by a 2-D grating when illuminated at normal incidence is [76]

$$2.12 \quad m\lambda_0 = an \sin 2\theta$$

where m is the diffraction order, a is the grating spacing, n is medium index of refraction, and 2θ is again the scattering angle (but θ is not necessarily a Bragg angle in this case).

Combining Eqs. 2.3 and 2.12 gives

$$2.13 \quad L = \frac{Ran}{m\lambda_0}$$

which can be used for an experimental determination of the camera length L . A value for L was determined for the Bertrand lens setup using the ratio of the phase plate diameter in images taken with the Bertrand lens and breadboard optics setups.

2.3.4 Image Processing and Data Analysis

For each image that was saved for analysis, 16 frames (typical) of video images were digitized and averaged to reduce image noise. For Bragg spots and circular cross-sections of Bragg rods, an OFT image was thresholded to isolate individual spots and the intensity-weighted center of each spot was calculated. Data points from Bragg streaks were gathered by visually marking points along individual streaks and extracting the coordinates of the marked points. Data points were then exported to a spreadsheet where the calculations described above were performed to obtain reciprocal lattice vectors from which orientation and structure information was extracted. Reciprocal lattice data was also exported into a crystallography software program (CaRine Crystallography) for interactive 3-D visualization.

2.4 Results

We examined a single crystallite within a polycrystalline colloidal sample using the technique described above. The crystallite measured about $90\mu\text{m} \times 100\mu\text{m}$ in the focal plane and $73\mu\text{m}$ along the optical axis. Above it was a thin layer of disordered spheres about two sphere diameters in thickness, and below it was a $36\mu\text{m}$ disordered layer. First, as much real-space crystallographic data as possible was obtained from real-

space images. Fig. 2 shows images of the crystallite using the darkfield (Fig. 2a) and phase contrast (Fig. 2b) imaging modes. In Fig. 2a, the only image processing performed besides frame averaging was to stretch the image histogram to produce optimal visual contrast. Fig. 2b was produced by averaging 10 video frames after each frame had been digitally sharpened using a real-time processor built into the video camera. After frame averaging, the image was converted from color to 8-bit grayscale and a best-fit histogram equalization was applied.

a)

b)

Fig. 2. Micrographs of crystallite studied in Chapter 2. a) Darkfield image. b) Phase contrast image of the same region. Portions of adjacent grains can also be seen. Scale bars = 10μm.

The most prominent features in the darkfield image (Fig. 2a) are the parallel bands of various colors running at an angle across the crystallite from lower left to upper right. In the phase contrast image (Fig. 2b), lines of spheres run in the same directions as the darkfield colored bands. These lines have a regular spacing perpendicular to the line direction. When viewed in certain directions other than the line direction, the spheres sometimes form straight rows of varying length, and in other places they form segments in which the spheres seemed to zigzag back and forth. When the microscope focus was scanned through the sample in the phase contrast mode, the straight lines of spheres appeared to roll in a direction perpendicular to the lines. The spacing in the focal plane was measured from an image similar to Fig. 2 and the vertical travel was determined from the motorized z-axis readout. The straight lines had an average spacing of $(0.987 \pm 0.004)\mu\text{m}$ and appeared to travel four line spacings in $(55.9 \pm 4.2)\mu\text{m}$ of stage travel. In addition to the lateral movement of rows of spheres, individual spheres within each row appeared to roll along the length of the row as the focus was scanned through the sample.

Next reciprocal space data was gathered. Using white light, a beam direction was located which produced a significant number of features in an OFT image, see Fig. 3a.

a)

b)

Fig. 3. OFT images of crystallite shown in Fig. 2. a) White light OFT image. The dark ring intersecting the central beam is the phase plate in the exit pupil of the phase contrast objective. b) corresponding OFT image with 546nm filter.

Images were then acquired using 436nm, 510nm, 546nm, and 680nm interference filters. The image obtained using the 546nm interference filter is shown in Fig. 3b. A subset of the prominent Bragg features were selected for detailed analysis. This data could be classified as isolated points, clusters of points, and strings of points.

2.5 Discussion

2.5.1 Real Space

Color variations in images of colloidal crystals are produced by Bragg scattering from various crystal planes [77]. Therefore, the diagonal bands of varying colors in Fig. 2a would indicate that the crystal structure, orientation, or both vary periodically in the direction perpendicular to the band edges. Monovoukas and Gast identified such color banding with face-centered cubic (fcc) twinning in charge-stabilized suspensions [78], which have a long-range repulsive interparticle potential. Similar behavior is expected in monodisperse hard sphere colloids, which are known to form crystals with a structure commonly referred to as random hexagonal close-packing (rhcp) [61]. This structure consists of a random sequence of the three possible positions that allow closest packing of hexagonal layers of spheres, typically labeled A, B, and C. Taking position A as a reference layer, the spheres in the other two layers are translated $(1/3\mathbf{a}_1 + 2/3\mathbf{a}_2)$ and $(2/3\mathbf{a}_1 + 1/3\mathbf{a}_2)$ relative to layer A where $\mathbf{a}_1$ and $\mathbf{a}_2$ are lattice vectors giving hexagonal symmetry, and the magnitude of each is equal to the sphere diameter for a close-packed arrangement. As long as any position is not repeated in two successive layers, the spheres of any given layer fit into the interstices of the adjacent layers giving a distance between hexagonal layers of $\sqrt{2/3}a$. There are two 3-D crystal symmetries which

produce close-packed lattices, fcc and hexagonal close packing (hcp). The fcc structure incorporates a regular pattern of all three layers such as ABCABC... or CABABC... whereas the hcp structure uses only two positions such as ABAB... or CBCB... In the rhcp structure, the stacking sequence is random such as ABCACAB... The randomness of the stacking sequence is defined by a parameter α which gives the probability that layers n and $n + 2$ are different [79]. This parameter varies between 0 and 1 which correspond to perfect hcp and perfect fcc, respectively. When repeated layers are excluded but the stacking sequence is otherwise completely random, $\alpha = 0.5$. The rhcp structure can be viewed as either fcc or hcp with a large number of stacking faults. Therefore, we would expect the color variations in our hard sphere sample to arise from regions of fcc and hcp separated by stacking faults. Nearly all the bands of color in Fig. 2a span the entire crystallite suggesting that the stacking sequence in each band is uniform across the entire sample. However, there are several instances where bands of color are not uniform across the entire sample. The most notable of these instances occurs at about 1/3 of the crystallite width from left border where a red band disappears in the middle of the crystallite. Such cases could be explained by the presence of Shockley partial dislocations in the crystallite where the stacking sequence changes within a close-packed layer.

The preceding discussion of the darkfield image suggests that the lines of spheres seen in Fig. 2b correspond to close-packed layers. If this is correct, the lateral rolling during translation along the optical axis of the microscope would indicate that the close-packed layers were tilted with respect to the focal plane. As the sample translates in the z-axis with respect to the fixed focal plane, the segment of any given close-packed layer

that is in focus shifts laterally. This results in the appearance that lines of spheres roll across the image. This is depicted graphically in Fig. 4.

Fig. 4. Geometry of tilted close-packed planes. OA = optical axis, FP = focal plane, d_{cp} = distance between close-packed planes, α = angle between focal plane and close-packed planes.

It can be seen from this figure that as the microscope stage is translated from FP_1 to FP_2 through a distance Δz , the line of spheres running through point A appears to shift by Δx in the focal plane to point B. Therefore, the angle between the close-packed planes and the focal plane is given by $\alpha = \tan^{-1}(\Delta z / \Delta x)$. This relationship yields a tilt of $(86.0 \pm 0.3)^\circ$ with respect to the focal plane. The lines of spheres represent the

intersection of close packed planes with the imaging plane. These lines make an angle of $(61.8 \pm 0.3)^\circ$ with the x-axis. The actual close-packed plane spacing is $d_{cp} = (\sin\alpha)(\Delta x)$ when Δx is the apparent distance in the focal plane between two adjacent lines of spheres. This gives $d_{cp} = (0.985 \pm 0.004)\mu\text{m}$ which corresponds to an hcp lattice parameter of $c = (1.97 \pm 0.01)\mu\text{m}$ and a fcc lattice parameter of $a = (1.71 \pm 0.01)\mu\text{m}$. Volume fraction, ϕ , is related to the fcc lattice parameter by the relationship

$$2.14 \quad \phi = \frac{2}{3} \pi \left(\frac{d}{a}\right)^3$$

where d is the particle diameter. Our lattice parameter yielded a volume fraction of 0.64 ± 0.02 which is higher than the initial volume fraction of 0.513 ± 0.005 . However, this value is reasonable given settling of the crystal under gravity and possible slow evaporation of fluid from the cell over time.

The apparent movement of the spheres along the lines of close-packed layers indicates that the orientation of the crystallite about the c-axis was different from that described in the approach of Elliot and Poon to determine the stacking disorder from real space images [67]. In their geometry, the c-axis is perpendicular to the optical axis and a $\{11-20\}$ plane is parallel to the focal plane which leads to the appearance that fcc crystals form straight rows inclined 70.5° to the close packed lines and hcp crystals zigzag back and forth forming kinked lines. Elliot and Poon showed that the stacking parameter α is given by

$$2.15 \quad \alpha = 1 - \frac{\kappa}{N - 2}$$

where κ is the number kinks in N layers. Although the angles observed in the geometry of the sphere patterns did not match their results, we were still able to count the number

of kinks and total layers in a phase contrast micrograph having higher magnification than Fig. 2b. This data yielded a value of $\alpha = 0.59$ which indicates that the stacking order slightly favors fcc over hcp, which is in line with previous studies [5, 67, 80].

2.5.2 Reciprocal Space

The reciprocal lattice of the rhcp structure is made up of both lattice points and rods [81]. This is due to the lack of true 3-D symmetry in the rhcp structure. Each close-packed plane possesses hexagonal symmetry, and the spacing of close-packed planes in the third dimension is regular. However, the randomness of the stacking sequence breaks the symmetry in the third dimension resulting in what could be viewed as 2 ½-D symmetry. In rhcp, lattice points exist wherever $(h-k)/3 = n$ where n is an integer, corresponding to planes that are common between fcc and hcp. Where $(h-k)/3 \neq n$, lattice points are broadened into rods whose intensity varies along the length of a rod as a function of stacking disorder. These Bragg rods are perpendicular to the $(hki0)$ plane in the reciprocal lattice and are arranged with hexagonal symmetry about the $\mathbf{c}^*$ axis.

Reciprocal lattice data was extracted from OFT images as described above. The analysis of the data was based on the working hypothesis that four strings of data points appearing to form parallel lines corresponded to reciprocal lattice Bragg rods. This hypothesis could be accepted if lines fit to this 3-D data were parallel and arranged with hexagonal symmetry with spacing consistent with the available real space data for this crystal. Judging from the distance of these data strings from the origin of the reciprocal lattice, it appeared that three strings were $\{10-1l\}$ rods and the fourth a $\{20-2l\}$ rod.

A linear least squares fit of each of the four data strings was performed using linear regressions of the data points projected onto orthogonal planes. The root-sum-of-squares (RSS) of the results from each combination of plane pairs produced direction cosines. The angles between the $\{10-1l\}$ rods ranged from 0.1° to 0.6° while the angles between the $\{20-2l\}$ rod and the $\{10-1l\}$ rods were on the order of several degrees. Additional data was gathered at other incident beam angles to see if that would reduce the angular variation between the $\{20-2l\}$ rod and the other rods. This did not provide any improvement, and the angles between the $\{20-2l\}$ rod and the $\{10-1l\}$ rods ranged from 2.0° and 2.3° . It is likely that the deviation of the $\{20-2l\}$ rod orientation with respect to the other rods is due to line broadening from crystal and instrument imperfections. The line broadening due to crystal size was calculated to be only about $\frac{1}{4}^\circ$ using the Scherrer formula [71]. This combined with the full cone beam divergence gives a potential FWHM line broadening of about 1.75° and polychromatic effects would increase this slightly more. For a Bragg spot, or for a Bragg rod that intersects the Ewald sphere radially, such line broadening effects simply result in a larger spot from which to calculate the intensity-weighted center. Therefore, feature broadening in these cases should not significantly affect the accuracy of the extracted data. However, it is likely that accuracy could be affected for Bragg rods approaching tangential intersection with the Ewald sphere as in the case of the $\{20-2l\}$ rod because the scattering intensity varies along the length of the Bragg rods in the rhcp reciprocal lattice. The ratio of maximum to minimum intensity can be as high as 9, which occurs for $\alpha = 0.5$ [81]. This leads to ambiguity in interpreting OFT images for nearly tangential Bragg rods since one can no longer assume that the highest intensity along a Bragg rod corresponds to the intersection

of the ideal rod axis with the Ewald sphere. Despite this possible ambiguity, the orientation of the $\{20-2l\}$ rod is still close enough to the other rods to retain the hypothesis that these features are indeed Bragg rods in the rhcp hexagonal lattice.

The reciprocal lattice vector $\mathbf{a}_1^*$ was determined using Bragg rod data. The reciprocal lattice point a_l^* lies on the $(10-1l)$ Bragg rod and $\mathbf{a}_1^*$ is perpendicular to the rod. If $\mathbf{v}$ is a vector described by the direction cosines of the Bragg rod, then

$$2.16 \quad \mathbf{v} \cdot \mathbf{a}^* = 0$$

From the symmetric equations of a line in three dimensions, it follows that

$$2.17 \quad \begin{aligned} y &= \frac{\cos \beta (x - x_1)}{\cos \alpha} + y_1 \\ z &= \frac{\cos \gamma (x - x_1)}{\cos \alpha} + z_1 \end{aligned}$$

where $\cos \alpha$, $\cos \beta$, and $\cos \gamma$ are the direction cosines of the line. By combining Eqs. 2.16 and 2.17, the x-component of $\mathbf{a}_1^*$ can be written as

$$2.18 \quad x = x_1 (\cos^2 \beta + \cos^2 \gamma) - \cos \alpha (y_1 \cos \beta + z_1 \cos \gamma)$$

and the other two components can be found by back substitution into Eq. 2.17. This approach was applied to produce reciprocal lattice vectors having the magnitude of $\mathbf{a}_1^*$ in the case of the $\{10-1l\}$ rods and $2\mathbf{a}_1^*$ in the case of the $\{20-2l\}$ rod. An averaged magnitude of $\mathbf{a}_1^*$ was then calculated to be $0.954 \pm 0.008 \mu\text{m}^{-1}$, which corresponds to a hexagonal lattice parameter $a = (1.21 \pm 0.01) \mu\text{m}$. The $\mathbf{a}_1^*$ direction corresponding to an arbitrarily chosen $\{10-1l\}$ rod completes the definition of the $\mathbf{a}_1^*$ reciprocal lattice basis vector.

Next, we examined a cluster of data points located in expected vicinity of the (0002) Bragg spot. All of these data points were taken at different wavelengths using the same incident beam angle. In an ideal crystal, one would have to vary the incident beam angle to meet the Bragg conditions for different wavelengths for the (0002) Bragg spot. The simultaneous appearance of Bragg spots at different wavelengths indicated node broadening similar to that discussed in relation to Bragg rods. However, the (0002) node is not broadened into a rod in the rhcp lattice so there is no complication of varying structure factor in this case. Therefore, refined data was gathered by finding the incident beam angle that maximized spot intensity for a given wavelength. Taking the centroid of these refined data as (0002) yielded a magnitude for $\mathbf{c}^*$ of $(0.508 \pm 0.008) \mu\text{m}^{-1}$. This corresponds to a hexagonal lattice parameter $c = (1.97 \pm 0.03) \mu\text{m}$, which coincides with the real space result. In a rhcp crystal, $\mathbf{c}^*$ should be parallel to the Bragg rods, and our data yielded an angle of 1.0° between $\mathbf{c}^*$ and the averaged rod direction. The angle between $\mathbf{c}^*$ and the optical axis of the microscope was $86.1 \pm 0.3^\circ$ in close agreement with the real-space results of $(86.0 \pm 0.3)^\circ$. Using $\mathbf{c}^*$, we calculated an angle of $(60.9 \pm 0.4)^\circ$ between the line formed by the intersection of the close-packed planes and the imaging plane. Using the RSS average rod direction instead of $\mathbf{c}^*$ gave an angle of $(61.6 \pm 0.5)^\circ$. The corresponding result from real space data was $(61.8 \pm 0.3)^\circ$. The c/a ratio based on OFT data is 1.63 ± 0.03 which coincides with the value for an ideal hcp cell of $\sqrt{8/3} \approx 1.633$. Table 1 summarizes the comparison of real space and reciprocal space lattice parameter and orientation data. A stereographic projection of the OA and $-\mathbf{g}$ is shown in Fig. 5.

	<u>real space measurements</u>	<u>reciprocal space measurements</u>
hcp lattice parameter, c	$(1.97 \pm 0.01)\mu\text{m}$	$(1.97 \pm 0.03) \mu\text{m}$
hcp lattice parameter, a	n/a	$(1.21 \pm 0.01) \mu\text{m}$
c/a (ideal = 1.633)	n/a	1.63 ± 0.03
Angle between optical axis and c-axis	$(86.0 \pm 0.3)^\circ$	$(86.1 \pm 0.3)^\circ$
Angle between x-axis and intersection of (0002) and focal plane	$(61.8 \pm 0.3)^\circ$	$(60.9 \pm 0.4)^\circ$ * $(61.6 \pm 0.5)^\circ$ **
		* using $\mathbf{c}^*$ ** using avg. Bragg rod direction

Table 1. Comparison of data from real space and reciprocal space measurements.
n/a = not accessible.

Fig. 5. Stereographic projection of crystal orientation. The figure shows the standard (0001) hcp projection for ideal c/a . The 3-symbol indices show the corresponding fcc planes. The small symbol marks the orientation of the OA and the large symbol marks the orientation of $-\mathbf{g}$. Filled symbol is in the (0001) hemisphere and open symbol is in the (000-1) hemisphere.

With the reciprocal lattice basis vectors determined, an attempt was made to index the previously discussed Bragg rods and the remaining features from the OFT data. The four Bragg rods could be indexed as $(10-1l)$, $(01-1l)$, $(-110l)$, and $(20-2l)$. Most of the remaining data could also be indexed to rhcp reciprocal lattice points and rods. Individual points or clusters corresponded to the reciprocal lattice points (-2110) , (-2112) , (-2114) , and $(11-26)$ and were determined using refined data as described above for (0002). Two additional points indexed to the $(-220l)$ and $(-321l)$ reciprocal lattice rods.

Using the reciprocal lattice basis vectors determined above, we calculated the expected magnitudes of the indexed reciprocal lattice vectors and the angles between them. For the Bragg rods, the reciprocal lattice vector corresponding to the intersection of the Bragg rod with the $(hki0)$ plane was calculated. For the two rods containing only one data point each, the RSS average direction of the other four rods was used. The experimental reciprocal lattice vectors varied in absolute magnitude between 0.2% and 1.8% from the calculated values, with a RSS mean error of 1.0%. The absolute difference between calculated and measured interplanar angles ranged from 0.01° to 1.4° with a RSS mean difference of 0.6° . The largest angular errors involved Bragg rods, which have already been shown to produce varying results. In contrast, the largest error between measurements involving only Bragg spots was 0.3° .

Fig. 6 shows several views of the indexed data. In Fig. 6a, it is clear that the data possesses hexagonal symmetry about the $\mathbf{c}^*$ axis. Fig. 6b and Fig. 6c show that data indexed to planes where $(h-k)/3 = n$ are spots and possess the symmetry expected for an hcp lattice, whereas the remaining data is scattered along lines running through $(h-k)/3 \neq n$ nodes. These results clearly indicate that the indexed data is consistent with the rhcp reciprocal lattice, confirming the hypotheses used to interpret the reciprocal space data.

For the rhcp structure, the minimum data required to define the reciprocal lattice is two data points in one of two combinations. The first combination is (0002) and a point anywhere on any Bragg rod. The vector $\mathbf{c}^*$ can be determined from (0002) , and $\mathbf{a}^*$ can be determined from the point on the Bragg rod using Eqs. 2.17 and 2.18 by assuming that the rod is parallel to $\mathbf{c}^*$. The second combination is to know any two points on any

single Bragg rod. The vector $\mathbf{a}^*$ is determined using Eqs. 2.17 and 2.18 with the line defined by the two Bragg rod points, which also define the direction of $\mathbf{c}^*$. The magnitude of $\mathbf{c}^*$ is determined from the magnitude of $\mathbf{a}^*$ and the ideal c/a ratio for close-packed layers.

Fig. 6. Indexed OFT data. Data is represented by colored circles: Blue = 435nm, green = 510/546nm, red = 680nm. The origin of the reciprocal lattice is shown as an open circle. The black lines are the linear fits to Bragg rods as discussed in the text. For the $(-220l)$ and $(-321l)$ rods, which contain only one data point each, the RSS average direction of the other four rods was used. a) view in the direction of $-\mathbf{c}^*$, b) view in the direction of $(\mathbf{c}^* \times \mathbf{a}_1^*)$, c) view in the direction of $\mathbf{a}_1^*$.

We compared our crystallite orientation to the Elliot and Poon orientation [67] to test our hypothesis concerning the rolling of spheres in the direction of the close-packed lines. In their work the spheres appeared to remain stationary as the focal plane was scanned through a crystallite. The c-axis was perpendicular to the optical axis in their work, whereas the c-axis of our crystallite formed an angle of 86.0° with the optical axis. The effect of this 4° tilt is the previously described lateral rolling of close-packed lines as the focal plane was moved through crystal. The orientation of the close-packed planes about the c-axis differed by $\sim 19^\circ$ from the Elliot and Poon orientation such that the focal plane was not parallel to any low index planes in our crystallite. This would indeed result in the appearance that spheres roll along the close-packed lines when the focal plane is scanned through the crystal since spheres in successive planes are offset from one another with respect to the focal plane. The fact that we were still able to determine the number of kinks in the crystallite suggests that the Elliot and Poon approach is rather tolerant to variations from their ideal orientation. However, we were unable to derive quantitative data from real-space images concerning the orientation of the close-packed layers about the c-axis. This prevented us from completely determine the crystallite orientation from real-space data. This underscores the limitation of real-space methods in gathering data from randomly oriented colloidal crystals.

Five individual data points, one data cluster, and one data string could not be indexed to the rhcp reciprocal lattice. Upon reexamination under the microscope, we found that the individual data points and the data cluster increased in intensity as the indexed features decreased in intensity (and vice versa) when the sample was translated in various directions the x-y plane. This indicates that these unindexed data points

belong to neighboring grains, which is possible since the minimum field aperture size was slightly larger than the crystallite under examination.

However, the intensity variations of the unindexed data string appeared to correlate with the indexed features as we varied the x-y stage position. The data points in this feature formed a slightly curved line with moderate intensity at the ends and very low intensity in the middle. A straight line fitted through these data points formed an angle of $(90.3 \pm 0.5)^\circ$ with $\mathbf{c}^*$. Fig. 7a shows the OFT image taken at 436nm and processed using a logarithmic histogram equalization in order to make this weak feature more apparent. This processing also revealed a weak dark line parallel to the weak bright line in question. This pair of bright and dark lines is reminiscent of Kossel lines from x-ray diffraction and Kikuchi lines from electron microscopy. Using the reciprocal lattice vectors derived above, we computed the position of the (0002) Kossel lines at 436nm. These computed Kossel lines are compared with the experimental data in Fig. 7b by scaling and positioning the computed Kossel lines and computed edges of the phase plate such that the computed phase plate edges coincide with the boundaries of the phase plate in the experimental data. As can be seen by comparing Fig. 7a and Fig. 7b, the computed Kossel lines fall directly on top of the light and dark lines in the experimental image. The perpendicular distance between these lines through the optical axis is related to the scattering angle $2\theta_B$ via Eq. 2.3 and to the plane spacing via Eq. 2.1. These equations yields a value for the (0002) plane spacing of $(0.974 \pm 0.013)\mu\text{m}$ which agrees to within experimental error with the value of $d_{0002} = (0.985 \pm 0.015)\mu\text{m}$ derived from the previously discussed reciprocal lattice basis vectors. Lastly, the measured angle of $(90.3 \pm 0.5)^\circ$ between the bright feature and $\mathbf{c}^*$ is consistent with (0002) Kossel lines since $\mathbf{c}^*$

is perpendicular to the (0002) plane, and a segment of a (0002) Kossel line approximated by a straight line would be parallel to the (0002) plane.

Fig. 7. Kossel lines in parallel-beam image. a) Light and dark Kossel line pair in 436nm OFT image. b) same image with calculated position of (0002) Kossel line pair (red) superimposed using the crystal orientation determined using the method described in the text. The calculated edges of the phase plate in the exit pupil of the microscope are shown in blue.

Though the above discussion strongly suggests that the light and dark lines are Kossel lines, such features are produced by divergent beams. Since incoming light from multiple angles is required to capture a Kossel line in a single image, why then would Kossel lines be observed using a parallel-beam technique? We believe this is due to the disordered region beneath the crystallite being examined. This region is a colloidal glass and exhibits the diffuse scattering pattern associated with glassy materials [71]. This appears as a series of diffuse concentric rings centered on the direct beam. Incident wave vectors meeting the Bragg conditions are scattered by $2\theta_B$ from the dark Kossel line into the bright Kossel line. This can be qualitatively verified by observing that the intensity along the bright Kossel line increases and decreases in parallel to the varying intensity of the glassy scattering pattern adjacent to the dark Kossel line. The observation of Kossel lines in our data suggests an alternative to our parallel-beam approach using a divergent beam. This might have the advantage of gathering more data in a single image than our technique, although it is likely that image interpretation would become more difficult for rhcp structures. The interpretation of divergent-beam images would also have to account for the microscope imaging geometry of Eq. 2.3.

2.6 Summary and Conclusions

We have developed an approach for obtaining orientation and structure information from closely index-matched colloidal crystals using conventional optical microscopy in which reciprocal lattice vectors are extracted from OFT images using a parallel incident beam. This approach was demonstrated by comparing information gathered from real space images to results of the proposed method for a single rhcp colloidal crystal grain. For this grain, we determined the magnitude and direction of the

hcp reciprocal lattice basis vectors. The hcp lattice data that was accessible in real space matched the corresponding reciprocal space results to within experimental error, and the c/a ratio determined from reciprocal space data matched the ideal close-packed c/a ratio. In addition, the reciprocal lattice vector magnitudes and interplanar angles for the indexed planes were in close agreement with values calculated from the measured reciprocal lattice basis vectors with a RSS mean error of 1.0% for magnitudes and a RSS mean difference of 0.6° for angles. However, for the rchp structure, the ability to measure the orientation of Bragg rods appeared to degrade to an accuracy of $\pm$ several degrees for Bragg rods approaching tangential intersection with the Ewald sphere. Aside from this limitation, this technique appears to be capable of measuring lattice parameters to within 1% and orientation to better than 1° .

Chapter 3

Divergent-beam Technique

3.1 Introduction

A second approach to determining *in-situ* orientation of colloidal crystals is a divergent-beam approach. Rather than illuminating the sample with a parallel beam of light, illumination from all possible angles is used. A first glimpse of this technique was seen in the parallel-beam results where scattering from a glassy layer produced an unexpected pair of lines. Others have used divergent-beam approaches with colloids [24, 46, 82-88] However, in all of these studies, a major symmetry axis of the colloidal crystal under investigation has been aligned with the optical axis of the experimental instrument. In our current study of solid-liquid interfacial energy in colloidal systems, we are interested not only in crystals whose symmetry axes are aligned with the optical axis of the microscope, but also with those with misalignments. Unlike the x-ray and electron microscopy techniques, it is not practical to reorient misaligned samples under an optical microscope except for a simple rotation about the OA. Therefore, the challenge for our study is to develop a method for interpreting Kossel lines and extracting orientation that is applicable to random crystal orientations. We expect such a technique will be equally useful for other colloidal studies, particularly those involving photonic band gap applications. [86, 87]

3.2 Background

3.2.1 Technique Overview

As discussed in Chapter 2, coherent scattering from crystal planes is governed by the Bragg conditions and can be visualized using the Ewald construction shown in Fig. 1. For a fixed wavelength of incident light, the set of all scattered wave vectors, $\mathbf{S}$, that satisfy the Bragg conditions for plane (hkl) form a cone of rays about σ_{hkl} as shown in Fig. 8. The half angle of this cone, ϕ , is given by the relationship

$$3.1 \quad \phi = 90^\circ - \theta_B$$

Due to symmetry, the corresponding Laue cone for (-h-k-l) is formed by rotating $\mathbf{S}_0$ about $-\sigma_{\text{hkl}} = \sigma_{-\text{h-k-l}}$. This pair of cones, known as Laue cones or Kossel cones, can be visualized as being formed by rotating the Ewald sphere shown in Fig. 8a through 360° about σ_{hkl} . An equivalent approach is to translate the tails of $\mathbf{S}$ and $\mathbf{S}_0$ to the reciprocal lattice origin and rotate these vectors about σ_{hkl} as shown in Fig. 8b. A divergent-beam image represents the intersection of these cones with the imaging plane. In divergent-beam electron microscopy, these are termed Kikuchi lines, which appear to straight lines due to the small scattering angles involved. [26] In divergent-beam x-ray techniques, the images may take the form of any of the conic sections: circle, ellipse, parabola, or hyperbola. The displacement of points from the center of the image in these scattering patterns is proportional to $\tan\psi$, where ψ is the angle between the scattered ray and the optical axis of the instrument. In optical microscopy, the Abbe sine condition discussed in Chapter 2 results in the replacement of the $\tan\psi$ relationship by a $\sin\psi$ relationship. The differences between the $\tan\psi$ and $\sin\psi$ relationships are illustrated in Fig. 9. These

curves were produced in a pointwise fashion using the following method: First, we calculated a series of scattering vectors around the Laue cone in a reference frame in which one of the axes is the reciprocal lattice vector. Next, we transformed the series of scattering vectors to a reference frame defined by the optical axis of the scattering source. Finally, we calculated the representation of each scattering vector as a point on the figure using the appropriate $\tan\psi$ or $\sin\psi$ relationship.

The blue curves in Fig. 9 are a series of divergent-beam patterns following the $\tan\psi$ relationship and the red curves are for the $\sin\psi$ relationship. Both sets of curves represent scattering from planes in which the half-angle of the Laue cone is $\phi = 23.2^\circ$. The center pattern of each set is a circle corresponding to the reciprocal lattice vector being perpendicular to the plane of the figure. Each successive pattern represents a 10° rotation of the cone axis about the vertical axis of the figure. These 10° rotations are in opposite directions for the $\tan\psi$ and $\sin\psi$ curves. The outer black circumference of the figure corresponds to scattering at 90° for the $\sin\psi$ curves, whereas the $\tan\psi$ scaling is arbitrarily reduced in order to show more of the curves. At $\alpha = 90^\circ$, the $\tan\psi$ relationship produces a circle where α is the angle between the cone axis and the image plane. For successive 10° rotations of the cone axis, the $\tan\psi$ curves are ellipses with increasing semi-minor and semi-major axes and increasing eccentricity for $\alpha > \phi$. When $\alpha < \phi$, the $\tan\psi$ curves become hyperbolae. At $\alpha = 90^\circ$, the $\sin\psi$ relationship also produces a circle. However, successive rotations of the cone axis produce ellipses regardless of inclination angle. The $\sin\psi$ ellipses have decreasing semi-major axes and increasing eccentricity with decreasing α until the pattern collapses to a straight line at $\alpha = 0^\circ$. The $\sin\psi$

relationship has the interesting property that the length of the semi-major axis is constant regardless of inclination angle.

Fig. 8. Laue cone geometry. a) Diametral plane of Ewald sphere, b) Laue cones constructed by rotating vectors S and S_0 about σ_{hkl} .

Fig. 9. Comparison of Kossel patterns from $\sin\psi$ and $\tan\psi$ scaling relationships. Red = $\sin\psi$, blue = $\tan\psi$. Solid curves = circles or ellipses, dashed = hyperbolae, dotted = straight line. Outer circle = scattering at 90° for $\sin\psi$ relationship. Scaling of $\tan\psi$ curves is arbitrary with respect to the $\sin\psi$ curves.

3.2.2 Analysis Procedure

A single divergent-beam image contains scattering information for the entire range of wave vectors accessible to the optical microscope for a particular wavelength. Therefore, determination of crystal orientation is possible from the analysis of a single image. Consider the scattering pattern shown in Fig. 10a. The angle ψ between the optical axis (OA) and a scattered ray in a divergent-beam image is described by Eq. 2.3. In Fig. 10a, $\mathbf{r}_1$ describe the vector from the center of the image to the point on the right-hand side (RHS) scattering pattern that is radial to the center. Vector $\mathbf{r}_2$ describes the corresponding relationship for the left-hand side (LHS) pattern. These vectors lie in a plane containing the OA, σ_{hkl} , σ_{-h-k-l} , $\mathbf{S}_0$, and $\mathbf{S}$. In most divergent-beam images, analysis is performed using Kossel pairs representing scattering from σ_{hkl} and $-\sigma_{hkl} = \sigma_{-h-k-l}$. With Kossel pairs, there are two possible geometries. The optical axis will fall either between both Kossel cones or within one of the cones as shown in Fig. 10a and Fig. 10c, respectively. It is also possible to observe backscattered Kossel patterns in which complete or nearly complete ellipses are present. In this case, data can be extracted from a single ellipse, and the optical axis will fall either outside or inside the Kossel cone as shown in Fig. 11a or Fig. 11c, respectively. The angular relationships necessary to determine the crystallographic orientation are given in Table 2 for the four possible geometric cases shown in Fig. 10 and Fig. 11. In these figures and in Table 2, $\psi_1 < \psi_2$ and $\delta_1 < \delta_2$.

		θ_B	ϕ	δ_1
Kossel pair	OA outside of Kossel cones	$(\psi_1 + \psi_2)/2$	$90^\circ - (\psi_1 + \psi_2)/2$	$\phi + \psi_1$
	OA inside one Kossel cone	$(\psi_2 - \psi_1)/2$	$90^\circ - (\psi_2 - \psi_1)/2$	$\phi - \psi_1$
Single ellipse	OA outside of Kossel cone	$90^\circ - (\psi_2 - \psi_1)/2$	$(\psi_2 - \psi_1)/2$	$\phi + \psi_1$
	OA inside Kossel cone	$90^\circ - (\psi_1 + \psi_2)/2$	$(\psi_1 + \psi_2)/2$	$\phi - \psi_1$

Table 2. Angular relationships for various divergent-beam geometries.

The magnitude of the reciprocal lattice vector is related to the plane spacing by the relationship [71]

$$3.2 \quad |\sigma_{hkl}| = K \frac{1}{d_{hkl}}$$

where K is a proportionality constant between the real and reciprocal lattices and d_{hkl} is the plane spacing. For $K = 1$, Eqs. 2.1 and 3.2 can be combined to give

$$3.3 \quad |\sigma_{hkl}| = \frac{2n}{\lambda_0} \sin \theta_B$$

The orientation of σ_{hkl} with respect to the microscope frame of reference in polar coordinates is given by:

$$\delta = \phi \pm \psi_1$$

$$\begin{aligned}
3.4 \quad \varepsilon &= \sin^{-1}\left(\frac{y'}{r}\right) && \text{for } y' \geq 0 \\
\varepsilon &= -\sin^{-1}\left(\frac{y'}{r}\right) && \text{for } y' < 0 \\
\rho &= |\sigma_{hkl}| = \frac{2n}{\lambda_0} \sin \theta_B
\end{aligned}$$

where δ is the angle between σ_{hkl} and the OA, and ε is the angle in the x-y plane of the microscope frame of reference with respect to the +x-axis. The $\pm$ determination for δ and the value for θ_B are given by Table 2 for the appropriate sample geometry. Eq. 2.6 can be used to convert from polar coordinates to Cartesian coordinates.

It can be seen from this discussion that a reciprocal lattice vector corresponding to a Kossel pattern present in a divergent-beam image can be extracted by determining the point on the scattering pattern that is radial to the OA, and from knowledge of the wavelength of light used to form the image. If the plane spacing corresponding to a single Kossel pattern is known *a priori*, then σ can be extracted without its pair being present in the image. This is also possible for a single backscatter Kossel pattern in which both points that are radial to the OA can be extracted from the image. The reciprocal lattice basis vectors can be determined from σ 's using the methodologies discussed in Chapter 2.

Fig. 10. Geometry of divergent-beam patterns for a Kossel pair. a) divergent-beam pattern with the OA outside of the Kossel cones. b) scattering geometry in the plane containing the OA, σ 's, S_0 , and S for the divergent-beam pattern shown in a). c) and d) correspond to a) and b) for the case where the OA falls within one of the Kossel cones.

Fig. 11. Geometry of divergent-beam patterns for a single Kossel cone. a) divergent-beam pattern with OA outside of the Kossel cone. b) scattering geometry in the plane containing the OA, σ 's, S_0 , and S for the divergent-beam pattern shown in a). c) and d) correspond to a) and b) for the case where the OA falls within the Kossel cone.

3.3 Experimental Procedure

3.3.1 Sample

We tested our divergent-beam approach with samples prepared from the 1.15 μm -diameter PMMA/PHSA spheres described in 2.3.1 and 0.504 μm diameter PMMA/PHSA spheres described later in 6.2.2. Observations were also made of some $\sim 1\mu\text{m}$ -diameter rhodamine-dyed PMMA/PHSA spheres and some PMMA/PHSA spheres with a diameter close to that of the 0.504 μm diameter spheres. The samples were suspended in either a mixture of decalin and tetralin or in pure cis-decalin. They were load into 1-2mm wide cells as described in 2.3.1 and 6.2.2.

3.3.2 Experimental Equipment

The experimental equipment used for the divergent-beam technique is the same as for the parallel-beam technique except that the full aperture of the condenser is used rather than a moveable pinhole. For a transmitted light oil immersion condenser with $\text{NA} = 1.4$, this results in a solid illumination cone with a half-cone angle of $\sim 68^\circ$. We used both the conventionally-oriented Zeiss Axioskop/color CCD camera setup described in 2.3.2 and the rotated Zeiss Axioplan/12-bit B/W camera setup described in 6.2.1.

3.3.3 Image Processing and Data Analysis

Frame-averaged images were gathered as described in 2.3.2. Data points along Kossel cones were extracted interactively using Image-Pro Plus software (Media Cybernetics) and exported to a spreadsheet. Typically, 10-20 data points were extracted for each Kossel line, and the center of the experimental image was calculated from a best-fit circle to the maximum illumination aperture in the image. We then fitted the data to

an ellipse model using a direct least squares fitting approach due to Fitzgibbon, Pilu, and Fisher [89] implemented in *Mathematica* (Wolfram Research) [90]. Using the calculated ellipse parameters, we then solved for the vectors from the center of the image to the ellipse that were radial to the ellipse. This would typically yield 2-4 vectors, and the correct solution was picked by visual analysis of the graphed data and solutions. This correct solution constituted the radial vector related to that Kossel pattern used for the calculations described in 3.2.2.

Since it is known that the chosen fitting method can result in a bias toward low eccentricity [89], we tested the effectiveness of the algorithm using a dataset of 31 closely spaced data points from a Kossel pattern representing $<1/2$ of an ellipse, which was the typical case for our images. We performed the calculation for the entire dataset and various subsets of the data, and compared the computed radial vectors. Although the overall ellipse shape varied noticeably between datasets, the computed radial vectors agreed to within 0.5% in magnitude and 0.1° in direction as long as the dataset bracketed the intersection of the radial vector with the ellipse. Results quickly degraded when the dataset did not bracket the radial vector. However, we never encountered Kossel lines where we could not meet this constraint. Occasionally, we encountered computation singularities, usually related to datasets which were nearly linear. We found that deleting data points from one end of the dataset to roughly "balance" the number of data points on either side of the radial vector solved this problem. Since this is a somewhat arbitrary procedure, we checked the reasonableness of the result by comparing the vector to that computed for the Kossel pair, which should be anti-parallel. The resulting deviation was

always on the same order as the average deviation of anti-parallel orientations from 180° for all computed datasets, which was $<1^\circ$.

3.4 Results

All images presented in this section were acquired at 546nm. A three-fold symmetric Kossel pattern from a $1\mu\text{m}$ diameter sphere sample can be seen in Fig. 12. The particles in this sample contained rhodamine dye which was thought to have also leached into the suspending fluid when this image was taken. The dark rectangular region in this figure is the stem of a cotton swab which was inserted into the front focal plane of the condenser as a beam block. Straightforward brightfield optics were used to acquire this image.

We found that Kossel line contrast could often be enhanced by using crossed polarizers and further enhanced using DIC optics. Fig. 13 shows a comparison between brightfield optics and optimized DIC optics with a sample of $0.504\mu\text{m}$ diameter spheres in cis-decalin.

Fig. 14 is a gallery of scattering pattern examples taken from $\sim 0.5\mu\text{m}$ sphere samples. The images in Fig. 14a,c-d are from $0.504\mu\text{m}$ diameter spheres in cis-decalin. It is not known with absolute certainty whether or not the $0.5\mu\text{m}$ spheres (also in cis-decalin) used for Fig. 14b are from the same lot as the other spheres in Fig. 14, which were extensively characterized as described in 6.2.2. Fig. 15 shows the divergent-beam pattern at two exposure times for the same crystallite formed from $1.15\mu\text{m}$ spheres studied in the parallel-beam section. This figure is the divergent-beam pattern corresponding to the parallel-beam pattern shown in Fig. 3b.

Fig. 12. Divergent-beam image with swab in front focal plane of the condenser blocking a portion of the scattering. Kossel pairs are marked with pairs of white arrows having the same orientation.

Fig. 13. Comparison of divergent-beam imaging modes. a) brightfield optics and b) optimized DIC optics.

Fig. 14. Examples of divergent-beam patterns seen in colloidal crystals formed from $1/2\mu\text{m}$ -diameter spheres.

Fig. 15. Divergent-beam pattern from same crystal examined using parallel-beam technique at two different camera exposures.

3.5 Discussion

Fig. 12 demonstrates the scattering relationship between Kossel pairs. In this figure, we broke off the tip of a cotton swab and inserted the remaining stick into the front focal plane of the condenser as a beam block. Three Kossel pairs are shown with white arrows. The presence of the beam block demonstrates that light scattered by one Kossel cone is scattered into its pair and vice versa. For example, consider the lower right pair of white arrows in the figure. The dark segment adjacent to the lower right arrow corresponds to the width of the beam block, which overlaps the upper left Kossel line in the pair. Light which would have otherwise been scattered out of the upper left line into the lower right line is blocked before it can be scattered by the crystal. However, light from the corresponding segment in the lower right line is not blocked, and is scattered into the upper right Kossel line, including the region overlapping the swab.

The increase in image contrast through the use of DIC optics is readily seen by comparing the two images in Fig. 13. In Fig. 13a, we used straightforward brightfield optics, and only a few prominent Kossel patterns are apparent. In Fig. 13b, we employ DIC optics to optimize contrast, and a number of additional fine Kossel lines become visible. The DIC optics consist of crossed polarizers and a pair of Wollaston prisms between the polarizers located before the condenser and after the objective. The Wollaston prisms consist of opposing wedges of birefringent materials whose optical axes are orthogonal to each other. The upper prism is moveable to allow the adjustment of the wave front retardation of one polarization direction with respect to the orthogonal polarization. [91] Transverse movement of the upper prism results in the ability to

manipulate the contrast of divergent-beam images in similar manner to the conventional adjustment of real-space image contrast with DIC optics.

The reason that DIC optics are effective for divergent-beam images of colloidal crystals lies in the polarization dependence of light that is Bragg scattered by colloidal crystals. This phenomenon was observed by Monvoukas, Fuller, and Gast [92] and quantitatively explained by them in the context of dynamical diffraction theory for colloidal crystals interacting with visible wavelengths of light. In our work, we are not concerned with quantitative intensity measurements, but rather we need only to determine the position of Kossel patterns in our images. Therefore, it is sufficient to note that the polarization dependence of Bragg scattered light allows the contrast of Kossel patterns to be increased by the use of crossed polarizers, and that the DIC bias adjustment allows the fine tuning of this contrast for a desired feature or set of features.

Fig. 14 shows divergent-beam images from various crystallites formed from $0.5\mu\text{m}$ -spheres. The patterns seen in Fig. 14a-c represent by far the most common types of patterns observed in our samples. The common feature in these three images is the presence of sets of closely spaced fine lines. In Fig. 14a, these lines manifest varying curvature as a function of position in the image and bear a general resemblance to Kossel patterns reported by Sogami and Yoshiyama for charged colloidal spheres. [85] They describe their images that are similar to Fig. 14b as having a stacking structure with multivariate periodicity in contrast to completely random stacking. This appears to be equivalent to having stacking sequences that fall between complete randomness and either fcc or hcp stacking. Their images were consistent with scattering from crystals having close-packed layers oriented parallel to the cell walls and perpendicular to OA.

Therefore, we will adopt a working hypothesis that Fig. 14a and similar images are close to this orientation, in which $\mathbf{c}^*$ and the c-axis are parallel to the OA.

In contrast to Fig. 14a, the fine lines in Fig. 14b-c have relatively consistent curvature but adjacent lines appear to rotate forming patterns that are reminiscent of a child's "string art" project. In addition, both of these images possess a pair of lines that are significantly more intense than the others. We surmise that this strong pair of lines arise from the $\{0002\}_{\text{hcp}}$ planes. Scattering from these planes would not be visible at the wavelength used for the assumed orientation of Fig. 14a, which lacks this feature. This implies that $\mathbf{c}^*$ is tilted with respect to the OA in Fig. 14b-c. We speculate that the fine lines seen in all three images arise from rhcp Bragg rods. Scattering from these rods would produce scattering along their length with the intensity at any given point being a function of the stacking disorder. [81]

The Kossel patterns seen in Fig. 14d are quite different from the rest, exhibiting threefold symmetry about the origin. Such symmetry would be consistent with the fcc structure with the image plane parallel to a $\{111\}$ plane.

In order to test our working hypotheses concerning the interpretation of the Kossel patterns seen in Fig. 14, we will apply the analysis procedure developed in 3.2.2. To begin, we will attempt to extract reciprocal lattice points along Bragg rods from Fig. 14a. Our hypothesis will be supported if we are able to reconstruct Bragg rods which are parallel to each other and arranged with hexagonal symmetry with spacing consistent with the known particle size. We also expect the Bragg rods to be nearly parallel to the OA. Close inspection of Fig. 14a reveals that pairs of Kossel lines can be distinguished by their varying intensity and spacing. Such pairs can be thought of as arising from

discrete reciprocal lattice vectors along Bragg rods. These pairs are related by inversion symmetry through the reciprocal lattice origin. As such, these discrete pairs can be treated in the same fashion as reciprocal lattice vectors in a true 3-D crystal. Several of the Kossel line pairs used for analysis are marked with arrows in Fig. 16. We extracted data from eight Kossel pairs from one Bragg rod pair and three Kossel pairs for the remaining two Bragg rod pairs. Several views of the results are shown in Fig. 17. The blue circles are σ 's extracted from image data, and the black lines are best fit lines to these points. The red circles on the lines are $\{10-10\}$ reciprocal lattice vectors extracted from the Bragg rod fits as described in Chapter 2. The remaining red circle is the $\{0001\}$ reciprocal lattice vector calculated from the $\{10-10\}$ reciprocal lattice vectors and assuming an ideal close-packed c/a ratio. The expected hexagonal symmetry can be clearly seen in Fig. 17a. Ideally, these reciprocal lattice vectors have angles of 60° , 120° , or 180° between each other. The RSS of difference between measured and expected values for these vectors was 0.3° .

The magnitude of $\mathbf{a}^*$ was $(2.083 \pm 0.005)\mu\text{m}^{-1}$. This implies a spacing of spheres along close-packed directions in close-packed planes of $(0.554 \pm 0.001)\mu\text{m}$. Assuming $\phi = \phi_m$, we would expect this spacing to be $(0.559 \pm 0.006)\mu\text{m}$ from the particle size of $(0.504 \pm 0.005)\mu\text{m}$ measured in 6.2.2.1. These results agree to within experimental error, lending more weight to the correctness of our Kossel line interpretation. The angles between the six calculated Bragg rods vary from 0.4° to 3.7° , and the RSS of the difference between rod orientations was 1.7° . This confirms that they are parallel to within a reasonable experimental error. These results are clearly consistent with our proposed interpretation of the Kossel lines.

For Fig. 14b, our goal is to test the proposed interpretations that 1) the pair of intense Kossel lines corresponds to $\{0002\}$ planes and 2) the "string art" patterns of fine lines correspond to scattering from Bragg rods which are inclined with respect to the OA. In addition to these features, there is also an interesting trio of Kossel lines that appear to be elliptical, with nearly the entire ellipse being visible for one of them. We calculated the reciprocal lattice basis vectors in two ways. First, we used the intense Kossel pair to calculate $\mathbf{c}^*$ and a pair of the fine Kossel lines combined with the direction of $\mathbf{c}^*$ to find $\mathbf{a}^*$. Secondly, we used the intense Kossel pair and two of the elliptical lines, assuming the former was (0002) and the latter arose from the (2-1-10) and (1-210) planes. These tentative indices were used along with extracted data to calculate the basis vectors using Eqs. 2.7 - 2.9 and 2.11. The magnitude of $\mathbf{a}^*$ calculated using these two methods agreed to within $< 2\%$ and the direction of $\mathbf{a}^*$ agreed to within $< 0.5^\circ$. The magnitude and direction of $\mathbf{c}^*$ agreed exactly. Fig. 18 contains a selection of calculated Kossel lines corresponding to the primary features seen in Fig. 14b. This figure was constructed using the calculated reciprocal lattice basis vectors as described in 3.2.1. There is excellent qualitative agreement between. As anticipated, the intense Kossel pair indexes to $\{0002\}$ planes and the "string art" pattern is accurately recreated from Bragg rod scattering, especially the pattern due to the (0-11 $\bar{l}$)/(01-1 $\bar{l}$) pair. In simulating the Bragg rod patterns, we made no attempt to recreate the exact pattern of spacings and intensities, which are both a function of stacking sequence. [81] Rather, we simply calculated Kossel lines corresponding to points along the Bragg rods over intervals selected to roughly represent the scattering patterns seen in the experimental image. The trio of elliptical Kossel lines index to $\{11-20\}$ planes. It should be noted that these features can

only be formed by backscattering in the calculated crystal orientation. Since the illumination/camera geometry our experimental setup can only record forward scattered patterns, we speculate that the illumination source for the $\{11-20\}$ Kossel lines may have been incoherent backscattering from sample particles, stray reflections in the instrument, or possibly a combination of both. In any case, the good agreement between Fig. 14b and Fig. 18 further supports our proposed interpretation of observed Kossel lines. The possibility of observing backscattered Kossel lines suggests that this technique might also be useful with colloidal systems which are not index-matched and could only be probed in a backscattering mode.

From the results of the preceding discussion, we would expect Fig. 14c to represent an rchp crystal in a different orientation. The position of the pair of intense Kossel lines suggests that the crystal is oriented with $\mathbf{c}^*$ nearly orthogonal to the OA. However, there are no obvious Kossel pairs within the sets of fine lines to use for extracting $\mathbf{a}^*$, so we find that our analysis technique breaks down for this experimental image.

In Fig. 14d, we assumed an fcc structure in which (111) was nearly parallel to the image plane and the three pairs of bright Kossel lines with 3-fold symmetry were the remaining $\{111\}$ planes. The reciprocal lattice vectors for the $\{111\}$ planes extracted using these assumptions made angles of $69.7 - 70.6^\circ$ and $109.4 - 110.3^\circ$ with each other. The expected interplanar angles are 70.5° and 109.5° so the measured interplanar angles agreed with ideal fcc values to within $< 1^\circ$. Several interplanar angles differed from expected values by only 0.01° . This excellent agreement shows that the indexed planes are consistent with the fcc structure. However, we were unable to index the darker lines

that form mirror images with the inner bright Kossel lines. We compared these lines with scattering patterns from first order fcc twins to the indexed orientation with no success. We speculate that these dark lines might arise from higher order twinning, but this possibility was not pursued.

Next, we examine Fig. 15 which consists of divergent-beam images at two camera exposures of the same crystallite examined using the parallel-beam method. We again extracted the reciprocal lattice basis vectors from $\{0002\}$ and Bragg rod Kossel lines. Fig. 19 shows a number of indexed Kossel patterns corresponding to Fig. 15. Note that several more families of planes are accessible in this image compared to Fig. 14. This is because the sphere size in the sample which produced Fig. 15 is about twice the sphere size of the samples responsible for the images in Fig. 14. Hence, corresponding reciprocal lattice features are about half the size in Fig. 15. Since the same interrogating wavelength of light is used in both experiments, more reciprocal lattice points are accessible in Fig. 15. Note that the inclination of $\mathbf{c}^*$ with respect to the OA of this crystallite appears to be nearly identical to that of Fig. 14c, yet we were able to identify individual Kossel pairs arising from Bragg rods in Fig. 15, whereas we were not able to do this in Fig. 14c. It is possible that the Bragg rod(s) responsible for the primary "string art patterns seen in Fig. 14c may be nearly tangential to the Ewald sphere. We found that accuracy degraded in the parallel-beam method in this situation in the case of the $\{20-21\}$ rod. It is possible that this situation which caused difficulty with the pointwise illumination of the parallel-beam method is not compatible with the full-field illumination of the divergent-beam method. If this is the cause of the difficulty with Fig.

14c, the problem might be solved by obtained data using a shorter wavelength, and hence a larger Ewald sphere.

Fig. 20 shows the measured orientations for both the parallel-beam and divergent-beam techniques. The two techniques differ in magnitude and orientation of $\mathbf{a}_1^*$ by 0.2% and 1.3° , respectively, and of $\mathbf{c}^*$ by 0.6% and 0.2° . Thus, the two techniques are in excellent agreement with each other.

Fig. 16. Divergent-beam image from Fig. 14a showing examples of Kossel lines used in analysis. Arrows having the same orientation mark Kossel pairs.

Fig. 17. Reciprocal lattice data extracted from Fig. 16. Blue circles are extracted Bragg rod data points. Open black circle is the reciprocal lattice origin. Red circles are select reciprocal lattice points derived from the extracted data. a) view in direction of $-\mathbf{c}^*$, b) view in direction of $(\mathbf{c}^* \times \mathbf{a}_1^*)$, c) view in direction of $\mathbf{a}_1^*$.

Fig. 18. Indexed Kossel lines corresponding to Fig. 14b.

Fig. 19. Indexed Kossel lines corresponding to Fig. 15. Planes related by symmetry are grouped by color.

Fig. 20. Stereographic projection of the orientation of the crystallite in Fig. 2. The figure shows the standard (0001) hcp projection for ideal c/a . The 3-symbol indices show the corresponding fcc planes. The small symbols mark the orientation of the OA and the large symbols mark the orientation of $-\mathbf{g}$. Filled symbols are in the (0001) hemisphere and open symbols are in the (000-1) hemisphere. Red = parallel-beam results and blue = divergent-beam results.

3.6 Conclusions

We have developed a second technique to extract quantitative crystallographic data from randomly oriented colloidal crystals using a divergent-beam approach. We tested this technique on a sampling of diverse experimental images and were able to extract quantitative reciprocal lattice basis vectors in all but one case. In the failed case, we were unable to extract $\mathbf{a}_1^*$ due to the inability to distinguish Kossel pairs in the Bragg rod scattering. We suggest that useful data might have been obtained at a shorter wavelength of illuminating light. When data extraction was successful, results appeared to be accurate to about 1% for lattice parameters and to within about 2° for orientation.

Chapter 4

Comparison of Techniques

We have developed two techniques for extracting crystallographic data from randomly oriented colloidal crystals. The first technique is a parallel-beam approach and the second employs a divergent beam. The accuracy of both techniques appears to be similar. In the experiments conducted, both appeared capable of measuring lattice parameters to within about 1%. The parallel-beam method measured orientation to about 1° , and the divergent-beam method measured orientation to about 2° . However, the parallel-beam method was applied to only one crystallite, whereas the divergent-beam method was successfully applied to 4 crystallites. In most cases, the divergent-beam orientation accuracy was also within about 1° of an idealized model, and in one case, several measured angles matched predictions to within 0.01° . More data is necessary before the parallel-beam method could be declared more accurate than the divergent-beam method. When both method were applied to the same crystallite, the results matched in magnitude and orientation of $\mathbf{a}_1^*$ by 0.2% and 1.3° , respectively, and of $\mathbf{c}^*$ by 0.6% and 0.2° . Therefore, the two techniques are in excellent agreement with each other.

We found that the divergent-beam method was much easier to implement since only one experimental image at a single wavelength is necessary for data extraction, and the only instrument adjustment needed is the simple optimization of image contrast using the DIC bias screw. In contrast, several images at several wavelengths and pinhole

locations are usually required for the parallel-beam method. In addition, it is necessary to scan the pinhole over the range of possible illumination angle in order to identify candidate positions that will yield useful data. However, In one of our test images, the divergent-beam approach failed. We speculated that this failure was due to Bragg rods being tangential to the Ewald sphere, and this problem might have been avoided by using shorter wavelength illumination. However, it is possible to imagine a situation in which this remedy would not work. For a truly random rchp structure, the intensity variations are continuous along the Bragg rods. Such structures were observed by Sogami and Yoshiyama. [85] In this situation, we would not expect to see fine divisions in the "string art" patterns caused by Bragg rods. For an image containing scattering from only $\{0002\}$ and Bragg rods, which was typical for $0.5\mu\text{m}$ particles, the divergent-beam technique would likely fail regardless of illumination wavelength or crystal orientation. However, it is just as likely that the parallel-beam method would be successful in such cases since a continuous distribution of intensity would not pose a problem with pointwise illumination.

Therefore, the divergent-beam method is the preferred technique for any true 3-D crystals because it is easier to implement. For rchp structures where scattering from Bragg rods must be analyzed, the divergent-beam method is also preferred whenever there is sufficient resolution of Kossel pairs along the Bragg rods. For situations where Kossel pairs cannot be resolved, the parallel-beam approach becomes the method of choice. Therefore, between these two methods it should be possible to extract quantitative crystallographic data from any colloidal crystal whose lattice parameters are compatible with visible wavelengths. Initial tests of these techniques suggest that they

are suitable for extracting lattice parameters to within about 1% and orientation data to within about 2°.

Part II: Grain Boundary Groove Techniques Applied to Colloids in a Gravitational Field

Chapter 5

Theory

5.1 Introduction

5.1.1 Literature Review

5.1.1.1 Grain Boundary Groove Techniques

When an interface forms between two phases, the free energy of the system increases. Interfacial free energy per unit area, γ , is defined as the work required to create a unit area of interface [93]. Free energy is minimized for a system in equilibrium. [94] This results in curvature at the interface and is known as capillarity or the Gibbs-Thomson effect. Following the discussion of interfacial free energy in ref. [17],

$$5.1 \quad G = G_0 + A\gamma$$

where G is the total free energy of the system, G_0 is the bulk free energy, and A is the surface area. It follows from Eq. 5.1 that the work required produce an infinitesimal increase in surface energy is

$$5.2 \quad FdA = dG = \gamma dA + Ad\gamma$$

Dividing through by dA gives

$$5.3 \quad F = \gamma + A \frac{d\gamma}{dA}$$

For liquids, γ is independent of surface area. Therefore $F = \gamma$, i.e., surface tension is equal to surface energy. However, as pointed out originally by Gibbs [94] this is not necessarily the case for solids for which there may also be a surface stress related to the

energy required to deform the surface elastically. This point has been brought up recently by Moy and Li [95] as a general criticism of GBG methods to be discussed below. As an example, they point to experimental results for gold in which the surface stress was found to be twice as large as the surface tension. [96] However, these experiments only made measurements up to a homologous temperature (T/T_m where T_m = melting temperature) of 0.5 for their gold samples. In contrast, all GBG techniques to be discussed are conducted at T_m for a planar interface (or for hard spheres, at the melting volume fraction). It is generally accepted that atom mobility is sufficiently high for solids near the melting point to justify the assumption that surface energy can be equated with surface tension. [17, 93]

Research concerning solid-liquid interfacial energy was reviewed by Jones. [45] Experimental techniques can be broken into two broad categories: methods based on the Gibbs-Thomson effect and those based in classical nucleation theory (CNT). Methods in the first category are considered direct techniques and include the GBG techniques to be discussed in following sections. Methods based on CNT are considered to be indirect methods. In addition, Jones discusses a number of uncertainties related to the CNT approaches that make their application to measuring macroscopic solid-liquid interfacial energy questionable.

5.1.1.1.1 Isotropic Models

For the case of typical engineering materials where a phase transition is produced by cooling, $\Delta G \approx \Delta S_f \Delta T$ where ΔS_f and ΔT are the entropy of fusion and undercooling, respectively. For the 2-D case in which there is no curvature in the third dimension, the

increase in free energy, $\Delta G = \gamma/r$ where r is the radius of curvature. Equating these two expressions for ΔG , $\gamma/r = \Delta S_f \Delta T$, giving

$$5.4 \quad \Delta T = \frac{\gamma}{\Delta S_f r}$$

The interface between the solid and its melt can be stabilized in fixed thermal gradient which brackets the material's melting point. A groove forms at the intersection of the solid-liquid interface with another surface, such as the container wall or a grain boundary. This curvature is the result of interfacial energy. Fig. 21 shows the geometry for the 2-D case, that is, where the interface profile is constant along a straight groove triple line formed by the intersection of the liquid with the grain boundary. In the figure, ψ is the contact angle, as measured through the liquid, α is the inclination of the planar container boundary, and ϕ is the inclination of the tangent to the interface curve at the point where the interface intersects the container wall.

Fig. 21. Interface geometry.

Bolling and Tiller [58] worked out equations to describe this 2-D curved interface for an isotropic material in a linear temperature gradient when the system is in thermodynamic equilibrium. The following outlines their derivation of an analytical expression for the interface shape: Using Newton's expression for curvature [97], Eq. 5.4 becomes

$$5.5 \quad T(\infty, 0) - T(x, y) = -\frac{\gamma}{\Delta S_f} \frac{d^2 y}{dx^2} \left[1 + \left(\frac{dy}{dx} \right)^2 \right]^{-\frac{3}{2}}$$

where $T(\infty, 0)$ is the equilibrium melting temperature and $T(x, y)$ is the local, undercooled temperature along the interface. Equation 5.5 can be rewritten as

$$5.6 \quad y \left[1 + \left(\frac{dy}{dx} \right)^2 \right]^{\frac{3}{2}} = K^2 \frac{d^2 y}{dx^2}$$

where $K^2 = \gamma/(G\Delta S_f)$, and G is a linear temperature gradient, $\Delta T/\Delta y$, in the direction of the y -axis. Eq. 5.6 can be integrated to yield

$$5.7 \quad \frac{y^2}{2} = -K^2 \left[1 + \left(\frac{dy}{dx} \right)^2 \right]^{-\frac{1}{2}} + K^2 B$$

For a material with an isotropic interfacial energy, the boundary condition $y' = 0$ when $y = 0$ yields $B = 1$. A solution to Eq. 5.7 for $B = 1$ is

$$5.8 \quad x = f(y) = K \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right] - (4K^2 - y^2)^{\frac{1}{2}} + A$$

where A is a constant of integration. For the boundary condition $x = 0$ at $y' = \infty$,

$$5.9 \quad A = K(\sqrt{2} - \ln(\sqrt{2} + 1))$$

Combining eqs. 5.8 and 5.9 gives

$$5.10 \quad x = f(y) = K \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right] - (4K^2 - y^2)^{\frac{1}{2}} + K[\sqrt{2} - \ln(\sqrt{2} + 1)]$$

which describes an interface whose "nose" lies on the y -axis.

For fixed entropy of fusion and temperature gradient, eq. 5.10 yields a family of curves that vary with γ . Fig. 22 shows a family of curves spanning two order of magnitude in γ .

Fig. 22. Family of interface curves.

By fitting an experimental interface to Eq. 5.10, γ can be determined using nonlinear regression. Bolling and Tiller also addressed some limited cases of anisotropy, though it appears that all experimental applications of their work have assumed isotropy. Bolling and Tiller also state that their approach could be adapted to specific departures from thermodynamic equilibrium and to non-linear temperature gradients as long as the temperature gradient could be expressed as a polynomial in the coordinate axis perpendicular to the planar solid-liquid interface.

Bolling and Tiller's work was first applied experimentally by Jones and Chadwick [98], who used this technique to measure the interfacial energy of several transparent materials. The technique was refined by Nash and Glicksman [99] to account for the typical situation where $\kappa_s \neq \kappa_m$, where κ is the thermal conductivity and

the subscripts s and m denote the solid and melt, respectively. Schaefer, Glicksman and Ayers [59] estimated the accuracy of this refined technique to be about $\pm 6\%$. In contrast, they point out that it is difficult to find systems in which literature values of γ for independent methods agree to within $\pm 50\%$.

A more general form of Eq. 5.10 is given by Schaefer, Glicksman, and Ayers [59], which also depends on groove root contact angle:

$$5.11 \quad \mu = \frac{1}{2} \ln \left[\frac{-\eta}{1 - (1 - \eta^2)^{1/2}} \right] - (1 - \eta^2)^{1/2} + \frac{1}{2} \ln \left(\tan \frac{\xi}{2} \right) + \cos \xi$$

where $\mu = x/2K$, $\eta = y/2K$, $\xi = (\pi - \Psi)/4$, and Ψ is the dihedral angle at the groove root of two symmetric grain boundaries where $\Psi = 2\psi$. Here $K^2 = \gamma/(-G\Delta S_f)$, where G is the gradient of ΔT (rather than T) along the y -axis where $\Delta T = (T - T_m)$ and T_m is the melting temperature. For $\Psi = 0$, Eq. 5.11 reduces to a form equivalent to Eq. 5.10 and gives a relationship for an experimentally useful parameter, the groove depth, h ,

$$5.12 \quad h = \left(\frac{2\gamma}{G\Delta S_f} \right)^{\frac{1}{2}} = \sqrt{2}K$$

It appears that in practice, the entire groove shape is typically analyzed using Eq. 5.10 rather than depending on a groove depth measurement using Eq. 5.12 due to ambiguity in determining the exact root of a grain boundary.

A similar method of measuring γ relies on measuring the contact angle at the groove root. [100] However, contact angle measurements are usually subject to relatively large measurement uncertainties. Furthermore, whenever the grain boundary energy is greater than twice the solid-melt surface energy, the contact angle goes to zero. This

typically limits contact angle methods to low angle grain boundaries, making the approach of fitting an entire groove profile a superior method.

A problem similar to the solid/liquid interface in a temperature gradient is the shape of a liquid/gas interface in a gravitational field. Solutions to the latter problem in 2-D have been given by Bankoff [101] and McNutt and Andes [102]. Their approaches are equivalent to beginning with the LaPlace -Young equation instead of the Gibbs-Thompson equation used in the thermal gradient case. The LaPlace –Young equation is $\Delta P = \gamma(1/r_1 + 1/r_2)$ where r_1 and r_2 are the two radii of curvature [103]. Both solutions are equivalent to Eq. 5.8 for $K^2 = \gamma/\Delta\rho g$ where $\Delta\rho$ is the density difference between the liquid and gas and g is the acceleration due to gravity. Bankoff gives a solution for the entire interface shape without solving for the integration constant, which determines the valid segment of the interface for given boundary conditions. McNutt and Andes give a solution for an interface contacting a vertical wall. McNutt and Andes write the solution as

$$5.13 \quad x = f(y) = \frac{K}{2} \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right]^2 - (4K^2 - y^2)^{\frac{1}{2}} + A$$

This solution is more general than Eq. 5.8 because it generates a pair of curves that are symmetrical about the x-axis. This addresses a wider range of physical problems than Eq. 5.8. For example, Eq. 5.13 can be used to describe systems in which the liquid phase is either wetting or non-wetting and is denser than the second phase, whereas Eq. 5.8 can only address the non-wetting case. The McNutt and Andes boundary conditions for interface contact with a vertical wall (i.e., parallel to the y-axis) are

- I. $y = 0$ at $y' = 0$
- II. $y = h$ at $y' = \cot \psi$
- III. $x = 0$ at $y = h$

where h is the difference between liquid levels at the wall and at infinity. Boundary conditions I and II applied to Eq. 5.7 yield

$$5.14 \quad h = \pm K \sqrt{2(1 - \sin \psi)}$$

which reduces to Eq. 5.12 for $\psi = 0$. Eq. 5.14 and boundary condition III can be used to determine the constant of integration in Eq. 5.13, though McNutt and Andes stopped short of giving an analytical form for the constant.

The thermal gradient and gravitational field problems are generalized by Arbel and Cahn [104]. For isotropic surfaces, a nonplanar surface balanced against a known variable $\Delta\Omega_V$ is in equilibrium when

$$5.15 \quad \gamma(\kappa_1 + \kappa_2) = -\Delta\Omega_V$$

where κ_1 and κ_2 are principle curvatures and

$$5.16 \quad \Delta\Omega_V \equiv \Omega_{V1} - \Omega_{V2}$$

where the numerical subscripts identify the two phases involved and Ω_V is the surface free energy, which is minimized at equilibrium. For the temperature gradient problem,

$$5.17 \quad \Delta\Omega_V = \frac{\Delta S_f \Delta T}{V_s}$$

where V_s is the molar volume. For the gravitational field problem,

$$5.18 \quad \Delta\Omega_V = -\Delta P$$

where ΔP is the pressure difference across the interface. This generalized approach will be used in section 5.2.1 using 5.15 as the starting point for developing a generalized solution for an equilibrium interface shape.

GBG approaches have been applied to a number of atomic and molecular systems. *In-situ* imaging has been used to take measurements in transparent systems [59, 98, 105-111], and post-experiment sectioning has been used in studies with opaque materials [58, 99, 112-119].

5.1.1.1.2 General Models

In addition to the isotropic models discussed in the last section, several models have also been developed that can also accommodate surface energy anisotropy. In an anisotropic material, γ is a function of crystallographic orientation. The most typical representation of anisotropy is a Wulff plot in which a surface is defined by vectors emanating from a common origin whose directions correspond to the normal vectors of crystal planes. [120] The length of each vector is proportional to the magnitude of γ , resulting in a scalar function $\gamma(\hat{n})$. Anisotropy in γ is of central importance in the area of solidification where it has been shown that dendritic growth requires anisotropic γ . [121-128]

Arbel and Cahn developed the concept of a capillarity vector, $\xi(\hat{n})$, where $\hat{n}$ is the surface normal [129, 130]. This approach is not restricted to cases of isotropic surface energy. $\xi(\hat{n})$ has the property that γ is the magnitude of ξ along $\hat{n}$, and the component of ξ tangent to the surface is a torque term, $d\gamma/d\theta$, which arises when the

surface energy is anisotropic [17]. Arbel and Cahn show that Eq. 5.15 can be rewritten as [104]

$$5.19 \quad \nabla \cdot \xi = \gamma(\kappa_1 + \kappa_2)$$

where $\nabla \cdot \xi$ is the surface divergence of ξ . Eq. 5.19 reduces to Eq. 5.15 when γ is isotropic. Arbel and Cahn show that the components of ξ can be written as

$$5.20 \quad \xi_x = -\int_{x_0}^x \Delta\Omega_V dx + (\xi_x)_{x=x_0}$$

$$5.21 \quad \xi_y = -\int_{x_0}^x W' \Delta\Omega_V dx + (\xi_y)_{x=x_0}$$

where the shape of the GBG is given by $y = W(x)$ and $W' = dW/dx$. If $\Delta\Omega_V$ is linear in W then

$$5.22 \quad \Delta\Omega_V = -BW$$

$$5.23 \quad \xi_x = B \int_{x_0}^x W dx + (\xi_x)_{x=x_0}$$

$$5.24 \quad \xi_y = \frac{1}{2} B [W^2(x) - W^2(x_0)] + (\xi_y)_{x=x_0}$$

These conditions are met for both the gravitational field problem and the linear temperature gradient problem when $\kappa_s = \kappa_m$. For a gravitational field,

$$5.25 \quad B = g\Delta\rho$$

and for a linear temperature gradient, G ,

$$5.26 \quad B = G\Delta S_f$$

Equations 5.23 and 5.24 are particularly useful to the experimentalist because they can be expressed in terms of distances and areas on a micrograph and the components of ξ at $x = x_0$. This is illustrated in Fig. 23 for point P at (x, w) . The integral in Eq. 5.23 is equal

to by the red shaded area between $x = 0$ and $y = W(x)$ over the interval from x_0 to x where w_0 and w are the distances between the x -axis and points P_0 and P , respectively.

Fig. 23. Geometry of the Arbel-Cahn method (after ref. [104]).

For crystal having point groups with at least two symmetry axes, a mirror plane perpendicular to a symmetry axis, or 3 orthogonal mirror planes, symmetry can be exploited to determine the components of the reference vector ξ_0 . These conditions hold true for 22 of the 32 point groups and include the $m\bar{3}m$ and $6/mmm$ point groups, which correspond to the fcc and hcp close-packed structures, respectively. An example of this is illustrated on the LHS of Fig. 23 for the case where a symmetry axis is perpendicular to the plane of the figure. The normal vectors of the surface are parallel to ξ when ξ lies along symmetry axes contained in the x - y plane since the symmetry elements of any physical property a crystal must include the symmetry elements of the point group of the crystal according to Neumann's Principle [131]. If vectors A and B in Fig. 23 are related by symmetry, then Arbel and Cahn showed that the components of ξ_A and ξ_B are given by

$$5.27 \quad \xi_{Ax} = -\frac{BW'_A}{W'_A - W'_B} \left[a_{AB} + \frac{1}{2} W'_B (y_A^2 - y_B^2) \right]$$

$$5.28 \quad \xi_{Ay} = \frac{B}{W'_A - W'_B} \left[a_{AB} + \frac{1}{2} W'_B (y_A^2 - y_B^2) \right]$$

$$5.29 \quad \xi_{Bx} = -\frac{BW'_B}{W'_A - W'_B} \left[a_{AB} + \frac{1}{2} W'_A (y_A^2 - y_B^2) \right]$$

$$5.30 \quad \xi_{By} = \frac{B}{W'_A - W'_B} \left[a_{AB} + \frac{1}{2} W'_A (y_A^2 - y_B^2) \right]$$

where a_{AB} is the red shaded area on the LHS of Fig. 23. For the special case where one of the symmetry axes coincides with the y-axis, these equations simplify even further. If vector $\mathbf{A}$ in Fig. 23 were vertical, then $W'_A = 0$, $y_A = 0$, $x_A \rightarrow \infty$, and Eqs. 5.27 - 5.30 reduce to

$$5.31 \quad \xi_{Ax} = 0$$

$$5.32 \quad \xi_{Ay} = B \left(\frac{1}{2} y_B^2 - \frac{a_{AB}}{W'_B} \right)$$

$$5.33 \quad \xi_{Bx} = Ba_{AB}$$

$$5.34 \quad \xi_{By} = -B \frac{a_{AB}}{W'_B}$$

where in this case W'_B is equal to the negative of the tangent of the angle between the two symmetry directions.

Despite the experimental simplicity of the Arbel-Cahn approach, only 3 applications of it to experimental systems appear in the literature. It has been applied one time each to succinonitrile [132], helium [133], and a liquid crystal [134].

In addition to the Arbel-Cahn method, the equilibrium shape technique is also able to measure anisotropy in γ by measuring the shape profiles of either liquid or solid droplets entrained in the coexisting solid or liquid phase at equilibrium conditions. A recent summary of experimental results is given by Napolitano, Liu, and Trivedi. [135] This technique is based on the relationship

$$5.35 \quad \frac{\gamma_1}{\gamma_2} = \frac{r_1}{r_2}$$

where r_1 and r_2 are experimentally measured radii. A normalized interfacial energy can be expressed as

$$5.36 \quad \bar{\gamma}(n) = \frac{\gamma(n)}{\gamma_0}$$

where $\gamma(n)$ is the interfacial energy of a crystallographic plane whose normal is given by $\mathbf{n}$ and γ_0 is the mean interfacial energy averaged across all planes. Symmetry considerations allow this equation to be expressed in terms of spherical harmonics. For fcc materials, Eq. 5.36 for planes perpendicular to $\langle 100 \rangle$ is commonly approximated as

$$5.37 \quad \bar{\gamma}(n) = 1 + \varepsilon_4 (\cos 4\theta)$$

where ε_4 is an anisotropy parameter related to the 4-fold symmetry about the $\langle 100 \rangle$ direction and is generally $\ll 1$. This parameter can be calculated from experimental data from the relationship [135]

$$5.38 \quad \varepsilon_4 = \frac{\Delta - 1}{\Delta + 1}$$

where $\Delta = r_{\max}/r_{\min}$.

Several other studies on grain boundary grooves in anisotropic systems are pertinent to this work. Avron, Taylor, and Zia performed a theoretical study of the equilibrium shape of crystals in a gravitational field in which the crystal/wall interface was perpendicular to gravity. [136] Their results pertinent to our work are 1) facets should only appear in a gravitational field for orientations exhibiting faceting without gravity except for a possible horizontal facet and 2) a possible horizontal equilibrium shape is that of infinitesimally corrugated facets. Voorhees, et al. performed a theoretical study of the shape of GBGs in a temperature gradient for anisotropic systems. [137] The key assumptions in their analysis were that $\kappa_s = \kappa_m$ and that the groove profile was 2-D. They found that both groove shape and groove depth vary as a function of crystal orientation in anisotropic systems. They also quantified the degree of anisotropy associated with the existence of missing plane orientations in the groove profile for a crystal with fourfold symmetry. They describe γ as a function of orientation, θ , about a fourfold axis with the equation

$$5.39 \quad \bar{\gamma}(\theta) = 1 + \varepsilon_4 \cos[4(\theta + \theta_0)]$$

where θ_0 is a phase angle. They show that missing orientations first appear for the fourfold case when

$$5.40 \quad \bar{\gamma} + \frac{d^2 \bar{\gamma}(\theta)}{d\theta^2} = 1 - 15\varepsilon_4 \cos[4(\theta + \theta_0)]$$

This expression yields missing orientations for $\varepsilon_4 > 1/15$. These missing orientations result in kinks in the groove profile which have the appearance of facets, but they actually possess slight curvature on either side of the kink.

Napolitano, Liu, and Trivedi [135] extended the work of Voorhees, et al. by deriving a coupled groove solution, addressing the interaction between the two curved interfaces associated with the intersection of a grain boundary with the solid-melt interface. They began with uncoupled numerical solutions similar to Voorhees, et al. for each groove and then searched for the lowest energy configuration using groove depth and grain boundary angle as parameters. They also assumed $\kappa_s = \kappa_m$ and a 2-D geometry. They assumed pure tilt boundaries, although the approach can be generalized to any type of grain boundary. They found that groove depth, groove angle, and groove root position vary systematically with grain boundary energy, grain orientation, and the anisotropy of γ .

5.1.1.2 Hard Sphere Colloids

The simplest form of an interparticle potential is the hard sphere potential. [138] In a hard-sphere system, the particles are infinitely repulsive when they touch, but their interaction equals zero otherwise. The hard-sphere potential is an idealized concept, and it is impossible to have perfectly hard spheres in a physical system. However, we will use the convenient description “hard spheres” in reference to colloidal systems with it being understood that in reality they are “slightly soft”. [16, 139, 140]

At first glance, the hard sphere potential appears to be a gross oversimplification of atomic and molecular potentials. When dealing with the condensation of a gas to form a liquid, it is true that attraction between atoms plays a key role. [141] However, in dealing with the behavior of condensed states of matter (liquids and solids), hard-sphere systems turn out to be very good models of atomic behavior and are frequently employed in condensed matter physics [138] and crystal chemistry [142]. In fact, hard-sphere

colloidal suspensions represent the simplest physical system known to exhibit crystallization. [66] It is the simplicity of a hard-sphere system that makes it the ideal tool for studying fundamental processes in liquids and solids by following the principle of working from the simple to the complex when solving difficult problems. In particular, hard spheres are a good model system for studying materials composed of similarly charged ions with close-packed structures, such as many metals and intermetallic compounds.

5.1.1.2.1 Phase Behavior

The hard-sphere phase transition was first suggested in 1939 by Kirkwood [143] and verified in 1957 by the molecular dynamics calculations of Alder and Wainwright [144] and the Monte Carlo simulations of Wood and Jacobson [145]. This transition, sometimes called the Kirkwood-Alder transition, was first observed in a colloidal system by Hachisu and Kobayashi [146] using charge-stabilized spheres. In 1986, the hard-sphere transition was first observed with sterically stabilized spheres by Pusey and van Megen [16]. Sterically stabilized suspensions of PMMA/PHSA particles in decalin and tetralin have been confirmed to closely follow hard-sphere behavior in experiments by Phan, et al. [60]. This was done by comparing the equilibrium density profile of suspensions via x-ray densitometry with the predictions of theoretical hard-sphere equations of state.

A coarse-grained approach is typically taken in dealing with the thermodynamics of colloidal phase transitions, as discussed by Pusey [4] and Poon and Pusey [5]. The discussion of this paragraph closely parallels the treatment of this topic by these authors. In this coarse-grained approach, the suspending liquid is viewed as an inert continuum

that defines macroscopic properties such as density and dielectric constant. The thermodynamic properties of interest are the excess properties of the system that remain after the properties of the fluid are subtracted away. For example, osmotic pressure Π is the thermodynamic variable of interest in colloidal systems rather than absolute pressure. Volume fraction, ϕ , the fraction of total volume occupied by spheres, is often used rather than absolute volume or density. This is primarily because it is the single important variable which the experimentalist can control. Experiments with colloids are typically conducted under conditions of constant volume, rather than the usual situation of constant pressure in most material science applications. Therefore, the appropriate equation for free energy in colloidal systems is the Helmholtz free energy, $A = E - TS$, where E is the internal energy, T is the absolute temperature and S is the entropy. As usual, phases may co-exist at equilibrium when the osmotic pressure, temperature, and chemical potential of both states are equal. Fig. 24 shows a schematic of the equilibrium phase diagram for monodisperse hard-spheres in a temperature vs. volume fraction representation. There are four phase regions: a colloidal fluid phase, a fluid-solid coexistence regime, a crystalline solid phase, and a glassy phase. As usual, tie lines (isotherms) in the coexistence region connect equilibrium volume fractions. The phase boundaries are vertical and intersect the volume fraction axis at a freezing volume fraction ϕ_f and a melting volume fraction ϕ_m , which will be discussed in more detail below. The implication of the vertical phase boundaries is that hard-sphere phase transitions are independent of temperature. This can be seen from the Helmholtz free energy. For a hard-sphere system, kinetic energy comprises the only contribution to internal energy E , which is directly proportional to temperature. Therefore, $A = T(\text{constant} - S)$.

Temperature is therefore merely a scaling factor that affects the rate at which a colloidal system moves towards equilibrium, but does not vary the shape of the equilibrium phase diagram. The topology of this phase diagram is similar to that commonly seen in T - X binary phase diagrams even though monodisperse hard spheres are treated as a one component system. This is because both Fig. 24 and common T - X phase diagrams incorporate one variable which must be identical for phases in thermodynamic equilibrium (temperature) and one which does not have this requirement (volume fraction and composition). [5, 147]

Fig. 24. Phase diagram for monodisperse hard spheres in 1-g.

The accepted values for the freezing and melting transitions for monodisperse spheres are $\phi_f = 0.494$ and $\phi_m = 0.545$, respectively. These values were set by the Monte Carlo simulations of Hoover and Ree. [148] Below ϕ_f , spheres exhibit no long-range order and can be viewed as a colloidal fluid. For $\phi_f < \phi < \phi_m$, regions of long range order between the spheres (colloidal crystals) are in equilibrium with regions of colloidal fluid forming a two-phase or coexistence region in the phase diagram. Composition in the coexistence region can be found as usual by using the lever rule with ϕ of the constituent phases corresponding to the respective values at the phase boundaries. Above ϕ_m , the

crystalline state is the equilibrium state. In 1-g, a glass transition has been observed to begin at $\phi = 0.58$ extending up to about $\phi = 0.63$, which is the volume fraction of random close packing (rcp) as shown below the volume fraction axis. This glassy state is thought to be a metastable state. In recent microgravity experiments, high volume fraction samples which remained glassy for over a year in 1-g readily crystallized in μg . [149, 150]

The degree of polydispersity in a colloidal sample affects the phase diagram and is defined as the standard deviation of the particle size distribution divided by the mean radius. Increasing polydispersity results in shifts of ϕ_f and ϕ_m to higher values and modifies the width of the coexistence regime. [151, 152] If the polydispersity rises above 0.057, formation of the crystalline state is not possible. [152]

It can be seen that ϕ is somewhat analogous to T in an atomic system. A colloidal crystal at $\phi_{cp}=0.74$ can be compared to an atomic material at absolute zero where the atoms possess no thermal energy and are therefore fixed in place. As volume fraction decreases, the crystal lattice expands until the melting point ϕ_m is reached. It is intriguing that crystallization takes place in hard-sphere systems in the absence of an attractive potential. Fundamentally, only a repulsive force is required (given the condition of constant volume) for crystallization to occur. A simplified system that still exhibits the phenomena of interest is exactly what is sought in a good model system.

Both theoretical and experimental work have been performed on the nucleation and growth of hard-sphere crystals. [18, 19, 153-155] Several studies have been performed on shear-induced melting [64] and ordering of hard-sphere colloids [156, 157]. Also, studies have been performed on the morphology of homogeneously nucleated hard-

sphere crystals [158], and on the macroscopic behavior of columnar crystals grown from sedimenting suspensions [159, 160]. Recent microgravity studies have yielded interesting results including the observation of crystallization in samples that remain glassy indefinitely in normal gravity, discovery of growth instabilities in hard-sphere crystals in co-existence samples, and observation of substantial interaction between growing crystallites. [149, 150, 161-163]

Microscopic studies in the bulk of colloidal suspensions have been performed. Most have used fluorescent-dyed spheres and confocal microscopy to study not only colloidal crystals [21, 25, 66, 164-166] but also colloidal glasses. [68, 69, 167-171] Relatively few studies have employed conventional optical microscopy to study index-matched hard-sphere systems. [67, 70, 157, 172]

5.1.1.2.2 Structure

The structure of hard sphere colloids has been studied using the visible-light equivalent to x-ray powder analysis. A polycrystalline suspension is illuminated with a laser beam and intensity measurements are made with a photomultiplier tube rotated about the sample on a goniometer. After compensating for the single-particle form factor, the Bragg peaks of an intensity vs. scattering angle plot can be indexed to determine the crystal structure. The structure of crystals formed in monodisperse sterically stabilized suspensions has been found to consist of randomly stacked planes of close-packed hexagonal layers [61] as discussed in 2.5.1. Values of the stacking parameter α for colloidal crystals typically range from ~ 0.5 - 0.6 [5], which represent quite significant departures from ideal hcp or fcc structures compared to close-packed atomic materials where, for example, a value of $\alpha = 0.1$ for hcp cobalt [79, 173] is considered

large (see 2.5.1 for a discussion of the stacking parameter, α). This would indicate that the free energy difference between the hcp and fcc structures in a hard-sphere system is quite small, but would tend to favor fcc, which is indeed the indication of theoretical calculations (e.g., refs. [174, 175]). Variations of α with ϕ and time are topics of current research. In general, α is observed to move from 0.5 (completely random stacking) toward fcc as ϕ moves from the freezing transition toward both higher and lower values. [5] Alpha also tends to move toward fcc over time in both 1-g [5, 80] and μg [62].

5.1.1.2.3 Interfacial Energy

For hard spheres, surface energy values are typically reported in nondimensional form as $\gamma\sigma^2/k_B T$ where σ is the particle diameter, k_B is the Boltzmann constant and T is absolute temperature. In this work, we will refer to this reduced surface energy commonly referenced in the literature as γ_{rl} . A number of theoretical predictions and a few experimental values for γ_{rl} have been published. These results are summarized in Table 3 and Fig. 25. All of these works assume the fcc structure in the crystalline phase.

The majority of computer simulations are based on density functional theory [30, 31, 32, 36, 38, 176]. The remaining computer simulations consisted of three molecular dynamics simulations [35, 39, 42] and two Monte Carlo simulations [40]. Calculation of γ_{rl} for a planar solid-liquid interface in a hard sphere system was the primary purpose of most of these efforts. Exceptions include the extrapolation to the hard sphere limit for adhesive spheres [35] and repulsive potentials [42], extrapolation to a planar interface from finite curvatures [40], and the recasting of results for a Lennard-Jones potential [177] in terms of an effective hard sphere diameter [37]. In addition to these simulations, Marr predicted values based on Turnbull's empirical correlation [178] which predicts that

$\gamma \sim 0.45\Delta H\rho_s^{2/3}$ for metals where ΔH is the latent heat of fusion and ρ_s is the solid phase density. Marr applied this correlation to data from early molecular dynamics [179] and Monte Carlo [148] simulations.

In contrast to the numerous computer simulations, only three experimental values have been published, all in colloidal systems using indirect methods based on CNT. The first experimental value for γ_{rl} was published by Marr and Gast [43] from the concentration-dependent induction times of nucleation experiments by Dhont, Smits, and Lekkerkerker [180] using silica spheres. CNT predicts that $\ln(t_i) \propto \gamma^3$ where t_i is the incubation or induction time for crystal nucleation. Palberg [44] used the same approach as Marr and Gast with several sizes of PMMA/PHSA spheres including data reported by Harland and van Megen [181]. The third experiment was by Gasser, et al. [21] who derived γ_{rl} from the equilibrium distribution of crystal nuclei surface area using the CNT prediction that $\ln(N(A)) \propto A\gamma$ where $N(A)$ is the number of equilibrium nuclei with surface area, A .

Table 3 compares published data for the magnitudes of γ_{rl} for three low index planes (when reported); an average value for γ_{rl} , γ_0 ; an anisotropy parameter, ϵ_4 , described in 5.1.1.1.2; and a comparison of the relative magnitudes of γ_{rl} for the low index planes. Fig. 25 graphs the values of γ_0 as a function of year published. It should be noted that this is not a perfect comparison since the value for γ_0 was derived in several different ways depending on the available data. In studies which did not (or could not) address anisotropy, γ_0 represents the single published value. Where data was published for more than one crystal plane, γ_0 is the mean value of the available data. Only in the case of the 2005 Davidchack and Laird study [42] does γ_0 represent a value for γ

averaged over all crystallographic planes. However, it is still useful to make a top-level comparison of results using γ_0 despite these differences. It can be seen from Table 3 and Fig. 25 that values for γ_0 range from 0.28 to 4.0. However, the majority of the results fall into a much narrower range of 0.28 to 0.70. Within this narrower range, results cluster primarily around values of about 0.30 and 0.55.

Only the computer simulation results of McMullen and Oxtoby [30, 31] and the experimental results of Gasser, et al. [21] fall outside the narrower range of 0.28 to 0.70. McMullen and Oxtoby were the very first to attempt calculations of γ and they clearly state in their original work [30] that their results should be viewed as an upper bound. Their results of 1.765 and 4.0 do indeed comprise an upper bound of all results reported to date. Conversely, the experimental result of 0.11 due to Gasser, et al. is the lowest of all values reported to date. It is lower than the other experimental values by about a factor of 5 and lower than the nearest simulation value by about a factor of 3. They speculated that this low value may have been due to a slightly softened interparticle potential due to leakage of fluorescent dye from the particles into the suspending fluid. However, this speculation conflicts with the most recent work by Davidchack and Laird [42] who computed γ_0 over the entire range of repulsive potentials for which the fcc structure is stable and found that γ_0 fell within the range of 0.530 ± 0.003 and 0.810 ± 0.005 . When extrapolated to the hard sphere limit, Davidchack and Laird's result of 0.573 ± 0.005 is in good agreement with many of the other studies including the other experimental values. Another possibility is that γ for finite curvature is substantially different from γ for a planar interface. However, Cacciuto, Auer, and Frenkel [40] showed that interfacial energy should increase, not decrease, with

decreasing nucleus size. Again, their result of 0.616 ± 0.003 is in good agreement with many other results. Gasser, et al. derived their value for γ from data on subcritical nuclei, and the Cacciuto, Auer, and Frenkel work predicts that such data should yield higher, not lower values. Therefore, subsequent work does not offer any explanation of the unusually low result obtained by Gasser, et al.

It is useful to compare the range of published values for γ_0 to ranges for atomic and molecular materials. Schaefer, Glicksman and Ayers point out that it is difficult to find systems in which literature values of γ for independent methods agree to within $\pm 50\%$ [59]. The range for hard spheres (excluding the outliers discussed above) of 0.28 to 0.70 can be written as 0.49 ± 0.21 , which is a variation of $\pm 43\%$. Therefore, the variation among the majority of the published hard sphere results is in line with the general trend for atomic and molecular materials.

In contrast to the reasonable agreement among hard sphere results for γ_0 , predictions concerning anisotropy vary considerably. Values for ϵ_4 in Table 3 were computed using Eq. 5.38 with γ_{100} and γ_{110} for $\gamma_{\max}$ and $\gamma_{\min}$ values. Note that there is disagreement in Table 3 concerning the order of magnitudes between these planes. This point will be discussed later. It can be seen from Table 3 that values for ϵ_4 range from 0 to 0.077. These results range from complete isotropy within the resolution of the method used for the calculation to rather high anisotropy with respect to measured or calculated values for atomic or molecular systems. For comparison, a representative low anisotropy for an fcc atomic system is $\epsilon_4 = 0.0097 \pm 0.0008$ for Al-4.0 wt%Cu. [135] A representative high anisotropy for an fcc system is 0.05 for polyvinyl alcohol (PVA). [126] Both of these results were determined experimentally using the equilibrium shape

method. Computer simulation results for several fcc metals fall between these values. For example, molecular dynamics results for ϵ_4 are 0.014 ± 0.002 , 0.016 ± 0.003 , 0.018 ± 0.003 , and for Ni [182], Ag [183] and, Au [183], respectively. It can be seen from these comparisons that all of the of hard sphere results for ϵ_4 appear to be reasonable, but the differences in magnitude across the hard sphere anisotropy range are significant.

In addition to considerable differences in hard sphere values for ϵ_4 , there is considerable disagreement in the order of γ -values for the (100), (110), and (111) planes. For the six studies that reported values for all three planes and showed measurable anisotropy, four of the six possible permutation of plane ordering are represented. Simulation results for Al [184], Au [183], Ag [183], Ni [182], Ni-Cu [182] and the Lennard-Jones potential [185] all predict $\gamma_{100} > \gamma_{110} > \gamma_{111}$. Only three of the hard sphere studies predicted this order. [34, 41, 42]

The literature to date for hard sphere interfacial energy shows a clear need for additional experiments to aid in sorting out many differences. Outstanding issues include the magnitude of γ_0 , the degree of anisotropy, and the ordering of γ -values for low index planes. However, indirect experiments based on CNT are not able to address anisotropy questions. In addition, a number of issues have been identified in regards to measuring γ using CNT assumptions. [45] In contrast, we expect to be able to address all three questions using the GBG approaches to be developed in this work.

Theory/Computer Simulations		method	γ_{100}	γ_{110}	γ_{111}	γ_0	ϵ_4	relative magnitudes	Ref.
McMullen and Oxtoby (1988)		DFT	1.766	1.767	1.762	<i>1.765</i>	~ 0	isotropic	[30]
Oxtoby and McMullen (1988)		DFT			4.00	4.00			[31]
Curtin (1989)		DFT	0.66(2)		0.63(2)	<i>0.56(2)</i>		$\gamma_{100} \succ \gamma_{111}$	[32]
Marr and Gast (1993)		DFT			0.60(2)	0.60(2)			[33]
Ohnesorge, Lowen, and Wagner (1994)		DFT	0.35	0.30	0.26	0.30	0.077	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[34]
Marr and Gast (1995)		DFT	0.70(1)	0.70(1)	0.70(1)	<i>0.70(1)</i>	0	isotropic	[35]
Kyrilidis and Brown (1995)		DFT	0.34	0.32	0.37	0.34	0.030	$\gamma_{111} \succ \gamma_{100} \succ \gamma_{110}$	[36]
			0.35	0.33	0.37	0.35	0.029		
			0.28	0.25	0.30	0.28	0.057		
Marr (1995)		EC				0.56			[37]
						0.54			
Marr (1995)		MD	0.53(3)	0.56(3)	0.55(3)	<i>0.55(3)</i>	0.028	$\gamma_{110} \succ \gamma_{111} \succ \gamma_{100}$	[37]
Choudhury and Ghosh (1998)		DFT			0.33	0.33			[38]
Davidchack and Laird (2000)		MD	0.62(1)	0.64(1)	0.58(1)	<i>0.61(1)</i>	0.016	$\gamma_{110} \succ \gamma_{100} \succ \gamma_{111}$	[39]
Cacciuto, Auer and Frenkel (2003)		MC				0.616(3)			[40]
Mu, Houk, and Song (2005)		MC	0.64(2)	0.62(2)	0.61(2)	0.62(2)	0.016	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[41]
Davidchack and Laird (2005)		MD	0.592(7)	0.571(6)	0.557(7)	<i>0.573(5)</i>	0.018	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[42]
Experiments									
Marr and Gast (1994)		IT				0.55(2)			[43]
Palberg (1999)		IT				0.50(1)			[44]
						0.54(3)			
Gasser, et. al (2001)		SA				0.11			[21]

Table 3. Summary of published values of γ_{rl} for hard spheres. DFT = density functional theory, EC = empirical correlation, MC = Monte Carlo, MD = molecular dynamics, IT = induction time, SA = equilibrium distribution of surface area. Values in parentheses are error bounds of the last significant digit. Italicized values for γ_0 are averaged values of the preceding columns.

Fig. 25. Published values of γ_{rl} . Results of theoretical calculations and computer simulations are shown as circles and experimental results are triangles. Abbreviations are the same as in Table 3. Inset: Subset of main graph showing values where $\gamma < 1$. Error bars are shown where reported.

5.2 Isotropic Theory for Colloids in a Gravitational Field

5.2.1 Development and Solution of General Equation for Interface Shape

As discussed in section 5.1.1, Eq. 5.15 holds for an isotropic surface in equilibrium. For a 2-D geometry in which the interface shape is not a function of the third spatial coordinate, $\kappa_2 = 0$. Fig. 26 defines the interface geometry used in subsequent equations. The difference between Fig. 21 and Fig. 26 is the lateral placement of the curve with respect to the y-axis. In Fig. 21, the nose of the curve touches the y-axis. In

Fig. 26, the intersection of the curve with the container surface lies on the y-axis. The dashed segment of the curve below this intersection is an extraneous segment and has no physical significance.

Fig. 26. Modified interface geometry.

A gradient (e.g., thermal or pressure difference) exists along the y-axis and the planar interface intersects $y = 0$ at $x = \infty$ where $\Delta\Omega_V = 0$ and $\kappa = \kappa_1 = 0$. Following the general approaches described in section 5.1.1 [58, 102], the analytic expression for 2-D curvature can be applied to Eq. 5.15 to give

$$5.41 \quad -\Delta\Omega_V(y(x)) = \frac{\gamma y''(x)}{(1 + y'(x)^2)^{3/2}}$$

A solution to the above differential equation would define a family of interface shapes that are a function of γ . A value for γ could then be obtained by fitting experimental data to the form of the solution using γ as the fitting parameter. Multiplying both sides of Eq. 5.41 by $y'(x)$ and integrating yields

$$5.42 \quad \int \Delta\Omega_v(y(x)) \, dy = -\frac{\gamma}{\sqrt{1+y'(x)^2}} + \gamma B$$

where B is a constant of integration. If we define

$$5.43 \quad f(y(x)) \equiv \int \Delta\Omega_v(y(x)) \, dy$$

then Eq. 5.42 becomes

$$5.44 \quad f(y(x)) = -\frac{\gamma}{\sqrt{1+y'(x)^2}} + \gamma B$$

For systems in which $\Delta\Omega_v$ varies only in y and not in x, we can write Eq. 5.44 as

$$5.45 \quad f(y) = -\frac{\gamma}{\sqrt{1+y'(x)^2}} + \gamma B$$

Solving for y',

$$5.46 \quad \frac{dy}{dx} = \pm \sqrt{\frac{\gamma^2}{B\gamma - f(y)^2} - 1}$$

Taking the positive solution in Eq. 5.46 and rearranging gives

$$5.47 \quad dx = \frac{1}{\sqrt{\frac{\gamma^2}{(B\gamma - f(y))^2} - 1}} dy$$

and integrating both sides of Eq. 5.47 yields

$$5.48 \quad x(y) = \int \frac{1}{\sqrt{\frac{\gamma^2}{(B\gamma - f(y))^2} - 1}} dy$$

If the interfacial energy is isotropic, then the planar interface lies along the x-axis for the boundary condition $y' = 0$ when $y = 0$ [58]. $B = 1$ if $f(y)$ is a polynomial in y where the coefficient of the y^0 term is zero, which is consistent with the preceding boundary condition. Therefore, Eq. 5.48 becomes

$$5.49 \quad x(y) = \int \frac{1}{\sqrt{\frac{\gamma^2}{(\gamma - f(y))^2} - 1}} dy$$

It can be seen from inspection that Eq. 5.49 will have a discontinuity when $\gamma = f(y)$, which would make it difficult to use. This can be overcome by dividing the integrand by $\gamma - f(y)$ and simplifying the resulting expression to get

$$x(y) = \int \frac{\gamma - f(y)}{\sqrt{(2\gamma - f(y))f(y)}} dy \quad \text{for } \gamma \neq f(y)$$

5.50

$$x(y) = 0 \quad \text{for } \gamma = f(y)$$

where $f(y)$ is defined by Eq. 5.43. Eq. 5.50 is a solution to Eq. 5.41 and describes the shape of the interface between two phases in a uni-directional gradient when $f(y)$ can be written as a polynomial function in y . When $f(y)$ is a linear function, eqs. 5.8 and 5.13 are solutions to Eq. 5.50. However, Eq. 5.50 is analytically intractable when $f(y)$ is a higher order polynomial, and the equation must be solved numerically. We choose to use Eq. 5.13 because it is more general than Eq. 5.8, as discussed previously.

It is useful to generalize both the variable K and the boundary conditions used with Eq. 5.13. For the case of a conventional solid-liquid interface in a linear thermal gradient, Ω_v is given by Eq. 5.17, Eq. 5.15 reduces to the Gibbs-Thompson equation, and $K^2 = \gamma/G\Delta S$. For a liquid-gas interface in a gravitational field, $\Delta\Omega_v$ is given by Eq. 5.18, Eq. 5.15 reduces to the LaPlace-Young equation, and $K^2 = \gamma/\Delta\rho g$. By comparing these two results, it can be seen that in general

$$5.51 \quad K^2 = \frac{\gamma}{d\Omega_V / dy}$$

It is also useful to generalize Eq. 5.8 by expressing the constant of integration as a function of both contact angle, ψ , and inclination angle of the intersecting surface, α . It can be seen from Fig. 26 that $\alpha = \phi + \psi$ for $\psi \leq \alpha$ where ϕ is the inclination of the tangent to the interface curve at the intersecting surface. For this generalized geometry, we can write the following boundary conditions:

- I. $y = 0$ at $y' = 0$
- II. $y = h$ at $y' = \tan(\alpha - \psi)$
- III. $x = 0$ at $y = h$

where h is the vertical height of the interface at the intersecting surface with respect to the planar interface at infinity. Boundary condition I follows from the assumption of interface isotropy and is the same as used by both Bolling and Tiller [58] and McNutt and Andes [102]. Boundary condition II follows from the angle relationships shown in Fig. 26 and the definition of the tangent of a curve. Boundary condition III is the same as given by McNutt and Andes. Applying the first two boundary conditions to Eq. 5.7 gives

$$5.52 \quad h = \pm K \sqrt{2(1 - \cos(\alpha - \psi))}$$

which reduces to Eq. 5.12 for $\alpha = \pi/2$ and $\psi = 0$.

Applying Eq. 5.52 and boundary condition III to equation 5.13 yields

$$5.53 \quad x = f(y) = \frac{K}{2} \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right]^2 - (4K^2 - y^2)^{\frac{1}{2}} \\ + \frac{K}{2} \left(2\sqrt{2}\sqrt{1 + \cos(\alpha - \psi)} - \ln \left[-\frac{(2 + \sqrt{2}\sqrt{1 + \cos(\alpha - \psi)})^2}{2(\cos(\alpha - \psi) - 1)} \right] \right)$$

The constant of integration in Eq. 5.13 is given by the last term of Eq. 5.53 as a function of both contact angle and the inclination of a planar bounding surface. Variation in α and ψ moves the curve back and forth parallel to the x-axis such that the intersection of the interface curve and the bounding surface always lies on the y-axis. Therefore, the intersection of the curve with the y-axis defines the termination of the physically valid segment of the curve. The remainder of the curve is extraneous for the given values of α and ψ . The interface curve shown in Fig. 26 was drawn for the boundary conditions $\alpha = 160^\circ$ and $\psi = 30^\circ$. From this figure, it can be seen that it is possible for the interface curve to intersect the y-axis at two points. Care must be taken to choose the termination point of the curve that corresponds to the desired contact angle.

Values for α of $\pi/2$ and π correspond to vertical and horizontal intersecting surfaces, respectively. For $\alpha = \pi/2$, Eq. 5.53 reduces to

$$5.54 \quad x = f(y) = \frac{K}{2} \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right]^2 - (4K^2 - y^2)^{\frac{1}{2}} + \frac{K}{2} \left(2\sqrt{2}\sqrt{1 + \sin \psi} - \ln \left[\frac{3 + \sin \psi + 2\sqrt{2}\sqrt{1 + \sin \psi}}{1 - \sin \psi} \right] \right)$$

Eq. 5.54 corresponds to the McNutt and Andes [102] solution with the constant of integration given by the last term of the equation and is also equivalent to Eq. 5.11. For $\alpha = \pi$, Eq. 5.53 reduces to

$$5.55 \quad x = f(y) = \frac{K}{2} \ln \left[\frac{2K + (4K^2 - y^2)^{\frac{1}{2}}}{y} \right]^2 - (4K^2 - y^2)^{\frac{1}{2}}$$

$$+ \frac{K}{2} \left(4 \sin\left(\frac{\psi}{2}\right) - \ln \left[\left(\sec\left(\frac{\psi}{2}\right) + \tan\left(\frac{\psi}{2}\right) \right)^2 \right] \right)$$

If it can be shown that a linear approximation to $f(y)$ is valid for given experimental conditions, then eqs. 5.53 - 5.55 can be used for fitting experimental interface shapes and extracting γ using nonlinear regression. The equation chosen for a particular data set will depend on the inclination of the contacting surface.

5.2.2 Application to Hard Sphere Colloids in a Gravitational Field

The goal of the theory being derived is to provide a mathematical description of the interface between a colloidal liquid and a colloidal solid in a gravitational field to which experimental data can be fit using γ as the fitting parameter. As discussed in 5.1.1.2, temperature is not a convenient variable with respect to hard sphere phase transitions, so the pressure approach will be applied to Eq. 5.50 developed in the previous section. For colloids, the appropriate pressure is the osmotic pressure, Π , which is the excess pressure due to the presence of the colloidal particles [141]. By modifying Eq. 5.18 accordingly, Eq. 5.16 becomes

$$5.56 \quad \Delta\Omega_V = -\Delta\Pi \equiv -(\Pi_s - \Pi_f) = \Pi_f - \Pi_s$$

where the subscripts s and f refer to the colloidal solid and colloidal fluid phases, respectively. Therefore, to evaluate eqs. 5.43 and 5.50 for a colloidal system, Π must be known as a function of height for both phases. The following outlines an approach to do this:

1. Derive general expressions for $\Pi(\phi)$ and $y(\phi)$ using the colloid equation of state and the fundamental relationship between pressure and height in a gravitational field.
2. For each phase (liquid and solid), apply an appropriate equation of state to the general equation for $y(\phi)$ to get an expression for $y(\phi)$ for each phase.
3. Invert the resulting equations for $y(\phi)$ using a series expansion to obtain analytical approximations for $\phi(y)$.
4. Substitute the expressions for $\phi(y)$ and the specific equations of state into the general expression for $\Pi(\phi)$ to obtain $\Pi(y)$ for each phase.

5.2.2.1 General Expressions for $\Pi(\phi)$ and $y(\phi)$

The colloid equation of state is [60, 186]

$$5.57 \quad \Pi(\phi) = nkTZ(\phi)$$

where n is the particle number density, k is the Boltzmann constant, and $Z(\phi)$ is the compressibility factor, which describes the system's departure from ideal behavior.

Particle number density is defined as defined as $n \equiv \phi/v_p$ where v_p is the particle volume.

Therefore, Eq. 5.57 can be rewritten as

$$5.58 \quad \Pi(\phi) = \frac{kT}{v_p} \phi Z(\phi)$$

A non-dimensional reduced pressure can be defined as

$$5.59 \quad \Pi_r(\phi) \equiv \Pi(\phi) \frac{v_p}{kT} = \phi Z(\phi)$$

Eqs. 5.58 and 5.59 give Π in terms of ϕ , but $\Pi(y)$ is required for the problem at hand. For a bulk fluid in equilibrium [187],

$$5.60 \quad \frac{dP}{dy} = -\rho g$$

where ρ is the fluid density, and g is the acceleration due to gravity. For colloids, Π is again the appropriate pressure and the pertinent density is the buoyant density of the particles, $\Delta\rho \equiv \rho_p - \rho_s$ where the subscripts p and s indicate quantities for the particles and solvent, respectively. Since the particles are a discontinuous phase, Eq. 5.60 must be scaled by the fraction of total volume occupied by the particles. Therefore, the equation for colloids that is equivalent to Eq. 5.60 is

$$5.61 \quad \frac{d\Pi}{dy} = -\Delta\rho g\phi(y)$$

Using the chain rule,

$$5.62 \quad \frac{d\Pi}{d\phi(y)} \frac{d\phi(y)}{dy} = -\Delta\rho g\phi(y)$$

A useful scaling parameter for colloids is gravitational height, l_0 , which reflects the ratio of a particle's thermal energy to the gravitational force exerted on it. It is defined as [60]

$$5.63 \quad l_0 \equiv \frac{kT}{\Delta\rho g v_p}$$

Combining eqs. 5.62 and 5.63 yields

$$5.64 \quad dy = -\frac{l_0 v_p}{kT} \frac{1}{\phi} \frac{d\Pi}{d\phi} d\phi$$

Evaluating $d\Pi/d\phi$ using Eq. 5.58 and integrating both sides of Eq. 5.64 gives

$$5.65 \quad y(\phi) = -l_0 (Z(\phi) + \int \frac{Z(\phi)}{\phi} d\phi) + C$$

where C is a constant of integration. Eq. 5.65 can be reduced on l_0 to give a dimensionless height:

$$5.66 \quad y_r(\phi) = -Z(\phi) - \int \frac{Z(\phi)}{\phi} d\phi + C'$$

The constant of integration can be obtained using the appropriate boundary condition (ϕ_f or ϕ_m , depending on the phase) for the planar interface at $y = 0$.

5.2.2.2 $y_r(\phi)$ and $\phi(y_r)$ for the Fluid Phase

The equation of state for a hard sphere colloidal fluid can be described using the Carnahan-Starling equation [188],

$$5.67 \quad Z_f = \frac{1 + \phi + \phi^2 - \phi^3}{(1 - \phi)^3}$$

Substituting Eq. 5.67 into Eq. 5.66 and applying the boundary condition $\phi_f = 0.494$ [148] at $y = 0$ yields $y_r(\phi)$ for the fluid state:

$$5.68 \quad y_{rf}(\phi) = \frac{3 - \phi}{(\phi - 1)^3} - \ln(\phi) + 18.638$$

Approximating Eq. 5.68 with a 10-term series expansion about ϕ_m and calculating the series inverse yields

$$\begin{aligned}
 5.69 \quad \phi_f(y_r) = & 0.494 - 9.175 \times 10^{-3} y_r - 3.132 \times 10^{-4} y_r^2 \\
 & - 1.206 \times 10^{-5} y_r^3 - 4.830 \times 10^{-7} y_r^4 - 1.947 \times 10^{-8} y_r^5 \\
 & - 7.740 \times 10^{-10} y_r^6 - 2.975 \times 10^{-11} y_r^7 - 1.074 \times 10^{-12} y_r^8 \\
 & - 3.428 \times 10^{-14} y_r^9 - 7.978 \times 10^{-16} y_r^{10}
 \end{aligned}$$

Fig. 27. Volume fraction vs. reduced height for a hard sphere liquid.

Fig. 27 is a graph of eq 5.69. Obviously, this approximation fails at $\sim y_r = 18$ since a negative volume fraction is not possible. However, the error in ϕ introduced by Eq. 5.69 is $< 10^{-4}$ over the range of $0.3 < \phi < 0.6$. Therefore, this equation is suitable for experimental results falling within this range.

5.2.2.3 $y_r(\phi)$ and $\phi(y_r)$ for the Solid Phase

The equation of state for the hard sphere colloidal solid phase can be described using an expression derived by Hall [189]:

$$5.70 \quad Z_s = 2.557696 + \frac{3(4-\beta)}{\beta} + 0.1253077\beta + 0.1762393\beta^2 - 1.053308\beta^3 + 2.818621\beta^4 - 2.921934\beta^5 + 1.118413\beta^6$$

where $\beta = 4(1-\phi)/\phi_{\max}$ and $\phi_{\max} = \pi/\sqrt{18} \approx 0.7404$. Substituting Eq. 5.70 into Eq. 5.66

and applying the boundary condition $\phi_s = 0.545$ [148] at $y = 0$ yields $y_r(\phi)$ for the solid state:

$$5.71 \quad y_{rs}(\phi) = \frac{1}{1-1.3506\phi} (43817(\phi-1.452)(\phi-.7400)(\phi-0.06566)(1.548 + (\phi-2.0747)\phi)(0.4699 + (\phi-0.4801)\phi) + (3-4.052\phi) \ln(0.7474-\phi) + (3037\phi-2249) \ln(\phi) - 6437$$

Approximating Eq. 5.71 with a 10-term series expansion about $\phi = 0.58$ and calculating the series inverse yields

$$5.72 \quad \phi_s(y_r) = 0.58 - 9.309 \times 10^{-3}(y_r + \delta) - 4.900 \times 10^{-4}(y_r + \delta)^2 - 2.602 \times 10^{-5}(y_r + \delta)^3 - 1.758 \times 10^{-6}(y_r + \delta)^4 - 1.793 \times 10^{-7}(y_r + \delta)^5 - 2.292 \times 10^{-8}(y_r + \delta)^6 - 3.003 \times 10^{-9}(y_r + \delta)^7 - 3.835 \times 10^{-10}(y_r + \delta)^8 - 4.845 \times 10^{-11}(y_r + \delta)^9 - 6.188 \times 10^{-12}(y_r + \delta)^{10}$$

where $\delta = 3.130$. Fig. 28 is a graph of Eqs. 5.69 and 5.72.

Fig. 28. Volume fraction vs. reduced height for the hard sphere solid and fluid phases.

The expansion was performed about $\phi = 0.58$ rather than $\phi_s = 0.545$ in order to minimize errors due to the approximation in the anticipated volume fraction range of interest. The error in ϕ introduced by Eq. 5.72 is $\ll 10^{-4}$ over the range of $0.52 < \phi < 0.62$. Therefore, this equation is suitable for experimental results falling within this range.

5.2.2.4 $\Delta\Pi_r(y_r)$ and $f_r(y_r)$

The reduced osmotic pressure as a function of reduced height for the fluid phase, $\Pi_{rf}(y_r)$, can be obtained by substituting eqs. 5.67 and 5.69 into Eq. 5.59. Likewise, $\Pi_{rs}(y_r)$ for the solid phase can be found by substituting eqs. 5.70 and 5.72 into Eq. 5.59. Implementing this in *Mathematica* yields lengthy expressions which can be tested for accuracy by comparing them to the results of Hoover and Ree [148], who calculated the

pressure of the coexisting liquid and solid phases to be $8.27 \rho_0 kT$ where $\rho_0 = \phi_{\max}/v_p$. To compare this to our results, the Hoover and Ree coexistence pressure is multiplied by v_p/kT to give a reduced pressure of 6.12. Our fluid and solid pressures evaluated at the appropriate coexistence volume fractions deviated from the Hoover and Ree result by $<1\%$ and $<0.03\%$, respectively. This indicates a high level of confidence in our approximations for $\Pi_{rf}(y_r)$ and $\Pi_{rs}(y_r)$. Following Eq. 5.56, Ω_v in reduced units is given by

$$5.73 \quad \Delta\Omega_{rV} = -\Delta\Pi_r \equiv \Pi_{rf} - \Pi_{rs}$$

With the constraint that $\Pi_{rf} = \Pi_{rs}$ at $y_r = 0$, $\Delta\Pi_r$ can be approximated by a 10-term series expanded about $y_r = -2$ as

$$5.74 \quad \begin{aligned} \Delta\Pi_r(y_r) = & 0.1092 - 5.762 \times 10^{-2}(y_r + 2) + 1.238 \times 10^{-3}(y_r + 2)^2 \\ & + 1.147 \times 10^{-4}(y_r + 2)^3 + 7.109 \times 10^{-6}(y_r + 2)^4 + 6.694 \times 10^{-7}(y_r + 2)^5 \\ & + 1.201 \times 10^{-7}(y_r + 2)^6 + 3.911 \times 10^{-8}(y_r + 2)^7 + 1.467 \times 10^{-8}(y_r + 2)^8 \\ & + 4.368 \times 10^{-9}(y_r + 2)^9 + 8.841 \times 10^{-10}(y_r + 2)^{10} \end{aligned}$$

$\Delta\Pi_r$ can be approximated as a linear function as

$$5.75 \quad \Delta\Pi_r(y_r) = -0.05762 y_r$$

Eqs. 5.74 and 5.75 are compared in Fig. 29. It can be seen that the linear approximation slightly over predicts $\Delta\Pi_r$ in the range $0 < y_r < -4$.

Fig. 29. Comparison of 10-term and linear approximations of $\Delta\Pi_r(y_r)$ given by eqs. 5.74 and 5.75.

Expressions for $f(y)$ in reduced units can now be obtained using eqs. 5.43, 5.73, 5.74, and 5.75. Using the 10-term approximation for $\Delta\Pi_r$ from Eq. 5.74,

$$\begin{aligned}
 f_r(y_r) = & 3.021 \times 10^{-7} y_r + 2.547 \times 10^{-2} y_r^2 \\
 & - 7.539 \times 10^{-4} y_r^3 - 7.570 \times 10^{-5} y_r^4 - 1.558 \times 10^{-5} y_r^5 \\
 & - 4.650 \times 10^{-6} y_r^6 - 1.174 \times 10^{-6} y_r^7 - 2.190 \times 10^{-7} y_r^8 \\
 & - 2.805 \times 10^{-8} y_r^9 - 2.205 \times 10^{-9} y_r^{10} - 8.038 \times 10^{-11} y_r^{11}
 \end{aligned}
 \tag{5.76}$$

and using the linear approximation for $\Delta\Pi_r$ from Eq. 5.75,

$$f_r(y_r) = 0.02881 y_r^2
 \tag{5.77}$$

where

$$5.78 \quad f_r(y_r) = \frac{v_p}{kT l_0} f(y)$$

Eqs. 5.76 and 5.77 are compared in Fig. 30. The linear approximation again yields slightly higher values than the 10-term series approximation in the range $0 < y_r < -4$.

Fig. 30. Comparison of 10-term and linear approximations of $f(y_r)$ given by eqs. 5.76 and 5.77.

5.2.2.5 Equation for the Interface Shape

As discussed in section 5.2.1, the interface shape given by Eq. 5.50 reduces to the analytical forms given by eqs. 5.53 - 5.55 if $\Delta\Omega_{rV}$ can be expressed as a linear equation. Interface shapes based on the expressions for $f_r(y_r)$ given by eqs. 5.76 and 5.77 can now be generated using Eq. 5.50 and compared with each other to see how much they differ.

If the difference between the curves is small compared to the anticipated error of the experimental data, then Eqs. 5.53 - 5.55 can be used to fit the experimental data and extract values for γ . Otherwise, numerical methods will be needed to determine γ . Three details need to be addressed before we can meaningfully assess the adequacy of a linear approximation of $\Delta\Omega_{rV}$ for interpreting experimental data:

1. Eq. 5.50 must be expressed in terms of nondimensional variables in keeping with the treatment of variables in the preceding sections.
2. We must derive a conversion factor that will allow us to compare our results to literature values.
3. Key physical parameters must be determined in order to obtain a value for l_0 , which is needed as part of the conversion factor between our results and literature values.

Eq. 5.50 and Eq. 5.78 can be combined to give

$$x_r(y_r) = \int \frac{\gamma_r - f_r(y_r)}{\sqrt{(2\gamma_r - f_r(y_r))f_r(y_r)}} dy_r \quad \text{for } \gamma_r \neq f(y_r)$$

5.79

$$x_r(y_r) = 0 \quad \text{for } \gamma_r = f(y_r)$$

where $x_r = x/l_0$, $dy_r/dy = 1/l_0$, and

$$5.80 \quad \gamma_r = \frac{v_p}{kT} \frac{\gamma}{l_0}$$

In the literature, hard sphere interfacial energy is most commonly reported in nondimensional units defined as

$$5.81 \quad \gamma_{rl} \equiv \frac{d^2}{kT} \gamma$$

where the subscript rl indicates the literature reduction and d is the particle diameter. Combining eqs. 5.80 and 5.81 gives a conversion factor between the two schemes for reducing hard sphere interfacial energy, which can be written in several forms as

$$5.82 \quad \frac{\gamma_{rl}}{\gamma_r} = \frac{l_0 d^2}{v_p} = \frac{6l_0}{\pi d} = \frac{36kT}{\Delta\rho g \pi^2 d^4}$$

Since l_0 is part of the conversion factor given by Eq. 5.82, we must calculate an appropriate value of l_0 if we wish to use literature values to guide the comparison of interface shapes. To calculate l_0 , $\Delta\rho$ and particle diameter, d must be known. For the present comparison, we will use $\Delta\rho = 0.285$ gm/ml and $d = 504$ nm. The experimental derivation of these parameters will be discussed later in section 6.2.1. Using the stated values for $\Delta\rho$ and d , standard values for k and g , and $T = 300$ K, Eq. 5.63 gives $l_0 = 22.2\mu\text{m}$.

We can now use Eq. 5.79 in conjunction with eqs. 5.76 and 5.77 to determine whether or not the interface shape corresponding to the linear form of $\Delta\Omega_v$ is an adequate approximation for the experimental conditions to be used in this work. This can be done by generating interface curves for a range of γ -values that bracket the theoretical and experimental literature results. For each value of γ chosen, we will generate two curves that represent the full interface shape assuming a horizontal container boundary and a contact angle of zero. The first curve is for the 10-term polynomial expansion given by Eq. 5.76, and the second curve is for the linear approximation given by Eq. 5.77. Throughout the remainder of this section we refer to these as the polynomial and linear cases, respectively.

In order to compare the interface shapes, each pair of interface curves will be constrained to a fixed crystal height. First, the interface curve for the linear case is generated by using a value of γ_r derived from a chosen value of γ_{rl} using Eq. 5.82. Next, we calculate the interface height for this curve, which can be derived from Eq. 5.79 as follows: The interface shape terminates at the point where the radicand in Eq. 5.79 equals zero, which occurs when $2\gamma_r = f_r(y_r)$. Therefore, the furthest extent of the crystal below the horizontal interface occurs when

$$5.83 \quad \gamma_r = \frac{f_r(y_r)}{2}$$

Using Eq. 5.77 for the linear case, Eq. 5.83 can be solved for y_r to give the maximum crystal height,

$$5.84 \quad y_{r\max} = \sqrt{\frac{2\gamma_r}{0.02881}}$$

Next, $y_{r\max}$ from Eq. 5.84 is used to calculate γ_r for the polynomial case using eqs. 5.76 and 5.83. Finally, this value for γ_r is used to generate the interface curve for the polynomial case.

We used numerical integration, implemented in *Mathematica*, to generate the interface curves using Eq. 5.79. The definite integral [190]

$$5.85 \quad I = \int_a^b h(y) dy$$

is the same as $I \equiv x(b)$ where $dx/dy = h(y)$ and $x(a) = 0$ so

$$5.86 \quad x(b) = \int_a^b h(y) dy$$

Using Eq. 5.79, let

$$5.87 \quad h(y) = \frac{\gamma_r - f_r(y_r)}{\sqrt{(2\gamma_r - f_r(y_r))f_r(y_r)}}$$

where $f_r(y_r)$ is given by eqs. 5.76 and 5.77 for the polynomial and linear cases, respectively. It can be seen from inspection of Eq. 5.87 that $x(a) = 0$ when $\gamma_r = f_r(y_r)$, which represents the “nose” of the curve. For the linear case given by Eq. 5.77, the lower limit of integration is given by

$$5.88 \quad a = \sqrt{\frac{\gamma_r}{0.02881}}$$

For the polynomial case given by Eq. 5.76, the lower limit of integration is determined numerically. As discussed in 5.1.1.2.3, the range of literature values is $0.1 < \gamma_{rl} < 4$. We bracketed this range by an order of magnitude in each direction by examining values in the range of $0.01 < \gamma_{rl} < 40$.

Fig. 31 shows the interface curves for $\gamma_{rl} = 10$ and represents a typical result for the range of γ_{rl} examined. It can be seen from the figure that the difference between the curves is very slight. Fig. 32 shows the orthogonal separation of the two curves in Fig. 31 as a function of position along the y-axis. The two curves coincide at a point situated between the two noses of the curves, and the maximum orthogonal separation of the two curves is slightly less than $\frac{3}{4}d$. Fig. 33 shows the maximum orthogonal separation of the curves as a function of γ_{rl} .

Fig. 31. Interface curves for $\gamma_{rl} = 10$.

Fig. 32. Orthogonal separation of the linear and polynomial cases vs. y_r for $\gamma_{rl} = 10$.

Fig. 33. Maximum separation between interface curves vs. γ_{rl} for the polynomial and linear cases.

We can anticipate that the error in locating the solid/liquid interface in experimental results will be related to the size of the transition zone between the two phases. Theoretical calculations predict the width of this zone to be about 3-7 particle diameters. [30, 32, 36, 38, 176] We would expect that error in determining the interface from particle-level images would fall within this range. Therefore, an *a priori* prediction of the experimental error of the interface position is $\pm(1.5 \text{ to } 3.5)d$. Since the maximum orthogonal separation in Fig. 33 is $<2.5d$, the difference between the polynomial and linear cases should not be significant over the anticipated range of interest, $0.01 < \gamma_{rl} < 40$. Therefore, the linear approximation for $f_r(y_r)$ should be appropriate for fitting our experimental results. This allows the use of eqs. 5.53 - 5.55 as analytical expressions for fitting the data and extracting γ by means of a nonlinear regression. For these equations, it follows from combining eqs. 5.51, 5.73, and 5.75 that

$$5.89 \quad \gamma_r = 0.05762K^2$$

Although the above analysis indicates that eqs. 5.53 - 5.55 can be used to model our experimental interfaces, we must also examine the error introduced by this process. For the condition of fixed crystal height, the ratio of γ calculated for the linear and polynomial cases can be derived from eqs. 5.83 and 5.84:

$$5.90 \quad \frac{\gamma_{lin}}{\gamma_{poly}} = \frac{2\gamma_{lin}}{f_{rpol}(y_{rmax}(\gamma_{lin}))}$$

where γ_{lin} and γ_{poly} indicate γ based on the linear and polynomial cases, respectively, and f_{rpol} is given by Eq. 5.76. Eq. 5.90 is plotted in Fig. 34. It can be seen from this figure that the linear approximation slightly over predicts γ_{rl} below $\gamma_{rl} = 58$ and slightly under predicts above this value. For our interval of interest, the over-prediction ranges from

13% for $\gamma_{rl} = 0.01$ to 1% for $\gamma_{rl} = 40$. A comparison of Fig. 33 and Fig. 34 shows that within this range, the over-prediction of γ increases as the maximum error in interface position decreases. However, the error introduced by fitting data to eqs. 5.53 - 5.55 can be eliminated completely by dividing by the result of Eq. 5.90.

Fig. 34. The ratio of γ_{lin} to γ_{poly} vs. γ_{rl} .

5.3 Summary and Conclusions

In summary, we have:

- developed a generalized equation describing the 2-D shape of an equilibrium interface balanced against a known variable,
- generalized existing analytical expressions for the interface to be functions of both contact angle and inclination of a planar bounding surface,

- used this generalized equation to develop an isotropic model for the solid/liquid interface shape in a hard sphere colloidal system in a gravitational field,
- demonstrated the validity of assuming a linear $\Delta\Pi$ gradient so that these analytical expressions could be used to derive γ from experimental data, and
- derived a correction factor to eliminate the systematic error associated with assuming a linear gradient.

These developments will allow the application of the Bolling-Tiller GBG approach to colloidal systems. In addition, the linear $\Delta\Pi$ gradient assumption is also applicable to the capillary vector approach, and we expect that the corresponding correction factor is a reasonable first approximation for anisotropic cases as well.

Chapter 6

Experiments

6.1 Introduction

In this section, we describe experiments with hard sphere colloids using optical microscopy to gather data in order to test the grain boundary groove methods discussed in the preceding section. We also employ the divergent-beam technique described in Chapter 3 to determine crystal orientation.

6.2 Experimental Procedure

6.2.1 Experimental Equipment

All data was gathered using a research-grade optical microscope (Zeiss Axioplan-2). We built a fixture that could rotate the microscope to any desired orientation about a single axis. For this experiment, the microscope was rotated and fixed into position such that the optical axis was perpendicular to the gravity vector as shown in Fig. 35.

Fig. 35. Microscope mounted in rotation fixture.

Fig. 36. Experiment geometry.

Mounting the microscope in this way enables the experiment geometry shown in Fig. 36. The planar solid-liquid interface is parallel to the x-axis, and the gravity vector is anti-parallel to the +y-axis. The image plane is parallel to the x-y plane, and the microscope optical axis is parallel to the z-axis. Without rotating the microscope, the optical axis is aligned with gravity and particle-level observations along the osmotic pressure gradient would be limited to the working distance of high numerical aperture (NA) lenses, which is typically about 90-100 μm , and an entire series of images at sequential z-positions (a z-stack) would be necessary to determine a single interface profile. With a 90° rotation, observations along the osmotic pressure gradient are limited only by the cell dimension in the y-direction, and an interface profile can be extracted from a single image. Besides simplifying data acquisition and reduction, this single image takes advantage of the superior lateral resolution of an optical microscope, which is roughly twice as good as the axial resolution. Not shown in Fig. 35 are a frame and opaque shroud used to exclude room light for long exposure imaging.

All images were gathered with trans-illumination from a standard 100W tungsten-halogen lamp using two imaging modes, darkfield contrast and differential interference contrast (DIC). The darkfield mode was used at low magnifications (5x and 10x) to survey the microstructural length scale of the samples. In this mode, the sample is illuminated with a hollow cone of light in which all the direct rays exceed the maximum angle of light gathered by the objective. Therefore, only light scattered by the sample is gathered by the objective. With the colloidal liquid phase, incoherent scattering from the particles results in a characteristic color determined by particle size, volume fraction, and the NA of the objective, where

6.1 $NA = n \sin \sigma$

where n is the index of refraction of the medium between the objective and the specimen and σ is the half angle of the cone of light accepted by the objective. Colloidal crystals formed from particles of the size used in this work have lattice parameters that are on the same length scale as the wavelengths of visible light. Therefore, they scatter light coherently when the Bragg conditions are met. For our samples, this happens for one or more crystal planes nearly all the time in the darkfield mode due to the wide band of wavelength used (white light) and the 360° cone of incoming rays. This results in a wide range of scattered colors that depend on particle size, crystal structure, crystal orientation, and objective NA. Therefore, crystallites of varying structure and/or orientation can be distinguished from each other and the liquid phase using the darkfield mode. The illumination geometry in darkfield microscopy is an axially symmetric version of the oblique illumination used in previous benchtop experiments with colloidal crystals. [18, 158]

The DIC mode is used at high magnification (63x – 100x) and high objective and condenser NA (1.4) for particle-level imaging. Because neither the particles nor the suspending fluid absorb appreciably in the visible spectrum, standard brightfield imaging is ineffective. DIC uses polarized light and a series of optically anisotropic prisms to create contrast proportional to optical path length gradients within a sample. [91] In addition to producing sample contrast, DIC has a smaller depth of field than bright field or other contrast methods such as phase contrast. This is advantageous in our experiment where we desire to acquire thin optical sections from the interior of a sample. For both

imaging modes, an intermediate magnification turret was available to increase the objective magnification to 1.25x, 1.6x, 2.0x, or 2.5x, if desired.

No published studies of crystallizing colloids using optical microscopy for *in-situ* experiments have combined multiple techniques to observe both the microstructural and particle length scales in the same sample. This is in contrast to the typical approach for experimental studies with conventional materials. For example, optical microscopy, scanning electron microscopy (SEM), and TEM are routinely used to image the same specimen at increasing magnifications. We hope to demonstrate with this work that a multi-length scale approach with crystallizing colloids is equally useful.

A high resolution 3-chip CCD video camera (Optronics DEI-750) was used to acquire images which in turn were digitized and stored on a PC for post processing. Image analysis was performed using Image-Pro Plus software (Media Cybernetics) with numerical data exported to a spreadsheet for calculations.

Samples were translated in the focal plane (x-y axes) via a motorized stage with step resolution of 1 μm . Movement along the optical axis (z-axis) was possible in 100nm increments. Stage movement in all three axes could be controlled either manually or via computer using the *Image-Pro Plus* commercial software package with *Scope-Pro* and *Stage-Pro* plug-in modules (Media Cybernetics).

We gathered data using two cameras. One was an 8-bit, 3-chip color NTSC video camera (Optronics DEI-750) and the other was a cooled, 12-bit, black and white digital camera with a 1344x1024 pixel array (Hamamatsu ORCA-ER). We used the color camera for visual surveys and to capture darkfield images. The color camera was also useful in setting up for DIC imaging since it provided video-rate feedback and could

perform real-time image sharpening. Images from the video camera were acquired via a frame grabber for computer storage and analysis. The black and white camera was used to capture high resolution DIC images for analysis.

There was no active temperature control. Therefore, the apparatus experienced the temperature variations arising from the building climate control system, which was typically about $\pm 1^\circ\text{C}$ during the heating season and about $\pm 3^\circ\text{C}$ during the cooling season with a typical set point of 20°C . Regular fluctuations of greater magnitude were prevented by removing the room that housed the apparatus from a centralized energy conservation program. However, there were several periods of much larger fluctuations due to building-wide maintenance activities and equipment failures. The apparatus experienced temperatures between $\sim 18 - 30^\circ\text{C}$ during these periods.

6.2.2 Samples

We used suspensions of nearly monodisperse spherical colloidal particles made of poly-(methyl methacrylate) (PMMA) sterically stabilized with short chains of poly-(12-hydroxy stearic acid) (PHSA) grafted to the surface of the particles. The particles were suspended in cis-decahydronaphthalene (decalin). This system closely approximates the hard sphere potential [60] in which crystallization occurs as a function of volume fraction [16]. The particles used in this experiment were synthesized by R. Ottewill and his group at the University of Bristol and kindly provided to us by W. Russel of Princeton University. These particles were originally prepared as flight spares for microgravity experiments conducted by NASA and Princeton University. [62, 149, 161, 162] They are also from one of the same batches of particles used for equation of state measurements. [60]

6.2.2.1 Particle Size Characterization

The Ottewill group used transmission electron microscopy (TEM) to measure a mean core diameter of (518 ± 26) nm. [191] Princeton researchers used dynamic light scattering to characterize particles from the same batch, obtaining a hydrodynamic radius of (500 ± 12) nm. [191] We performed a third measurement of particle size using the divergent-beam technique described in Chapter 3. We used this technique to measure the hcp {0002} plane spacing at the liquid/crystal interface of 6 crystal grains from three cells. This plane spacing is equal to the {111} plane spacing in the fcc structure. The particle diameter, d , is given by the relationship

$$6.2 \quad d = a \left(\frac{3\phi}{2\pi} \right)^{1/3}$$

where a is the fcc lattice parameter, and ϕ is the volume fraction. Plane spacing is related to lattice parameter in cubic systems by

$$6.3 \quad a = d_{hkl} \sqrt{h^2 + k^2 + l^2}$$

where d_{hkl} is the plane spacing and h , k , and l are the plane indices. The separation of spheres is quite small at volume fractions of interest. For perfectly monodisperse spheres at $\phi_m = 0.545$, the centers of nearest neighbors are separated by $\sim 1.11d$, leaving only $\sim 0.11d$ between their surfaces.

Phan determined the polydispersity of our particles to be 0.05 [191] for which the hard sphere melting volume fraction, $\phi_m = 0.555$ [151]. We took this value to be the crystal volume fraction at the solid/liquid interface. Each image was captured with the microscope field aperture at minimum ($\sim 40 \mu\text{m}$ diameter) and the translation stage

positioned such that $\sim 1/4$ of the field aperture diameter intersected the crystalline region while the rest of the field of view was filled with colloidal liquid. We calculated the change in volume fraction over the height of the crystalline region within the field of view to introduce $<0.2\%$ error into the resulting particle size calculation. Bragg scattering from $\sim 7 \times 10^5$ particles contributed to our estimate. With this approach, we measured a particle diameter of $(504 \pm 5) \mu\text{m}$ with the error representing a 95% confidence interval about the mean value. This value falls between the DLS and electron microscopy measurements discussed above and agrees to within the experimental errors reported with these values. We used our measured diameter value for calculations in this work.

6.2.2.2 Particle and Fluid Density Characterization

Suspension density measurements were made using a Paar DMA60/602 densitometer. Temperature control was achieved using a Neslab EX-211/FTC-350 water bath which could be controlled to within $\pm 0.01^\circ\text{C}$. Actual temperature was monitored using a GE Thermometrics thermistor with a Hart 1504 controller having a combined accuracy of $\pm 0.01^\circ\text{C}$. The instrument was calibrated using air and distilled water. All measurements were taken at 15°C , 20°C , and 25°C to establish relationships between density and temperature for each component. First, multiple measurements were taken using pure cis-decalin. Next, density measurements were taken of suspensions with varying particle mass fractions. First, the particles were dried to constant weight in a vacuum oven to assure all solvent had been removed. Next, a suspension of known particle mass fraction was prepared using the already characterized cis-decalin with component masses determined using a calibrated Mettler AE160 analytical balance. Two

serial dilutions of the suspension provided density data at a total of three particle mass fractions plus the zero particle mass fraction data of the pure cis-decalin. The suspension density, ρ_s follows the relationship

$$6.4 \quad \rho_s = \frac{\rho_f}{1 - x_p + \frac{x_p \rho_f}{\rho_p}}$$

where x is mass fraction and the subscripts f and p denote the fluid and particles, respectively. Density data was fit to Eq. 6.4 using a nonlinear least squares fit with ρ_p as the unknown parameter. The results of the density measurements and analysis are shown in Table 4. Error bounds represent a 95% confidence interval.

	density (gm/ml)		temperature coefficient (gm/ml-C)	
	20.00 C	$\pm$		$\pm$
Cis-decalin	0.89693	0.00007	-0.000767	0.000002
Particles	1.182	0.002	-0.000202	0.000002
Δ density	0.285	0.002	0.000565	0.000002

Table 4. Density data

6.2.2.3 Sample Preparation

Sample cells were constructed using flat microcapillary cells (Vitrocom) with a nominal internal cross section of 0.1mm x 2mm. Cell lengths were either 40mm or 50mm. Five cells were carefully mounted parallel to each other on a standard 25mm x 75mm microscope slide using optical epoxy in order to provide a standard attachment interface to the microscope stage. Three such slides were constructed for a

total of 15 cells. A suspension was prepared at $\phi \sim 0.1$ from dry particles by adding the appropriate mass of cis-decalin and homogenizing with a vortex mixer until the suspension achieved a uniform appearance. We then used a syringe to inject the homogenized suspension into each cell and sealed both ends with UV-curing epoxy. In many of the samples, the sealing process resulted in small bubbles (1mm typical) being trapped at one or both ends of the cell. In addition to the primary cells just described, we also obtained useful data from a precursor cell prepared in a 1mm wide (vs. 2mm) cell. The suspension for this precursor experiment was prepared without precise measurements, but observations after settling indicate a bulk volume fraction of ~ 0.02 .

After the samples were filled and cured under a UV lamp for up to 1.5 hrs with the slides flat on a workbench, they were mounted on the microscope stage with the microscope rotated as described above. The samples were then allowed to equilibrate for one month while an automated sequence captured images from a location near the bottom of one of the cells with a 5x objective in the darkfield mode once an hour in order to observe the dynamics of the settling suspension. The microscope lamp was shuttered between exposures to avoid heating the sample. In order to estimate the time required for the samples to reach sedimentation equilibrium, we calculated the time required for the particles to settle the height of our sample cells at the initial volume fraction. [75] This estimate predicted a settling time of about one week, but we allowed the particles to settle for one month in order to ensure sedimentation equilibrium.

6.2.3 Image Processing

Scale factors for all camera/microscope objective/intermediate magnification combinations were derived from images taken of a traceable test target (Richardson Technologies, Inc.). The image processing steps for DIC images consisted of frame averaging, background subtraction, and display range manipulation. Frame averaging was performed during image capture by averaging of 16 consecutive frames to reduce image noise. For DIC images, we found that frame averaging in combination with long exposure times (4-10s) significantly enhanced interface images as can be seen in Fig. 37. A single exposure is shown in Fig. 37a. Colloidal fluid occupies the top third of the image and two crystallites can be seen in the lower 2/3 of the image with a grain boundary in the center. Though it is possible to make out a grain boundary groove in this image, it is much more apparent in Fig. 37b where 16 frames have been averaged together. The time span encompassed by the 16-frame average (~ 72 s) is sufficient to allow fluid particles to diffuse far enough over the course of the exposures to "smear out" distinct particle images leading to a nearly homogeneous gray level in the fluid phase.

Fig. 37. Comparison of single and frame-averaged DIC images. a) Single frame image (4.5s exposure), b) 16-frame average of the same field of view and same exposure.

This effect does not occur in the crystal phases because each particle is normally limited to a lattice cage with a typical distance between particles of about 1.1 particle diameters at ϕ_m . Therefore, particle contrast in the crystalline phases is retained when frame averaging with long time exposures. This results in an enhanced distinction between the colloidal liquid and colloidal crystal phases.

Background subtraction was performed by using the following algorithm at each (x,y) pixel location,

$$6.5 \quad CI_{x,y} = I_{x,y} - BI_{x,y} + M$$

where CI is the corrected image, I is the original image, BI is the background image, M is the average pixel value of the background image and the subscripts x and y denote the pixel location (x,y). The background image was obtained for each series of DIC images by capturing a frame-averaged image at the same time exposure with the plane of focus positioned in the front cell wall $\sim 25\mu\text{m}$ away from the sample volume.

The display range of each background-subtracted image was adjusted to optimize visual contrast. The intensity range of the DIC images typically occupied only a small portion of the 12-bit camera dynamic range, and we manipulated the microscope illumination level with filters such that the image histogram occupied the top of the camera dynamic range in order to minimize dark-current noise. Adjusting the display range effectively remapped the intensity range of the image to correspond to the limits of the display monitor, which is less than 12-bits. In this way the ability of a 12-bit camera to resolve small intensity differences was meshed with the more limited grayscale range of standard computer monitors and the human visual system.

For darkfield images, we performed frame-averaging as described for the DIC images but we did not perform background subtraction. Display range manipulation with darkfield images was employed as needed.

Image mosaics were produced at both low and high magnification by image tiling. The x-y stage repeatability was approximately equal to the color camera pixel size at 10x so low magnification darkfield mosaics were generated by simply using a software routine to control stage movements and assemble adjacent fields of view. These low magnification darkfield mosaics images could then be used as “feature maps” to position the stage for high magnification DIC imaging. At high magnification (e.g. 100x), the stage repeatability was equal to about 15 pixels in each dimension on the black and white camera. Therefore, we could not rely on programmed stage movements to produce properly aligned mosaics. Instead, we captured images with overlapping fields of view and manually aligned them using the layering and transparency capabilities of Adobe Photoshop. Proper registration was achieved by aligning defects in the crystalline phases that were visible in adjacent images.

6.3 Results

After allowing the 15 sample cells to sediment for one month, we reviewed the sequence of low magnification darkfield images taken at 1-hr intervals. A growing colloidal liquid phase could be seen over time, but there was no indication of crystallization within the field of view (FOV) of the time-lapse sequence. We then surveyed all samples at 10x in the darkfield mode. One sample had dried up completely, apparently from a leak in the epoxy seal. All other samples contained crystalline regions that extended across only part of the sample. Expecting that a slight

tilt of the cells with respect to gravity might be the cause of this, we used 10x darkfield images to measure the tilt of our apparatus about the optical axis and found that our instrument appeared to be tilted with respect to the theoretical horizontal by $\sim 0.5^\circ$.

As expected, each crystalline region was made up of a number of individual grains impinging on each other with GBGs at the intersection of a grain boundary with the colloidal liquid phase. In each sample, the crystalline region terminated in a curved tip which we will refer to as a grain tip. In all of the surviving samples, the bubbles present at the initial sealing grew to various sizes and in some instances new bubbles formed near cell ends that had initially been bubble-free. In some cells the bubble growth was very small (1-2mm). In other cells, bubbles up to 25mm long occupied a significant portion of the cell and some even extended above portions of the crystalline region. In some cells where the bubbles terminated near or above the crystalline region, the crystalline region was "pinched off" within the region with two adjacent "interior" grain tips in addition to the terminal grain tip.

Over the course of many months, the bubbles in all cells continued to grow. In most cells, the bubbles overlapped the crystalline regions and in some cases they encompassed the entire cell and caused the sample to dry up completely. However, in 5 cells the bubble growth was very slow and the bubble remained $> 5\text{mm}$ from the crystalline region. It was from a subset of these cells that we acquired particle-level DIC images for detailed analysis. We will break the description and discussion of our data into three sections: interface cross sections, grain boundary grooves, and grain tips.

6.3.1 Interface Cross Sections

A key assumption in the interface shape theory described in Chapter 5 is that the interface is 2-D. This means that the interface profile must be constant along the third dimension in the vicinity of the region used for analysis. To test this assumption, we took z-stacks of images through the entire cell depth along the optical axis of the microscope at several macroscopically flat regions of the colloidal liquid/crystal interface in the x-y plane far from any grain boundary grooves or grain tips. The center frame from a typical sequence is shown in Fig. 38.

Fig. 38. DIC image from center of a z-stack used to examine interface cross-section. Scale bar = 10μm.

In Fig. 38, the colloidal liquid occupies the upper third of the image and is lighter than the crystalline region below. Though individual spheres can be seen in the crystalline region, the ordering is not obvious. This is common in DIC imaging with

particles of this size when low index crystal planes are neither parallel nor perpendicular to the image plane. This occurs because the microscope depth of field is about the same as the sphere diameter resulting in overlapping of higher index planes. It can be seen in the figure that the liquid/crystal interface is macroscopically planar but rough on the particle scale with slight undulations along the interface. In this image stack, images were captured at $2\mu\text{m}$ intervals along the z-axis. The nominal cell depth was $100\mu\text{m}$, but the actual depth was typically closer to $90\mu\text{m}$. We recorded the interface position at 5 locations along the x-axis of the field of view for each image. The resulting interface profile is shown in Fig. 39. In this figure, $z = 0$ corresponds to the inside of the cell wall nearest the microscope objective and $y = 0$ corresponds to the lowest data point in the series. The data points in the graph represent the average of the 5 data points taken in each image and the error bars represent $\pm$ one standard deviation of each data set.

Fig. 39. Interface cross-section.

6.3.2 Grain Boundary Grooves

A representative section of one sample is shown in Fig. 40, which is a darkfield mosaic image that spans the entire height of the cell from top to bottom. The image shows a multicolored crystalline phase at the bottom of the cell beneath a greenish-gray colloidal fluid phase that decreases in intensity with height. The majority of the cell

volume is comprised of black supernatant. Fig. 41 is a darkfield mosaic of a 3.4mm wide portion of the crystalline region in the same sample. The image represents a continuous width of the sample with the right side of the top two segments continuing at the left side of the following segments. This image is representative of the variation in both the color and widths of crystallites typically seen in this experiment. We chose three GBGs in this sample for detailed analysis in which the grain boundary plane was perpendicular to the image plane to within $<5^\circ$. In addition, we picked GBGs which displayed a variety of colors in the darkfield images with the expectation that this would lead to a variety of crystal orientations being represented in our analysis. Darkfield images of these GBGs are shown in Fig. 42, and DIC images are shown in Fig. 43-Fig. 45. Divergent-beam OFT images of each side of these GBGs are shown in Fig. 46.

Some GBGs appeared to be generally symmetrical between LHS and RHS, while others had varying degrees of asymmetry. Also, some GBGs appeared to have kinks in their curvature followed by a flattened segment such as can be seen on the LHS of Fig. 47. This image is from a precursor experiment prepared from a different bulk suspension than that used from our primary experiments, and we are not certain whether or not the particles in this suspension are from the same lot as the one we characterized for particle size and density. However, the sample is still useful for qualitative observations.

Fig. 40. Darkfield image showing entire height of cell. Scale bar = 500 μ m

Fig. 41. Darkfield image of a portion of the crystalline region in a sample. Most of the crystallites in this image are also seen at the bottom of Fig. 40. The red and blue boxes correspond to the fields of view in Fig. 42b and Fig. 42c, respectively. Scale bar = 100 μ m.

Fig. 42. Darkfield images of the GBGs analyzed in this work. a) GBG C206c-1, b) GBG C206c-2, and c) GBG C206c-3. The red boxes correspond to the field of view in Fig. 43, Fig. 44, and Fig. 45, respectively. Scale bar = 100 μ m.

Fig. 43. DIC image of GBG 206c-1. Arrows mark examples of possible interface kinks. Scale bar = 10 μ m.

Fig. 44. DIC image of GBG 206c-2. Arrows mark examples of possible interface kinks. Scale bar = 10 μ m.

Fig. 45. DIC image of GBG 206c-3. Scale bar = 10 μ m.

Fig. 46. Divergent-beam images of the GBGs shown in Fig. 43-Fig. 45. a) C206c-1 LHS, b) C206c-1 RHS, c) C206c-2 LHS, d) C206c-2 RHS, e) C206c-3 LHS, f) C206c-3 RHS. All images were taken at 546nm.

Fig. 47. A GBG with a noticeably asymmetric interface shape between sides. The arrow marks an example of a possible interface kink. Scale bar = 10μm.

6.3.3 Grain Tips

As previously discussed, the crystalline phase terminated part way across each sample. Fig. 48 shows DF images of the grain tips which were far from any bubble at 7 weeks after the experiment was initiated. Significant variations in tip shape can be seen in this figure. Variation in color scattered by different tips is also apparent. All images were taken using a dry darkfield condenser. The grain tips grew slowly from left to right over time. The direction of the slight tip of the apparatus was such that the bottom of the cells were tilted "up hill" to the right by $\sim 0.5^\circ$. Fig. 49 shows darkfield images of the C204b grain tip at various times. Fig. 49a corresponds to Fig. 48a and was taken using a dry

condenser. The remaining images in Fig. 49 were taken using an oil immersion condenser. It can be seen from this figure that the crystal shape changed significantly over time.

We took detailed DIC images of the C204b grain tip 11 weeks into the experiment along 1.2mm of the crystal. These images were taken at the center of the cell with respect to the z-axis and were assembled into a mosaic for the extraction of interface data. About 10% of the mosaic width is shown in Fig. 54.

A z-scan of the C204b tip at 2 μ m intervals was performed 62 weeks into the experiment. Projections of the interface onto the x-y and x-z planes are shown in Fig. 55. The top data points in the x-z plane are comparable to Fig. 39, which is corresponding data for a planar interface. In contrast to Fig. 39, the z-profile of the grain tip displays complex curvature and appears to be comprised of three asymmetric humps.

The length of the C204b crystalline region is plotted as a function of time in Fig. 52. It can be seen in this figure that the tip velocity varied considerably over the course of the experiment. We took a detailed series of divergent-beam OFT images along the length of the C204b tip crystal 12 weeks into the experiment. An OFT image of the grain tip from this dataset is shown in Fig. 58a. The orientation of the tip crystal appeared to rotate about the optical axis of the microscope along the length of the crystal. This phenomenon was also observed in qualitative OFT observations of the grain tips in other samples.

We also observed changes over time in the crystalline region at the epoxy plug interface in several samples as can be seen in Fig. 50. In this figure, the crystal appears to "melt" near the plug and then regrow. Given the shape changes over time at the

extremes of the crystals, we looked at the stability of several grain boundaries in C204b.

Fig. 51 shows two C204b grain boundaries at the same time intervals as in Fig. 50. These images were extracted from the same absolute crystal locations by aligning the epoxy plug in each image in Photoshop. In Fig. 53, we plot the groove root positions of these two grain boundaries from data extracted for the images. The groove root coordinates are relative to the intersection of the grain boundary with the bottom of the cell. We estimated the position error to be $\pm 2\mu\text{m}$ in both the x-axis and the y-axis, giving an RSS error of $\pm 3\mu\text{m}$.

Fig. 56 shows the grain tip of sample C206e 96 weeks into the experiment. The grain tip appears to have several kinks in the tip curvature followed by flattened segments as was seen in Fig. 47 for a GBG. Fig. 57 is a DIC image taken near the center of the cell along the z-axis covering the x-y field of view shown by the red box in Fig. 56. Several kinks and flattened regions are clearly seen in the DIC image also. A divergent-beam image of this grain tip is shown in Fig. 58b.

Fig. 48. Darkfield images of grain tips 7 weeks after initiating experiment. a) sample C204b, b) C204c, c) C204d, d) C205a, e) C205b, f) C06a, g) C206c, h) C206d, i) C206e. Scale bar = 50 μ m.

Fig. 49. Time series of C204b grain tip. a) 7 weeks after start of experiment, b) 12 weeks, c) 16 weeks, d) 35 weeks, e) 48 weeks, f) 58 weeks, g) 62 weeks, h) 97 weeks, i) 98 weeks. Scale bar = 50 μ m.

Fig. 50. Time series of C204b at LHS epoxy plug. a) 12 weeks after start of experiment, b) 48 weeks, c) 62 weeks, d) 97 weeks. Scale bar = 100 μ m.

Fig. 51. Time series of two grain boundaries in C204b. These grain boundaries were located 1.9mm (top row) and 3.9mm (bottom row) from LHS epoxy plug shown in Fig. 50. Images in both rows, from left to right, were taken 12, 48, 62, and 97 weeks after start of experiment. Scale bar = 50 μ m.

Fig. 52. Length of C204 crystalline region vs. time. The dashed line is added as a guide to the eye.

Fig. 53. Grain boundary groove positions over time. Data is relative to grain boundary positions at bottom cell. GB1 and GB2 refer to the upper and lower rows of Fig. 51, respectively.

Fig. 54. High magnification DIC mosaic of C204b tip. Arrows mark examples of possible interface kinks. Scale bar = 100 μ m.

Fig. 55. Projections of 3-D data from C204b grain tip.

Fig. 56. Oblique darkfield image of C206e grain tip. Arrows mark examples of possible interface kinks. Red box shows field of view of Fig. 57. Scale bar = 25 μ m.

Fig. 57. DIC image of C206e grain tip. Arrows mark examples of possible interface kinks. Scale bar = 10 μ m.

Fig. 58. Divergent-beam images of two grain tips. a) C204b at 12 weeks and b) C206e at 96 weeks. Both images were taken at 546nm.

6.4 Discussion

6.4.1 Interface Cross Sections

In Fig. 39, there is obvious curvature at each cell wall. This is expected since the cell walls form interface boundaries, just as do the grain boundaries. However, the wall-induced curvature ends far from the center of the cell. The center portion of the profile is predominantly flat with some small undulations similar to those seen in Fig. 38 in the x-y plane. This flat region encompasses the center of the cell $\pm \sim 20\mu\text{m}$. Since the z-axis of the microscope can be controlled to within $\pm 0.1\mu\text{m}$, the width of this flat region is more than sufficient to ensure the condition of 2-D curvature for the combination of cell depth and particle size used in this work. Additional observations along a grain boundary groove showed qualitatively similar results.

It is noteworthy that the curvature at the two walls does not appear to be symmetrical. The sample was level along the z-axis to within $\sim 1/4^\circ$ so this apparent

anisotropy is not the result of the instrument being tipped with respect to gravity. It is possible that this lack of symmetry is a result of the z-step size. The interface falls off quickly near $z = 0$ and it is possible that the steep drop-off was missed at the other wall due to the step size granularity. Other z-scans also showed similar anisotropy. Another possible reason for this lack of symmetry is surface energy anisotropy.

6.4.2 Grain Boundary Grooves

It can be seen from Fig. 40 and Fig. 41 that the crystalline phase is comprised of many grains of varying width and crystallographic orientation. Each individual grain has a characteristic color or pattern of colors due to orientation-dependent Bragg scattering. The colorful grains are Bragg scattering visible wavelengths at angles within the NA of the objective. In contrast, the large black grain in the center right of Fig. 40 is Bragg scattering at angles outside of the objective NA. The colloidal liquid rapidly decreases in volume fraction resulting in a gradient in scattering intensity with increasing height in the cell. The volume fraction in the majority of the cell volume is so low that scattered light is below the detection threshold for the exposure duration used to capture this image. The vertical features seen in the crystalline and liquid phases correspond to edges of the individual image frames of this mosaic and are due to slight anisotropy in the darkfield illumination.

An interesting feature was sometimes seen at the solid-liquid interface at high magnification and is worth mentioning in passing. This was the existence of "ghost crystals" extending above the solid-liquid interface into the colloidal liquid. These were regions up to about 8-10 particle diameters in height that appeared to be somewhat ordered, but had much lower contrast in our time-averaged images than the primary

crystalline region. A good example can be seen Fig. 37b at the far right of the image. The lower contrast suggests that the order in these regions fluctuated on a time scale shorter than that used to capture the image. A detailed study of this observation will be left for a future study.

6.4.2.1 Groove Stability

As can be seen in Fig. 49 - Fig. 53, our samples continued to change over time. Therefore, it is important to understand the effect of these changes on the GBGs since our theoretical models assume equilibrium conditions. The most dramatic changes occurred at the extremes crystalline regions. All grain tips continued to grow throughout the course of the experiment. This would be expected given the slow growth of bubbles in the samples. Evaporation of solvent would lead to an increase in suspension volume fraction, which would result in growth of the grain tip toward the evaporation source. This would also explain the increase in crystal height in GB2 of Fig. 53 and the increase in crystal height in GB1 through 62 weeks. However, evaporation does not explain the decrease in GB1 height between 62 and 97 weeks. A possible explanation for this height decrease is a slight rotation of the microscope about the optical axis. The microscope rotation fixture was mounted on a pneumatic vibration isolation table as shown in Fig. 35. It is possible for the table orientation to drift slightly over time, particularly in response to operator disturbances. We measured the orientation of the microscope stage several times during the experiment using a bubble level accurate to $\sim \pm 1/4^\circ$ and could not detect any changes in orientation. However it is possible for significant changes to occur within the range of the experimental error of our measurement. Consider a simple geometric model of the colloidal crystal which neglects the capillarity effect at the grain tip. As can

be seen from Fig. 52, the length of the crystalline region in C204b at 97 weeks was about 15mm. A rotation of this sample by $\frac{1}{4}^\circ$ about the optical axis would result in one end of the crystalline layer being $65\mu\text{m}$ higher than the other end with respect to gravity. The particles would slowly settle and diffuse to regain gravitational equilibrium with the result being an increase in the height of one end of the crystalline layer by $32.5\mu\text{m}$, an equal decrease in the height of the opposite end, and zero net change at the center of the sample. This is more than enough change to account for $\sim 10\mu\text{m}$ decrease in GB1 height between 62 and 97 weeks. This scenario is also qualitatively consistent with the lack of measured change in the same time period for GB2, which was closer to the center of the cell. Operator induced tipping might also give some insight into the varying crystal growth rate seen in Fig. 52. However, instrument tipping does completely explain the unusual behavior seen at the epoxy plug in Fig. 50. The crystalline region starts out looking "normal" in Fig. 50a but is completely melted away from the plug in Fig. 50b. It is partially regrown in Fig. 50c, and is higher than the starting level in Fig. 50d. Given the curvature of the epoxy plug, perhaps this unusual behavior is a combination of contact angle constraints between the crystal and plug, instrument tipping, and slow evaporation.

It is evident from the preceding discussion that the GBGs in our samples are not in perfect equilibrium. Particle diffusion in response to slow evaporation and possibly slight instrument rotations resulted in slow growth and melting of the crystalline regions. However, it can be seen from Fig. 53 that the x-position of the two groove roots studied appeared to remain constant to within the experimental error of our measurements. Overall changes in y-position were $< 30\mu\text{m}$ over an 85 week timeframe and all growth

velocities based on the data from this figure are $< 1\mu\text{m/wk}$. In contrast to the significant changes seen in the grain tip and the region close to the epoxy plug in Fig. 49 and Fig. 50, changes over time in the shape of the GBGs in Fig. 51 are very modest. In GB1, the variation in sharpness of the grain boundary image could be due to variations in focus due to stage positioning or residual immersion oil on the cell surface, or possibly to changes in the GB twist angle. The shape of GB 2 appears to be the same at all times within the resolution of the images. Given the general consistency of the grain boundary shapes seen in Fig. 51 and the very low growth velocities in Fig. 53, it is reasonable to assume equilibrium conditions for our detailed analysis of GBG shapes.

6.4.2.2 Crystal Orientation

Darkfield images of the GBGs used for detailed analysis are shown in Fig. 42. The orientation of the grain on each side of these GBGs was extracted from the images shown in Fig. 46. All of the divergent-beam images shown in Fig. 46 exhibit the characteristics of the rhcp structure except for the image corresponding to C206c-3 RHS. This divergent-beam image lacks the prominent "string art" appearance of Bragg rods. Some of the strongest Kossel lines in this image have near 3-fold symmetry about the approximate center of the image. These lines are consistent with an fcc crystal with (111) nearly parallel to the OA. Other lines in Fig. 46f index to a first order twin of the fcc orientation with (111)//OA, as shown in Fig. 59. The twin is related to the parent crystal through a 180° rotation about (11-1), and the (-1-11) and (-220) planes are aligned in both orientations. Not indexed in Fig. 59 are portions of the (0002) Kossel pair from the LHS grain which can be seen in the upper right portion of Fig 46f. If the display range of

Fig. 46f is manipulated to enhance the dark regions, some evidence of the rhcp structure can be seen. However, the twinned fcc structure clearly dominates in this grain.

The orientations of the OA and $-\mathbf{g}$ for all of the GBG grains are shown in Fig. 60. There are two possible symmetry-related orientations for $\mathbf{c}^*$ and six for $\mathbf{a}_1^*$. For each grain, we chose the crystal orientation in which the angle between the OA and $\mathbf{c}^*$ was $\leq 90^\circ$ and in which the angle between $-\mathbf{g}$ and $+\mathbf{a}_1$ was minimized. In four of the grains, the OA is aligned with the (0001)/(111) pole to within 4° . This suggests that the cell walls influenced crystal orientation by acting as a template on which close-packed planes tended to stack. The C206c-2 grain boundary has a nearly pure tilt character with a 7.9° tilt between the grains about their $\mathbf{c}^*$ axes, which are closely aligned with the OA. The (-12-10) pole of the C206c-2 LHS grain is aligned with $-\mathbf{g}$ to within $<1^\circ$. We will make use of this close alignment in calculating γ . The grains in the other two GBGs have a mixture of tilt and twist in their orientation relationships. It is interesting to note that the orientation of the C206c-1 LHS grain and the parent orientation of the C206c-3 RHS grain are identical to within $<1^\circ$. The study of more grains would be necessary to determine whether this is some sort of preferred orientation or merely a coincidence.

Fig. 59. Indexed Kossel lines from C206c-3 RHS. Black lines correspond to the primary orientation and red lines correspond to the first-order twin.

Fig. 60. Stereographic projection of GBG crystal orientations. The figure shows the standard (0001) hcp projection for ideal c/a . The 3-symbol indices show the corresponding fcc planes. The small symbols mark the orientation of the OA and the large symbols mark the orientation of $-g$. Filled symbols are in the (0001) hemisphere and open symbols are in the (000-1) hemisphere. Left triangles = LHS grains, and right triangles = RHS grains. Red = C206c-1, green = C206c-2, blue = C206c-3, and cyan = C203c-3 RHS twin.

6.4.2.3 Analysis using Isotropic Theory

In order to apply the isotropic theory developed in 5.2, we extracted interface profiles, contact angles, and grain boundary orientation from DIC image mosaics using *Image Pro-Plus* software (Media Cybernetics). For each grain boundary groove, three adjacent frames were captured. The middle frame contained the GBG and the outside frames contained an extended view of the horizontal solid/liquid interface. The center DIC images of these mosaics are shown in Fig. 43 - Fig. 45. Interface profiles were obtained by interactively marking points along an interface using a computer mouse and then exporting the position data to a spreadsheet. First, points along the horizontal interface were captured and fit to a straight line. This line was assumed to be perpendicular to gravity and it deviated from the image x-axis by $0.2 - 1.3^\circ$ in the GBGs selected for analysis. The mosaic image was then rotated to compensate for this misalignment so that the y-axis was parallel to the gravity vector and the x-axis was parallel to the averaged horizontal interface. Data points were then extracted from the curved portion of each side of the grain boundary groove and processed in the following manner. First, all position coordinates were normalized by l_0 . Next, the data was transformed into a standardized orientation for analysis with the horizontal interface extending along the +y-axis and the groove curvature extending along the +x-axis. This was necessary since the analytical expression for the interface given by Eq. 5.53 is in the form of $x = f(y)$. The data was then translated such that $x = 0$ corresponded to the average horizontal position of the planar interface for that grain and $y = 0$ corresponded to the groove root. The groove root was determined by fitting the 4-6 data points nearest the grain boundary to a parabolic model. The groove root was taken as the intersection of

the parabolic curves from the two sides of the groove. The contact angle for each grain was determined using the slope of the tangent to the polynomial fit at the calculated groove root position. In the analysis of GBG 206e-2, we deviated slightly from this procedure in determining the groove root because we found that the z-position for best contrast in the crystalline region varied between the two sides of the GBG. Therefore, two different image sets were used to extract the groove profiles for the RHS and LHS, and the position of the groove root was determined visually for each set. We estimate the accuracy of the contact angle measurements to be about $\pm 5^\circ$.

Grain boundary grooves were chosen in which the grain boundary plane was within 5° of being perpendicular to the field of view. The degree of grain boundary twist about the gravity vector of a candidate GBG was assessed by measuring the lateral shift of the grain boundary position between two known z-axis positions. Grain boundary twist results in distortion of the y-coordinates proportional to the cosine of the twist. [114] By limiting this twist to $<5\%$, this distortion is limited to $< 0.4\%$ and can therefore be neglected. Grain boundary tilt in the image plane was measured either by visually matching a computer-generated line to the grain boundary orientation or by fitting a straight line to a series of data points marked along the grain boundary. We estimate the accuracy of the grain boundary tilt measurements to be about $\pm 1^\circ$. Grain boundary tilt and contact angle measurements for all three GBGs are shown in Table 5. The magnitude of the GB tilt values vary from 3.6° to 8.5° with respect to the vertical. The contact angles vary from 5.9° to 35.6° .

GBG	Side	GB tilt (deg)	Contact angle (deg)
C206e-1	LHS	98.5	26.7
	RHS	81.5	14.4
C206e-2	LHS	93.6	5.9
	RHS	86.4	13.0
C206e-3	LHS	83.1	34.5
	RHS	96.9	35.6

Table 5. Grain boundary tilt and contact angle measurements. Tilt values are given with respect to the horizontal.

The data extracted from the GBG images was fit to Eq. 5.53 using nonlinear least-squares regression implemented in *Mathematica*. Results were generated using four combinations of input and fitting parameters as shown in Table 6. The parameters K , α , and ψ are as defined by Eq. 5.53. The parameter y_0 describes an offset from the average planar interface, which is set to $y = 0$. For models 3 and 4, Eq. 5.53 was modified by replacing y with $(y - y_0)$ to include this offset as a model fitting parameter. For all models, γ_r was calculated from K using Eq. 5.89, converted to γ_{yr} using Eq. 5.82, and corrected for error due to the $\Delta\Pi$ linear approximation using Eq. 5.90.

The results of fitting the GBG profiles to isotropic models 1-4 are shown in Table 7. In some instances, we had to omit data points nearest the horizontal interface in order to avoid failures in the fitting routines. This is understandable since a vertical line, such as the planar crystal/liquid interface in the fitting orientation, has an undefined slope.

	Input Parameters	Fitting Parameters
Model 1	Interface points, α , ψ	K
Model 2	Interface points, α	K, ψ
Model 3	Interface points, α , ψ	K, y_0
Model 4	Interface points, α	K, ψ , y_0

Table 6. Model parameters.

GBG	Side	Model	γ_{rl}	K	ψ (deg)	y_0 (μm)	R^2	Fit
C206c-1	LHS	1	0.42 ± 0.03	0.31 ± 0.01			0.938	poor
		2	0.40 ± 0.05	0.31 ± 0.02	9 ± 10^9		0.952	poor
		3	0.92 ± 0.15	0.46 ± 0.04		-2.1 ± 0.6	0.993	good
		4	0.77 ± 0.15	0.42 ± 0.04	9 ± 10^8	-1.7 ± 0.5	0.996	good
	RHS	1	0.61 ± 0.05	0.38 ± 0.02			0.904	poor
		2	0.58 ± 0.08	0.37 ± 0.02	-9 ± 10^9		0.925	poor
		3	1.33 ± 0.20	0.55 ± 0.04		-1.9 ± 0.6	0.983	good
		4	1.09 ± 0.29	0.50 ± 0.07	-8 ± 10^8	-1.5 ± 0.6	0.985	good
C206c-2	LHS	1	0.76 ± 0.04	0.42 ± 0.01			0.978	fair
		2	0.76 ± 0.10	0.42 ± 0.03	5 ± 490		0.978	fair
		3	0.88 ± 0.12	0.45 ± 0.03		-0.4 ± 0.4	0.984	fair
		4	2.01 ± 0.51	0.68 ± 0.08	49 ± 4	-2.1 ± 0.7	0.997	good
	RHS	1	0.63 ± 0.07	0.38 ± 0.02			0.893	fair
		2	0.61 ± 0.14	0.37 ± 0.04	-4 ± 10^{10}		0.900	fair
		3	0.97 ± 0.09	0.47 ± 0.02		-0.7 ± 0.2	0.990	good
		4	1.13 ± 0.25	0.51 ± 0.06	27 ± 12	-0.9 ± 0.4	0.992	good
C206c-3	LHS	1	0.77 ± 0.13	0.42 ± 0.04			0.685	poor
		2	0.65 ± 0.19	0.39 ± 0.06	-7 ± 10^{11}		0.782	fair
		3	1.76 ± 0.18	0.63 ± 0.03		-1.3 ± 0.3	0.988	good
		4	1.68 ± 0.43	0.62 ± 0.08	33 ± 10	-1.3 ± 0.4	0.988	good
	RHS	1	0.88 ± 0.08	0.45 ± 0.02			0.937	fair
		2	1.09 ± 0.21	0.50 ± 0.05	57 ± 12		0.950	poor
		3	0.63 ± 0.04	0.38 ± 0.01		0.35 ± 0.03	0.979	good
		4	1.06 ± 0.40	0.49 ± 0.09	58 ± 16	0.0 ± 0.2	0.953	fair

Table 7. Results of fitting to isotropic models.

The error bounds shown in Table 7 for K , ψ , and y_0 represent the 95% confidence interval of these fit parameters, and the error bounds on γ_{rl} are derived from the confidence interval of K . The goodness-of-fit statistic, R^2 , is the ratio of the difference between the corrected total sum of squares and the residual sum of squares to the corrected total sum of squares. In addition, we made a visual assessment of each fit as noted in the last column of Table 7. A fit was assessed as good if the model closely matched all of the data without obvious systematic deviations. A fair fit contained moderate systematic deviation, and a poor fit showed significant systematic deviations from the data, especially near the groove root. Fig. 61 contains examples of all three levels of fit assessment. Model 1 was considered a poor fit. Model 2 was a fair fit, and models 3 and 4 were considered good fits. We note that even the good fits often showed localized deviations not observed in the literature for conventional materials in a temperature gradient (e.g. see refs. [59, 106]).

Fig. 61. Isotropic model fits to GBG C206c-3 LHS data. a) model 1, b) model 2, c) model 3, d) model 4.

The values for γ_{rl} in Table 7 range 0.40 to 2.01. However, the goodness of fit, confidence interval of the fit parameters, and reasonableness of the fit parameters must be assessed before accepting these results. We evaluated these results using the following criteria. First, results where the model was determined to be a poor fit to the data were eliminated. Next, results were eliminated where the confidence interval of a fit parameter was unreasonably large, indicating that the model used was inappropriate for the data. This occurred frequently in models 2 and 4 for ψ . Lastly, we eliminated results in which model parameters clearly conflicted with directly measured results. This occurred once, for model 4 with C206c-2 LHS where the predicted value of ψ was clearly out of line with the measured value from Table 5. All predicted values for y_0 were small and fell

within the range of experimental error, indicating that these predicted values were reasonable.

The fitting results after applying the above criteria are shown in Table 8, where eliminated results are shown in light gray text and the reason for elimination is shown in the "fit" column. The remaining predictions for γ_{rl} range from 0.63 to 1.76. The average of these predictions is 1.1 ± 0.4 with the error bar representing the standard deviation of the data. There is no clear trend in the results between fits qualitatively assessed as "good" and "fair", and it is interesting to note that "good" fits span the range of predicted values. We also note that highest predicted values correspond to the orientations in which the c-axis is not aligned with the microscope optical axis (C206c-1 RHS and C206c-3 LHS). The values predicted for C206c-3 where the fcc (111) direction aligns with the microscope optical axis is roughly the same as the range predicted for the rhcp crystals where the c-axis is similarly aligned (C206c-1 LHS, and both sides of C206c-2).

GBG	Side	Model	γ_{rl}	K	ψ (deg)	y_0 (μm)	R^2	Fit
C206c-1	LHS	1	0.42 ± 0.03	0.31 ± 0.01			0.938	PF
		2	0.40 ± 0.05	0.31 ± 0.02	9 ± 109		0.952	PF
		3	0.92 ± 0.15	0.46 ± 0.04		-2.1 ± 0.6	0.993	good
		4	0.77 ± 0.15	0.42 ± 0.04	9 ± 108	-1.7 ± 0.5	0.996	UCI
	RHS	1	0.61 ± 0.05	0.38 ± 0.02			0.904	PF
		2	0.58 ± 0.08	0.37 ± 0.02	-9 ± 109		0.925	PF
		3	1.33 ± 0.20	0.55 ± 0.04		-1.9 ± 0.6	0.983	good
		4	1.09 ± 0.29	0.50 ± 0.07	-8 ± 108	-1.5 ± 0.6	0.985	UCI
C206c-2	LHS	1	0.76 ± 0.04	0.42 ± 0.01			0.978	fair
		2	0.76 ± 0.10	0.42 ± 0.03	5 ± 490		0.978	UCI
		3	0.88 ± 0.12	0.45 ± 0.03		-0.4 ± 0.4	0.984	fair
		4	2.01 ± 0.51	0.68 ± 0.08	49 ± 4	-2.1 ± 0.7	0.997	CEM
	RHS	1	0.63 ± 0.07	0.38 ± 0.02			0.893	fair
		2	0.61 ± 0.14	0.37 ± 0.04	-4 ± 1010		0.900	UCI
		3	0.97 ± 0.09	0.47 ± 0.02		-0.7 ± 0.2	0.990	good
		4	1.13 ± 0.25	0.51 ± 0.06	27 ± 12	-0.9 ± 0.4	0.992	good
C206c-3	LHS	1	0.77 ± 0.13	0.42 ± 0.04			0.685	PF
		2	0.65 ± 0.19	0.39 ± 0.06	-7 ± 1011		0.782	UCI
		3	1.76 ± 0.18	0.63 ± 0.03		-1.3 ± 0.3	0.988	good
		4	1.68 ± 0.43	0.62 ± 0.08	33 ± 10	-1.3 ± 0.4	0.988	good
	RHS	1	0.88 ± 0.08	0.45 ± 0.02			0.937	fair
		2	1.09 ± 0.21	0.50 ± 0.05	57 ± 12		0.950	PF
		3	0.63 ± 0.04	0.38 ± 0.01		0.35 ± 0.03	0.979	good
		4	1.06 ± 0.40	0.49 ± 0.09	58 ± 16	0.0 ± 0.2	0.953	fair

Table 8. Isotropic fit results after evaluation of parameters. PF = poor fit, UCI = unreasonable confidence interval, CEM = conflicts with experimental measurement.

6.4.2.4 Analysis using the Capillarity Vector Approach

In this section we will apply the Arbel-Cahn capillarity vector approach to our GBGs [104]. Recall from section 5.1.1.1 that this model is appropriate for either isotropic or anisotropic systems. For the LHS of C206c-1 and both sides of C206c-2, the c-axis is nearly aligned the optical axis of the microscope. If we neglect the randomness associated with the rhcp structure and model these crystals as hcp, we can use symmetry considerations to obtain absolute values for γ_{rl} . In this treatment, we assume that the c-axis was perpendicular to the image plane, neglecting the small deviations from this condition in our measured orientations. The space group for the hcp structure is $P6_3/mmc$ (No. 194) and the point group associated with this space group is $6/mmm$. When the hcp c-axis is perpendicular to an experimental image, the 6-fold symmetry axis of the $6/mmm$ point group is perpendicular to the image. There are a number of symmetry elements in the image plane, and we chose to measure γ_{rl} for the $\{11-20\}_{hcp}$ family of planes which is perpendicular to the $(10-10)_{hcp}$ family of directions. The $(10-10)_{hcp}$ directions appear as close-packed lines of spheres in the images. In the $6/mmm$ point group, 2-fold symmetry axes lie in these directions. In addition, both $(10-10)_{hcp}$ and $(0001)_{hcp}$ lie in mirror planes. Therefore, $\{11-20\}_{hcp}$ planes meet the symmetry requirements discussed by Arbel and Cahn for obtaining absolute measurements of γ [104]. In order to make use crystal symmetry, two $(10-10)_{hcp}$ directions must intersect the GBG curvature in an image. This is a reasonable constraint since it is possible for the angular range of a GBG to be greater than the minimum angle between $(10-10)_{hcp}$ planes, which is 60° . This constraint was met for all three crystals chosen for analysis. For the LHS of GBG C206c-2, a $(10-10)_{hcp}$

direction is within $<1^\circ$ of the y-axis, so we neglected this slight misalignment and applied Eqs. 5.31 - 5.34. For the remaining two crystals, we used Eqs. 5.27 - 5.30.

We calculated the values needed for the above equations in two ways. First, we used interactive measurements with the *Image Pro Plus* software package to construct lines parallel and perpendicular to the pertinent $(10\text{-}10)_{\text{hcp}}$ directions, and visually placed these lines where the perpendiculars were tangent to the GBG interface. A horizontal line was constructed at the y-value corresponding to the average y-position discussed in the isotropic fitting section. Next, the appropriate area and distances as shown in Fig. 23 were determined using interactive measurements. In the second method, we fit the interface data points extracted from the images to an empirical 10-term polynomial model and calculated the necessary areas and distances analytically. One exception to this second approach was taken with the RHS of GBG C206c-2 when the original calculation did not make sense. The placement of one of the tangent points in the graphical analysis appeared to be at the cusp of a kink, and the granularity of our data points did not capture this feature, thereby introducing significant error in the analytical solution. Therefore, we used the coordinates of the manually placed tangent line in the analytical calculation. We used 0.05762 for the value of B from Eq. 5.75 in accordance with Eq. 5.25 applied to a colloidal system. The sign reversal for the value of B with respect to Eq. 5.75 is due to the transformation of data to analysis coordinates as previously described. The results for all three crystals are shown in Table 9. In this table, we show both the direct results of the calculations described above and values corrected for the linear $\Delta\Pi$ gradient assumption of Eq. 5.75 using Eq. 5.90 as previously described. Though this correction

was developed for isotropic theory, we assumed that the results are also reasonable if γ is anisotropic.

	Graphical analysis		<i>Mathematica</i> analysis	
	uncorrected	corrected	uncorrected	corrected
C206e-1 LHS A	0.682	0.615	0.662	0.597
C206e-1 LHS B	0.679	0.613	0.614	0.553
C206e-2 LHS A	0.630	0.568	0.594	0.535
C206e-2 LHS B	0.684	0.617	0.710	0.641
C206e-2 RHS A	0.688	0.621	0.663	0.598
C206e-2 RHS B	0.645	0.582	0.581	0.523
Average	0.669	0.603	0.645	0.582
Standard deviation	0.026	0.024	0.052	0.047

Table 9. Values for γ_{H} from Arbel-Cahn approach. Corrected values refer to application of correction for linear $\Delta\Pi$ gradient approximation developed for isotropic theory.

The graphical approach yielded an average uncorrected value of 0.67 ± 0.03 and an average corrected value of 0.60 ± 0.02 where the error bounds represent one standard deviation of the data. The analytical approach yielded an average uncorrected value of 0.65 ± 0.05 and an average corrected value of 0.58 ± 0.05 . The results of the two methods agree to within experimental error. Since the result of the analytical approach with gradient correction encompasses the corresponding result using the graphical method, we will use $\gamma_{\text{H}} = 0.58 \pm 0.05$ as the summary result for this analysis.

6.4.2.5 Interfacial Energy Anisotropy

The results of our analysis of GBG data up to this point give indirect indications of anisotropy in γ for hard spheres. The spread of values for γ_H from our isotropic models was quite broad (1.1 ± 0.4) in contrast to our result using the Arbel-Cahn approach (0.58 ± 0.05), which is equally applicable for both isotropic and anisotropic γ . However, the shape of some of our GBGs give a more direct indication of γ anisotropy. As discussed in section 5.1.1.1, Vorhees, et al. showed that there is a critical degree of anisotropy for a crystal with 4-fold symmetry above which a GBG in a thermal gradient will exhibit missing orientations. [137] These missing orientations are manifested in kinks in the GBG shape. This most obvious example of a possible interface kink is marked by a red arrow on the LHS of Fig. 47 where the curvature suddenly flattens out. Kinks also appear to exist in Fig. 43 and Fig. 44, and examples are marked by red arrows in these figures. There may also be kinks in the RHS of Fig. 45, but the contrast in this grain is the poorest of all of the GBG DIC images. Because of this, the presence of kinks in this grain is uncertain. These kinks appear to be direct evidence of missing crystal orientation in the GBGs, which implies that the degree of anisotropy is above the pertinent threshold value. For 4-fold symmetry, Vorhees, et al. showed that missing orientations appeared when $\gamma_4 > 1/15 \cong 0.067$. In section 6.4.2.2, we found that four of the six grains were oriented with close-packed planes nearly perpendicular to the OA. These were the three rhcp grains used for the capillary vector analysis in the preceding section and a twinned fcc crystal. An hcp crystal has 6-fold symmetry in this plane and an fcc crystal has 3-fold symmetry. The relationship for 6-fold symmetry that corresponds to Eq. 5.39 is

$$6.6 \quad \varepsilon(\theta) = 1 + \varepsilon_6 \cos[6(\theta + \theta_0)]$$

Following Vorhees, et al. [137], missing orientations for the 6-fold case first appear when

$$6.7 \quad \varepsilon + \frac{d^2 \varepsilon(\theta)}{d\theta^2} = 1 - 35\varepsilon_6 \cos[6(\theta + \theta_0)]$$

which corresponds to Eq. 5.40 for the 4-fold case. Eq. 6.7 yields missing orientations for $\varepsilon_6 > 1/35 \cong 0.029$. An equivalent treatment for 3-fold symmetry yields missing orientations for $\varepsilon_3 > 1/8 = 0.125$. We found that the RHS grain in Fig. 45 was a twinned fcc crystal. Therefore, the higher ε_3 result would be appropriate to apply. However, the poor contrast in this grain makes the identification of kinks difficult, as described previously. The other three favorably oriented grains had the rhcp structure. Therefore, the smaller of ε_6 and ε_3 would represent a conservative estimate of the lower bound of the anisotropy for a crystal containing a mixture of these two symmetries. Therefore, the presence of interface discontinuities in our data suggests that a conservative estimate for the lower bound of ε_6 for hard spheres is 0.029.

6.4.3 Grain Tips

Significant variations can be seen in the shape of the grain tips shown in Fig. 48. Some tips are blunt while others are pointed, and there is great variation in the interface profile shape. There is also variation in the color patterns of the grain tips. Some are solid blue or black while others have linear striations. Striations would be consistent with variations in Bragg scattering arising from changes in the stacking sequence in an rhcp crystal. Therefore, these striations might represent the projection of close-packed layers

onto the image plane. The height of the grains at the LHS of the images in Fig. 48 are roughly the same.

In Fig. 49, the shape of the grain tip in a single sample, C204b, is shown at various times. Fig. 49a corresponds to Fig. 48a. It can be seen from Fig. 49 that there is significant variation in the shape of the C204b grain tip over time. However, the color in each individual image is relatively uniform and devoid of striations. If the interpretation of grain striations in darkfield images discussed above is correct, then the uniform color in the Fig. 49 images suggests that the close-packed planes in the crystal are close to being perpendicular to the image plane. The change in color from Fig. 49a to Fig. 49b is due to a change from a dry to an oil immersion microscope condenser. We believe the difference in color between Fig. 49b-g and Fig. 49h-i is due to a change in the video camera white balance. Unlike Fig. 48, there are noticeable height differences in the Fig. 49 images, particularly between Fig. 49h-i and the rest of the images in this figure. Crystal height measurements at the LHS of the images in Fig. 49 vary from 79 μm in Fig. 49a to 53 μm in Fig. 49i, with no clear trend except that the Fig. 49h-i crystals are noticeably shorter than the others. We believe that this variation might be partially explained by the presence of particle clumps in the cells. In Fig. 49, the disordered region of the sample scatters uniformly in each image. In Fig. 49d-g, the disordered region appears to extend beneath the crystal, while in Fig. 49h-i, the disordered region appears to terminate close to the tip. This distinction is somewhat ambiguous in Fig. 49a-c. Similar variations can also be seen in Fig. 48, though the clarity of this distinction varies.

We believe that the disordered layer seen beneath the crystal in Fig. 49d-g is due to the presence of small particle clumps that were not broken apart when the dry particles were resuspended during sample preparation. Such clumps would quickly sink to the bottom of the cell forming variations in the effective cell bottom as the tip crystal advances. Such variations can be seen at the particle level at the bottom of Fig. 54. It is not possible to distinguish between colloidal liquid and fused particle clumps. However, irregular variations can be seen in the interface between ordered and disordered regions at the bottom of the crystal. Such an irregular interface would not be expected if, for example, the disordered layer beneath the crystal arose solely from the cell wall being wetted by the colloidal liquid. However, an irregular interface would be consistent with the presence of particle chunks that quickly settled to the bottom of the sample and then formed an irregular layer over which the grain tip advanced as it grew. From interface shape considerations to be discussed in section 6.4.3.3, we place the intersection of the grain tip with the disordered layer as shown by the blue arrow in Fig. 54, setting the height of the disordered layer at about $11\mu\text{m}$. Assuming the disordered layer in Fig. 49i to be of negligible height, the actual height difference between Fig. 49a, and Fig. 49i reduces from $26\mu\text{m}$ to $15\mu\text{m}$ when the disordered layer of Fig. 49a is taken into account. The remaining difference could possibly be the result of anisotropy. [137]

6.4.3.1 Tip Stability

Fig. 52 clearly shows that the tip of sample C204b was not in equilibrium. Tip velocities deduced from this figure range between 6 and $276\mu\text{m/wk}$ in contrast to the estimated maximum vertical velocity of $< 1\mu\text{m/wk}$ for GBGs. Note that these are average velocities calculated from the available data points. It is possible that

instantaneous velocities at any time during the experiment could be significantly different with the uncertainty rising with the space between data points. As discussed previously, the air bubbles in all of the cells grew slowly over time. Typically, these bubbles grew from the right epoxy plug toward the left. In all cases, the grain tips grew from left to right. In the samples used for analysis, the left tip of the bubble remained $> 5\text{mm}$ from the advancing grain tip.

We attribute the bubble growth to slow evaporation from the right epoxy plug. After filling the cell with colloid, epoxy was applied first to the left side of the cell, resulting in epoxy wicking into the cell by capillary action and pushing the suspension toward the opposite end. When epoxy was applied next to the right side, no wicking action took place. Therefore, the RHS epoxy plugs did not extend into the cell. The uncured epoxy appeared to be miscible with decalin and there was likely some mixing of epoxy and suspension before curing was complete. This may have led to microscopic leak paths in the RHS plugs. As decalin slowly evaporated, the local volume fraction would increase leading to diffusion of particles toward the crystal tip, which would then advance toward the bubble.

There are several possible implications of this tip growth scenario to the shape of the tip profile: 1) a modified osmotic pressure profile, 2) 3-D curvature, and 3) non-equilibrium conditions. First, we would expect this diffusion of particles in the horizontal direction to modify the gravity-driven vertical volume fraction profile for the colloidal liquid described by Eq. 5.69. Qualitatively, this horizontal diffusion would tend to increase the local volume fraction. From Eqs. 5.59 and 5.67, it can be seen that this would increase Π_{rf} which would then decrease the absolute value of $\Delta\Pi_{\text{r}}$. Therefore, any

calculation of γ based on experimentally-derived values of K using 5.89 would yield artificially high results. However, if the $\Delta\Pi_r$ profile change were linear, we would still expect our isotropic theory to allow fitting of experimental data. A non-linear $\Delta\Pi_r$ profile change would result in a different family of profile shapes.

The second implication of a growing tip is the possibility of morphological instability. Mullins-Sekerka type instabilities have been observed in hard sphere systems in a microgravity environment [162] and in 1-g experiments with charged colloids [192]. In an equilibrium situation, we would expect the z -profile along a grain tip to resemble the profile shown in Fig. 39 with slight curvature at the cells walls and a wide flat region in the center. Our measured tip profile in C204b at 62 weeks is represented by the highest data points in the x - z plane in Fig. 55. This profile differs from Fig. 39 in that it has the appearance of three slight lobes which are reminiscent of the onset of a Mullins-Sekerka instability [193]. The presence of 3-D curvature implies that the assumption of 2-D curvature implicit in our isotropic theory may be unsupportable. We offer a rudimentary comparison to probe the expected effect of improperly assuming 2-D curvature. Recall from section 5.1.1.1 that the equation for the interface shape with 2-D curvature was derived from the relationship $\Delta G = \gamma/r$ based on a cylindrical geometry. The corresponding relationship for a 3-D spherical geometry is $\Delta G = 2\gamma/r$. Therefore, $\gamma = r\Delta G$ for the 2-D case, and $\gamma = r\Delta G/2$ for the 3-D case. In this simple example of constant radius, a calculation of γ based on a 2-D radius measurement would be high by a factor of 2 if the 2-D relationship was incorrectly applied to 3-D data. We can therefore expect that results derived from our data using isotropic theory to again be artificially high. A detailed Mullins-Sekerka instability analysis of our system is beyond the scope

of this work and will be reserved for future work. However, we note in passing that we observed similar interface instability in a precursor experiment where the growth velocity was driven by gravitational settling in the vertical direction. The instability wavelength scale observed in this precursor experiment was $\sim 30\mu\text{m}$ to $40\mu\text{m}$ which is roughly consistent with the lobe spacing in Fig. 55 of $20\mu\text{m}$ to $38\mu\text{m}$. We also note that the most developed cellular structures in this precursor experiment occurred at an intermediate interface velocity. This is reminiscent of the behavior of conventional materials in a thermal gradient where morphological instability is confined to a finite interface velocity range for a given gradient. [194]

The last implication of a growing tip is a possible violation of the assumption of equilibrium conditions. Depending on the growth rate, a growing tip might have a different shape profile than a stationary tip.

6.4.3.2 Tip Orientation

The orientations of the C204b grain tip at 12 weeks and the C206e grain tip at 96 weeks are shown in Fig. 62. It can be seen from this figure that the angle between the c-axis and the OA is $\sim 10^\circ$ for C204b and $\sim 30^\circ$ for C206e. As described in section 6.3.3, the orientation of the grain tips appeared to rotate along their length. From the divergent-beam OFT dataset taken along the length of C204b at 12 weeks, we found that the orientation rotated 87° about the optical axis over $4400\mu\text{m}$ along the length of the crystal in a uniform manner, giving a rotation rate of $0.020^\circ/\mu\text{m}$ in the clockwise direction from left to right toward the grain tip. Similar rotation was also deduced from qualitative OFT observations of the crystalline tips in other samples.

We propose a simple geometric argument to explain this rotation of the grain tips. In the crystalline phase, volume fraction, ϕ , increases with increasing depth below the horizontal interface according to Eq. 5.72. At the planar interface, $\phi = \phi_m = 0.545$ as discussed in 5.1.1.2. From Fig. 54, we measured the height of the crystal at the tip to be $57\mu\text{m}$. Using Eqs. 5.63 and 5.72, $\phi = 0.575$ at the bottom of the crystal at the tip. By modeling the crystal as an fcc structure for simplicity, we can rearrange Eq. 6.2 using the above values for ϕ and the measured particle diameter to obtain values for the fcc lattice parameter of $0.789\mu\text{m}$ and $0.776\mu\text{m}$ at the top and bottom of the crystal, respectively. If a thin section of crystal one unit cell wide with this lattice parameter distortion from top to bottom were constructed with one side perfectly vertical, the other side would be inclined with respect to the vertical by 0.014° . If a series of such sections were stacked side by side, the crystal structure would appear to rotate in the clockwise direction from left to right. Using the average of the top and bottom lattice parameters, the rotation rate would be $0.018^\circ/\mu\text{m}$, in excellent agreement with our measured rotation rate of $0.020^\circ/\mu\text{m}$. Therefore, we conclude that the rotation observed in the tip crystals is due to the gravity-induced distortion of the crystal lattice normal to the growth direction.

Fig. 62. Stereographic projection of grain tip orientations. The figure shows the standard (0001) hcp projection for ideal c/a . The 3-symbol indices show the corresponding fcc planes. The small symbols mark the orientation of the OA and the large symbols mark the orientation of $-g$. Filled symbols are in the (0001) hemisphere and open symbols are in the (000-1) hemisphere. Red = C204b at 12 weeks and blue = C206e at 96 weeks.

6.4.3.3 Analysis using Isotropic Theory

A DIC image data set was gathered 11 weeks into the experiment when the tip velocity appears to be at a maximum of $276 \mu\text{m/wk}$. It is unlikely that equilibrium conditions can be assumed for this data. In contrast, the 3-D dataset shown in Fig. 55 was taken at 62 weeks when the tip velocity appeared to be at a minimum of $6 \mu\text{m/wk}$. The assumption of equilibrium conditions seems more likely to be appropriate for this data.

Interface data for detailed analysis was extracted from the mosaic image from which Fig. 54 was derived. As described in section 6.3.3, Fig. 54 represents about 10% of the width of a DIC mosaic image of the C204b grain tip taken 11 weeks into the

experiment along 1.2mm of the crystal length. This data set was taken at the center of the cell with respect to the optical axis of the microscope. In contrast to the GBG data, some of the fundamental assumptions of our isotropic theory are questionable for this tip data as discussed in 6.4.3.1. In spite of these possible assumption violations, we will attempt to fit interface data extracted from the mosaic image using our isotropic theory and take these possible violations into consideration when interpreting the results.

The leftmost 800 μm -portion of the mosaic image was used to establish the position of the horizontal interface. Interface points were extracted along the 300 μm portion of the image closest to the grain tip. As described at the beginning of section 6.4.2, we believe that there is an irregular layer of clumped particles between the tip crystals and the cell bottom. We placed the intersection of the grain tip with this disordered layer at a point where the interface curvature changed sharply. The height of this point is consistent with the height variation of disordered regions seen beneath the crystal in the image mosaic. Assuming that the disordered layer is horizontal at the point of intersection, we measured the contact angle to be 42° . However, it is possible that the disordered layer was curved, which would result in a smaller contact angle. Therefore, there is a great deal of uncertainty associated with this contact angle measurement. We fitted data points up to $\sim 75\mu\text{m}$ from the tip to the 4 isotropic models used for the grain boundary data. Fit attempts including data points along greater lengths of the interface failed. The data points and fitted curves are shown in Fig. 63 and the fitting results are shown in Table 10. As can be seen in Fig. 63, model 4 failed, and the remaining models returned poor fits. Therefore, we do not consider any of the values for γ_{rl} shown in Table 10 to be valid.

Fig. 63. Fits of C204b tip interface data to isotropic models. a) model 1, b) model 2, c) model 3.

Model	γ_{rl}	K	ψ (deg)	y_0 (μm)	R^2	Fit
1	17 ± 2	1.9 ± 0.1			0.831	poor
2	14 ± 3	1.7 ± 0.2	66 ± 38		0.889	poor
3	7 ± 2	1.2 ± 0.2		0.29 ± 0.05	0.883	poor
4						failed

Table 10. Results of fitting C204b grain tip data to isotropic models.

We also tried to estimate γ_{rl} from the grain tip depth and the overall crystal depth at the tip. The tip of the crystal corresponds to the minimum of $x[y]$, which occurs at

$y = 0$ in Eq. 5.79. It can be seen from inspection of Eq. 5.79 that $y = 0$ when $\gamma = f(y)$ and y is the vertical distance between the planar interface and the tip of the crystal. This distance was determined to be $36.5\mu\text{m}$ from the C204b DIC mosaic and we used Eq. 5.76 to calculate a corresponding value of 6.0 for γ_{rl} .

It can also be seen from Eq. 5.79 that the interface shape terminates at the point where the radicand equals zero, which occurs when $2\gamma = f(y)$. Larger values of $f(y)$ would result in a negative square root. Therefore, the maximum height of the crystal is given by $\gamma = f(y)/2$ when y is the overall depth of the crystal below the planar interface when $\psi = 0$ and $\alpha = 180^\circ$. As previously discussed, we determined the contact angle at the intersection of the grain tip with the disordered boundary layer to be 42° . Therefore, we proceeded by solving Eq. 5.53 for K with $\psi = 42^\circ$, $\alpha = 180^\circ$, and y equal to the measured depth of the crystal. We then used Eq. 5.89 to obtain γ from K and applied the correction for the linear $\Delta\Pi$ gradient using Eq. 5.90 to obtain $\gamma_{\text{rl}} = 8.7$. As previously discussed, there is great uncertainty in the contact angle measurement due to the uncertainty in the local shape of the disordered layer. From the range of contact angles measured for GBG in Table 5, we would expect this uncertainty to be in the direction of a smaller contact angle, which would result in even larger values of γ_{rl} .

In Fig. 64, the C204b data used for fitting is plotted along with the fitted curves based on isotropic model 3 (fitting K and y_0), tip depth, and overall crystal depth at the tip. The values for γ_{rl} corresponding to the model 3, tip depth and crystal depth curves are 7, 6.0, and 8.7, respectively. Though these values are reasonably close to each other, they are about an order of magnitude larger than the values obtained from GBGs, and it can be seen from the figure that none of these curves are good fits to the data.

Fig. 64. C204b grain tip data and selected isotropic model fits. Blue line = isotropic model 3 (fitting K and l_0 , same as Fig. 63c), green line = K derived from grain tip depth, and red line = K derived from overall crystal depth.

We suggest 4 possible reasons for the poor fits to the data in Fig. 64 and for the discrepancy between values of γ_{tl} obtained from tip and GBG data : 1) the osmotic pressure gradient leading to Eq. 5.89 differed from that developed in our theory, 2) the curvature was not 2-D, 3) the grain tip was not in equilibrium, and 4) γ is anisotropic. In section 6.4.3.1, we concluded that this first possibility of a modified osmotic pressure gradient due to horizontal diffusion of particles toward a growing tip would lead to inflated values of γ_{tl} using our isotropic theory. This is consistent with our results from tip data with respect to our GBG results, which are roughly an order of magnitude smaller. We therefore conclude that a modified osmotic pressure gradient might be at least partly responsible for these high values. However, this would not affect the ability to fit data to our isotropic theory unless the $\Delta\Pi$ change was nonlinear.

The second possible reason for poor tip fits is that the C204b tip violated the assumption of 2-D curvature at 11 weeks. Given the common tip depth measurement between weeks 11 and 62, it is very possible that the z-profile at week 11 is similar to Fig. 55, which was taken at 62 weeks. Since a tip with a 2-D profile comparable to the 2-D profile shown in Fig. 39 was never observed, this possibility cannot be tested rigorously with the available data. However, our simple comparison between 2-D and 3-D curvature in section 6.4.3.1 predicted artificially high values of γ_{tl} to result from improperly assuming 2-D curvature. Therefore, we conclude that 3-D curvature is a contributing factor to the high values obtained from tip data. It is also very likely that 3-D curvature contributed to the poor fits, though the development of predictions for 3-D curvature in our system is beyond the scope of this work.

The third possible reason for the difficulties with the tip data is that the system was out of equilibrium. We can test this possibility by comparing the above results obtained at the maximum observed tip velocity to data from the minimum observed tip velocity at 62 weeks. We do this by comparing tip depths. From the darkfield mosaic corresponding to Fig. 49g, we measured the vertical distance between the planar interface and the tip of the crystal to be $(33 \pm 3)\mu\text{m}$, which agrees with the measurement from 11 weeks to within experimental error. This indicates that the large values of γ_{tl} obtained from the C204b tip data and the corresponding poor fits are probably not due to variations in tip velocity. However, this is not conclusive evidence of equilibrium. Voorhees, et al. [137] showed that groove depth varies with crystal orientation when γ is anisotropic. This corresponds to tip depth for our grain tips. Therefore, it is conceivable

that a height difference resulting from tip velocity might be offset by a height difference arising from anisotropy.

The fourth possible reason for the poor tip fits is anisotropy in γ . We showed in section 6.4.2.5 that kinks observed in GBG profiles suggested an anisotropy factor $\varepsilon_6 > 0.029$. Kinks in grain tip profiles also exist. They are most prominent in Fig. 56 and Fig. 57 but can also be seen in Fig. 48, Fig. 49, and Fig. 54. We conclude that γ anisotropy is also a likely factor in the poor fits to tip data. Also, we note that if γ is anisotropic, the observed rotation of the crystal orientation as a function of position may further complicate the interface shape and contribute to the poor fits.

In summary, it appears likely that 3-D curvature and anisotropy in γ contributed to the poor fits of the grain tip data to isotropic models. The consistently high values of γ_{H} obtained from tip data might be related to a modified osmotic pressure gradient and 3-D curvature. It is uncertain whether or not tip growth rates contributed to these issues. Given the osmotic pressure gradient and 3-D geometry concerns, we did not apply the capillary vector model to grain tip data, since this model also relies on these assumptions.

Despite the difficulties with our particular samples, we note several potential advantages of grain tips over GBG's. First, the grain tips contain > 5 times the vertical height of typical GBGs. Second, they contain up to 180° of interface orientations (depending on the contact angle at the tip termination) compared to a maximum of 90° for GBGs. Both of these advantages could result in increased accuracy for both the isotropic and capillary vector approaches when applied to equilibrium grain tips compared to GBGs. In particular, the increased range of accessible crystallographic orientations would be a significant advantage with the capillary vector approach for

systems with less than six-fold symmetry. For example, a system with four-fold symmetry requires a sample with a "perfect" vertical orientation and a zero contact angle in order to make the required absolute reference measurement for γ as described in 5.1.1.1.2. It would be impossible to extract an absolute measurement from a sample with only three-fold symmetry with GBGs. However, this is well within the realm of possibility with an equilibrium grain tip. These potential advantages of grain tips over GBGs suggest that they should be pursued in future studies in both colloidal systems and conventional materials. In the case of the latter system, an appropriate tilt of the temperature gradient with respect to the cell wall might produce useful grain tips.

6.4.3.4 Interfacial Energy Anisotropy

We found in 6.4.2.5 that the presence of kinks in the interface profile of GBGs suggested a minimum bound for the anisotropy of γ . Similar kinks are also appear to be present in grain tips as can be seen from Fig. 48, Fig. 49, Fig. 54, Fig. 56, and Fig. 57. Apparent kinks are marked in the latter three of these figures. Given the questions about tip stability discussed in 6.4.3.1, we did not attempt to use tip data to refine the minimum bound estimate. Rather we point to the frequent presence of apparent interface kinks in grain tips as further qualitative evident of appreciable anisotropy in γ .

6.4.4 Comparison with Literature Results

In this section, we compare our experimental results for γ with results from the literature, which were discussed in 5.1.1.2.3 . We do so only for the GBG results since factors discussed in 6.4.3 precluded quantitative results from the grain tips. Our results are summarized along with the literature results in Table 11 and Fig. 65.

Isotropic models applied to our 6 GBG profiles produced values for γ_{rl} ranging from 0.63 to 1.76 with an average value of 1.1 ± 0.4 . These results fall within the range of 0.1 – 4.0, which encompasses the literature results. However, only several of our results fall within the narrower range of 0.28 – 0.70 which encompasses the majority of the literature predictions. Also, our average result is higher than this narrower range, though the lower end of our error interval nearly coincides with the upper end of this range.

We also compared the spread of our isotropic model results with typical results in the literature from GBG measurements in a thermal gradient. In two papers, results are presented for 10 GBGs each for three alloy systems (solid Al – liquid AlCu, solid Al – liquid AlSi, and Zn solid solution in Zn-Al Eutectic liquid). [112, 118] The ratio of the standard deviation of the data to the mean value for γ in these works varies from 0.05 to 0.07. In contrast, the same ratio for our results is 0.4, approximately an order of magnitude higher.

There are several possible reasons for this large spread of results. First, 10 GBG pairs are represented in each cited paper from the literature, whereas our data represents only 3 GBG pairs. Therefore, the larger spread of our data could be due to the limited dataset. Another possibility is that our system is significantly more anisotropic than those used in this comparison. It is possible that both our hard sphere colloids and the comparison systems have anisotropy, but the cited studies may have systematically avoided GBGs exhibiting anisotropy. A similar report by several of the same authors cites GBG symmetry as a selection criterion. [110] In contrast, we did not enforce such a criterion. In fact, we sought to represent a variety of GBG shapes in our analysis. The

inconsistency in fitting our data to isotropic models, the large spread of our results, and the high value of γ_{sl} predicted by our isotropic models compared to the majority of literature results seems to indicate that isotropic models are less than ideal for fitting our GBG data.

Using the Arbel-Cahn capillary vector approach, we obtained $\gamma_{rl} = 0.58 \pm 0.05$ for the $\{110\}_{fcc}/\{11-20\}_{hcp}$ plane from analysis of 3 grains which were suitably oriented to extract absolute data for γ . All published results are for an fcc solid phase, and our results are for an rhcp solid phase indexed to the hcp system. In the standard hcp/fcc epitaxy, $(0001)_{hcp} // (111)_{fcc}$ and $[11-20]_{hcp} // [-110]_{fcc}$. [17] This epitaxy relationship holds true for an rhcp crystal. In this epitaxy relationship, $\{11-20\}_{hcp}$ planes corresponds to $\{110\}_{fcc}$ planes. Using Monte Carlo computer simulations, Pronk and Frenkel calculated γ_{rl} between hcp and fcc to be the extremely small value of $26 \pm 6 \cdot 10^{-5}$. [195] Strictly speaking, this value would apply to the interface between $(0001)_{hcp}$ and $(111)_{fcc}$, but given the extremely small value obtained by Pronk and Frenkel, it is reasonable to equate other corresponding planes between fcc and hcp. Therefore, we compare our results for $\{11-20\}_{hcp}$ planes with literature results for $\{110\}_{fcc}$ since no predictions for rhcp crystals are available in the literature.

Our capillary vector result of $\gamma_{rl} = 0.58 \pm 0.05$ falls in the middle of the 0.28 - 0.70 range, which encompasses the majority of the published theoretical predictions and experimental results as discussed in 5.1.1.2.3. Our result overlaps the experimental results of Marr and Gast for silica spheres [43] and of Palberg for $0.402\mu\text{m}$ -diameter PMMA spheres [44] and is close to Palberg's result for $0.890\mu\text{m}$ -diameter spheres PMMA [44]. It differs considerably from the low value obtained by Gasser, et al. [21]

The good or reasonable agreement between our result and all but one of the CNT experimental results implies that the uncertainties in these approaches [45] might not be so significant after all. However, further GBG results for hard spheres are necessary before drawing firm conclusions.

Our capillary vector result agrees to within experimental error with four of the eight computer simulation studies shown in Table 11 which report values for γ_{110} . Five remaining computer simulations did not make specific predictions for γ_{110} . However, results for non-hard sphere systems predict the order of magnitudes to be $\gamma_{100} > \gamma_{110} > \gamma_{111}$, as discussed in 5.1.1.2.3. It can be seen in Table 11 that the value of γ_{110} is very close to γ_0 for the three simulation studies that also obtained this ordering of magnitudes. Therefore, it is reasonable to compare our result with γ_0 values for the remaining five computer simulations, and our result overlaps 3 of them. In addition, our result agrees to within experimental error with the Turnbull empirical correlations given by Marr [37]. To summarize, our result for γ_{110} using the Arbel-Cahn capillary vector approach agrees with the majority of the previous studies of γ for hard spheres to within experimental error.

In addition, the spread of the capillary vector results was much smaller than for the isotropic models. From Table 9 for the capillary vector results, the ratio of the standard deviation to the average value is 0.04 for the graphical method and 0.08 for the analytical method. In contrast to our isotropic fitting results, these values are in line with literature thermal gradient results as discussed above.

The presence of interface kinks in three grains with (0001)/(111) perpendicular to the image plane suggested a minimum anisotropy for hard spheres of $\varepsilon_6 = 0.029$. As can

be seen in Table 11, our lower limit is equal to the value of predicted by Kyrilidis and Brown [36], and is greater than 4 of the remaining 7 literature results for ε_4 . Note however, that our lower bound is not directly comparable to the literature values because it represents the anisotropy for a different symmetry. However, both ε_4 and ε_6 represent the dominant term of a spherical harmonic expansion for their respective symmetries. Therefore, our result is a useful rough comparison to the literature results.

In summary, the results of fitting our GBG data to isotropic models fell within the overall range of literature predictions, but were in poor agreement with the majority of literature results. In contrast, our result for γ_{110} using the Arbel-Cahn capillary vector approach was in excellent agreement with the majority of literature results. The primary difference between these models is that the capillary vector model can handle anisotropy in γ but the isotropic models cannot. Therefore, these results are consistent with an appreciable anisotropy in γ for hard spheres. In addition, the presence of interface kinks in three rhcp grains with (0001)/(111) perpendicular to the image plane suggest a minimum anisotropy for hard spheres of $\varepsilon_6 = 0.029$. This value is equal to or greater than the value of ε_4 for 4 of 8 values reported in the literature. The excellent agreement between our capillary vector result and the majority of the literature results is a good indication of the validity of our adaptations of GBG techniques to colloidal systems.

Theory/Computer Simulations

	method	γ_{100}	γ_{110}	γ_{111}	γ_0	ϵ_4	relative magnitudes	Ref.
McMullen and Oxtoby (1988)	DFT	1.766	1.767	1.762	<i>1.765</i>	~ 0	isotropic	[30]
Oxtoby and McMullen (1988)	DFT			4.00	4.00			[31]
Curtin (1989)	DFT	0.66(2)		0.63(2)	<i>0.56(2)</i>		$\gamma_{100} \succ \gamma_{111}$	[32]
Marr and Gast (1993)	DFT			0.60(2)	0.60(2)			[33]
Ohnesorge, Lowen, and Wagner (1994)	DFT	0.35	0.30	0.26	<i>0.30</i>	0.077	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[34]
Marr and Gast (1995)	DFT	0.70(1)	0.70(1)	0.70(1)	<i>0.70(1)</i>	0	isotropic	[35]
Kyrlidis and Brown (1995)	DFT	0.34	0.32	0.37	<i>0.34</i>	0.030	$\gamma_{111} \succ \gamma_{100} \succ \gamma_{110}$	[36]
		0.35	0.33	0.37	<i>0.35</i>	0.029		
		0.28	0.25	0.30	<i>0.28</i>	0.057		
Marr (1995)	EC				0.56			[37]
					0.54			
Marr (1995)	MD	0.53(3)	0.56(3)	0.55(3)	<i>0.55(3)</i>	0.028	$\gamma_{110} \succ \gamma_{111} \succ \gamma_{100}$	[37]
Choudhury and Ghosh (1998)	DFT			0.33	0.33			[38]
Davidchack and Laird (2000)	MD	0.62(1)	0.64(1)	0.58(1)	<i>0.61(1)</i>	0.016	$\gamma_{110} \succ \gamma_{100} \succ \gamma_{111}$	[39]
Cacciuto, Auer and Frenkel (2003)	MC				0.616(3)			[40]
Mu, Houk, and Song (2005)	MC	0.64(2)	0.62(2)	0.61(2)	0.62(2)	0.016	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[41]
Davidchack and Laird (2005)	MD	0.592(7)	0.571(6)	0.557(7)	<i>0.573(5)</i>	0.018	$\gamma_{100} \succ \gamma_{110} \succ \gamma_{111}$	[42]
Experiments								
Marr and Gast (1994)	IT				0.55(2)			[43]
Palberg (1999)	IT				0.50(1)			[44]
					0.54(3)			
Gasser, et. al (2001)	SA				0.11			[21]
This work - isotropic models	GBG				1.1(4)			
This work - capillary vector model	GBG		0.58(5)		0.58(5)			

Table 11. Summary of values of γ_{H} for hard spheres. DFT = density functional theory, EC = empirical correlation, MC = Monte Carlo, MD = molecular dynamics, IT = induction time, SA = equilibrium distribution of surface area, GBG = grain boundary groove. Values in parentheses are error bounds of the last significant digit. Italicized values for γ_0 are averaged values of the preceding columns.

Fig. 65. Comparison with published values of γ_{rl} . Results of theoretical calculations and computer simulations are shown as circles and experimental results are triangles. Abbreviations are the same as in Table 11. Inset: Subset of main graph showing values where $\gamma < 1.5$. Error bars are shown where reported.

6.5 Summary and Conclusions

In this Chapter, we tested the GBG techniques discussed in Chapter 5 by performing experiments with well-characterized PMMA/PHSA spheres in cis-decalin using an optical microscope that was rotated such that the optical axis was perpendicular to the gravity vector. First, we discussed data on the solid-liquid interface profile in the direction of the optical axis to test the validity of assuming a 2-D interface geometry. Next, we examined detailed interface and orientation data on three sets of GBGs. We also observed and gathered data on grain tips which were present at the termination of the

crystalline region of our samples. These grain tips were unanticipated and resulted from a slight side-to-side tilt of our samples. They continued to grow laterally into the colloidal liquid throughout the course of the experiments and the crystal orientation rotated along the length of each tip. The major results and observations of our experiments are summarized as follows:

- 3-D data taken along the optical axis of the microscope verified the validity of the 2-D geometry assumption for GBGs. Also, data indicated the reasonableness of assuming that the GBGs were in equilibrium.
- The fit of GBG profiles to isotropic models was inconsistent, and results from isotropic models yielded values for γ_{rl} that were higher than majority of the literature results. In addition, the spread of γ -values from isotropic models was about an order of magnitude greater than representative results from the literature. These results are consistent with an appreciable anisotropy in γ for hard spheres.
- The crystal orientations of 3 of the 6 grains studied were suitable for extraction of absolute γ -values using the capillary vector approach, which is not limited to isotropic γ . From these 3 grains we extracted a value for γ_{rl} of 0.58 ± 0.05 for the $(11-20)_{hcp}/(110)_{fcc}$ plane, which coincides with the majority of published values for hard spheres to within experimental error. This agreement includes two of the three previous experimental results based on CNT and the two most recent computer simulations.
- Data indicated that the grain tips violated the 2-D geometry assumptions of our models. In addition, slow evaporation may have modified the $\Delta\Pi$ gradient from the assumptions used to determine the linear approximation to the $\Delta\Pi$ gradient. The

interface profile for one grain tip studied in detail could not be fit to isotropic models at all. We conclude that the factors described above precluded the extraction of quantitative results from our grain tips. We did not attempt to fit the tip data to capillary vector models.

- We observed that the grain tips provided > 5 times the interface height and about twice the range of accessible crystallographic orientations as typical GBGs. Therefore, grain tips in equilibrium may be a better source of data than GBGs for determining γ in both colloidal systems and in atomic/molecular systems using temperature gradients.
- We observed kinks in the interface profiles of GBGs and grain tips. The presence of interface kinks in three rhcp grains with (0001)/(111) perpendicular to the image plane suggest a minimum anisotropy for hard spheres of $\epsilon_6 = 0.029$.
- Our use of darkfield and DIC imaging to access both the microstructural and particle length scales of our samples illustrates the usefulness of multilength scale imaging in colloidal studies. Darkfield imaging on the microstructural length scale allowed us to survey entire sample cells, and DIC imaging on the particle length scale facilitated the extraction of accurate interface profiles.

From these results and observations we draw the following conclusions:

- Anisotropy in γ is the likely reason that fits of GBG data to isotropic models produced a wide spread of results which were in fair to poor agreement with literature values.

- The capillary vector result of $\gamma_{110} = 0.58 \pm 0.05$ is the best quantitative result of this study. The excellent agreement of this result with the majority of literature values indicates that our adaptations of GBG techniques to colloidal systems are valid.
- The observation of kinks in the GBG and grain tip interface profiles suggests a minimum anisotropy for hard spheres of $\varepsilon_6 = 0.029$.
- Grain tips may provide a richer source of data for measuring γ than GBGs for both colloids in a $\Delta\Pi$ gradient and conventional materials in a temperature gradient.
- Imaging on multiple length scales was critical to the success of our experiments.

Chapter 7

Concluding Remarks

7.1 Summary and Conclusions

We have developed two techniques for extracting lattice parameter and orientation data from randomly oriented single colloidal crystals, developed adaptations of GBG techniques for measuring γ for colloidal systems in a gravitational field, and validated these techniques and adaptations in experiments with hard sphere colloids using optical microscopy.

In Part I, we developed two techniques for in-situ crystallography of colloidal crystals using optical microscopy. Chapter 2 developed a parallel-beam approach, and Chapter 3 developed a divergent-beam approach. Both techniques were tested using hard sphere colloidal crystals. In Chapter 4, we compared the two techniques. We found that:

- the divergent-beam approach was easier to implement, but
- the parallel-beam approach was more robust in some scenarios with rhcp crystals.

Namely, the divergent-beam approach failed when Bragg rods were close to being tangential to the Ewald sphere. Also, we anticipate that the divergent-beam approach would fail near maximum randomness in plane stacking where the intensity distribution along the Bragg rods is continuous. The parallel-beam approach was successful in the first scenario, and we expect that it would also be successful in the latter.

- initial tests of both techniques suggest that they are suitable for extracting lattice parameters to within about 1% and orientation data to within about 2°.

In Part II, we adapted several GBG techniques to colloids in a gravitational field and tested these techniques with experiments using hard sphere colloids. In Chapter 5, we adapted the Bolling and Tiller GBG technique for conventional materials in a temperature gradient to colloids in a gravitational field. In particular, we:

- developed a generalized equation describing the 2-D shape of an equilibrium interface balanced against a known variable,
- generalized existing analytical expressions for the interface to be functions of both contact angle and inclination of a planar bounding surface,
- used this generalized equation to develop an isotropic model for the solid/liquid interface shape in a hard sphere colloidal system in a gravitational field,
- demonstrated the validity of assuming a linear $\Delta\Pi$ gradient so that these analytical expressions could be used to derive γ from experimental data, and
- derived a correction factor to eliminate the systematic error associated with assuming a linear gradient.

These developments allowed the application of the Bolling-Tiller GBG approach to colloidal systems. The linear $\Delta\Pi$ gradient assumption is also applicable to the capillary vector approach, which is not limited to isotropic systems, and we expect that the corresponding correction factor is a reasonable first approximation for anisotropic cases as well.

In Chapter 6, we tested the GBG techniques discussed in Chapter 5 by performing experiments with well-characterized PMMA/PHSA spheres in cis-decalin using an optical microscope that was rotated such that the optical axis was perpendicular to the gravity vector. We gathered data to confirm our 2-D geometry assumption for GBGs and detailed interface and orientation data on three sets of GBG's for analysis. We also observed and gathered data on grain tips which were present at the termination of the crystalline region of our samples. These grain tips were unanticipated and resulted from a slight side-to-side tilt of our samples. They continued to grow laterally into the colloidal liquid throughout the course of the experiments, and the crystal orientation rotated along the length of each tip. We obtained results from GBGs of $\gamma_0 = 1.1 \pm 0.4$ using isotropic models and $\gamma_{110} = 0.58 \pm 0.05$ using the capillary vector model. The latter is in close agreement with the majority of the literature results while the former is not. Violation of the 2-D geometry assumption and other factors precluded quantitative results from grain tip data. We drew the following conclusions from our experimental results:

- Anisotropy in γ is the likely reason that fits of GBG data to isotropic models produced a wide spread of results which were in fair to poor agreement with literature values.
- The capillary vector result of $\gamma_{110} = 0.58 \pm 0.05$ is the best quantitative result of this study. The excellent agreement of this result with the majority of literature values indicates that our adaptations of GBG techniques to colloidal systems are valid.
- The observation of kinks in the GBG and grain tip interface profiles suggests a minimum anisotropy for hard spheres of $\varepsilon_6 = 0.029$.

- Grain tips may provide a richer source of data for measuring γ than GBGs for both colloids in a $\Delta\Pi$ gradient and conventional materials in a temperature gradient.
- Imaging on multiple length scales was critical to the success of our experiments.

In summary, we have developed two techniques for extracting lattice parameter and orientation data from randomly oriented single colloidal crystals, developed adaptations of GBG techniques for measuring γ for colloidal systems in a gravitational field, and validated these techniques and adaptations in experiments with hard sphere colloids using optical microscopy. Though only hard spheres were used in our experiments, these techniques are not limited to this system. The crystallography techniques are applicable to any index-matched system and portions could be adapted to backscattering observations in suspensions that are not index-matched. The GBG techniques should be applicable to any crystallizing colloid for which the solid and liquid equations of state can be calculated. We anticipate that our techniques will find wide application in the study of crystallizing colloids, both as precursors to engineering materials such as photonic crystals and as physical models.

7.2 Future Work

This work is a first step in the *in-situ* crystallography of single colloidal crystals and the use of GBG techniques with colloids, and there are many possible extensions. Examples of specific extensions to our hard sphere experiments include:

- conducting further analysis of the existing GBG data using the capillary vector approach to extract values for γ as a function of orientation. In particular, it might be possible to produce a Wulff plot for the $\langle 111 \rangle$ zone.

- gathering data on more GBGs to increase the accuracy of the γ -value obtained from this work and extend the knowledge of γ as a function of orientation in the hard sphere system.
- performing experiments with other sizes of spheres to test the assumption that γ scales with σ^2 .
- constructing well-sealed samples cells with the hope of observing and gathering data on grain tips in equilibrium.

Farther reaching possibilities include:

- using our *in-situ* crystallography techniques to characterize index-matched colloidal precursors to photonic crystals.
- applying our adapted GBG techniques to other colloidal systems. The charged-sphere system is particularly appealing since it is possible to avoid the ambiguities introduced by the rhcp structure of hard spheres. Charged spheres at various ionic strengths could be used to explore γ for both fcc and bcc solid phases. [46]
- attempting to create grain tips using atomic or molecular systems in a temperature gradient. It would probably be easiest to try with a transparent system, and most useful to do so with a system for which γ has already been measured such as succinonitrile or pivalic acid [126].

In addition, we made several qualitative observations which deserve a closer look. It would be interesting to perform in-depth studies of:

- the possible Mullins-Sekerka instability discussed in 6.4.3.1. Mixtures of suspending fluids could be used to create varying $\Delta\Pi$ gradients.

- the "ghost crystals" sometimes seen at the solid-liquid phase boundary discussed in 6.4.2. Time-resolved confocal microscopy would be an excellent tool for this.

These are but a few examples of the many possible studies that could build upon this work.

References

- [1] Yablonovitch, E. "Inhibited spontaneous emission in solid-state physics and electronics." *Phys. Rev. Lett.* 58, no. 20 (1987): 2059-2062.
- [2] John, S. "Strong localization of photons in certain disordered dielectric superlattices." *Phys. Rev. Lett.* 58, no. 23 (1987): 2486-2489.
- [3] Joannopoulos, J. D., R. D. Meade, and J. N. Winn. *Photonic Crystals: Molding the Flow of Light*. Princeton: Princeton University Press, 1995.
- [4] Pusey, P. N. "Colloidal suspensions." In *Les Houches Session LI: Liquids, Freezing, and the Glass Transition*. ed. J. P. Hansen, D. Levesque and J. Zinn-Justin. Amsterdam: North-Holland, 1991, 765-942.
- [5] Poon, W. C. K., and P. N. Pusey. "Phase transition of spherical colloids." In *Observation, Prediction and Simulation of Phase Transitions in Complex Fluids*. ed. M. Baus et al. Netherlands: Kluwer Academic Publishers, 1995, 3-51.
- [6] Astratov, V. N., V. N. Bogomolov, A. A. Kaplyanskii, A. V. Prokofiev, L. A. Samoilovich, S. M. Samoilovich, and Y. A. Vlasov. "Optical spectroscopy of opal matrices with CdS embedded in its pores: Quantum confinement and photonic band gap effects." *Nuovo Cimento D* 17, no. 11-12 (1995): 1349-1354.
- [7] Tsunekawa, S., Y. A. Barnakov, V. V. Poborchii, S. M. Samoilovich, A. Kasuya, and Y. Nishina. "Characterization of precious opals: AFM and SEM observations, photonic band gap, and incorporation of CdS nano-particles." *Microporous Mater.* 8, no. 5-6 (1997): 275-282.
- [8] Bogomolov, V. N., S. V. Gaponenko, I. N. Germanenko, A. M. Kapitonov, E. P. Petrov, N. V. Gaponenko, A. V. Prokofiev, A. N. Ponyavina, N. I. Silvanovich, and S. M. Samoilovich. "Photonic band gap phenomenon and optical properties of artificial opals." *Phys. Rev. E* 55, no. 6 (1997): 7619-7625.
- [9] Wijnhoven, J. E. G. J., and W. L. Vos. "Preparation of photonic crystals made of air spheres in titania." *Science* 281, no. 5378 (1998): 802-804.
- [10] Holland, B. T., C. F. Blanford, and A. Stein. "Synthesis of macroporous minerals with highly ordered three-dimensional arrays of spheroidal voids." *Science* 281, no. 5376 (1998): 538-540.
- [11] Wang, D. Y., V. Salgueirino-Maceira, L. W. Liz-Marzan, and F. Caruso. "Gold-silica inverse opals by colloidal crystal templating." *Adv Mater* 14, no. 12 (2002): 908-912.

- [12] Miguez, H., N. Tetreault, S. M. Yang, V. Kitaev, and G. A. Ozin. "A new synthetic approach to silicon colloidal photonic crystals with a novel topology and an omnidirectional photonic bandgap: Micromolding in inverse silica opal (MISO)." *Adv Mater* 15, no. 7-8 (2003): 597-600.
- [13] Jiang, P., J. F. Bertone, and V. L. Colvin. "A lost-wax approach to monodisperse colloids and their crystals." *Science* 291, no. 5503 (2001): 453-457.
- [14] Bragg, L., and J. F. Nye. "A dynamical model of a crystal structure." *Proceedings of the Royal Society of London Series A-Mathematical and Physical Sciences* 190, no. 1023 (1947): 474-481.
- [15] Jackson, K. A., and J. D. Hunt. "Transparent compounds that freeze like metals." *Acta Met.* 13 (1965): 1212-1215.
- [16] Pusey, P. N., and W. van Megen. "Phase-behavior of concentrated suspensions of nearly hard colloidal spheres." *Nature* 320, no. 6060 (1986): 340-342.
- [17] Porter, D. A., and K. E. Easterling. *Phase Transformations in Metals and Alloys*. London: Chapman and Hall, 1992.
- [18] Aastuen, D. J. W., N. A. Clark, L. K. Cotter, and B. J. Ackerson. "Nucleation and growth of colloidal crystals." *Phys. Rev. Lett.* 57, no. 14 (1986): 1733-1736.
- [19] Ackerson, B. J., and K. Schatzel. "Classical growth of hard-sphere colloidal crystals." *Phys. Rev. E* 52, no. 6 (1995): 6448-6460.
- [20] Rogers, R. B. "Physical Modeling of Materials Science Phenomena using Hard-Sphere Colloidal Suspensions." Ph.D. diss., Case Western Reserve University, 2000.
- [21] Gasser, U., E. R. Weeks, A. Schofield, P. N. Pusey, and D. A. Weitz. "Real-space imaging of nucleation and growth in colloidal crystallization." *Science* 292, no. 5515 (2001): 258-262.
- [22] Lipowsky, P., M. J. Bowick, J. H. Meinke, D. R. Nelson, and A. R. Bausch. "Direct visualization of dislocation dynamics in grain-boundary scars." *Nat.Mater.* 4, no. 5 (2005): 407-411.
- [23] Jorand, M., F. Rothen, and P. Pieranski. "Dislocation-motion in colloidal crystals." *Journal De Physique* 46, no. C3 (1985): 245-255.
- [24] Pieranski, P. "Colloidal crystals." *Contemp.Phys.* 24, no. 1 (1983): 25-73.
- [25] Schall, P., I. Cohen, D. A. Weitz, and F. Spaepen. "Visualization of dislocation dynamics in colloidal crystals." *Science* 305, no. 5692 (2004): 1944-1948.
- [26] Williams, D. B., and C. B. Carter. *Transmission Electron Microscopy: A Textbook for Materials Science*. New York: Plenum, 1996.

- [27] Van Blaaderen, A. "Imaging individual particles in concentrated colloidal dispersions by confocal scanning light-microscopy." *Adv Mater* 5, no. 1 (1993): 52-54.
- [28] Barrett, C. R., W. D. Nix, and A. S. Tetelman. *The Principles of Engineering Materials*. Englewood Cliffs, NJ: Prentice-Hall, 1973.
- [29] Everett, D. H. *Basic Principles of Colloid Science*. London: Royal Society of Chemistry, 1988.
- [30] McMullen, W. E., and D. W. Oxtoby. "A theoretical-study of the hard-sphere fluid solid interface." *J.Chem.Phys.* 88, no. 3 (1988): 1967-1975.
- [31] Oxtoby, D. W., and W. E. McMullen. "A theoretical-study of the hard-sphere fluid-solid interface .2. test of an alternative variational form." *Phys Chem Liq* 18, no. 2 (1988): 97-105.
- [32] Curtin, W. A. "Density-functional theory of crystal-melt interfaces." *Phys. Rev. B* 39, no. 10 (1989): 6775-6791.
- [33] Marr, D. W., and A. P. Gast. "On the solid fluid interface of adhesive spheres." *J.Chem.Phys.* 99, no. 3 (1993): 2024-2031.
- [34] Ohnesorge, R., H. Lowen, and H. Wagner. "Density-functional theory of crystal fluid interfaces and surface melting." *Phys. Rev. E* 50, no. 6 (1994): 4801-4809.
- [35] Marr, D. W. M., and A. P. Gast. "Orientational dependence of the interfacial-tension in the adhesive-sphere system." *Phys. Rev. E* 52, no. 4 (1995): 4058-4062.
- [36] Kyrlidis, A., and R. A. Brown. "Density-functional theory and atomistic simulation of the hard-sphere melt-solid interface." *Phys. Rev. E* 51, no. 6 (1995): 5832-5845.
- [37] Marr, D. W. M. "Toward determining the true hard-sphere interfacial free-energy." *J.Chem.Phys.* 102, no. 20 (1995): 8283-8284.
- [38] Choudhury, N., and S. K. Ghosh. "Modified weighted density-functional approach to the crystal-melt interface." *Phys. Rev. E* 57, no. 2 (1998): 1939-1945.
- [39] Davidchack, R. L., and B. B. Laird. "Direct calculation of the hard-sphere crystal/melt interfacial free energy." *Phys. Rev. Lett.* 85, no. 22 (2000): 4751-4754.
- [40] Cacciuto, A., S. Auer, and D. Frenkel. "Solid-liquid interfacial free energy of small colloidal hard-sphere crystals." *J.Chem.Phys.* 119, no. 14 (2003): 7467-7470.
- [41] Mu, Y., A. Houk, and X. Y. Song. "Anisotropic interfacial free energies of the hard-sphere crystal-melt interfaces." *J Phys Chem B* 109, no. 14 (2005): 6500-6504.

- [42] Davidchack, R. L., and B. B. Laird. "Crystal structure and interaction dependence of the crystal-melt interfacial free energy." *Phys.Rev.Lett.* 94, no. 8 (2005): 086102.
- [43] Marr, D. W., and A. P. Gast. "Interfacial free-energy between hard-sphere solids and fluids." *Langmuir* 10, no. 5 (1994): 1348-1350.
- [44] Palberg, T. "Crystallization kinetics of repulsive colloidal spheres." *J.Phys.-Condes.Matter* 11, no. 28 (1999): R323-R360.
- [45] Jones, D. R. H. "Free-energies of solid-liquid interfaces." *J.Mater.Sci.* 9, no. 1 (1974): 1-17.
- [46] Monovoukas, Y., and A. P. Gast. "The experimental phase-diagram of charged colloidal suspensions." *J.Colloid Interface Sci.* 128, no. 2 (1989): 533-548.
- [47] Yethiraj, A., and A. van Blaaderen. "A colloidal model system with an interaction tunable from hard sphere to soft and dipolar." *Nature* 421, no. 6922 (2003): 513-517.
- [48] Leunissen, M. E., C. G. Christova, A. P. Hynninen, C. P. Royall, A. I. Campbell, A. Imhof, M. Dijkstra, R. van Roij, and A. van Blaaderen. "Ionic colloidal crystals of oppositely charged particles." *Nature* 437, no. 7056 (2005): 235-240.
- [49] Hachisu, S., and S. Yoshimura. "Optical demonstration of crystalline superstructures in binary-mixtures of latex globules." *Nature* 283, no. 5743 (1980): 188-189.
- [50] Bartlett, P., R. H. Ottewill, and P. N. Pusey. "Superlattice formation in binary-mixtures of hard-sphere colloids." *Phys. Rev. Lett.* 68, no. 25 (1992): 3801-3804.
- [51] Lekkerkerker, H. N. W., W. C. K. Poon, P. N. Pusey, A. Stroobants, and P. B. Warren. "Phase-behavior of colloid plus polymer mixtures." *Europhys.Lett.* 20, no. 6 (1992): 559-564.
- [52] Ilett, S. M., A. Orrock, W. C. K. Poon, and P. N. Pusey. "Phase-behavior of a model colloid-polymer mixture." *Phys. Rev. E* 51, no. 2 (1995): 1344-1352.
- [53] Chou, C. S., A. Kowalski, J. M. Rokowski, and E. J. Schaller. "Nonspherical acrylic lattices." *J.Coatings Technol.* 59, no. 755 (1987): 93-102.
- [54] Velikov, K. P., T. van Dillen, A. Polman, and A. van Blaaderen. "Photonic crystals of shape-anisotropic colloidal particles." *Appl.Phys.Lett.* 81, no. 5 (2002): 838-840.
- [55] Manoharan, V. N., and D. J. Pine. "Building materials by packing spheres." *MRS Bull* 29, no. 2 (2004): 91-95.
- [56] van Kats, C. M., P. M. Johnson, J. E. A. M. van den Meerakker, and A. van Blaaderen. "Synthesis of monodisperse high-aspect-ratio colloidal silicon and silica rods." *Langmuir* 20, no. 25 (2004): 11201-11207.

- [57] Yi, G. R., V. N. Manoharan, E. Michel, M. T. Elsesser, S. M. Yang, and D. J. Pine. "Colloidal clusters of silica or polymer microspheres." *Adv Mater* 16, no. 14 (2004): 1204-1208.
- [58] Bolling, G. F., and W. A. Tiller. "Growth from the melt .1. influence of surface intersections in pure metals." *J.Appl.Phys.* 31, no. 8 (1960): 1345-1350.
- [59] Schaefer, R. J., M. E. Glicksman, and J. D. Ayers. "High-confidence measurement of solid-liquid surface-energy in a pure material." *Philosophical Magazine* 32, no. 4 (1975): 725-743.
- [60] Phan, S. E., W. B. Russel, Z. D. Cheng, J. X. Zhu, P. M. Chaikin, J. H. Dunsmuir, and R. H. Ottewill. "Phase transition, equation of state, and limiting shear viscosities of hard sphere dispersions." *Phys. Rev. E* 54, no. 6 (1996): 6633-6645.
- [61] Pusey, P. N., W. van Megen, P. Bartlett, B. J. Ackerson, J. G. Rarity, and S. M. Underwood. "Structure of crystals of hard colloidal spheres." *Phys. Rev. Lett.* 63, no. 25 (1989): 2753-2756.
- [62] Cheng, Z. D., J. X. Zhu, W. B. Russel, W. V. Meyer, and P. M. Chaikin. "Colloidal hard-sphere crystallization kinetics in microgravity and normal gravity." *Appl.Opt.* 40, no. 24 (2001): 4146-4151.
- [63] Sanders, J. V. "Diffraction of light by opals." *Acta Crystall. A - Crys. A* 24 (1968): 427-434.
- [64] Ackerson, B. J., and N. A. Clark. "Shear-induced melting." *Phys. Rev. Lett.* 46, no. 2 (1981): 123-126.
- [65] Amos, R. M., J. G. Rarity, P. R. Tapster, T. J. Shepherd, and S. C. Kitson. "Fabrication of large-area face-centered-cubic hard-sphere colloidal crystals by shear alignment." *Phys. Rev. E* 61, no. 3 (2000): 2929-2935.
- [66] Verhaegh, N. A. M., J. S. Vanduijneveldt, A. van Blaaderen, and H. N. W. Lekkerkerker. "Direct observation of stacking disorder in a colloidal crystal." *J.Chem.Phys.* 102, no. 3 (1995): 1416-1421.
- [67] Elliot, M. S., B. T. F. Bristol, and W. C. K. Poon. "Direct measurement of stacking disorder in hard-sphere colloidal crystals." *Physica A* 235, no. 1-2 (1997): 216-223.
- [68] van Blaaderen, A., and P. Wiltzius. "Real-space structure of colloidal hard-sphere glasses." *Science* 270, no. 5239 (1995): 1177-1179.
- [69] Weeks, E. R., J. C. Crocker, A. C. Levitt, A. Schofield, and D. A. Weitz. "Three-dimensional direct imaging of structural relaxation near the colloidal glass transition." *Science* 287, no. 5453 (2000): 627-631.

- [70] Elliot, M. S., and W. C. K. Poon. "Conventional optical microscopy of colloidal suspensions." *Adv. Colloid Interface Sci.* 92, no. 1-3 (2001): 133-194.
- [71] Azaroff, L. *Elements of X-Ray Crystallography*. New York: McGraw-Hill, 1968.
- [72] Pluta, M. *Advanced Light Microscopy: Volume 1 - Principles and Basic Properties*. Amsterdam: Elsevier, 1988.
- [73] Inoue, S., and K. R. Spring. *Video Microscopy: The Fundamentals*. 2nd ed. New York: Plenum Press, 1997.
- [74] Lipson, S. G., H. Lipson, and D. S. Tannhauser. *Optical Physics*. 3rd ed. Cambridge: Cambridge University Press, 1995.
- [75] Paulin, S. E., and B. J. Ackerson. "Observation of a phase-transition in the sedimentation-velocity of hard-spheres." *Phys. Rev. Lett.* 64, no. 22 (1990): 2663-2666.
- [76] Hecht, E. *Optics*. 2nd ed. Reading, MA: Addison-Wesley, 1987.
- [77] Sanders, J. V. "Colour of precious opal." *Nature* 204, no. 496 (1964): 1151-1153.
- [78] Monovoukas, Y., and A. P. Gast. "A study of colloidal crystal morphology and orientation via polarizing microscopy." *Langmuir* 7, no. 3 (1991): 460-468.
- [79] Wilson, A. J. C. "Imperfections in the structure of cobalt II. mathematical treatment of proposed structure." *Proc. Roy. Soc. London Ser. A* 180 (1942): 277-285.
- [80] Martellozzo, V. C., A. B. Schofield, W. C. K. Poon, and P. N. Pusey. "Structural aging of crystals of hard-sphere colloids." *Phys. Rev. E* 66, no. 2 (2002): 021408.
- [81] Guinier, A. *X-Ray Diffraction in Crystals, Imperfect Crystals, and Amorphous Bodies*. San Francisco: W.H. Freeman, 1963.
- [82] Yoshiyama, T., I. Sogami, and N. Ise. "Kossel line analysis on colloidal crystals in semidilute aqueous-solutions." *Phys. Rev. Lett.* 53, no. 22 (1984): 2153-2156.
- [83] Yoshiyama, T., and I. S. Sogami. "Photographic records of ordered and disordered structures in polymer latex dispersions." *Langmuir* 3, no. 5 (1987): 851-853.
- [84] Monovoukas, Y., and A. P. Gast. "Microstructure identification during crystallization of charged colloidal suspensions." *Phase Transit.* 21, no. 2-4 (1990): 183-195.
- [85] Sogami, I. S., and T. Yoshiyama. "Kossel line analysis on crystallization in colloidal suspensions." *Phase Transit.* 21, no. 2-4 (1990): 171-182.
- [86] Tarhan, I. I., and G. H. Watson. "Photonic band structure of fcc colloidal crystals." *Phys. Rev. Lett.* 76, no. 2 (1996): 315-318.

- [87] Pradhan, R. D., J. A. Bloodgood, and G. H. Watson. "Photonic band structure of bcc colloidal crystals." *Phys.Rev.B* 55, no. 15 (1997): 9503-9507.
- [88] Shinohara, T., H. Yamada, I. S. Sogami, N. Ise, and T. Yoshiyama. "Gravitational, vertical compression of colloidal crystals as studied by the kossel diffraction method." *Langmuir* 20, no. 12 (2004): 5141-5144.
- [89] Fitzgibbon, A., M. Pilu, and R. B. Fisher. "Direct least square fitting of ellipses." *IEEE Trans.Pattern Anal.Mach.Intell.* 21, no. 5 (1999): 476-480.
- [90] Lichtblau, D. "MathGroup Archive 2001, Re: MATLAB to Mathematica 4.1." , September 19, 2001, <http://forums.wolfram.com/mathgroup/archive/2001/Sep/msg00179.html> (accessed January 6, 2006).
- [91] Pluta, M. *Advanced Light Microscopy: Volume 2 - Specialized Methods*. Amsterdam: Elsevier, 1989.
- [92] Monovoukas, Y., G. G. Fuller, and A. P. Gast. "Optical anisotropy in colloidal crystals." *J.Chem.Phys.* 93, no. 11 (1990): 8294-8299.
- [93] Woodruff, D. P. *The Solid-Liquid Interface*. London: Cambridge University Press, 1973.
- [94] Gibbs, J. W. *The Scientific Papers of J. Willard Gibbs*. Woodbridge, CT: Ox Bow Press, 1993.
- [95] Moy, E., and D. Li. "Solid fluid interfacial-tensions from contact angles - corroboration by independent approaches." *Adv.Colloid Interface Sci.* 39 (1992): 257-297.
- [96] Solliard, C., and M. Flueli. "Surface stress and size effect on the lattice-parameter in small particles of gold and platinum." *Surf Sci* 156 (1985): 487-494.
- [97] Thomas, G. B., and R. L. Finney. *Calculus and Analytic Geometry*. 5th ed. Reading, MA: Addison-Wesley, 1979.
- [98] Jones, D. R. H., and G. A. Chadwick. "Experimental measurement of solid-liquid interfacial energies of transparent materials." *Philosophical Magazine* 22, no. 176 (1970): 291-300.
- [99] Nash, G. E., and M. E. Glicksman. "General method for determining solid-liquid interfacial free energies." *Philosophical Magazine* 24, no. 189 (1971): 577-592.
- [100] Glicksman, M. E., and C. L. Vold. "Determination of absolute solid-liquid interfacial free energies in metals." *Acta Metallurgica* 17, no. 1 (1969): 1-11.

- [101] Bankoff, S. G. "The contortional energy requirement in the spreading of large drops." *J.Phys.Chem.* 60, no. 7 (1956): 952-955.
- [102] McNutt, J. E., and G. M. Andes. "Relationship of the contact angle to interfacial energies." *J.Chem.Phys.* 30, no. 5 (1959): 1300-1303.
- [103] Adamson, A. W., and A. P. Gast. *Physical Chemistry of Surfaces*. 6th ed. New York: Wiley-Interscience, 1997.
- [104] Arbel, E., and J. W. Cahn. "Method for absolute measurement of anisotropic surface free-energies." *Surf Sci* 66, no. 1 (1977): 14-24.
- [105] Jones, D. R. H., and G. A. Chadwick. "Experimental measurement of solid-liquid interfacial energies - ice-water sodium chloride system." *J.Cryst.Growth* 11, no. 3 (1971): 260-264.
- [106] Hardy, S. C. "Grain-boundary groove measurement of surface-tension between ice and water." *Philosophical Magazine* 35, no. 2 (1977): 471-484.
- [107] Stalder, I., and J. H. Bilgram. "The measurement of the solid-liquid surface free energy of xenon." *J.Chem.Phys.* 118, no. 17 (2003): 7981-7984.
- [108] Bayender, B., N. Marasli, E. Cadirli, H. Sisman, and M. Gunduz. "Solid-liquid surface energy of pivalic acid." *J.Cryst.Growth* 194, no. 1 (1998): 119-124.
- [109] Bayender, B., N. Marasli, E. Cadirli, and M. Gunduz. "Solid-liquid interfacial energy of camphene." *Mater.Sci.Eng.A-Struct.Mater.Prop.Microstruct.Process.* 270, no. 2 (1999): 343-348.
- [110] Marasli, N., K. Keslioglu, and B. Arslan. "Solid-liquid interface energies in the succinonitrile and succinonitrile-carbon tetrabromide eutectic system." *J.Cryst.Growth* 247, no. 3-4 (2003): 613-622.
- [111] Boyuk, U., K. Keslioglu, M. Erol, and N. Marasli. "Measurement of solid-liquid interfacial energy in succinonitrile-pyrene eutectic system." *Mater Lett* 59, no. 23 (2005): 2953-2958.
- [112] Gunduz, M., and J. D. Hunt. "The measurement of solid-liquid surface energies in the al-cu, al-si and pb-sn systems." *Acta Metallurgica* 33, no. 9 (1985): 1651-1672.
- [113] Gunduz, M., and J. D. Hunt. "Solid-liquid surface-energy in the al-mg system." *Acta Metallurgica* 37, no. 7 (1989): 1839-1845.
- [114] Marasli, N., and J. D. Hunt. "Solid-liquid surface energies in the al-CuAl₂, al-NiAl₃ and al-ti systems." *Acta Mater.* 44, no. 3 (1996): 1085-1096.

- [115] Keslioglu, K., M. Erol, N. Marasli, and M. Gunduz. "Experimental determination of solid-liquid interfacial energy for solid cd in bi-cd liquid solutions." *J.Alloys Compounds* 385, no. 1-2 (2004): 207-213.
- [116] Keslioglu, K., M. Gunduz, H. Kaya, and E. Cadirli. "Solid-liquid interfacial energy in the al-ti system." *Mater Lett* 58, no. 24 (2004): 3067-3073.
- [117] Keslioglu, K., and N. Marasli. "Experimental determination of solid-liquid interfacial energy for zn solid solution in equilibrium with the zn-al eutectic liquid." *Metall.Mater.Trans.A-Phys.Metall.Mater.Sci.* 35A, no. 12 (2004): 3665-3672.
- [118] Keslioglu, K., and N. Marasli. "Solid-liquid interfacial energy of the eutectoid beta phase in the al-zn eutectic system." *Mater.Sci.Eng.A-Struct.Mater.Prop.Microstruct.Process.* 369, no. 1-2 (2004): 294-301.
- [119] Erol, M., N. Marasli, K. Keslioglu, and M. Gunduz. "Solid-liquid interfacial energy of bismuth in the bi-cd eutectic system." *Scr.Mater.* 51, no. 2 (2004): 131-136.
- [120] Sutton, A. P., and R. W. Balluffi. *Interfaces in Crystalline Materials*. Oxford: Oxford University Press, 1995.
- [121] Brower, R. C., D. A. Kessler, J. Koplik, and H. Levine. "Geometrical approach to moving-interface dynamics." *Phys.Rev.Lett.* 51, no. 13 (1983): 1111-1114.
- [122] Kessler, D. A., J. Koplik, and H. Levine. "Geometrical models of interface evolution .2. numerical-simulation." *Phys.Rev.A* 30, no. 6 (1984): 3161-3174.
- [123] Kessler, D. A., and H. Levine. "Stability of dendritic crystals." *Phys.Rev.Lett.* 57, no. 24 (1986): 3069-3072.
- [124] Langer, J. S. "Existence of needle crystals in local models of solidification." *Phys.Rev.A* 33, no. 1 (1986): 435-441.
- [125] Barbieri, A., and J. S. Langer. "Predictions of dendritic growth-rates in the linearized solvability theory." *Phys.Rev.A* 39, no. 10 (1989): 5314-5325.
- [126] Glicksman, M. E., and N. B. Singh. "Effects of crystal melt interfacial energy anisotropy on dendritic morphology and growth-kinetics." *J.Cryst.Growth* 98, no. 3 (1989): 277-284.
- [127] Akamatsu, S., G. Faivre, and T. Ihle. "Symmetry-broken double fingers and seaweed patterns in thin-film directional solidification of a nonfaceted cubic-crystal." *Phys Rev E.* 51, no. 5 (1995): 4751-4773.
- [128] Kobayashi, R. "Modeling and numerical simulations of dendritic crystal-growth." *Physica D* 63, no. 3-4 (1993): 410-423.

- [129] Hoffman, D. W., and J. W. Cahn. "Vector thermodynamics for anisotropic surfaces .1. fundamentals and application to plane surface junctions." *Surf Sci* 31, no. 1 (1972): 368-388.
- [130] Cahn, J. W., and D. W. Hoffman. "Vector thermodynamics for anisotropic surfaces .2. curved and faceted surfaces." *Acta Metallurgica* 22, no. 10 (1974): 1205-1214.
- [131] Nye, J. F. *Physical Properties of Crystals*. Oxford: Oxford University Press, 1957.
- [132] Lee, J. K. "Determination of solid-liquid interface energy with arbel-cahn method." *Scripta Metallurgica* 12, no. 5 (1978): 449-451.
- [133] Lipson, S. G. "The surface of solid helium." *Physica B & C* 110, no. 1-3 (1982): 1805-1810.
- [134] Sallen, L., P. Oswald, J. C. Geminard, and J. Malthete. "Surface-tension and elasticity of hexagonal columnar mesophases." *J.Phys.II* 5, no. 7 (1995): 937-961.
- [135] Napolitano, R. E., S. Liu, and R. Trivedi. "Experimental measurement of anisotropy in crystal-melt interfacial energy." *Interface Sci.* 10, no. 2-3 (2002): 217-232.
- [136] Avron, J. E., J. E. Taylor, and R. K. P. Zia. "Equilibrium shapes of crystals in a gravitational-field - crystals on a table." *J.Stat.Phys.* 33, no. 3 (1983): 493-522.
- [137] Voorhees, P. W., S. R. Coriell, G. B. McFadden, and R. F. Sekerka. "The effect of anisotropic crystal melt surface-tension on grain-boundary groove morphology." *J.Cryst.Growth* 67, no. 3 (1984): 425-440.
- [138] Chaikin, P. M., and T. C. Lubensky. *Principles of Condensed Matter Physics*. Cambridge: Cambridge University Press, 1995.
- [139] Auer, S., W. C. K. Poon, and D. Frenkel. "Phase behavior and crystallization kinetics of poly-12-hydroxystearic-coated polymethylmethacrylate colloids." *Phys Rev E.* 67, no. 2 (2003): 020401.
- [140] Auer, S., W. C. K. Poon, and D. Frenkel. "Phase behavior and crystallization kinetics of poly-12-hydroxystearic-coated polymethylmethacrylate colloids (vol E 67, art no 020401, 2003)." *Phys Rev E.* 67, no. 3 (2003): 039904.
- [141] Atkins, P. *Physical Chemistry*. 6th ed. New York: Freeman, 1998.
- [142] Evans, R. C. *An Introduction to Crystal Chemistry*. 2nd ed. Cambridge: Cambridge University Press, 1964.
- [143] Kirkwood, J. G. "Molecular distributions in liquids." *J. Chem. Phys.* 7 (1939): 919-925.

- [144] Alder, B. J., and T. E. Wainwright. "Phase transition for a hard sphere system." *J.Chem.Phys.* 27, no. 5 (1957): 1208-1209.
- [145] Wood, W. W., and J. D. Jacobson. "Preliminary results from a recalculation of the monte carlo equation of state of hard spheres." *J.Chem.Phys.* 27, no. 5 (1957): 1207-1208.
- [146] Hachisu, S., and Y. Kobayashi. "Kirkwood-alder transition in monodisperse latexes .2. aqueous latexes of high electrolyte concentration." *J.Colloid Interface Sci.* 46, no. 3 (1974): 470-476.
- [147] DeHoff, R. T. *Thermodynamics in Materials Science*. New York: McGraw-Hill, 1993.
- [148] Hoover, W. G., and F. H. Ree. "Melting transition and communal entropy for hard spheres." *J.Chem.Phys.* 49, no. 8 (1968): 3609-3617.
- [149] Zhu, J. X., M. Li, R. Rogers, W. Meyer, R. H. Ottewill, W. B. Russell, and P. M. Chaikin. "Crystallization of hard-sphere colloids in microgravity." *Nature* 387, no. 6636 (1997): 883-885.
- [150] Cheng, Z., P. M. Chaikin, W. B. Russel, W. V. Meyer, J. Zhu, R. B. Rogers, and R. H. Ottewill. "Phase diagram of hard spheres." *Mater Des* 22, no. 7 (2001): 529-534.
- [151] Bolhuis, P. G., and D. A. Kofke. "Monte carlo study of freezing of polydisperse hard spheres." *Phys Rev E.* 54, no. 1 (1996): 634-643.
- [152] Kofke, D. A., and P. G. Bolhuis. "Freezing of polydisperse hard spheres." *Phys Rev E.* 59, no. 1 (1999): 618-622.
- [153] Schatzel, K., and B. J. Ackerson. "Observation of density-fluctuations during crystallization." *Phys. Rev. Lett.* 68, no. 3 (1992): 337-340.
- [154] Schatzel, K., and B. J. Ackerson. "Density-fluctuations during crystallization of colloids." *Phys. Rev. E* 48, no. 5 (1993): 3766-3777.
- [155] He, Y. M., B. J. Ackerson, W. van Megen, S. M. Underwood, and K. Schatzel. "Dynamics of crystallization in hard-sphere suspensions." *Phys. Rev. E* 54, no. 5 (1996): 5286-5297.
- [156] Ackerson, B. J. "Shear induced order of hard-sphere suspensions." *J.Phys.-Condes.Matter* 2 (1990): SA389-SA392.
- [157] Haw, M. D., W. C. K. Poon, and P. N. Pusey. "Direct observation of oscillatory-shear-induced order in colloidal suspensions." *Phys Rev E.* 57, no. 6 (1998): 6859-6864.

- [158] He, Y. M., B. Olivier, and B. J. Ackerson. "Morphology of crystals made of hard spheres." *Langmuir* 13, no. 6 (1997): 1408-1412.
- [159] Russel, W. B., D. A. Saville, and W. R. Schowalter. *Colloidal Dispersions*. Cambridge: Cambridge University Press, 1989.
- [160] Ackerson, B. J., S. E. Paulin, B. Johnson, W. van Meegen, and S. Underwood. "Crystallization by settling in suspensions of hard spheres." *Phys. Rev. E* 59, no. 6 (1999): 6903-6913.
- [161] Rogers, R. B., W. V. Meyer, J. X. Zhu, P. M. Chaikin, W. B. Russel, M. Li, and W. B. Turner. "Compact laser light-scattering instrument for microgravity research." *Appl. Opt.* 36, no. 30 (1997): 7493-7500.
- [162] Russel, W. B., P. M. Chaikin, J. Zhu, W. V. Meyer, and R. Rogers. "Dendritic growth of hard sphere crystals." *Langmuir* 13, no. 14 (1997): 3871-3881.
- [163] Cheng, Z. D., J. X. Zhu, P. M. Chaikin, S. E. Phan, and W. B. Russel. "Nature of the divergence in low shear viscosity of colloidal hard-sphere dispersions." *Phys. Rev. E* 65, no. 4 (2002): 041405.
- [164] van Blaaderen, A., R. Ruel, and P. Wiltzius. "Template-directed colloidal crystallization." *Nature* 385, no. 6614 (1997): 321-324.
- [165] Sullivan, M., K. Zhao, C. Harrison, R. H. Austin, M. Megens, A. Hollingsworth, W. B. Russel, Z. D. Cheng, T. Mason, and P. M. Chaikin. "Control of colloids with gravity, temperature gradients, and electric fields." *J. Phys.-Condes. Matter* 15, no. 1 (2003): S11-S18.
- [166] Martinez, C. J., J. W. Liu, S. K. Rhodes, E. Luijten, E. R. Weeks, and J. A. Lewis. "Interparticle interactions and direct imaging of colloidal phases assembled from microsphere-nanoparticle mixtures." *Langmuir* 21, no. 22 (2005): 9978-9989.
- [167] Dinsmore, A. D., E. R. Weeks, V. Prasad, A. C. Levitt, and D. A. Weitz. "Three-dimensional confocal microscopy of colloids." *Appl. Opt.* 40, no. 24 (2001): 4152-4159.
- [168] Weeks, E. R., and D. A. Weitz. "Subdiffusion and the cage effect studied near the colloidal glass transition." *Chem. Phys.* 284, no. 1-2 (2002): 361-367.
- [169] Weeks, E. R., and D. A. Weitz. "Properties of cage rearrangements observed near the colloidal glass transition." *Phys. Rev. Lett.* 89, no. 9 (2002): 095704.
- [170] Courtland, R. E., and E. R. Weeks. "Direct visualization of ageing in colloidal glasses." *J. Phys.-Condes. Matter* 15, no. 1 (2003): S359-S365.
- [171] Habdas, P., D. Schaar, A. C. Levitt, and E. R. Weeks. "Forced motion of a probe particle near the colloidal glass transition." *Europhys. Lett.* 67, no. 3 (2004): 477-483.

- [172] Elliot, M. S., S. B. Haddon, and W. C. K. Poon. "Direct observation of pre-critical nuclei in a metastable hard-sphere fluid." *J.Phys.-Condes.Matter* 13, no. 23 (2001): L553-L558.
- [173] Edwards, O. S., and H. Lipson. "Imperfections in the structure of cobalt I. experimental work and proposed structure." *Proc. Roy. Soc. London Ser. A* 180 (1942): 268-276.
- [174] Woodcock, L. V. "Entropy difference between the face-centred cubic and hexagonal close-packed crystal structures." *Nature* 385, no. 6612 (1997): 141-143.
- [175] Bolhuis, P. G., D. Frenkel, S. C. Mau, and D. A. Huse. "Entropy difference between crystal phases." *Nature* 388, no. 6639 (1997): 235-236.
- [176] Marr, D. W., and A. P. Gast. "Planar density-functional approach to the solid-fluid interface of simple liquids." *Phys Rev E*. 47, no. 2 (1993): 1212-1221.
- [177] Broughton, J. Q., and G. H. Gilmer. "Molecular-dynamics investigation of the crystal fluid interface .6. excess surface free-energies of crystal liquid-systems." *J.Chem.Phys.* 84, no. 10 (1986): 5759-5768.
- [178] Turnbull, D. "Formation of crystal nuclei in liquid metals." *J.Appl.Phys.* 21, no. 10 (1950): 1022-1028.
- [179] Alder, B. J., W. G. Hoover, and D. A. Young. "Studies in molecular dynamics .V. high-density equation of state and entropy for hard disks and spheres." *J.Chem.Phys.* 49, no. 8 (1968): 3688-3696.
- [180] Dhont, J. K. G., C. Smits, and H. N. W. Lekkerkerker. "A time resolved static light-scattering study on nucleation and crystallization in a colloidal system." *J.Colloid Interface Sci.* 152, no. 2 (1992): 386-401.
- [181] Harland, J. L., and W. vanMegen. "Crystallization kinetics of suspensions of hard colloidal spheres." *Phys Rev E*. 55, no. 3 (1997): 3054-3067.
- [182] Asta, M., J. J. Hoyt, and A. Karma. "Calculation of alloy solid-liquid interfacial free energies from atomic-scale simulations." *Phys.Rev.B* 66, no. 10 (2002): 100101.
- [183] Hoyt, J. J., and M. Asta. "Atomistic computation of liquid diffusivity, solid-liquid interfacial free energy, and kinetic coefficient in au and ag." *Phys.Rev.B* 65, no. 21 (2002): 214106.
- [184] Morris, J. R. "Complete mapping of the anisotropic free energy of the crystal-melt interface in al." *Phys.Rev.B* 66, no. 14 (2002): 144104.
- [185] Morris, J. R., and X. Y. Song. "The anisotropic free energy of the lennard-jones crystal-melt interface." *J.Chem.Phys.* 119, no. 7 (2003): 3920-3925.

- [186] Rutgers, M. A., J. H. Dunsmuir, J. Z. Xue, W. B. Russel, and P. M. Chaikin. "Measurement of the hard-sphere equation of state using screened charged polystyrene colloids." *Phys. Rev. B* 53, no. 9 (1996): 5043-5046.
- [187] Sears, F. W., M. W. Zemansky, and H. D. Young. *University Physics, Part 1*. 6th ed. Reading, MA: Addison-Wesley, 1982.
- [188] Carnahan, N. F., and K. E. Starling. "Equation of state for nonattracting rigid spheres." *J.Chem.Phys.* 51, no. 2 (1969): 635-636.
- [189] Hall, K. R. "Another hard-sphere equation of state." *J.Chem.Phys.* 57, no. 6 (1972): 2252-2254.
- [190] Press, W. H., B. P. Flannery, S. A. Teukolsky, and W. T. Vetterling. *Numerical Recipes: The Art of Scientific Computing*. Cambridge: Cambridge University Press, 1986.
- [191] Phan, S. E. "Thermodynamic and Rheological Properties of Hard Sphere Dispersions." Ph.D. diss., Princeton University, 1998.
- [192] Gast, A. P., and Y. Monovoukas. "A new growth instability in colloidal crystallization." *Nature* 351, no. 6327 (1991): 553-555.
- [193] Mullins, W. W., and R. F. Sekerka. "Morphological stability of a particle growing by diffusion or heat flow." *J.Appl.Phys.* 34, no. 2 (1963): 323-329.
- [194] Kurz, W., and D. J. Fisher. *Fundamentals of Solidification*. 3rd ed. Aedermannsdorf, Switzerland: Trans Tech Publications, 1992.
- [195] Pronk, S., and D. Frenkel. "Can stacking faults in hard-sphere crystals anneal out spontaneously?" *J.Chem.Phys.* 110, no. 9 (1999): 4589-4592.