ANGULAR LIGHT SCATTERING STUDIES
ON THE INTERACTION BETWEEN
POLY-4-VINYL-N-n-BUTYL-PYRIDINIUM BROMIDE
AND CRYSTALLINE EGG ALBUMIN

DISSERTATION

Presented in Partial Fulfillment of the Requirements
for the Degree Doctor of Philosophy in the
Graduate School of the Ohio State
University

By

ISRAEL JOEL HEILWEIL, B.S., M.S.

The Ohio State University
1954

Approved by:

Adviser
Department of Chemistry

ACKNOWLEDGMENT

I wish to thank my adviser, Professor Quentin Van Winkle, for his encouragement and assistance throughout all my graduate studies.

I would like to express also, my grateful appreciation to the generous people of the United States, and those of the State of Ohio in particular, who made this work possible.

To my wife, Harriet

TABLE OF CONTENTS

	<u>PAGE</u>
I. INTRODUCTION	1
II. LITERATURE REVIEW OF POLYELECTROLYTE INTERACTIONS	1
III. REVIEW OF THEORETICAL ASPECTS OF LIGHT SCATTERING	7
1. Fundamental Equations.	8
a. Zimm's Double Extrapolation Method	14
b. Dissymmetry Method	18
c. Turbidity Extrapolation Method	19
d. Transmission Method.	22
2. Polydispersity	22
3. Multicomponent Systems	25
a. General Theory	25
b. Interacting Systems.	27
4. Polyelectrolytes	32
a. Swamping Ionic Strength.	33
b. Zero Ionic Strength.	33
c. Moderate Ionic Strength.	36
IV. EXPERIMENTAL	40
1. Calibration and Modification of the Light Scattering Apparatus.	40

	<u>PAGE</u>
a. Centration of the Photometer . .	41
b. The Light Scattering Cell and Its Alignment.	42
c. Neutral Density Filters.	43
d. Calculation of Reduced Scattered Intensity.	44
e. Effect of Narrow Slits Upon Apparent Reduced Intensity . . .	48
f. Correction Factors for R_{θ}	49
g. Experimental Check of R_{θ} Values. .	51
h. Final Expression for Calculating the Scattering Data	53
2. The Differential Refractometer	54
3. pH Measurements.	55
4. Viscosity.	55
5. Experimental Procedure	58
a. Preparation of Compounds	58
b. Preparation of Solutions	58
c. Cleaning of Glassware.	60
d. Filtration	61
6. Experimental Results	64
a. pH Titration	64
b. Variation of Turbidity with Time	69
c. Light Scattering Experiments . .	70
1) Pure Components.	71
2) PVP-EA at Varying Ionic Strength	77
3) PVP-EA at Varying pH . . .	83

	<u>PAGE</u>
4) PVP-EA at Varying r . . .	84
5) PVP-SA	90
d. Correlation of Light Scattering Work with Viscosity, Sedimenta- tion, and Diffusion, and Calcu- lations of $P(\theta)$	93
V. DISCUSSION	103
VI. SUMMARY.	114
APPENDIX.	115

I. INTRODUCTION

The purpose of this investigation was to study polyelectrolyte-polyelectrolyte interactions by means of angular light scattering.

Because poly-4-vinyl-N-n-butylpyridinium bromide (hereafter called PVP) and crystalline egg albumin (hereafter called EA) are individually of great interest to the physical chemistry of polyelectrolytes, and because PVP and EA do form soluble complexes under suitable conditions, it was deemed desirable to study this interaction and, thus, in some measure, to add to the information currently being amassed on the physical structure, behavior, and interactions of large polyions.

II. LITERATURE REVIEW OF POLYELECTROLYTE INTERACTIONS

Complete surveys in the field of protein interaction with small ions and detergents were recently published by Klotz (1) and by Putnam (2). During the last decade, interaction studies were extended to specific protein-protein

(1) I. M. Klotz, in The Proteins, Vol. I, Part B, eds. H. Neurath and K. Bailey, Academic Press, New York, p. 727 (1953).

(2) F. W. Putnam, Ibid., p. 807.

interactions (3), protein-enzyme (4), and antibody-antigen (5) systems, and to salt-like protein complexes with naturally occurring polyelectrolytes, such as nucleic acids (6) and polysaccharides (7).

Until now most of the workers concentrated their efforts on the application of analytical and electrophoretic techniques to the study of these complexes, but recent use of x-rays (8), diffusion (9), osmotic pressure (10), and streaming birefringence (11) has yielded very promising information.

It was to be expected that the field of protein interactions would be extended to interactions with synthetic

-
- (3) L. G. Longsworth, R. K. Cannan, and D. A. MacInnes, J. Am. Chem. Soc. 62, 2480 (1940).
- (4) H. Neurath and G. W. Schwert, Chem. Revs. 46, 69 (1950).
- (5) R. J. Goldberg and D. H. Campbell, J. Immunol. 66, 79 (1951).
- (6) E. Goldwasser and F. W. Putnam, J. Phys. & Coll. Chem. 54, 79 (1950).
- (7) J. Einbinder and M. Schubert, J. Biol. Chem. 188, 335 (1951).
- (8) D. P. Riley and U. W. Arndt, Nature 172, 294 (1953).
- (9) E. Stenhagen, J. Immunol. 70, 372 (1953).
- (10) H. Gutfreund, Trans. Far. Soc. 50, 628 (1954).
- (11) J. F. Foster and D. Zucker, J. Phys. Chem. 56, 170 (1952).

polyelectrolytes. Morawetz and Hughes (12, 13) made use of the interaction of polyelectrolytes with proteins for the specific separation of proteins from their natural mixtures. Quastel (14) found that the interactions of synthetic polymeric acids and of acidic biocolloids with soils are closely similar. Turbidimetric and surface film studies of the interactions of proteins and synthetic polypeptides with silicic acid, made by Holt and Bowcott (15), gave evidence that proteins combine with polyelectrolytes principally through specific groups, but that hydrogen bonding and van der Waals forces are also involved. Similar conclusions were advanced by Saito (16) from his viscosity studies of complex formation between synthetic polyelectrolytes and detergents. Soluble complexes were formed upon interaction of lysine polypeptides and bovine plasma albumin at high ionic strength and excess of either of the complexing components. Analysis of the electrophoretic data indicated, however, that the complexes formed could not be accounted for on the basis of existing

-
- (12) H. Morawetz and W. L. Hughes, J. Phys. Chem. 56, 64 (1952).
- (13) M. Berdick and H. Morawetz, J. Biol. Chem. 206, 959 (1954).
- (14) J. H. Quastel, Soil Sci. 73, 419 (1952).
- (15) P. F. Holt and J. E. L. Bowcott, J. Biochem. 57, 471 (1954).
- (16) S. Saito, Kolloid Zeitschrift 137, 94 (1954).

theories (17). The fluorescence polarization method, based on the theory developed by Weber (18), was recently applied by Steiner (19) to the study of the reversible electrostatic type of interaction between oppositely charged macromolecular constituents. These interactions were found to be very sensitive to ionic strength. The method could readily be extended to the study of synthetic polyelectrolyte complexes at zero ionic strength. The phenomena of polyelectrolyte aggregation (20) and gelation (21) might be included under the heading of polyelectrolyte interactions.

Light scattering is particularly suited to the study of high molecular weight materials. Doty, et al. (22) and Nord, et al. (23) employed light scattering to study the aggregation of polyvinyl acetates in various solvents and at different temperatures, and found that the amount of

-
- (17) R. V. Rice, M. A. Stahman, and R. A. Alberty, *J. Biol. Chem.* 209, 105 (1954).
- (18) G. Weber, *Biochem. J.* 51, 145 (1952).
- (19) R. F. Steiner, Naval Medical Research Institute Report NM 000 018.06.29, 11, 1117 (1953).
- (20) P. Doty and E. Mishuk, *J. Am. Chem. Soc.* 69, 1631 (1947).
- (21) A. Katchalsky, S. Lifson, and H. Eisenberg, *J. Polymer Sci.* 8, 476 (1952).
- (22) P. Doty, H. Wagner, and S. Singer, *J. Phys. Coll. Chem.* 51, 32 (1947).
- (23) F. F. Nord, M. Bier, and S. N. Timasheff, *J. Am. Chem. Soc.* 73, 289 (1951).

association could be explained on the basis of secondary bonds of various strengths. Upon heating, the weakest fraction of secondary bonds would be broken, and, upon cooling, the molecules would return to the aggregated form slowly as the secondary bonds would reform. Measurement of the light scattering of solutions of crystalline zinc insulin showed that aggregation occurred at high salt concentrations (24). Similar conclusions were reached by Halwer (25) from his work on caseins. Light scattering and viscosity measurements on aqueous mixtures of serum albumin and sodium dodecyl sulfate provided evidence for the existence of stoichiometric complexes in the work of Harrap and Schulman (26). The molecular weight of these complexes, determined at zero ionic strength, remained constant at 0.05 ionic strength, but the addition of salt did affect the uncoiling of the complex. While there was no evidence for aggregation in these studies of Harrap and Schulman, according to light scattering studies by Hanna and Foster (27), ovalbumin unfolds in the presence of cationic detergents, and subsequently laterally aggregates with time.

(24) F. Tietze, and H. Neurath, J. Biol. Chem. 194, 1 (1952).

(25) M. Halwer, Arch. Biochem. Biophys. 51, 79 (1954).

(26) B. S. Harrap, and J. H. Schulman, Disc. Far. Soc. 13, 197 (1953).

(27) G. F. Hanna, and J. G. Foster, J. Phys. Chem. 57, 614 (1953).

Blum and Morales (28) recently reported that the addition or removal of adenosine triphosphate to myosin caused angular light scattering changes which were attributed to the contraction and extension of the myosin molecule, and were not due to depolymerization as had previously been suspected from 90° scattering. Angular light scattering measurements have been employed by Ferry, et al. (29) to study the size, shape, and dissociation equilibria of a fibrinogen polymer formed in the presence of traces of thrombin in 0.5 M hexamethylene glycol solution at 0.45 ionic strength.

One of the first light scattering studies on two dissimilar interacting polyelectrolytes was made by Geiduschek and Doty (30) on a complex formed between sodium desoxyribonucleate and bovine serum albumin. This report was followed shortly by a study by Yasnoff and Bull (31) on an egg albumin--pepsin association. A series of theoretical and experimental papers was just published by Steiner (32, 33, 34) on the reversible

-
- (28) J. J. Blum, and M. F. Morales, Arch. Biochem. Biophys. 43, 208 (1953).
- (29) J. D. Ferry, S. Shulman, K. Gutfreund, and S. Katz, J. Am. Chem. Soc. 74, 5706 (1952).
- (30) E. P. Geiduschek, and P. Doty, Biochem. Biophys. Acta 9, 609 (1952).
- (31) D. S. Yasnoff, and H. B. Bull, J. Biol. Chem. 200, 619 (1953).
- (32) R. F. Steiner, Arch. Biochem. Biophys. 44, 120 (1953).
- (33) R. F. Steiner, Arch. Biochem. Biophys. 49, 71 (1953).
- (34) R. F. Steiner, Arch. Biochem. Biophys. 47, 56 (1953).

association between globular proteins.

With the exception of the work by Geiduschek and Doty (30), all the light scattering investigations reported on the interaction of two dissimilar polyelectrolyte species were carried out using the 90° scattering method. It thus seemed desirable to extend the study of polyelectrolyte interactions to complex formation between a synthetic polyelectrolyte (PVP) and a well-characterized crystalline protein (EA) employing the angular light scattering method, which has come into use in the last three years or so, and which is capable of yielding more complete information than 90° scattering. It was hoped that, by varying the experimental conditions of pH, ionic strength, and mixing ratio, a better understanding of the behavior of such a system could be obtained.

III. REVIEW OF THEORETICAL ASPECTS OF LIGHT SCATTERING

Several excellent surveys on light scattering have appeared in the literature since 1951 (35, 36, 37, 38, 39, 40).

-
- (35) P. J. Flory, Principles of Polymer Chemistry, Cornell University Press, Ithaca, pp. 283-315 (1953).
 - (36) J. T. Edsall, and W. B. Dandliker, Fortschr. Chem. Forsch. 2, 1 (1951).
 - (37) P. Doty, and J. T. Edsall, in Advances in Protein Chemistry, Vol. VI, Academic Press, New York, pp. 35-121 (1951).
 - (38) H. A. Stuart, ed., Die Struktur des Freien Moleküls, Vols. I and II, Springer Verlag, Berlin (1952).
 - (39) Ch. Sadron, J. Polymer Sci. 12, 69 (1954).
 - (40) B. Sedlacek, Chem. Listy 47, 1113 (1953).

Thorough discussions of the basic principles have been presented in the Doctoral Dissertations from these laboratories by Davidson (41) and Goodman (42).

1. Fundamental Equations

It can be shown that, for ideal, isotropic, monodisperse particles, whose dimensions are small compared with the wavelength of the light used, Rayleigh's Law applies:

$$R_{eu} = \frac{I_{\theta}^{\circ} r^2}{I_0} = \frac{8 \pi^4 \alpha^2 v}{\lambda^4} (1 + \cos^2 \theta) \quad [1]$$

where R_{eu} = Rayleigh's ratio for unpolarized incident light, measured at angle θ ; known, also, as "reduced scattered intensity"

I_{θ}° = scattered intensity at angle θ

I_0 = intensity of unpolarized incident beam

r = distance from the center of scattering to the observer

v = number of particles per unit volume

α = excess polarizability of the particles over the surrounding medium

λ = wavelength of the light used in vacuum

For non-ideal, small, monodisperse particles, one has to consider scattering due to concentration fluctuation

(41) D. Davidson, Doctoral Dissertation, The Ohio State University (1951).

(42) P. Goodman, Doctoral Dissertation, The Ohio State University (1952).

in a volume element δV , small compared to the wavelength (35). V in the preceding treatment is replaced by $\frac{1}{\delta V}$, the number of volume elements per unit volume, and, instead of α^2 , one has to consider $\overline{(\Delta\alpha)^2}$, the average square excess polarizability for all volume elements due to the deviation of the concentration within these volume elements from the average concentration of the bulk solution. It can be shown that

$$\overline{(\Delta\alpha)^2} = \frac{\overline{(\Delta\epsilon)^2} \delta V}{16 \pi^2} \quad [2]$$

where $\overline{(\Delta\epsilon)^2}$ is the average square excess optical dielectric constant for all volume elements as compared with the average for the entire solution. Since

$$\overline{(\Delta\epsilon)^2} = \left(\frac{\partial \epsilon}{\partial c} \right)^2 \overline{(\Delta c)^2} \quad [3]$$

and

$$\left(\frac{\epsilon - \epsilon_0}{c} \right)^2 = \left(\frac{n^2 - n_0^2}{c} \right)^2 \approx \left(\frac{\partial n^2}{\partial c} \right)^2 \approx \left(2 n_0 \frac{\partial n}{\partial c} \right)^2 \quad [4]$$

where n = refractive index of the solution

n_0 = refractive index of the solvent,

we have

$$\overline{(\Delta\epsilon)^2} = \left(2 n_0 \frac{\partial n}{\partial c} \right)^2 \overline{(\Delta c)^2} \quad [5]$$

Substituting equations [2] and [5] into equation [1],

we obtain

$$R_{\text{eu}} = \frac{2 \pi^2 \delta V}{\lambda^4} \left(n_0 \frac{\partial n}{\partial c} \right)^2 \overline{(\Delta c)^2} \quad [6]$$

To evaluate $\overline{(\Delta c)^2}$ we proceed as follows (43): The probability, P , that some thermodynamic quantity fluctuates from its average value is given by

$$P = A e^{-\frac{\Delta F}{kT}}$$

where P = probability of a fluctuation

A = constant

ΔF = increase of free energy

$k = \frac{R}{N}$ = Boltzman constant

T = absolute temperature

Let $\bar{c}$ = average concentration of bulk solution

δV = small volume element

x = variable change in concentration of solute in δV

V_1 = molar volume of solvent

$\bar{F}_1$ = partial molal free energy of solvent.

For the transfer of n_1 moles of solvent from δV , at concentration $\bar{c} + \Delta c$, to the outer solution at concentration c

$$\Delta F = \int_0^{\Delta c} \Delta \bar{F}_1 dn_1$$

$$\Delta \bar{F}_1 = \bar{F}_1(\bar{c}) - \bar{F}_1(\bar{c} + x) = - \frac{\partial \bar{F}_1}{\partial \bar{c}} x$$

$$n_1 = \frac{\delta V}{V_1} \frac{x}{\bar{c}} \quad \text{or} \quad dn_1 = \frac{\delta V}{V_1} \frac{dx}{\bar{c}}$$

(43) J. J. Hermans, and P. H. Hearn, in Colloid Science, ed. H. R. Kruyt, Elsevier Publishing Company, New York, pp. 145-149 (1949).

$$\Delta F = - \frac{\delta V}{\bar{c} V_1} \frac{\partial \bar{F}_1}{\partial \bar{c}} \int_0^{\Delta c} x dx = - \frac{\delta V}{2c} \frac{1}{V_1} \frac{\partial \bar{F}_1}{\partial \bar{c}} \overline{(\Delta c)^2} \quad [7]$$

This, then, is the change in free energy when a fluctuation of magnitude Δc takes place in δV . The probability that such a fluctuation occurs is proportional to $e^{-\frac{\Delta F}{RT}}$, so that

$$\overline{(\Delta c)^2} = \frac{\int_{-\infty}^{\infty} (\Delta c)^2 e^{-\frac{\Delta F}{RT}} d(\Delta c)}{\int_{-\infty}^{\infty} e^{-\frac{\Delta F}{RT}} d(\Delta c)} \quad [8]$$

Substituting equation [7] into equation [8] and integrating, we obtain

$$\overline{(\Delta c)^2} = - \frac{RT V_1 c}{\left(\frac{\partial \bar{F}_1}{\partial c} \right)} \quad [9]$$

Then, substituting equations [9] and [10] into equation [6], and remembering that

$$\frac{\partial \bar{F}_1}{\partial c} = - V_1 \frac{\partial \pi}{\partial c} \quad [10]$$

π being the osmotic pressure, we obtain

$$R_{\theta u} = \frac{2\pi^2 n_0^2}{\lambda^4 N} \left(\frac{dn}{dc} \right)^2 \frac{cRT}{\frac{\partial \pi}{\partial c}} (1 + \cos^2 \theta) \quad [11]$$

or

$$R_{\theta u} = K \frac{cRT}{\frac{\partial \pi}{\partial c}} (1 + \cos^2 \theta) \quad [12]$$

where

$$K = \frac{2\pi^2 n_o^2}{\lambda^4 N} \left(\frac{dn}{dc} \right)^2 \quad [13]$$

Now, since

$$\frac{\partial \pi}{\partial c} = RT \left(\frac{1}{M} + Bc + Cc^2 + \dots \right)$$

it follows that

$$\frac{Kc}{\left(\frac{R_{\theta u}}{1 + \cos^2 \theta} \right)} = \frac{1}{M} + 2Bc + 3Cc^2 + \dots$$

where M is the molecular weight of the solute, and B and c are interaction constants. For brevity let us set

$$\frac{R_{\theta u}}{1 + \cos^2 \theta} = R_{\theta} \quad [14]$$

We obtain, finally,

$$\frac{Kc}{R_{\theta}} = \frac{1}{M} + 2Bc + 3Cc^2 + \dots \quad [15]$$

This equation is equivalent to a form suggested by Flory (35):

$$\frac{Kc}{R_{\theta}} = \frac{1}{M} \left(1 + 2\Gamma_2 c + 3\Gamma_2^2 c^2 + \dots \right) \quad [16]$$

The preceding discussion dealt with monodisperse isotropic particles, not larger than one-twentieth of the wavelength of the light used, whose refractive index is not too different from that of the solvent. For larger monodisperse, isotropic, non-ideal particles, the oscillating dipoles in different parts of the particles are no longer in phase,

and i_θ will be reduced on account of intraparticle interference by a factor $P(\theta)$, which, for a given wavelength, depends upon the size and shape of the particles, as well as upon the angle θ . This factor is given by

$$P(\theta) = \int_0^\infty \rho(r) \frac{\sin \mu r}{\mu r} dr = \frac{R_\theta}{R_0}$$

where R_0 is the Rayleigh ratio which would be observed at angle $\theta = 0$, where no interference effects are present.

$P(\theta)$ is so normalized that $P(0) = 1$. $\rho(r)$ is the distribution function for the occurrence of the distance r between pairs of scattering elements in the same solute molecule, and $\mu = \frac{4\pi n}{\lambda} \sin \frac{\theta}{2}$. Since the equation for $P(\theta)$ holds strictly only in very dilute solutions, equation [15] has to be rewritten in the following form:

$$\left(\frac{Kc}{R_\theta} \right)_{c=0} = \frac{1}{MP(\theta)} = \frac{1}{M} P^{-1}(\theta) \quad [17]$$

The derivations presented thus far involved isotropic monodisperse particles. The electric moment induced in an isotropic molecule is parallel to the electric field vector, and the light scattered in the plane perpendicular to this vector (the horizontal plane) is completely polarized in the vertical direction. When the above condition no longer holds, appropriate corrections have to be applied. These corrections will be discussed further on.

Four methods have been developed for the determination of molecular weights and particle dimensions by light scattering.

a. Zimm's Double Extrapolation Method (Angular Light Scattering)

For isotropic monodisperse particles, Zimm has shown (44) that light scattering data are best plotted as $\frac{Kc}{R_\theta}$ against $\sin^2 \frac{\theta}{2} + kc$, where k is an arbitrary constant. Smoothed lines are drawn through the points at constant angle and through those at constant concentration, thereby forming a grid. Each of these lines is then extrapolated to zero angle or to zero concentration, and the extrapolated points are joined to give two lines which intercept the $\frac{Kc}{R_\theta}$ axis at a single point.

At low concentrations one can write

$$\frac{Kc}{R_\theta} = \frac{1}{M} P^{-1}(\theta) + 2Bc \quad [18]$$

$P^{-1}(\theta)$ for various particle shapes can, in general, be expanded into a series of the form (36)

$$P^{-1}(\theta) = 1 + A \sin^2 \frac{\theta}{2} + A' \sin^4 \frac{\theta}{2} + \dots \quad [19]$$

(44) B. H. Zimm, J. Chem. Phys. 16, 1909 (1948).

where $A = f(\lambda, n, [D]) = \text{constant}$
 $A' = \text{constant}$
 $[D] = \text{characteristic dimension for a given shape}$

Thus

$$P^{-1}(\theta)_{\theta=0} = 1$$

It then becomes obvious that one can obtain the molecular weight of the particles directly, without any assumptions as to the particle shape, for

$$\left(\frac{Kc}{R\theta}\right)_{\substack{c=0 \\ \theta=0}} = \frac{1}{M} \quad [20]$$

Furthermore, from equations [18], [19], and [20] we have

$$\frac{1}{\left(\frac{Kc}{R\theta}\right)_{\substack{c=0 \\ \theta=0}}} \left[\frac{d \left(\frac{Kc}{R\theta}\right)_{c=0}}{d \sin^2 \frac{\theta}{2}} \right]_{\theta=0} = A \quad [21]$$

and, also,

$$\frac{1}{2} \left[\frac{d \left(\frac{Kc}{R\theta}\right)_{\theta=0}}{dc} \right]_{c=0} = B \quad [22]$$

where A, called the "limiting slope", determines the dimensions of the particle whose shape has now to be assumed; and B, the osmotic pressure virial coefficient, is a function of molecular interaction. In addition

$$P(\theta)_{\text{experimental}} = \left(\frac{K_c M}{R_\theta} \right)^{-1}_{c=0} \quad [23]$$

It is thus feasible, by a trial and error method, to compare an experimental plot of $P(\theta)$ vs. $f(\theta)$ with theoretical $P(\theta)$ curves calculated for given sizes and shapes, and thus to ascertain the shape and dimensions of the particle under consideration.

Closed expressions have been calculated for $P(\theta)$ for monodisperse spheres, rods, Gaussian coils (37), coils having non-Gaussian distributions (45), and cylindrical disks (46). Power series expressions are available for ellipsoids, cylindrical disks (37), non-Gaussian chains (47), and randomly oriented cylindrical rods (48). Values of $P(\theta)$ for spheres, rods, and random coils are tabulated by Doty and Steiner (49).

For more complicated shapes, the quantity unambiguously obtained from the limited slope is the radius of gyration,

(45) H. Benoit, and M. Goldstein, J. Chem. Phys. 21, 947 (1953).

(46) N. Saito, and Y. Ikeda, J. Phys. Soc. Japan 6, 305 (1951).

(47) H. Benoit, and P. Doty, J. Phys. Chem. 57, 958 (1953).

(48) R. W. Greene, J. Clin. Invest. 31, 969 (1952).

(49) P. Doty, and R. F. Steiner, J. Chem. Phys. 18, 1211 (1950).

R_G , given by the following expression:

$$R_G = \frac{\sqrt{3} \lambda}{4 \pi n_o} \left[\frac{d P^{-1}(\theta)}{d \sin^2 \frac{\theta}{2}} \right]_{\theta=0} \quad [24]$$

In terms of molecular models, the following simple relationships exist between R_G and molecular dimensions (50):

$$\begin{aligned} R_G &= (6)^{-\frac{1}{2}} (\overline{r^2})^{\frac{1}{2}} && \text{(coil)} \\ R_G &= \left(\frac{20}{3}\right)^{-\frac{1}{2}} D && \text{(sphere)} \\ R_G &= (12)^{-\frac{1}{2}} L && \text{(rod)} \\ R_G &= (8)^{-\frac{1}{2}} D' && \text{(thin disk)} \end{aligned} \quad [25]$$

where

$(\overline{r^2})^{\frac{1}{2}}$ = root mean square distance between ends of the random coil

D = diameter of the sphere

L = length of the rod

D' = large diameter of the thin disk

From the review presented by Sadron (39), it is evident that the treatment presented thus far becomes more complicated for large anisotropic particles. For rods and coils having anisotropy δ ,

(50) A. P. Brady, A. G. Brown, and H. Huff, J. Coll. Sci. 8, 252 (1953).

$$\begin{aligned}
 P(0) &= 1 + \frac{4\delta^2}{5} && \text{(rod)} \\
 P(0) &= 1 + \frac{4\delta^2}{5n} && \text{(coil)}
 \end{aligned}
 \tag{26}$$

where n , here, is the degree of polymerization. For high molecular weight coils the anisotropy correction is not significant. For rod-like shapes, however, the omission of the anisotropy factor tends to give high molecular weights. Unfortunately, δ is not a readily determined quantity, and approximate values only can be obtained from birefringence measurements.

For small anisotropic particles it can be shown (49) that equation [17] has to be modified as follows:

$$\left[\frac{K_C}{R_\theta} \right]_{c=0} = \left[\frac{b - 7\rho_u}{b + 6\rho_u} \right] \frac{1}{M} P^{-1}(\theta)
 \tag{27}$$

where $\rho_u = \frac{H_v}{V_u}$, V denotes the vertically polarized component of Rayleigh's ratio, and H denotes the horizontally polarized component. The subscripts u , v , and h indicate, respectively, that the incident beam is unpolarized, vertically polarized, or horizontally polarized.

b. Dissymmetry Method

In using this method, R_θ is measured at 90° and at two angles symmetrical with respect to 90° , the angles usually chosen being 45° and 135° . The ratio

$$Z = \frac{R_{45^\circ}}{R_{135^\circ}}$$

is known as the dissymmetry. Z , for a given molecular model, can be calculated theoretically from $P(\theta)$ as a function of $\frac{[D]\eta}{\lambda}$, where $[D]$, as before, is a characteristic dimension for a given shape. For a given $\frac{\lambda}{\eta}$ the determination of Z fixes a value of $[D]$, if a model is assumed. Once $[D]$ has been determined from the measured value of Z , $P(\theta)$ or $P^{-1}(\theta)$ is readily calculated for any angle θ and the assumed model. For the 90° measurement,

$$\left[\frac{K_c}{R_{90^\circ}} \right]_{c=0} = \frac{1}{M} P^{-1}(90^\circ) \quad [28]$$

Values of Z vs. $\frac{[D]\eta}{\lambda}$, and Z vs. $P^{-1}(90^\circ)$, are given by Doty and Steiner (49).

For small anisotropic particles the same anisotropy correction factor has to be applied as in equation [27]. For large rod-like anisotropic particles, graphs are available for $\frac{L\eta_0}{\lambda}$ vs. Z for various values of δ (51).

The chief disadvantage of the dissymmetry method lies in the fact that the molecular weight cannot be determined free of an assumption as to particle shape.

c. Turbidity Extrapolation (Absorption) Method

For ideal isotropic particles, small compared with λ , turbidity, τ° , is defined as

(51) P. Horn, H. Benoit, and G. Oster, J. Chim. phys. 48, 530 (1951).

$$\tau^{\circ} = \frac{1}{I_0 V} \int_0^{\pi} i_{\theta}^{\circ} \pi r^2 \sin \theta d\theta \quad [29]$$

where V = illuminated volume, and the superscript $^{\circ}$ indicates a value for a small particle. It can be shown that τ° is the fraction of the incident light scattered in all directions from the primary beam per cm. of path; that is,

$$\frac{I}{I_0} = e^{-\tau^{\circ} x} \quad [30]$$

and τ° is experimentally equivalent to the familiar Beer-Lambert absorption coefficient. I is the transmitted intensity, I_0 the incident intensity, and x the path length. Since it follows from equation [1] that

$$i_{\theta}^{\circ} = \frac{i_{90^{\circ}}^{\circ}}{2} (1 + \cos^2 \theta) = i_{90^{\circ}}^{\circ} (1 + \cos^2 \theta) \quad [31]$$

equation [29] yields, on integration, a relationship between τ° and $R_{90^{\circ}}^{\circ}$:

$$\tau^{\circ} = \frac{16\pi}{3} \cdot \frac{i_{90^{\circ}}^{\circ} r^2}{I_0} = \frac{16\pi}{3} R_{90^{\circ}}^{\circ} \quad [32]$$

When we deal with isotropic particles large in comparison with λ , we have

$$P(\theta) = \frac{R_{\theta u}}{R_{90^{\circ} u}}, \quad [33]$$

$$i_{\theta} = i_0 \frac{1 + \cos^2 \theta}{2} P(\theta)$$

and an expression for τ , similar to equation [29] for τ^0

$$\tau = \frac{1}{I_0 V} \int_0^\pi I_0 (1 + \cos^2 \theta) P(\theta) \pi r^2 \sin \theta d\theta \quad [34]$$

We may set

$$f = \frac{\tau^0}{\tau}$$

where f , calculated from equations [29] and [34], corrects the experimentally determined turbidity for interference effects. It has been shown by Cashin and Debye (52) that

$$\left[\frac{H_c}{\tau^0} \right]_{\substack{c=0 \\ \lambda \rightarrow \infty}} = \frac{1}{M} \quad [35]$$

where

$$H = \frac{32 \pi^3 n_0^2}{3 N \lambda^4} \left(\frac{dn}{dc} \right)^2$$

from which it follows that, for large particles

$$\frac{H_c}{\tau} = \frac{f}{M} + B'c \quad [36]$$

where B' is an interaction constant. Billmeyer (53) expanded f in a power series similar to that usually given for $P^{-1}(\theta)$

$$f = 1 + A' \left(\frac{1}{\lambda} \right)^2 + \dots \quad [37]$$

(52) W. M. Cashin, and P. Debye, Phys. Rev. 75, 1307A (1949).

(53) F. W. Billmeyer, J. Am. Chem. Soc. 76, 4636 (1954).

where $A' = f(n_0, [D])$.

Thus it becomes apparent that a plot of $\frac{H_c}{\tau}$ vs. a function of $\left(\frac{1}{\lambda}\right)^2 + kc$ would yield the same information as Zimm's double extrapolation method.

For small anisotropic particles, the anisotropy correction term for τ^0 differs from the correction for R_0 and is applied as follows:

$$\left[\frac{H_c}{\tau^0}\right]_{c=0} = \left[\frac{6 - 7\rho_a}{6 + 3\rho_a}\right] \frac{1}{M} \quad [38]$$

d. Transmission Method

The fourth technique, the transmission method, is complementary to the dissymmetry method and has been discussed fully by Doty and Steiner (49) and by Harkness and Wassermann (54).

2. Polydispersity.

For polydisperse systems the molecular weight obtained from light scattering measurements is $\bar{M}_w$, the weight average molecular weight. When $(\bar{r}^2)^{1/2}$ is about 2000 Å, a curvature in the plot of $\left[\frac{Kc}{R_0}\right]_{c=0}$ vs. $\sin^2 \frac{\theta}{2}$ is observed, and $\bar{M}_n$, the number average molecular weight, can be determined from the intercept of the asymptote. For large values of $\sin^2 \frac{\theta}{2}$, Benoit, et al. (55), have shown that

(54) M. L. R. Harkness, and A. Wassermann, *Nature* 173, 167 (1954).

(55) H. Benoit, A. M. Holtzer, and P. Doty, *J. Phys. Chem.* 58, 635 (1954).

$$\left[\frac{K_c}{R_\theta} \right]_{c=0} = \frac{1}{M} \left[\frac{1}{2} + n \left(\frac{4\pi}{\lambda'} \sin \frac{\theta}{2} \right)^2 \frac{b^2}{6} + \dots \right]$$

where λ' = wavelength of the light used in solution
 b = effective bond length
 n = degree of polymerization

Thus

$$\left[\frac{K_c}{R_\theta} \right]_{c=0, \theta=0, \text{ for asymptote}} = \frac{1}{2 \bar{M}_N} \quad [39]$$

Kinell (56) has expanded the expression

$$\sum_i R_i = K V_i \sum_i \frac{c_i}{\frac{1}{RT} \left(-\frac{d \Delta F}{d c_i} \right)} \quad [40]$$

in terms of $w_i = \frac{c_i}{c}$, and he obtained

$$\left[\frac{K_c}{R_\theta} \right] = \frac{1}{\bar{M}_w} + \frac{2B}{RT} \frac{\bar{M}_z}{\bar{M}_w} c \quad [41]$$

Thus it appears possible to obtain $\bar{M}_z$, the Z-average molecular weight, from light scattering data, if B can be determined independently.

Whereas for monodisperse systems $P(\theta)$ is of the form

$$P_M(\theta) = 1 + a R_G^2 \sin^2 \frac{\theta}{2} + \dots, \quad [42]$$

$P(\theta)$ for polydisperse systems is given, according to Zimm (44), by

(56) P. O. Kinell, Särtryck ur Svensk Kennisk Tidskrift 61, 19 (1949).

$$P(\theta) = \frac{\int_0^{\infty} P_M(\theta) M w(M) dM}{\int_0^{\infty} M w(M) dM} \quad [43]$$

where $w(M)$ is the fraction of polymer having a molecular weight in the range M to $M + dM$. Ehrlich and Doty (57) have expressed equation [43] in terms of equation [42], and they obtained

$$P(\theta) = 1 + a \cdot \frac{\int_0^{\infty} M w(M) R_G^2 dM}{\int_0^{\infty} M w(M) dM} \sin^2 \frac{\theta}{2} \quad [44]$$

Comparing equation [44] with equation [42], we see that

$$R_G^2 = \frac{\int_0^{\infty} M w(M) R_G^2 dM}{\int_0^{\infty} M w(M) dM} \quad [45]$$

Since the weighing factor in equation [45] is the same as that in the expression for a Z-average molecular weight, we see that R_G^2 is the Z-average of the square of the radius of gyration.

In treating polydisperse systems, it is convenient to express the distribution of molecular weights in terms of a parameter z , defined by

(57) G. Ehrlich, and P. Doty, J. Am. Chem. Soc. 76, 3764 (1954).

$$w(M) dM = \frac{\ell^{z+1} M^z e^{-\ell M} dM}{\Gamma[z+1]} \quad [46]$$

For monodisperse systems, $z = \infty$. A recent discussion of this distribution is given by Shultz (58). When $P(\theta)$ functions calculated for a given model, but for various degrees of polydispersity in terms of the parameter z , are plotted against $R_G \sin \frac{\theta}{2}$, where R_G is the directly measurable radius of gyration, then it turns out that the curves for polydisperse cases lie above the curve for the monodisperse case (59, 60).

Theoretical methods have been outlined by Atherton and Peters (61) for obtaining the particle size distribution for spheres, and these might readily be extended to other particle shapes in the future.

3. Multicomponent Systems

a. General theory.

The refractive index of a multicomponent system is a thermodynamic variable dependent upon the temperature,

(58) A. R. Shultz, J. Am. Chem. Soc. 76, 3422 (1954).

(59) H. Benoit, J. Polymer Sci. 11, 507 (1953).

(60) M. Goldstein, J. Chem. Phys. 21, 1255 (1953).

(61) A. Atherton, and R. H. Peters, Brit. J. Applied Physics 4, 366 (1953).

pressure, and the molalities of the components of the system. Fluctuations in the concentrations in a given volume under consideration affect the mean square value of the fluctuation in refractive index, $\overline{(\Delta n)^2}$, which, in turn, determines the total turbidity. The form of the equation for reduced intensity for a multicomponent system prescribed by Stockmayer (62) is

$$\frac{R_o}{K'} = \frac{\sum_i \sum_j \psi_i \psi_j A_{ij}}{|a_{ij}|} \quad [47]$$

where the summation extends over all components other than the solvent.

$$K' = 1000 K / \left(\frac{dn}{dc} \right)^2$$

$$\psi_i = \text{molar refractive index of component } i$$

$$m = \text{molarity}$$

$$a_i = \text{activity of component } i$$

$$a_{ij} = \frac{\partial \ln a_i}{\partial m_j}$$

$$|a_{ij}| = \text{determinant of } a_{ij} \text{ terms}$$

$$A_{ij} = \text{cofactor of the term } a_{ij} \text{ in } |a_{ij}|. \text{ This cofactor is positive when } i + j \text{ is even and negative when } i + j \text{ is odd.}$$

It was later shown by Krigbaum and Flory (63) that

(62) W. H. Stockmayer, J. Chem. Phys. 18, 58 (1950).

(63) W. R. Krigbaum, and P. J. Flory, J. Chem. Phys. 20, 873 (1952).

equation [47], for a system of two polymers and one solvent, can be reduced to

$$\frac{K''c}{R_0} = \frac{1}{\sum_i \phi_i^2 w_i M_i} + 2c_i \frac{\sum_i \sum_j \phi_i \phi_j w_i w_j M_i M_j A_{ij}}{\left(\sum_i \phi_i^2 w_i M_i\right)^2} \quad [48]$$

where

$$K'' = \frac{2\pi^2 n}{N \lambda^4}$$

$$\phi_i = \partial n / \partial c_i$$

$$w_i = \text{weight fraction of } i$$

$$A_{ij} = \text{interaction function}$$

By defining a parameter, v

$$v^2 = \frac{\sum_i \phi_i w_i M_i}{\sum_i w_i M_i}$$

equation [48] can be written in a form from which the molecular weight of a complex system may be obtained readily:

$$\frac{K''c v^2}{R_0} = \frac{1}{\bar{M}_w} + B''c \quad [49]$$

Blum and Morales (64) have derived an expression similar to equation [49] directly from Zimm's assumptions (44) in which the scattering equation is explicitly stated in terms of $P_i(\theta)$.

b. Interacting Systems

In treating these systems, in order to avoid very

(64) J. J. Blum, and M. F. Morales, J. Chem. Phys. 20, 1822 (1952).

cumbersome equations, it is the practice to assume that no association-fluctuation coupling occurs (65), that the departure from randomness is negligible, and that the activity coefficients are unity.

For a polymerizing system of the type $A_1 + A_i \rightleftharpoons A_{i+1}$, characterized by an equilibrium constant k_i , Steiner (32) has shown that, by determining the average degree of polymerization, $\frac{\bar{M}_w}{M_1}$, where M_1 is the molecular weight of the monomer, one can easily obtain the successive association constants for the polymerization reaction.

For a reaction $A + B \rightleftharpoons AB$, the equilibrium constant K may be obtained (33) from

$$\bar{M}_w - (M_A^2 m_A^t + M_B^2 m_B^t) = 2K \frac{c_A^t c_B^t}{c} \quad [50]$$

where m_A^t, m_B^t = total molar concentration
 c_A^t, c_B^t = total concentration in g/ml
 c = total weight concentration of both A and B in g/ml

Thus, the only quantity necessary to determine K is the weight average molecular weight of the system, $\bar{M}_w$, as a function of concentration.

When A and B associate to form reversible complexes of the type AB_i , successive association constants can be

(65) R. F. Steiner, Naval Medical Research Institute Report, 11, 579 (1953).

determined, but one must be able to extrapolate the light scattering data to a point where complete dissociation takes place. The equation to be evaluated for such a system is given by Steiner (34) and has the following form:

$$\left[\frac{M_A \Delta}{c_B^t} \right]_{\substack{c_T=0 \\ X_B=1}} = 2 M_A K_{AB} \quad [51]$$

where
$$\Delta = \frac{R_o}{\bar{K} c_A^t} - \frac{1}{c_A^t} (M_A^2 m_A^t + M_B^2 m_B^t),$$

$$\bar{K} = K'' \left(\frac{d\bar{n}}{dc} \right)^2,$$

and
$$\left(\frac{d\bar{n}}{dc} \right) = \frac{\sum_i c_i \frac{\partial \bar{n}}{\partial c_i}}{c^t}$$

Here, k_{AB} is the association constant for the first complex, and X_B is the mole fraction of uncombined B. In cases where the light scattering data can be used to determine $\bar{M}_N$, the problem of evaluating association constants becomes very simple.

If we write the reaction as $A + iB \rightleftharpoons AB_i$, and assume the concentration of free A to be negligible, then, as Geiduschek and Doty have shown (30), it is possible to determine the weight of B that combines with unit weight of A. Since this treatment will be applied to the system studied herein, let us set A = PVP and B = EA. Following the authors' symbolism, let us define the necessary quantities, using the subscript 2 for PVP, 4 for EA, and 6 for the

PVP-EA complex:

$$\begin{aligned} \delta &= \text{grams of EA bound/ gram of PVP} & [52] \\ c_2 &\approx 0 \\ c_4 &= c_4^0 - \delta c_2^0 \\ c_6 &= c_2^0 (1 + \delta) \\ \phi_6 &= \frac{\phi_2 + \delta \phi_4}{1 + \delta} \end{aligned}$$

where c_2 , c_4 , and c_6 are the final concentrations of the components in g/ml, and c_2^0 and c_4^0 are the initial concentrations. Since

$$(R_{\theta i})_{c=0} = K'' \phi_i^2 c_i M_i P_i(\theta)$$

and

$$(R_{ot})_{\theta=0}^{c=0} = \sum_i (R_{oi})$$

then it follows, using the relations of [52] and remembering that $P_i(0) = 1$, that

$$(R_{ot})_{\theta=0}^{c=0} = K'' M_4 \phi_4^2 (c_4^0 - \delta c_2^0) + K'' M_2 (\phi_2 + \delta \phi_4)^2 c_2^0$$

and

$$\left[\frac{K'' (c_2^0 + c_4^0)}{R_{ot}} \right]_{\theta=0}^{c=0} = k = \frac{c_2^0 + c_4^0}{c_2^0 M_2 (\phi_2 + \delta \phi_4)^2 + (c_4^0 - \delta c_2^0) M_4 \phi_4^2} \quad [53]$$

The left-hand side of equation [53], k , is an experimental quantity which permits the evaluation of δ . Let us divide the numerator and denominator of the right-hand side of equation [53] by c_2^0 , and let us define r as

Then equation [53] becomes

$$\delta^2 + \left[2 \frac{\phi_2}{\phi_4} - \frac{M_4}{M_2} \right] \delta + \left[\left(\frac{\phi_2}{\phi_4} \right)^2 + \gamma \frac{M_4}{M_2} - \frac{(\gamma+1)}{R M_2 \phi_4^2} \right] \quad [54]$$

In a rather non-rigorous manner we can proceed to determine the kind of average that δ represents. From equation [53] we may write

$$\begin{aligned} \sum_i c_{2i}^\circ M_{2i} (\phi_2 + \delta_i \phi_4)^2 + (c_{4i}^\circ - \delta c_{2i}^\circ) M_{4i} \phi_4^2 \\ = c_2^\circ \bar{M}_2 (\phi_2 + \delta \phi_4)^2 + (c_4^\circ - \delta c_2^\circ) \bar{M}_4 \phi_4^2 \end{aligned}$$

and
$$\bar{M}_w = \frac{\sum_i c_{2i}^\circ M_{2i}}{c_2}$$

Collecting terms and cancelling

$$\begin{aligned} 2 \phi_2 \left(\sum_i c_{2i}^\circ M_{2i} \delta_i - c_2^\circ \bar{M}_2 \delta \right) + \phi_4 \left(\sum_i c_{2i}^\circ M_{2i} \delta_i^2 \right. \\ \left. - \sum_i c_{2i}^\circ M_{4i} \delta_i - c_2^\circ \bar{M}_2 \delta + c_2^\circ \bar{M}_4 \delta \right) = 0 \end{aligned}$$

If we assume that each expression in parentheses is equal to 0, then

$$\sum_i c_{2i}^\circ M_{2i} \delta_i = c_2^\circ \bar{M}_2 \delta$$

and

$$\delta = \frac{\sum_i c_{2i}^\circ M_{2i} \delta_i}{\sum_i c_{2i}^\circ M_{2i}}, \quad \text{a } Z\text{-average} \quad [55]$$

It is interesting to note that when no assumptions are made as to the ideality of the system, then theory predicts low apparent molecular weights for cases where equilibria are slowly attained in comparison with the concentration fluctuation rate, and high apparent molecular weights where association-fluctuation coupling occurs (65).

4. Polyelectrolytes

A very complete review on polyelectrolytes is given by Katchalsky (66). In describing the behavior of polyelectrolytes, it is of primary importance to evaluate the electrostatic potential of the charged macromolecules. Significant progress along these lines has been reported in the literature within the last few months (67, 68, 69). Strauss and Fuoss (70) summarize the essential characteristics of a polyelectrolyte along these lines: The electrostatic forces of a charged polymer manifest themselves in two ways. On the one hand, the repulsion between ionizable groups along the polymer backbone causes the polymer to expand, and, thus, the shape and size of the polyelectrolyte is a function

-
- (66) A. Katchalsky, J. Polymer Sci. 12, 159 (1954).
 - (67) S. Lifson, and A. Katchalsky, J. Polymer Sci. 13, 43 (1954).
 - (68) F. Osawa, N. Imai, and I. Kagawa, J. Polymer Sci. 13, 93 (1954).
 - (69) F. E. Harris, and S. A. Rice, J. Phys. Chem. 58, 725 (1954).
 - (70) U. P. Strauss, and R. M. Fuoss, in Die Struktur des Freien Moleküls, Vol. II, ed. H. A. Stuart, Springer Verlag, Berlin, p. 680 (1952).

of its net charge. On the other hand, the increasing charge on the polyion, caused by dissociation of the counter-ions, exerts an attractive force on the remaining counter-ions, causing a certain portion of the counter-ions to become associated with the polyion. This association has two effects. First, the expansion of the polyelectrolyte is arrested due to screening of the charges; and, second, the degree of screening becomes a function of the concentration of counter-ions in solution, which, in turn, is a function of polyelectrolyte concentration and total ionic strength.

The discussion of the light scattering behavior of polyelectrolytes will be divided into three areas: light scattering in solutions of swamping ionic strength, light scattering at zero ionic strength, and light scattering at moderate ionic strengths.

a. Swamping Ionic Strength

At very high salt concentration the methods outlined above for the determination of molecular weights and sizes of polymers still hold, provided no complexing takes place between the polyion and the salt.

b. Zero Ionic Strength

At zero ionic strength long range forces cause a non-random arrangement of polyelectrolyte molecules in the solution, and it is this ordering effect that causes destructive interference of light. Doty and his coworkers

(71, 72) have treated the problem of calculating the diminution of scattering by making use of functions analogous to those employed in low angle xray diffraction studies.

Assuming a "hard sphere" distribution function, they have arrived at the expression

$$\frac{K_c}{R_\theta} = \frac{1}{M P(\theta)} \left[1 + 2 \frac{B'}{M} c \phi(hD) \right] \quad [56]$$

where

$$B' = \frac{2}{3} \pi D^3 N$$

$$N = \text{Avogadro's number}$$

$$D = \text{hard sphere diameter}$$

$$\phi = \frac{3}{x^3} (\sin x - x \cos x), \text{ the usual scattering function}$$

$$x = hD$$

$$L = \frac{4 \pi n}{\lambda} \sin \frac{\theta}{2}$$

Similar functions can be formulated for distributions other than the hard sphere. $2B'$ can be identified as what is commonly known as the excluded volume and is directly related to B , the second virial coefficient in the light scattering equation. The function ϕ is a decreasing monotonic function for low values of x , but at higher values of x it is no longer single-valued. The authors have shown that, when it

(71) P. Doty, and R. F. Steiner, J. Chem. Phys. 20, 85 (1952).

(72) A. Oth, and P. Doty, J. Phys. Chem. 56, 43 (1952).

is assumed that the hard sphere diameter D is equivalent to the sum of the concentration independent protein ion diameter and a counter-ion atmosphere diameter whose effective distance varies as the inverse cube root of the counter-ion concentration, then the plots of reduced intensity and dissymmetry against concentration could be fitted closely with the theoretical curve. Equation [56] predicts that, when D is properly accounted for, one should observe, at first, a rapid decrease in dissymmetry with increasing concentration, followed by return to the initial value. It predicts, too, a leveling off of the reciprocal reduced intensity at high polymer concentration after an initial rapid linear rise. This last effect can be responsible for erroneous molecular weight determinations if the data are extrapolated from high concentrations. Equation^[56] further shows that it is still possible to obtain the correct molecular weight if data is extrapolated to zero angle and zero concentration, as is done in a Zimm plot.

The same group~~s~~ of workers found that polymethacrylic acid gave results essentially similar to those obtained with a protein, but in this case they had to assume a variable diameter of the polymer, the diameter increasing with dilution. The size obtained from extrapolated Z values agreed quite well with that obtained by independent measurements. They were unable to explain the leveling off of

Z values after the minimum, however, without requiring the size of the polyion to be independent of concentration. A very elegant proposal to account for this effect was put forth by Veiss and Eggenberger (73) and will be discussed later.

c. Moderate Ionic Strength

In solutions of moderate ionic strength where the equivalent polyelectrolyte concentration is smaller than the equivalent simple electrolyte concentration, it is possible to evaluate light scattering data by methods outlined by Stockmayer (62). Edsall, et al. (74), using definitions for components suggested by Scatchard (75), were able to derive the following expression:

$$\frac{Kc_2}{R_{90^\circ}} = \frac{1}{M_2} + \frac{1000}{M_2^2} \left[\frac{z_2^2}{2m_3} + \beta_{22} - \frac{f_{23}^2 m_3}{2 + \beta_{33} m_3} \right] c_2 \quad [57]$$

where c_2 = concentration of polymer
 M_2 = molecular weight of polymer
 z_2 = valence of polymer
 m_3 = molarity of simple electrolyte
 $\beta_{ij} = \frac{\partial f_i}{\partial m_j}$, where m_j is the molarity of component j, and $\beta_i = \ln \gamma_i$, γ_i being the activity coefficient of component i

-
- (73) A. Veiss, and D. N. Eggenberger, J. Am. Chem. Soc. 76, 1560 (1954).
 (74) J. T. Edsall, H. Edelhoch, R. Lontie, and P. Morrison, J. Am. Chem. Soc. 72, 4641 (1950).
 (75) G. Scatchard, J. Am. Chem. Soc. 68, 2315 (1946).

From equation [57] it is apparent that the second term on the right-hand side, usually associated with B, is a complex function of the charge on the polyelectrolyte, the ionic strength, and the effect of activity coefficients. In ideal solutions, where activity coefficients are unity, $\frac{z_2^2}{2 m_3}$ is the significant term. Therefore, reduced intensities obtained in solutions of increasing electrolyte content, when no complexing occurs between the polyelectrolyte and the simple salt, should yield, when plotted against polyelectrolyte concentration, a group of lines, with a common intercept, whose slopes should decrease with increasing m_3 . This has been shown to be true for solutions of polyphosphates as well as for proteins (76).

When complexing between the salt and the polyelectrolyte does occur, the intercepts are found to vary. Katz (77), proceeding along the lines laid down by Edsall and his co-workers, has shown that, under such conditions, it is possible to evaluate α , the molal binding coefficient.

Lifson and Katchalsky (67), following an independent approach, have shown that

(76) U. P. Strauss, E. H. Smith, and P. L. Wineman, J. Am. Chem. Soc. 75, 3935 (1953).

(77) S. Katz, Doctoral Dissertation, Harvard University (1950).

$$\left(\frac{K_c}{R_\theta}\right)_{\theta=0} = \frac{1}{M} \left(1 + v \varphi(\lambda, \beta) \right) \quad [58]$$

where v = number of ionized groups on the polyelectrolyte molecule

$\varphi(\lambda, \beta)$ = the osmotic coefficient as a function of a parameter proportional to the number of charges per unit length of macromolecule

β = an integration constant in a potential function

Only recently, Mysels (78), making the assumption that it is primarily the fluctuation in the polyelectrolyte concentration that contributes to scattering, derived equations for calculating the charge of simple colloidal particles. Mysels' approach to colloidal electrolytes, as well as that of Debye and his group (79, 80), has been criticized and reevaluated in a paper by Hutchinson (81).

Veiss and Eggenberger (73), in their light scattering studies on arabic acid at zero as well as at moderate values of ionic strength, have obtained results similar to those of Doty and Steiner (71) on salt-free solutions of serum albumin and polymethacrylic acid. Whereas the

(78) K. J. Mysels, J. Phys. Chem. 58, 303 (1954).

(79) P. Debye, J. Phys. Coll. Chem. 53, 18 (1949).

(80) E. W. Anacker, J. Coll. Sci. 8, 402 (1953).

(81) E. Hutchinson, J. Coll. Sci. 9, 191 (1954).

reduced intensity curves seemed to level off at high concentrations of polymethacrylic acid, a similar plot for arabic acid reveals an additional rise in $\frac{K_c}{R_\theta}$ vs. c after a level portion. Graphs of Z against concentration go through a minimum, but then, at higher concentrations, reach a maximum value, and there follows a further decrease in Z . The maximum value of Z varies with ionic strength, and the highest value reached exceeds the value of Z at $c = 0$. Veiss and Eggenberger explain their results in the following fashion: Coiled polyelectrolytes, in their attempt to attain a minimum free energy, contract as the polymer concentration and, consequently, repulsion between neighboring molecules increases. When further contraction becomes hindered on account of steric effects and repulsion between various segments of the same molecule, then, in order to attain the minimum free energy, the molecules become more rod-like. This new shape has a lower free energy and a smaller effective volume. As the concentration increases further, interpenetration of portions of neighboring molecules becomes possible. Intermolecular electrostatic repulsion would then replace intramolecular repulsion, but the size of the molecules would not necessarily change. This independence of size with increasing concentration corresponds to the plateau in the reduced intensity plot at zero ionic strength, and to the points of inflection at higher ionic strengths. The subsequent rise in $\frac{K_c}{R_\theta}$ vs. c is indicative of a high

order built into the system of interpenetrating coils. Recapitulating, the leveling off of Z values at high concentrations of polymer that was observed by Oth and Doty (72) could indeed mean that the size of the polyelectrolyte becomes independent of its concentration at high concentrations.

IV. EXPERIMENTAL

1. Calibration and Modification of the Light Scattering Apparatus.

The light scattering photometer used in this investigation is a commercial model produced by the Phoenix Precision Instrument Co. according to the original design of Brice, et al. (82).

A few changes were made to increase the sensitivity and improve the performance of the instrument. The original high pressure AH-3 mercury light source was replaced by the higher wattage AH-4 lamp. The opal depolarizer plate mounted in front of the photomultiplier tube was removed, thus increasing the sensitivity ten-fold. Better regulation of the light source and photomultiplier output was achieved by connecting the light source and the photomultiplier, individually, to two Sorensen voltage regulators,

(82) B. A. Brice, M. Halwer, and R. Speiser, J. Opt. Soc. Am. 40, 768 (1950).

Model 1000S, capable of regulation within 0.1% of the required voltage. The photomultiplier tubes used throughout this work were RCA 931A tubes, specially selected by RCA for low dark current, high gain, and minimum sensitivity to variation of the plane of polarization of the incident beam. The galvanometer used had a sensitivity of $0.00064 \mu\text{a/mm}$. In order to permit angular measurements down to 20° , special sleeve-type diaphragm caps were constructed, reducing the original limiting slits in the primary beam to $12 \times 3 \text{ mm}^2$. The entrance diaphragm to the phototube housing was found to be unsymmetrical with respect to the optical axis and had to be remachined.

a. Centration of the Photometer

A detailed description of the apparatus and of the actual measurement procedures is given in Davidson's Dissertation (41). The apparatus was centered as follows: With all the slits removed, the lamp was positioned approximately so as to give the maximum galvanometer deflection at 0° . The sleeve-type slits were then placed in position, and, with the shutter partly closed and the phototube still set at 0° , the slits were adjusted until the images of the illuminated slits and their back reflections fell symmetrically upon each other. The cathode of the phototube was then set at 45° to the incident beam and the deflection of the galvanometer at 0° noted. The entire procedure was

repeated until the galvanometer deflection was a maximum. At this point, the original slits were firmly secured, and then both the original slits and the sleeve-type reducing slits were marked to match.

Following each removal of the reducing slits and prior to each series of angular measurements, the slits were matched according to their markings and their exact positions checked for symmetry of the beam and maximum galvanometer deflection at 0° , without changing the position of the lamp or the phototube. Occasionally, however, the lamp or the phototube had to be replaced, and then the entire centering procedure was essentially repeated. In order to avoid overall recalibration of the photometer, the lamp or the phototube was replaced, but not both at the same time.

b. The Light Scattering Cell and Its Alignment

For dissymmetry work the familiar semi-octagonal cell was used, allowing scattering measurements to be made at 45° , 90° , and 135° . The cylindrical cell used for angular measurements was purchased from Phoenix Precision Instrument Co. The cell, designed by Witnauer and Scherr (83), has two plane faces permitting normal incidence of the beam at 0° and 180° . The back half of the cell is frosted over

(83) L. P. Witnauer, and H. J. Scherr, Rev. Sci. Instruments 23, 99 (1952).

its full inside length to reduce multiple reflections of light. To cut down the reflections still further, the outside of the frosted wall was covered with optical black paint. The bottom of the cell was cemented to a square piece of glass that just fit into the recess of the platform on which the scattering cell is placed for light scattering measurements. Before the cement hardened, a 1×10^{-4} mg/ml solution of sodium fluorescein was added to the cell, and the cell was so aligned on its base that the fluorescent intensity, in arbitrary galvanometer units, varied with angle symmetrically with respect to the galvanometer deflection at 90° . The cell now being centered on its base, the cement was allowed to harden 24 hours without disturbing the cell. In order to obtain corrections at various angles for imperfections in the cell symmetry, the fluorescent solution was again measured at a series of angles, and the galvanometer deflection, G_θ , at each angle θ was multiplied by $\sin \theta$ to correct for the volume viewed. $G_\theta \sin \theta$ should be constant, and deviations from the average can be used to correct all subsequent values of R_θ . Since it was found that $G_\theta \sin \theta$ was constant within 0.6%, no symmetry correction for the cell was applied.

c. Neutral Density Filters

In order to decrease the incident intensity, neutral density filters are used throughout scattering measurements.

The transmittances of the filters were redetermined by means of the light scattering photometer and, also, by means of the Beckman DU Spectrophotometer. The values found, with one exception, agreed very well with the values given by the manufacturer and are listed on p. 47.

d. Calculation of Reduced Scattered Intensity

A number of authors have recently discussed the absolute turbidities of pure liquids (84, 85), and it appears now that absolute values of reduced intensity can be determined from the geometry of the apparatus, without any recourse to indirect calibration (86, 87). Brice, et al. (82) give an expression for absolute turbidity for their instrument in terms of a calibrated opal glass standard diffusor.

$$\tau_{\lambda, 90^\circ} = \frac{16 TD \alpha}{3 (1.045) h} \frac{K_w}{R_c} n^2 \frac{G_{90^\circ}}{G_{0^\circ}} \frac{F_{0^\circ}}{F_{90^\circ}} \quad [59]$$

where $\tau_{\lambda, 90^\circ}$ = turbidity at wavelength λ and 90°
 T = apparent diffuse transmittance of the opal glass standard

-
- (84) H. J. L. Trap, and J. J. Hermans, Rec. Trav. Chim. 73, 167 (1954).
 (85) S. H. Maron, and R. L. H. Lou, J. Polymer Sci. 14, 273 (1954).
 (86) J. Kremen, and J. J. Shapiro, J. Opt. Soc. Am. 44, 500 (1954).
 (87) L. M. Kushner, J. Opt. Soc. Am. 44, 155 (1954).

D	=	light diffusion correction to adjust for the fact that the reference standard is not a perfect diffuser.
1.045	=	reflection correction for the emergent beam.
h	=	width of the incident beam
$\frac{R_w}{R_c}$	=	refraction correction dependent upon the refractive index of the solution
n	=	refractive index of the solution
G	=	galvanometer deflection
F	=	filter factor (transmittance)

Evaluation of TD

Recent reevaluation of the absolute values of T and D showed that the previous methods for their respective determination were in error (88). This error, however, is not propagated in the product TD. The transmittance of the reference standard was remeasured by the Phoenix Precision Instrument Co. prior to this work, and its value, as well as that for D, is listed on p. 47.

Refraction Correction

In work with rectangular scattering cells, it was shown by Brice, et al. (82) that a refraction correction factor, n^2 , should be used in the expression for turbidity.

(88) B. A. Brice, and M. Halwer, J. Opt. Soc. Am. 44, 340 (1954).

Calculations by Carr and Zimm (89) indicated that the factor n ought to be used for cylindrical cells. A recent theoretical derivation by Hermans and Levinson (90) and experimental work by other authors (91, 92) has shown, however, that n^2 is to be used for cylindrical cells just as it is for rectangular ones. The factor n^2 , therefore, was retained in the calculation of R_θ .

The Factor a

The determination of the factor a has been described (41). Because of the removal of the depolarizer plate, this factor had to be redetermined. It is necessary to check the value of a whenever the phototube or the lamp is replaced. The value was checked periodically, and small corrections for a were applied to R_θ whenever necessary.

-
- (89) C. I. Carr, and B. H. Zimm, J. Chem. Phys. 18, 1616 (1950).
- (90) J. J. Hermans, and S. Levinson, J. Opt. Soc. Am. 41, 460 (1951).
- (91) P. Bosworth, C. R. Masson, H. W. Melville, and F. W. Peaker, J. Polymer Sci. 9, 565 (1952).
- (92) D. A. I. Goring, Canad. J. Chem. 31, 1078 (1953).

TABLE I
CONSTANTS USED IN CALCULATING TURBIDITY
WITH THE DISSYMMETRY CELL (LARGE SLITS)

	436 m μ	546 m μ
T	0.288	0.328
D	0.840	0.862
a	0.266	0.293
n	1.340	1.330
$\frac{R_W}{R_C}$	1.025	1.025
h	1.20	1.20

Transmittances of Neutral Density Filters

Filter No.	436 m μ	546 m μ
1	0.471	0.540
2	0.220	0.254
3	0.104	0.131
4	0.0277	0.0402

e. Effect of Narrow Slits Upon Apparent Reduced Intensity

The relationship between R_{θ} and τ is given by equation [32]. Substituting the constants listed on p. 47 into equation [59], one obtains, for $436 \text{ m}\mu$ and large slits

$$R_{90^{\circ}\mu} = 0.3006 \frac{G_{90^{\circ}}}{G_{0^{\circ}}} \frac{F_{0^{\circ}}}{F_{90^{\circ}}}$$

Since $R_{\theta} = R_{90^{\circ}}(1 + \cos^2 \theta)$, and $G_{\theta} = G_{90^{\circ}}(1 + \cos^2 \theta)$, it follows that

$$R_{\theta\mu} = 0.3006 \frac{G_{90^{\circ}}}{G_{0^{\circ}}} \frac{F_{0^{\circ}}}{F_{90^{\circ}}} = 0.3006 \frac{I_{\theta}}{I_0}$$

The cylindrical and dissymmetry cells were filled with the same solution of approximately 0.5% Ludox (93), and values of R_{θ} were obtained using both cells. Since the measurements with the dissymmetry cell were made using large slits, and those with the cylindrical cell using small slits, the values of R_{θ} obtained were the true and the apparent reduced intensities, respectively. The ratio

$$k' = \frac{R_{\theta \text{ true}}}{R_{\theta \text{ apparent}}}$$

is used to correct values of R_{θ} measured by means of the cylindrical cell using small slits.

(93) The sample of Ludox used was obtained through the courtesy of Dr. R. K. Iler, E. I. DuPont de Nemours & Co., Grasselli Chemicals Department, Wilmington, Delaware.

Repeated measurements at $436\text{ m}\mu$ gave an average value of $k'_{436} = 1.390 \pm 1.9\%$, and k' was found to be independent of angle. For $546\text{ m}\mu$, $k'_{546} = 1.424 \pm 1.5\%$. Thus the final expression for obtaining R_θ from measurements using the cylindrical cell and narrow slits is given by

$$R_{\theta u} = 0.4397 \frac{G_\theta}{G_0} \frac{F_0}{F_\theta} \quad [60]$$

f. Correction Factors for R_θ

Absorption. Although scattering measurements are usually made in a wavelength region where the molecule does not absorb, it is possible to correct R_θ for absorption if necessary (94).

$$R_{\theta, \text{true}} = R_{\theta, \text{observed}} \times \frac{1}{\alpha^{l_1 + l_2}}$$

Where α = intensity of light passing through 1 cm. of absorbing solution / intensity of light passing through 1 cm. of non-absorbing solution of the same n

l_1 = distance traveled by the incident beam through the solution

l_2 = distance traveled by the scattered beam through the solution

(94) P. Alexander, and K. A. Stacey, Proc. Roy. Soc. Lond. A212, 274 (1952).

Fluorescence. Fluorescence may be detected in a solution by interposing a monochromatic filter transmitting the same wavelength as that used for light scattering measurements, first in the path of the incident beam, and then in the path of the emergent beam at 90° , and noting whether there is a difference in galvanometer readings. If fluorescence is present, formulas are available for correction of R_θ (95).

Reflection. Sheffer and Hyde (96) pointed out that corrections have to be made for back-reflection of the incident beam from the emergent face of the scattering cell, which superimposes its own interference pattern on the primary interference pattern in asymmetric scattering. This type of correction is extremely important in dissymmetry measurements. Correction formulas for reflection are given by Cantow and Schultz (97) and by Oth, et al. (98).

Volume Correction. The volume of scattering solution viewed by the receiver is proportional to $\frac{1}{\sin \theta}$.

-
- (95) B. A. Brice, G. S. Nutting, and M. Halwer, J. Am. Chem. Soc. 75, 824 (1953).
- (96) H. Sheffer, and J. C. Hyde, Can. J. Chem. 30, 817 (1952).
- (97) H. J. Cantow, and G. V. Schultz, Z. physik. Chem. 1, 365 (1954).
- (98) A. Oth, J. Oth, and V. Desreux, J. Polymer Sci. 10, 551 (1953).

All R_{θ} values, therefore, must be multiplied by $\sin \theta$ in order to obtain scattered intensities for the same volume (84).

Correction for Phototube Sensitivity to the Direction of Polarization. Using unpolarized incident radiation, with the standard opal glass at the table center, the ratio, b , of galvanometer deflections was determined when the analyzer was set to pass first horizontal and then vertical electric vector vibrations:

$$b = \frac{H_u}{V_u}$$

The value of b differs for each phototube and was found to be approximately equal to 1.04.

Depolarization. The method for the measurement of depolarization has been covered by Davidson (41), and the use of depolarization factors for the correction of molecular weights has been discussed previously.

g. Experimental Check of R_{θ} Values

Although a controversy still rages as to the correctness of absolute values of R_{θ} for solvents used in calibration, the great weight of evidence seems to indicate that methods similar to that used by Brice, et al. (82), are valid (85, 86).

Equations [30] and [32] have frequently been used to check the value of τ by comparison of the results from both the transmission and scattering methods. Caution must be exercised, however, in the interpretation of the data (99). Several samples of the same solution of approximately 0.5% Ludox, carefully filtered through Millipore filters (see p. 61), were used to determine τ using both the light scattering photometer and the Beckman Model DU Spectrophotometer. τ measurements with the spectrophotometer were made using matched 10-cm. Beckman cells at 436 and 546 $m\mu$, at a slit opening of 0.04 mm. (98). Values of τ_{90° and τ_{Beckman} were corrected for depolarization using ρ extrapolated to $c = 0$, as given by Mommaerts (100). No corrections for dissymmetry were found to be necessary. The following results were obtained:

TABLE II

τ_{Beckman}		τ_{90°	
436 $m\mu$	546 $m\mu$	436 $m\mu$	546 $m\mu$
4.72×10^{-2}	1.87×10^{-2}	4.72×10^{-2}	1.83×10^{-2}
4.76×10^{-2}	1.87×10^{-2}	4.73×10^{-2}	1.89×10^{-2}
		4.65×10^{-2}	1.85×10^{-2}
		4.63×10^{-2}	1.78×10^{-2}

(99) S. H. Maron, and R. L. H. Lou, J. Polymer Sci. 14, 29 (1954).

(100) W. F. H. M. Mommaerts, J. Coll. Sci. 7, 71 (1952).

$R_{90^\circ, u}$ for C. P., thiophene-free benzene, F. P. $5.8^\circ\text{C}.$, was measured by means of the cylindrical cell and found to be $R_{90^\circ, u} = 4.93 \times 10^{-6}$ at $436 \text{ m}\mu$ and at approximately $25^\circ\text{C}.$ This value is in agreement with an average of $R_{90^\circ, u} = 4.94 \times 10^{-6}$ for the values obtained by several authors and tabulated by Trap and Hermans (84).

h. Final Expressions for Calculating the Scattering Data.

The two corrections which must be applied, in the absence of all other effects, are the volume correction, $\sin \theta$, and the correction for the sensitivity of the phototube to direction of polarization. According to equation [14],

$$R_\theta = \frac{R_{\theta u}}{1 + \cos^2 \theta}$$

When $(1 + \cos^2 \theta)$ is corrected for phototube sensitivity, it becomes $(1 + b \cos^2 \theta)$. Then the corrected value of R_θ , is given by

$$R_\theta (\text{corrected}) = 0.4397 \frac{G_\theta}{G_o} \frac{F_o}{F_\theta} \frac{\sin \theta}{1 + b \cos^2 \theta} \quad [61]$$

Having measured $\frac{dn}{dc}$ by means of the differential refractometer as described in the next section, application of equation [13] gives the value of K ,

$$K = \frac{2\pi^2 n_o^2}{\lambda^4 N} \left[\frac{dn}{dc} \right]^2$$

Since c , in g/ml, is known, $\frac{Kc}{R_\theta}$ at each angle θ and concentration c is determined and can be plotted as a function of $\sin^2 \theta/2 + kc$, as described on p. 14.

2. The Differential Refractometer

The theory and operation of the differential refractometer used in these laboratories has been described fully (41, 101). Preliminary determinations made with this instrument indicated that recalibration was in order. Using 0.1992 N KCl standardized against AgNO_3 and four carefully prepared aqueous sucrose solutions ranging in concentration from 0.5 to 2.0 g/100 ml., new values for the apparatus constants were determined at several wavelengths.

$$\Delta n = k_\lambda \Delta d$$

where Δn = difference between refractive indices of solvent and solution

k_λ = apparatus constant for a given wavelength

Δd = an experimentally determined quantity

The $\frac{dn}{dc}$ values used in the calibration with KCl were extrapolated from data given by Kruis (102), and those for sucrose were obtained from a paper by Svenson and Odengrim (103).

(101) B. A. Brice, and M. Halwer, J. Opt. Soc. Am. 41, 1033 (1951).

(102) A. Kruis, Z. physik Chem. 34B, 13 (1936).

(103) H. Svenson, and K. Odengrim, Acta Chem. Scand. 6, 720 (1952).

TABLE III
APPARATUS CONSTANTS FOR THE DIFFERENTIAL REFRACTOMETER

Wavelength (m μ)	$k_{\lambda} \times 10^4$
436	9.559
546	9.559
588	9.598

The value of $k_{436 \text{ m}\mu}$ was frequently checked using the standard KCl solution and was found to remain constant. It is advisable that the refractometer cell be carefully cleaned and dried subsequent to each determination, and that the use of syringes for filling and cleaning the cell be absolutely avoided.

3. pH Measurements

pH values were determined by means of the Beckman Model G pH meter, using an 1190-80 external glass electrode. The pH meter was standardized against Beckman buffer solution, pH 7, and the standardization was checked against standard sodium hydroxide- potassium acid phthalate buffers prepared by the reagent laboratory. All measurements were performed in a constant temperature room at 25° C.

4. Viscosity

An apparatus was set up to measure viscosities under variable pressure conditions. The pressure system was assembled according to instructions given by De Wind and Hermans (104). All viscosity measurements were made at $25 \pm 0.005^\circ\text{C}.$, using a Cannon and Fenske type of viscosimeter, No. 50. Radii of all viscosimeters available were measured and found to be: 0.02349 cm. for No. 50, 0.03246 cm. for No. 100, and 0.05035 cm. for No. 200. The capillary length for Viscosimeter No. 50 is 7.020 cm.

The well-established viscosity equation may be given in the form

$$p = p_e + A = \frac{B}{t} + \frac{C}{t^2} \quad [62]$$

where

$$B = \frac{8\eta_0 L V}{\pi R^4 g}$$

$$C = \frac{m_s V^2}{\pi^2 R^4 g}$$

p = total pressure in g/cm^2

p_e = excess pressure in g/cm^2

A = effective hydrostatic head in g/cm^2

η = viscosity in poises

L = capillary length in cm.

V = volume of solution in cc.

R = radius of capillary in cm.

(104) G. De Wind, and J. J. Hermans, *Rec. Trav. chim.* 70, 615 (1952).

g = acceleration of gravity in cm/sec^2

m = apparatus constant ≈ 1.12

s = density of solution

t = time in seconds

From equation [62] it can be shown (104) that

$$\frac{p_e t}{t_0 - t} - A (t_0 + t) + B = 0 \quad [63]$$

where t_0 is the time of flow of the solution when $p_e = 0$. The time of efflux for distilled water was determined at excess pressures varying between 0 and 25 g/cm^2 , and the constants A and B were evaluated from equation [63] by the method of least squares.

$$A_{\text{H}_2\text{O}} = 10.24$$

$$B_{\text{H}_2\text{O}} = 1771$$

From data for η_r and s for 0.2 N NaCl (105) it can be shown (104) that

$$A_{0.2 \text{ N NaCl}} = 10.32$$

$$B_{0.2 \text{ N NaCl}} = 1804$$

For shear dependent viscosities Strauss and Fuoss (106) recommend plotting the data in the form

(105) G. Jones and S. M. Christian, J. Am. Chem. Soc. 59, 484 (1937).

(106) U. P. Strauss, and R. M. Fuoss, J. Polymer Sci. 8, 593 (1952).

$$\frac{1}{\rho t} = \frac{B'}{\eta_{p=0}} + kp \quad [64]$$

where k is a constant. It can be shown that

$$B' = \frac{\eta_0}{B} = \frac{\eta_0}{1804}$$

where η_0 is the viscosity of 0.2 N NaCl. Thus

$$\frac{1}{\rho t} = \frac{\eta_0}{\eta_{p=0} 1804} + k p$$

and the extrapolated value $\left(\frac{1}{\rho t}\right)_{p=0}$ yields the relative viscosity of the polymer at a given concentration in 0.2 N NaCl and at zero shear.

5. Experimental Procedure

a. Preparation of Compounds

Three times recrystallized egg albumin was prepared according to a standard procedure by Kekwick and Cannan (107) and kept at 4°C. in a closed container in a desiccator over P_2O_5 .

The PVP used was from the batch prepared and studied by P. Goodman of these laboratories (42).

b. Preparation of Solutions

Approximately 100 ml. of 1.5% aqueous egg

(107) R. A. Kekwick, and R. K. Cannan, *Biochem. J.* 30, 227 (1936).

albumin was prepared at a time by dialysis with mechanical stirring against water at 4° C. The solutions were dialyzed against distilled water for at least four days and then against doubly distilled water for two days, comprising a total volume of about forty liters of water. After dialysis the solutions were centrifuged at top speed in a Servall S-1 centrifuge. Stainless steel centrifuge tubes covered with teflon caps were used for this purpose. Stock solutions clarified in this manner were kept in the refrigerator at about 2° C., but never for longer than one week.

Similarly, portions of about 200 ml. of dialyzed 2% aqueous PVP were prepared as needed and kept at room temperature.

All buffers were sodium acetate- acetic acid buffers made up according to the tables of Green (108). Stock solutions of 0.2 ionic strength were prepared, which gave, on dilution, solutions of the desired pH and ionic strength.

The following procedure was employed in making up solutions for light scattering determinations: Sufficient volumes of the concentrated aqueous EA and PVP stock solutions were first filtered through Millipore HA filters (see p. 61), and then their concentrations were determined by means of the differential refractometer, at $436\text{ m}\mu$,

(108) A. A. Green, J. Am. Chem. Soc. 55, 2331 (1933).

using the value of $\frac{dn}{dc} = 0.2036 \text{ ml/g.}$ for PVP (42) and $\frac{dn}{dc} = 0.1883 \text{ ml/g.}$ for EA (109). In making up the stock PVP-EA mixtures at the various pH's, ionic strengths, and EA/PVP ratios studied, the necessary amounts of PVP, buffer, water, and EA were calculated and delivered by volume from graduated pipets, in the order given, into 150-ml. glass-stoppered Erlenmeyer flasks. The EA was added very slowly, and care was taken to keep the tip of the pipet always below the surface of the solution. Each solution was then gently swirled and set in the refrigerator at 2° C. if not needed for immediate use. Each dilution of the stock mixtures to be used for light scattering measurements was prepared separately by adding the desired volume of the appropriate concentrated stock solution slowly to a given volume of the proper buffer, the final total volume being 100 ml. Again, care was taken to keep the tip of the pipet below the surface of the solution. After the dilution, the solution was swirled gently and kept at about 27° C. for a period of one hour prior to use in light scattering experiments. Solutions not in use were stored in the refrigerator.

c. Cleaning of Glassware

The usual methods for cleaning glassware were

-
- (109) M. Halwer, G. S. Nutting, and B. A. Brice, J. Am. Chem. Soc. 73, 2786 (1951).

found unsatisfactory for glassware contaminated with PVP. PVP was readily removed, however, by hot Haemo-Sol (110) detergent solutions. Therefore, all glassware used in the light-scattering work was boiled in or scrubbed with hot detergent solution, then thoroughly rinsed with distilled water, and, finally, dried in an oven. The cylindrical light scattering cell, when not in use, was kept filled with the detergent solution and never allowed to dry. Final rinsing of all glassware was always carried out with solutions that had been filtered twice through a Millipore filter (see p. 61).

d. Filtration

Careful and repeated examination of solutions filtered through sintered glass filters proved that glass particles were the chief contaminants, despite all precautions taken to clean the filters prior to their use by a variety of methods. Preselection of these filters was not warranted, because they deteriorated quickly and unexpectedly. It was learned from the members of the research group under Dr. E. Mack of this department that a new type of membrane filter was coming into use for certain biological work. These Millipore HA filter disks (supported by a specially designed Pyrex filter assembly), manufactured by

(110) Product of Meinecke and Co., Inc., 225 Varick Street, New York, N. Y.

the Lovell Chemical Company, Watertown, Massachusetts, were found to be excellently suited for light scattering work. They are capable of quantitative retention of particles of 0.5 microns and higher in diameter, are rather inexpensive so that they can be changed frequently, and they pass solutions very rapidly. While this work was in progress, Edelhoch, et al. (111), reported their use of Millipore filters for light scattering work.

The usual methods for the preparation of a concentration series for light scattering measurements are: 1) successive additions of clarified concentrated stock solution to clarified solvent; 2) successive dilutions of clarified concentrated solution with clarified solvent. It was found that, despite all precautions, contamination occurred at each transfer in either of these methods, so that the degree of cleanliness necessary for angular light scattering measurements was not achieved. It was far more reliable and more convenient as well to prepare each dilution of the stock separately, as described above, and then to filter it directly into the scattering cell (112).

As has already been indicated in the section on solution preparation, special precautions have to be taken

(111) H. Edelhoch, E. Katchalski, R. H. Maybury, W. L. Hughes, and J. T. Edsall, J. Am. Chem. Soc. 75, 5058 (1953).

(112) J. T. Edsall, R. M. Maybury, R. B. Simpson, and R. Straessle, J. Am. Chem. Soc. 76, 3131 (1954).

when handling EA solutions because of the extreme susceptibility of EA to surface denaturation (113). For this reason, the stem of the Pyrex filter assembly was bent at a very gentle angle, so that the tip touches the wall of the scattering cell during filtration, thus permitting the filtered solution to flow down the wall in a continuous, thin, gentle stream, and thereby avoiding precipitation.

A brief outline of the procedure followed for filling the scattering cell in preparation for measurements of R_{θ} is given here:

1. Rinse the detergent solution from the filter assembly and backwash the fritted glass section of the filter with about forty liters of distilled water.
2. Assemble the filter without the Millipore disk, and pass through it a minimum of two liters of prefiltered distilled water.
3. Set the Millipore disk in place, and pass through about 200 ml. of prefiltered water to rinse the scattering cell.
4. Pass through about 40 ml. of the solution of lowest concentration in the series, in two or three portions, to rinse the cell with the filtered solution.
5. Pass about 30 ml. of the solution into the scattering cell, and cover the cell immediately. Make the

(113) H. B. Bull, and H. Neurath, J. Biol. Chem. 125, 113 (1938).

light scattering measurements, but be certain that some of the solution is left in the funnel to keep the Millipore disk wet at all times.

6. When the light scattering measurements are completed, save the solution, and rinse the cell with the solution of next highest concentration in the series, as in step 4.

7. Repeat steps 5 and 6. No more than two solutions should be filtered without recleaning the equipment and changing the Millipore disk.

8. Disassemble the filter, boil the glassware in detergent solution, scrub the scattering cell, and repeat the procedure from the beginning.

6. Experimental Results

a. pH Titration of Proteins with PVP

The first qualitative indication that PVP and EA combine chemically was the formation of a turbid solution when aqueous PVP was added to aqueous EA. The turbidity disappears on the addition of excess PVP or simple electrolytes and reappears on dilution with solvent following the addition of simple electrolytes.

pH measurements were carried out upon titration of isoelectric EA with aqueous PVP at various initial concentrations of EA, keeping the initial volume constant. As can be seen from Figure 1, pH decreases in three distinct

linear steps with increasing concentration of PVP. The initial pH was found to vary slightly with EA concentration, so that a small correction was applied to make all the curves start from the same point. As titration progresses, turbidity decreases and disappears completely when the horizontal portion of the curve is reached. Repeated runs have shown that pH values are reached immediately on mixing and that the first and the second break-points occur at constant ratios, r , of the weight concentrations of EA and PVP, independent of the initial volumes and initial concentrations of EA or PVP. The data is collected in Table IV.

A similar experiment was performed with crystalline bovine serum albumin (hereafter called SA), Lot No. M66909, purchased from the Armour Laboratories, Chicago, Illinois. The SA stock solution was not dialyzed, as less than 0.0002 equivalents per liter of salt would be present for the highest concentration of SA used. As Figure 2 shows, three distinct breaks, instead of two, are evident, the values of r at the break-points now being linearly dependent upon the initial concentration of SA.

For both SA and EA the total decrease in pH varies inversely with initial protein concentration, but, interestingly, the total change in pH is about the same when the same initial weight concentration of either protein is used.

EA solutions, after titration with PVP, were back-titrated with 0.016 N NaCl and with 0.016 N NaF, and it was

TABLE IV
r AT THE BREAK-POINTS AS A FUNCTION OF
INITIAL PROTEIN CONCENTRATION

EA					
Initial [EA] in per cent	Initial Volume of EA, ml.	Initial [PVP] in per cent	r at First Break	r at Second Break	
0.050	25	0.100	20.0	11.1	
0.250	20	0.100	19.2	11.9	
0.253	20	0.118	21.4	10.7	
0.421	20	0.118	22.3	11.0	
0.586	20	1.184	22.7	10.9	
0.842	20	0.118	23.0	11.4	
1.17	20	1.184	21.5	10.9	
1.76	20	1.184	26.2	11.7	
Average:			22.0 ±6.9%	11.2 ±3.1%	
SA					
Initial [SA] in per cent	Initial Volume of SA, ml.	Initial [PVP] in per cent	r at First Break	r at Second Break	r at Third Break
0.426	20	0.999	47.4	24.4	11.2
0.853	20	0.999	63.3	34.1	13.7
1.279	20	0.999	73.1	40.7	17.1
1.705	20	0.999	85.4	48.8	21.3

TITRATION OF ISOELECTRIC EA AT VARIOUS CONCENTRATIONS WITH PVP AT $C^\circ = .118\%$

FIGURE 1

FIGURE 2

found that pH increases with addition of the electrolyte solution in a characteristic fashion. On addition of NaCl, the pH increases in a series of slowly rising steps, and no sign of turbidity is apparent even at as high a pH as 4.8. With NaF, however, the pH values at first duplicate the values obtained with NaCl, but then the two curves separate. Here, turbidity reappears at a pH around 4.7.

b. Variation of Turbidity with Time

For light scattering measurements it is desirable to work in a region where interactions are time-independent. Turbidity was measured as a function of time for unfiltered EA-PVP solutions in water having values of r less than 11.2, and it was found that, at any given value of r , turbidity, in relative units, increases linearly with time, reaches a maximum, and then decreases in a non-linear fashion. The rate of turbidity increase rapidly approaches zero as r approaches the value of 11.2.

Similar turbidity versus time experiments were carried out, in duplicate, on a filtered PVP-EA solution at $r = 6$, ionic strength (μ) = 0.001, pH = 4.6, and total concentration = 0.1%, and it was found that the turbidity was constant with time. At this point it was desirable to examine the effect of filtration upon total concentration in solution. Concentration determinations were carried out at several wavelengths, using the Beckman DU Spectrophoto-

meter, before and after filtration of the above buffered PVP-EA solution, and no change of concentration with filtration was detected. It might be included here that similar checks were made on time-dependence and the effect of filtration upon concentration in subsequent light scattering runs, and neither time-dependence nor change in concentration on filtration were observed.

c. Light Scattering Experiments

All light scattering measurements were carried out at about 27° C., at angles between 30° and 135°, using blue light of wavelength 436 m μ . Because the scattered intensities are less at 546 m μ , it was found, in agreement with Mommaerts (114), that measurements with blue light are subject to less error than those carried out at 546 m μ . The errors are due chiefly to dust and spurious light effects in the apparatus.

The methods for the preparation of solutions, actual measurement procedures, and the method of calculating data for a Zimm plot were discussed in previous sections. Calculations of $\bar{s}$ are carried out according to equation [54]. B, the interaction constant for the system, and R_G , the radius of gyration for the system, are obtained from equation [22] and equation [24], respectively. Since R_G obtained

(114) W. F. H. M. Mommaerts, J. Biol. Chem. 198, 445 (1952).

from light scattering is a Z-average, R_G for the system can be taken as equal to R_{G_6} when $\delta > 0.3$. At lower values of δ , R_{G_6} was determined according to equation [7] given in reference (30). The experimental $P(\theta)$ is given by equation [23].

The light scattering experiments of this investigation may be divided into five groups:

- 1) light scattering of pure components
- 2) light scattering of PVP-EA mixtures at constant r and pH and varying ionic strength
- 3) light scattering of PVP-EA mixtures at constant r and μ and varying pH
- 4) light scattering of PVP-EA mixtures at constant μ and pH and varying values of r
- 5) light scattering of PVP-SA mixtures at $r = 1.0$, $\text{pH} = 5.08$, and $\mu = 0.004$.

1) Light Scattering of Pure Components

The molecular weight of EA at $\mu = 0.001$ and $\text{pH} 4.62$ was found to be $44,800 \pm 2\%$, in agreement with accepted values (115). $B = 0$. This determination of the molecular weight was carried out, using the dissymmetry method, on an aqueous solution of EA which had been stored in the refrigerator at about 2°C . for one week following dialysis and

(115) R. C. Warner, in The Proteins, Vol. II, Part A, eds. H. Neurath and K. Bailey, Academic Press, New York, p. 448 (1954).

which was then adjusted to the desired μ and pH. Although visible aggregates were seen in the original unadjusted solution, examination of the angular scattering yielded a constant value of $\frac{R_{90}}{1 + b \cos^2 \theta}$, shown in Table V. This constancy ($P(\theta) = 1$) and the fact that the accepted value for the molecular weight was obtained are evidence of the efficiency of the filtration and the accuracy of the photometer calibration.

TABLE V
DETERMINATION OF R_{θ} FOR EA AT $c = 2.9 \times 10^{-3}$ g/ml.

Angle	G_{θ}^*	$R_{\theta} \times 10^5$
0	78.0 (1234)	
30	88.3 (13)	7.84
35	70.3	7.64
40	59.1	7.54
45	50.2	7.58
50	91.4 (3)	7.61
60	71.1	7.56
70	58.4	7.61
80	51.3	7.62
90	49.0	7.57
100	51.3	7.55
110	57.8	7.45
120	70.6	7.42
130	89.7	7.40
135	43.3 (13)	7.49
Average:		7.56 ± 0.076 or $\pm 1.0\%$

*The numbers in parentheses after the G_{θ} values, here and in succeeding tables, indicate the filter combinations used; where no values are given, the nearest preceding filter combination applies.

The molecular weight of PVP in 0.2 N NaCl, after correction for back-reflection (97), was found to be 654,000. This value agrees with the value calculated on the basis of the molecular weight of the unquaternized parent polymer, as given by Goodman (42). Taking the molecular weight of the parent polymer as 269,000, the molecular weight of the unquaternized monomer unit as 105, and that of the quaternized monomer unit as 242, the calculated molecular weight is $269,000 \times 242/105 = 620,000$. The molecular weight not corrected for back-reflection, as determined from Figure 3, is 641,000. It was estimated that molecular weights uncorrected for back-reflection were never more than 5% lower than corrected weights, and, therefore, no corrections for back-reflection were applied. Although 0.2N NaCl is considered to be sufficiently high in ionic strength for typical light scattering measurements, so that ideal behavior was expected, deviation from linearity, due to omission of higher virial coefficients in the molecular weight equation, is apparent in the neighborhood of 5×10^{-3} g/ml.

Light scattering results for PVP in 0.2 N NaCl were correlated with viscosity measurements and with sedimentation and diffusion work from these laboratories by Maio (116), and the correlations observed will be given in section d.

(116) N. J. Maio, Master's Thesis, The Ohio State University (1953).

FIGURE 3

At lower ionic strengths, molecular weights of PVP in the neighborhood of 530,000 were found, both by actual measurements at $\mu = 0.03$ and $\mu = 0.004$, and, also, by calculation from runs on PVP-EA mixtures for which there was no evidence for interaction. The results are tabulated below.

TABLE VI
MOLECULAR WEIGHTS OF PVP
UNDER VARIOUS EXPERIMENTAL CONDITIONS

Molecular Weight	Experimental Conditions
641,000	0.2 N NaCl
530,000	$\mu = 0.03$, pH = 4.20
556,000	$\mu = 0.004$, pH = 4.60
510,000	PVP-EA mixture, $\mu = 0.01$, pH = 4.60
510,000	PVP-EA mixture, $\mu = 0.004$, pH = 4.20
538,000	PVP-EA mixture, $\mu = 0.004$, pH = 4.38

Taking the molecular weight (average) as 530,000 gave consistent results in calculations of data obtained at 0.03 ionic strength and lower. A Zimm plot for PVP at $\mu = 0.03$ and pH = 4.20 is given in Figure 4.

Flory and Krigbaum (117) have shown that it is possible to evaluate Γ_3 , the third virial coefficient in

(117) P. J. Flory, and W. R. Krigbaum, J. Chem. Phys. 18, 1086 (1950).

FIGURE 4

the virial expression for the osmotic pressure, on the basis of a hard sphere molecular model.

$$\Gamma_3 = \frac{5}{8} \Gamma_2^2 = g \Gamma_2^2$$

Later work by Stockmayer and Casassa (118) indicated that $g < 5/8$ should be used. Using $g = 1/3$, equation [16] becomes

$$\frac{Kc}{R_\theta} = \frac{1}{M} (1 + \Gamma_2 c)^2$$

which suggests plotting light scattering data as $\left(\frac{Kc}{R_\theta}\right)^{1/2}$ versus concentration, rather than $\frac{Kc}{R_\theta}$ versus concentration. Figure 5, for PVP at $\mu = 0.03$ and pH = 4.20, shows that a straight line is obtained for a plot of $\left(\frac{Kc}{R_{90}}\right)^{1/2}$ versus c , but that curvature is observed in the usual reduced intensity plot. The same is true for all other runs made. Application of equation [16] with $g = 1/3$ eliminates curvature, also, in reduced intensity plots for PVP in HBr solutions, for the data collected by Goodman (42).

2) Light Scattering of PVP-EA Mixtures at Constant r and pH and Varying Ionic Strength.

The observations noted in the following paragraphs apply not only to PVP-EA mixtures at constant r and pH and varying ionic strength, but also to mixtures under other conditions discussed in subsequent sections.

(118) W. H. Stockmayer, and E. F. Casassa, J. Chem. Phys. 20, 1560 (1952).

EFFECT OF HIGHER VIRIAL COEFFICIENTS ON PLOTS OF REDUCED INTENSITY vs.
C FOR PVP AT $\mu = .03$, pH = 4.20

FIGURE 5

Whereas Zimm plots for uncharged polymers usually consist of a grid system formed by two series of parallel lines, a similar plot for a PVP-EA mixture at $r = 1.0$, $\mu = 0.0025$, and $\text{pH} = 4.60$ (Figure 6) evidences several interesting features generally found in these studies. First, the slopes of $\frac{c_T}{R_\theta}$ versus $\sin^2 \theta/2$ at various total concentrations, c_T , decrease with increasing c_T . Secondly, the slopes of $\frac{c_T}{R_\theta}$ versus c_T , at various angles, decrease with increasing angle of observation, and curvature is apparent at about $c_T = 6 \times 10^{-4}$ g/ml. Recent angular light scattering work by Benoit, et al. (55), and by Shultz (58) on polyelectrolyte systems gives evidence that these observations are not unique.

In the discussion beginning on p. 33 it was pointed out that the ordering effect in polyelectrolyte systems disappears at low polyelectrolyte concentrations. Light scattering measurements, therefore, were carried out at the lowest accessible concentrations, usually in the neighborhood of 0.8×10^{-4} g/ml. Below this concentration large solvent corrections make readings inaccurate. That ordering effects are present in salt solutions as well as at zero ionic strength can be seen clearly from Figure 7, which gives z versus c_T for a PVP-EA mixture at $r = 1$, $\mu = 0.001$, and $\text{pH} = 4.60$. With increasing polyelectrolyte concentration z decreases rapidly and linearly, goes through a shallow minimum, and then rises slowly at higher

DISSYMMETRY vs. C_T FOR PVP- γ EA AT $\gamma = 1.0$, $\mu = 0.001$, AND $\text{pH} = 4.60$

FIGURE 7

concentrations. It is interesting to note that Z , in this case, goes below $Z = 1$. In other runs Z decreased linearly with increasing concentration, but the minima, with the exception of a run at $\mu = 0.0025$, were not reached.

In previous light scattering studies on associating systems, minima, indicating dissociation of the complex at low c_T , were observed in plots of reduced intensity versus total concentration at c_T as high as 10×10^{-4} g/ml. (30, 32, 33, 34). No such minima were observed for PVP-EA mixtures at concentrations as low as $c_T = 0.5 \times 10^{-4}$ g/ml. Thus, the method for evaluating the molecular weight of the complex, M_6 , and δ , the weight absorption coefficient, as developed by Geiduschek and Doty (30), seemed particularly well-suited for the system PVP-EA studied here.

The light scattering data for PVP-EA mixtures at constant r and pH and varying ionic strength are tabulated in Table VII.

TABLE VII

LIGHT SCATTERING DATA FOR PVP-EA MIXTURES
AT VARIOUS IONIC STRENGTHS, $r = 1$, pH = 4.60

μ	$\left(\frac{c}{R_0}\right)_{c_T=0}$	δ	$R_G^2 \times 10^{-5}$	$M_6 \times 10^{-6}$	$B \times 10^5$
0.001	1.53	1.01	6.10	1.068	34.0
0.0025	1.60	0.97	5.42	1.044	18.5
0.004	2.30	0.61	3.77	0.853	15.0
0.005	3.27	0.34	2.38	0.710	13.3
0.010	5.68	0.00			13.0

As can be seen from Figure 11, δ reaches the maximum allowable value, $\delta = 1$ when $r = 1$, at $\mu = 0$, then decreases sigmoidally with increasing ionic strength and levels off to zero at $\mu = 0.01$, where no interaction takes place. From the plot of limiting interaction constant, B , versus μ (Figure 12), it is apparent that the effective volume of the system decreases as the ionic strength is increased. The value of B at $\mu = 0.004$ was found to be out of line with the other values listed, and an interpolated value of B at $\mu = 0.004$ was therefore used throughout this work. As M_6 ($M_6 = M_2 [1 + \delta]$) increases due to decreasing ionic strength, R_G^2 increases linearly (Figure 13).

3) Light Scattering of PVP-EA Mixtures at Constant μ and r and Varying pH.

TABLE VIII
LIGHT SCATTERING DATA FOR PVP-EA MIXTURES AT
VARIOUS pH's, $r = 1$

μ	pH	$\left(\frac{c}{R_\theta}\right)_{c \rightarrow 0}$	δ	$R_{G6}^2 \times 10^{-5}$	$M_6 \times 10^{-6}$	$B \times 10^5$
0.004	4.20	5.95	0.0			46.1
0.004	4.38	5.60	0.0			40.3
0.004	4.50	4.70	0.085	3.40	0.575	26.3
0.004	4.60	2.30	0.610	3.77	0.853	15.0
0.004	4.88	1.70	0.915	3.81	1.01	17.1
0.004	5.23	0.725	1.07	5.20	2.26	27.9
0.030	4.20	5.95	0.0			9.04
0.002	4.88	1.63	0.950	5.48	1.03	18.5

The data from Table VIII is presented in three graphs, as in the preceding section (Figures 11, 12, and 13).

From Figure 11 it is seen that no interaction takes place up to pH 4.40, that δ reaches a value of 0.853 at pH 4.60, and that the shape of the δ versus pH curve resembles that of the δ versus μ curve. At pH 5.23 an apparent value of about 2.0 for δ was first obtained. Since $r = 1$ in these experiments, δ could not possibly exceed unity. If it is granted that at this pH, where the protein and the polyelectrolyte are oppositely charged, aggregation is feasible, then a value of $\delta \approx 1.0$ may be obtained by assuming that two molecules of PVP, with their bound EA, form a new molecular unit. For this one case, at pH 5.23, in contrast with the other Zimm plots, the slopes of plots of $\frac{c_r}{R_\theta}$ versus $\sin^2\theta/2$ at constant c_T increase with c_T . Figure 12 shows that B decreases with pH, reaches a minimum at a pH near 4.70, and then goes up again as the EA becomes positively charged. R_G^2 (Figure 13) increases linearly with M_0 ; the slope, however, although still positive, is not as high as is found for the runs at variable ionic strength.

4) Light Scattering of PVP-EA Mixtures at Constant μ and pH and Varying Values of r .

The higher the value of r , the higher the turbidity of PVP-EA solutions. The highest r used was 4.33, where

$$M_6 = 1.84 \times 10^6.$$

Zimm predicted (44) that curved Zimm plots are to be expected when B and M are very high. This can be seen in Figure 8. It was found convenient to plot the data as $\left(\frac{c_T}{R_\theta}\right)^{1/2}$ versus c_T at various angles, and then to use the extrapolated values at $c_T = 0$ to plot $\left(\frac{c_T}{R_\theta}\right)^{1/2}_{c_T=0}$ versus $\sin^2 \theta/2$. The molecular weight is then determined from $\left(\frac{c_T}{R_\theta}\right)^{1/2}_{c_T=0, \theta=0}$. This method was used in preparing Figures 9 and 10.

The light scattering results are summarized in Table IX.

TABLE IX
LIGHT SCATTERING DATA FOR PVP-EA MIXTURES
AT VARIOUS VALUES OF r , $\mu = 0.004$, pH = 4.60

r	w_{PVP}	$\left(\frac{c_T}{R_\theta}\right)_{c_T=0}$	δ	$R_G^2 \times 10^{-5}$	$M_6 \times 10^{-6}$	$B \times 10^5$
4.33	0.188	1.39	2.48	2.46	1.84	1.45
1.96	0.337	1.90	1.18	2.66	1.16	7.89
1.00	0.500	2.30	0.61	3.77	0.853	15.0
0.429	0.700	3.55	0.06	3.46	0.663	26.8 (corrected)

δ is found to vary linearly with r , and this relationship can be expressed by the equation (see Figure 11)

$$\delta = 0.586 r$$

The point corresponding to $r = 0.429$ deviates most from the line; the possible explanation for this deviation will be

RECIPROCAL REDUCED INTENSITY FOR PVP-EA AT $\gamma = 4.33$, $\mu = 0.004$ AND $\text{pH} = 4.60$

FIGURE 8

FIGURE 9

FIGURE 10

δ vs μ , pH, and γ

89

FIGURE 11

examined in the discussion section. B is a quadratic function of w_{PVP} , the weight fraction of PVP, as seen in Figure 12 (119). An example of A linear type of relationship between B and the weight fraction of one of the components of a reacting mixture is given by Morawetz and Gobran (120) for an osmotic pressure study on an associating system consisting of an acidic and a basic polymer in butanone and benzene solutions. R_G^2 is found to decrease linearly with M_6 as r is varied but pH and μ are kept constant (Figure 13). This is in contrast with the increase of R_G^2 with increasing M_6 in the previous experiments at variable μ and pH .

5) Light Scattering of PVP-SA Mixtures at $r = 1.0$,
 $\text{pH} = 5.08$, and $\mu = 0.004$.

It was of interest to obtain δ and M_6 for the PVP-SA system at the isoelectric point of SA ($\text{IP} = 5.10$). δ was found to be 0.715 and M_6 to be 9.09×10^5 . It can be seen that δ for PVP-SA at the IP of SA is less than δ for PVP-EA at the IP of EA, at the same μ and the same value of r (IP for EA = 4.90, $\delta = 0.915$).

-
- (119) G. Scatchard, A. Gee, and J. Weeks, J. Phys. Chem. 58, 783 (1954).
 (120) H. Morawetz and R. H. Gobran, J. Polymer Sci. 12, 133 (1954).

FIGURE 12

FIGURE 13

d. Correlation of Light Scattering Work with Viscosity, Sedimentation, and Diffusion, and Calculations of $P(\theta)$

Flory and Fox (121) have been able to show that the hydrodynamic behavior of coiled polymer molecules can be approximated by treating an equivalent sphere, the radius of which is proportional to the root mean square end-to-end length, $(\overline{r^2})^{1/2}$, which characterizes the Gaussian distribution of chain segments. They have shown that $(\overline{r^2})^{1/2}$ is related to the molecular weight and intrinsic viscosity by the equation

$$(\overline{r^2})^{3/2} = \frac{[\eta] M}{\phi} \quad [65]$$

where $[\eta]$ = intrinsic viscosity

ϕ = a constant having the value 2.1×10^{21}

It has been shown by several authors that equation [65] can be used successfully, even for polydisperse systems of coils, to obtain semi-quantitative data, provided $(\overline{r^2})^{1/2}/L$ is less than $1/4$, where L is the contour length of the polymer molecule (122). If the molecular weight used in equation [65] is determined by means of light scattering, then, as Ehrlich and Doty (57) have shown

(121) P. J. Flory and T. G. Fox, J. Am. Chem. Soc. 73, 1904 (1954).

(122) S. Newman and P. J. Flory, J. Polymer Sci. 10, 121 (1953).

$$\left(\overline{r^2}\right)_{\text{viscosity}}^{3/2} = \left(\overline{r^2}\right)_N^{3/2} \cdot \frac{\bar{M}_w}{\bar{M}_N} \quad [66]$$

On the other hand, light scattering yields, for polydisperse coils, a Z-average of $(\overline{r^2})$ (123), which can be converted to $(\overline{r^2})_N$ if random-flight conditions are assumed (58).

For then

$$\left(\overline{r^2}\right)_N = \left(\overline{r^2}\right)_Z \cdot \frac{z}{(z+2)} = \left(\overline{r^2}\right)_Z \cdot \frac{\bar{M}_N}{\bar{M}_z} \quad [67]$$

Here, Z indicates Z-average,

N indicates number average,

z is a measure of the breadth of the distribution of molecular weights.

For a distribution of coiled polymer molecules for which

$z = 1$, it can be shown that light scattering theory gives

(44)

$$\left(\overline{r^2}\right)_{z=1}^{1/2} = 0.817 \left(\overline{r^2}\right)_{\text{monodisperse}}^{1/2}$$

For the case under consideration, $(\overline{r^2})_{z=1}^{1/2} = 899 \text{ \AA}$. Since calculations of $P(\theta)$ given at the end of this section seem to indicate that a polydisperse coil model with $z = 1$ fits the light scattering data for PVP, and since PVP behaves in 0.2 N NaCl like an uncharged polymer, it was possible to use the relationships presented in this section, which were developed for uncharged coiled polymers. From viscosity

(123) B. H. Zimm and W. H. Stockmayer, J. Chem. Phys. 17, 1301 (1949).

measurements on PVP in 0.2 N NaCl at several concentrations, it was determined that $[\eta] = 1.083 \text{ 100 ml./g}$, from which

$$(\bar{r}^2)^{1/2}_{\text{viscosity}} = 700 \text{ \AA}$$

according to equation [65], if the light scattering molecular weight of 6.54×10^5 is used. For a $z = 1$ distribution, $\bar{M}_N : \bar{M}_W : \bar{M}_Z = 1 : 2 : 3$. Making use of equations [66] and [67], it can be shown that

$$\frac{(\bar{r}^2)_{z=1}}{(\bar{r}^2)_{\text{viscosity}}} = 1.89 \quad \text{and} \quad \frac{(\bar{r}^2)_{z=2}}{(\bar{r}^2)_{\text{viscosity}}} = 1.53$$

while the actual experimental ratio is

$$\frac{(\bar{r}^2)_{z=1}}{(\bar{r}^2)_{\text{viscosity}}} = 1.65 \quad \text{and} \quad \frac{(\bar{r}^2)_{z=2}}{(\bar{r}^2)_{\text{viscosity}}} > 1.65$$

This suggests that the PVP sample studied is a heterogeneous mixture with z between 1 and 2.

Polyelectrolyte behavior approaches the behavior of uncharged polymers at high salt concentration not only in light scattering work, but also in sedimentation and diffusion measurements. On purely empirical grounds, Howard and Jordan (124) suggested plotting $1/S$, where S is the sedimentation constant measured at various ionic strengths, as a

(124) G. J. Howard and D. O. Jordan, *J. Polymer Sci.* 12, 199 (1954).

function of $1/y$, where

$$y = \frac{\text{total molarity of cations}}{\text{grundmolarity of polymer}}$$

The fraction y , according to recent work by Kraut (125), probably has theoretical as well as empirical significance. Maio (116), in his sedimentation studies on PVP in various HBr solutions, plotted $1/S$ versus $1/y$ and obtained a straight line relationship, from which he calculated a value of S^0 , the sedimentation constant at infinite ionic strength and zero polymer concentration. Similarly, D^0 , the diffusion constant at infinite ionic strength and zero polymer concentration, was obtained by plotting D as a function of $1/y$. His results show, also, that at $\mu = 0.2$ all charge effects are eliminated. Knowing that $S_{20^\circ\text{C.}}^0 = 7.28 \times 10^{-13}$ and $D_{20^\circ\text{C.}}^0 = 1.13 \times 10^{-7}$, he obtained 6.04×10^5 as the molecular weight for PVP. The value obtained from light scattering in the present work is 6.41×10^5 in 0.2 N NaCl. Maio calculated D by the so-called area-height method, and S according to

$$S = \frac{1}{\omega^2} \left(\frac{d \ln x}{dt} \right)$$

It can be shown that, for this method of calculating molecular weight from sedimentation and diffusion data (126),

(125) J. J. Kraut, J. Polymer Sci. 14, 222 (1954).

(126) G. Meyerhoff, Makromol. Chem. 12, 61 (1954).

$$\bar{M}_N \leq \bar{M}_{S-D} \leq \bar{M}_W$$

Since light scattering yields a weight average molecular weight, then a lower molecular weight from sedimentation and diffusion data is to be expected.

Mandelkern, et al. (127), have derived a relationship between M , $[\eta]$, and S for uncharged coils

$$M = \left[\frac{S [\eta]^{1/3} \eta^0 N}{2.5 \times 10^{-6} (1 - \bar{v}\rho)} \right]^{3/2} \quad [68]$$

where η^0 = viscosity of the solvent
 $\bar{v}$ = partial specific volume of the solute
 ρ = density of the solvent

If it is assumed that $[\eta]$ for PVP in 0.2 N NaCl is about equal to $[\eta]$ for an uncharged polymer, then, using

$$\frac{\eta^0_{20^\circ\text{C.}}}{\eta^0_{25^\circ\text{C.}}} = 1.125 \quad (128)$$

to correct for the temperature dependence of S^0 , and substituting the appropriate values of $\bar{v} = 0.770$ and $\rho = 0.998$ (116) and of $[\eta] = 1.083$, obtained in this investigation, into equation [68], one obtains $M = 5.76 \times 10^5$. Thus it is possible to obtain the molecular weight of a polymer at infinite ionic strength if S and $[\eta]$ are known.

(127) L. Mandelkern, W. R. Krigbaum, H. A. Scheraga, and P. J. Flory, J. Chem. Phys. 20, 1392 (1952).

(128) P. M. Kampfner, J. Appl. Phys. 23, 99 (1952).

A relationship can be shown to exist, as well, between D^0 , $[\eta]$, and M for uncharged coils (129).

$$\phi^{1/3} P^{-1} = \frac{\eta^0}{kT} D^0 ([\eta] M)^{1/3} \quad [69]$$

where $\phi^{1/3} P^{-1}$ is a constant equal to 2.62×10^6 . Correcting for the temperature dependence of D^0 , and using the value of $M = 6.54 \times 10^5$, as obtained from light scattering, one finds, from equation [69], that $\phi^{1/3} P^{-1} = 2.49 \times 10^6$, with a deviation of -5% from the theoretical value.

Angular light scattering measurements, in contrast with measurements at 90° , make it possible to obtain an experimental particle scattering factor, $P(\theta)$ (equation [23]), which can be compared with a theoretical $P(\theta)$ calculated for a model of a given size and shape. From the limiting slope of a Zimm plot, R_G is readily obtained (equation [24]). Once the value of R_G is known, it can be translated into a characteristic particle dimension, as was shown on p. 17. Once a characteristic dimension is calculated, then theoretical values of $P(\theta)$ as a function of θ can be obtained for various molecular models from available tables and equations (p. 16) and compared with the experimental $P(\theta)$ versus θ plot.

(129) T. G. Fox, J. Chem. Phys. 21, 187 (1953).

The data for PVP-EA at $r = 1.0$, $\mu = 0.001$, and $\text{pH} = 4.60$ are suited to the determination of the shape of the PVP-EA complex, because the dissymmetry coefficient, Z , is high, and, at the same time, these data yield information as to the breadth of the molecular weight distribution of the original sample of PVP, because binding is complete. When the polymer is not too extended (Z is 1.4 or lower), then the $P(\theta)$ curves for rods and coils tend to be very much alike. When Z is high, however, the distinction between particle shape factors is more marked, so that the choice of a model is more easily made.

Values of $P(\theta)$ for various values of $\sin \theta/2$ were calculated for rods, monodisperse coils, and spheres from tables prepared by Doty and Steiner (49), and values for cylindrical and ellipsoidal disks were interpolated from enlarged graphs given by Saito and Ikeda (46). (See Figures 14 and 15.) The $P(\theta)$ values for polydisperse coils, assuming $z = 1$ ($\bar{M}_Z : \bar{M}_W : \bar{M}_N = 3 : 2 : 1$), were calculated from an equation given by Zimm (44) and are tabulated in Table X along with the experimental $P(\theta)$ values.

COMPARISON BETWEEN THEORETICAL AND EXPERIMENTAL SCATTERING FACTORS
FOR PVP-EA, $R_G^2 = 6.10 \times 10^5$, AT $\tau = 1.0$, $\mu = 0.001$, AND pH = 4.60

FIGURE 14

FIGURE 15

TABLE X

COMPARISON BETWEEN THEORETICAL AND EXPERIMENTAL
SCATTERING FACTORS FOR PVP-EA,
 $R_G^2 = 6.10 \times 10^5$, $r = 1.0$, $\mu = 0.001$, and $\text{pH} = 4.60$

$\sin \theta/2$	$P(\theta)_{\text{experimental}}$	$P(\theta)_{z=1}$ for poly- disperse coils
.259	0.836	0.831
.300	.793	.785
.342	.739	.740
.383	.695	.693
.423	.646	.648
.500	.567	.569
.574	.498	.500
.643	.440	.444
.707	.394	.398
.766	.355	.360
.824	.328	.330
.866	.303	.306
.910	.285	.287
.924	.278	.279

Comparison of the experimental $P(\theta)$ curve with the $P(\theta)$ curves obtained theoretically leads to the conclusion that the complex has the shape of a coil, and that PVP is polydisperse, having a molecular weight distribution characterized by $z = 1$. The preceding discussion of the correlation between viscosity and light scattering data led to similar conclusions.

V. DISCUSSION

Angular light scattering measurements were carried out on PVP-EA mixtures at pH's below the isoelectric point of EA and at various ionic strengths and mixing ratios in the range where interaction occurs without precipitation. Even though the net charge on the protein is positive under these conditions, complexing takes place with the cationic polyelectrolyte. The ratios r chosen in this study were below 11.2, in order to avoid consideration of turbidity-time effects. Values of r , μ , and pH were selected which would characterize the complexing system over a wide range of experimental conditions and which would give values of δ , the weight absorption coefficient, sufficiently high to measure and yet not so high that there would be a possibility of removing large complexes in the filtration procedure. Equation [53] was developed for angular light scattering studies of interacting systems in which the free concentration of one of the components is negligible and in which δ is constant in the concentration region under consideration. Since the complexing between PVP and EA falls into the category just described, the use of equation [53] appears justified.

Because ordering effects become important at zero and intermediate ionic strengths, and because higher virial

coefficients become important at high polyelectrolyte concentrations, it was necessary, at the ionic strengths chosen, to work with solutions of the lowest feasible polyelectrolyte concentrations. The work of Oth and Doty (72) indicates that measurements carried out in the polyelectrolyte concentration range where the dissymmetry Z decreases with increasing polyelectrolyte concentration may be used to give correct values for molecular weights and particle scattering factors. In all cases studied here this condition was fulfilled. Ordering phenomena are demonstrated in Figure 7, and the effects of higher virial coefficients can be seen in Figures 5 and 8. In no case studied was there evidence of dissociation of the PVP-EA complex, even at the lowest concentrations reached. This fact suggests that the equilibrium constants for association must be very high.

That the PVP-EA system is in equilibrium was shown by the following: The same R_θ values for a given concentration were observed whether a given solution was prepared directly or by dilution from a concentrated stock solution. Also, R_θ values for a solution at $c_T = 10^{-3}$ g/ml, $r = 1.0$, $\mu = 0.01$, and $\text{pH} = 4.60$ were found to be within $\pm 2.7\%$ of the R_θ values obtained by concentration of a solution originally at $c_T = 5 \times 10^{-4}$ g/ml, $r = 1.0$, $\mu = 0.005$, and $\text{pH} = 4.60$.

Although the pH titration studies of EA and SA with PVP were not exhaustive, several interesting features may be considered. Gibbs, et al. (130), in their studies of the interaction between EA and cationic detergents, obtained curves very similar to those in Figure 1 and attempted to correlate the pH decrease up to the first break point with detergent micelle formation and the decrease before the second break point with complex formation between the detergent cations and the EA carboxyl groups. Curves not too different from those obtained by Gibbs, et al., and those in the present investigation are shown by Tanford (131) for his pH titrations of a sodium acetate-acetic acid buffer system with salt solutions, except that no discontinuities occurred.

In the present case, the decrease in pH before the first break point on the addition of PVP to isoelectric protein cannot be ascribed to micelle formation, and it is unlikely that discontinuous curves of this nature would result solely from changes in the activity coefficients of the hydrogen ions. The decrease in pH on the addition of PVP can be attributed, however, to a successful competition of the positive groups on the PVP molecule with hydrogen

(130) R. J. Gibbs, S. N. Timasheff, and F. F. Nord, Arch. Biochem. Biophys. 40, 85 (1952).

(131) C. Tanford, J. Am. Chem. Soc. 76, 945 (1954).

ions for the carboxyl groups on the protein. It is to be noted that the overall decrease in pH is smaller the higher the initial protein concentration, very likely because of the self-buffering action of the protein. The level portion of the titration curve from the second break point on would seem to indicate that no further liberation of hydrogen ions occurs after this point; that is, that all groups on the protein capable of reacting have reacted. Since it has been shown that the system is reversible, it seems reasonable to assume that some type of redistribution of EA molecules among the available PVP molecules takes place on further addition of PVP beyond the second break point, while the number of reacted groups remains essentially constant. The constancy of r at the second break point, independent of the component concentrations, indicates that the equilibrium constants for interaction are very high and that the interaction proceeds essentially to completion in the absence of added electrolytes. At the second break point, where $r = 11.3$, even if it is assumed that every quaternary nitrogen on the PVP is involved in binding to EA, then only about one-third of the total of 52 carboxyl groups per EA molecule are involved. This represents the very maximum fraction of the EA carboxyl groups which are bound. Further, it can be calculated that, at this point, about 130 EA molecules are bound to one PVP molecule. Because

not enough supporting evidence is available, an interpretation of the first break in the titration curve for EA or of the first two breaks in that for SA would not be in order, but it might be said that these break points indicate significant alterations in the behavior of the solution or of its components.

Recent studies on the interaction of cationic detergents with EA and SA (132) have revealed a difference in the chemical behavior of the two proteins. The titration studies reported here support this view. Light scattering determinations on the interaction of PVP with EA and SA at their respective isoelectric points shows that for SA $\int = 0.715$, as compared with $\int = 0.915$ for EA. Further investigation along these lines may indicate whether there is any relationship between $\int$ and the higher content of carboxyl groups per unit weight of EA.

As the back titrations with NaCl and with NaF indicate, competitive binding effects, depending not only upon the ionic strength of the solution, but also upon the nature of the simple electrolyte present, are to be considered when interaction studies are carried out in salt solutions (119). For this reason sodium acetate-acetic acid buffers were used to adjust the ionic strength and pH of the solutions throughout the light scattering work.

(132) J. F. Foster and J. T. Yang, J. Am. Chem. Soc. 76, 1015 (1954).

It is to be noted that the titrations of protein with PVP were carried out in the absence of added salt.

Light scattering investigation shows that the interaction between the two polyelectrolytes PVP and EA is typical of an electrostatic type of interaction as found in simpler systems, and indicates that the interaction is, in large measure, between the cationic loci on the PVP and the carboxyl groups on the protein. As seen in Figure 11, interaction increases with decreasing ionic strength, which is to be expected when interaction takes place between oppositely charged groups. With increasing pH, the competition of hydrogen ions for the carboxylate groups decreases, and, thus, the amount of interaction of EA with PVP increases. The fact that δ varies linearly with r , for $r < 11.3$, is a consequence of the redistribution of EA molecules among the available PVP molecules as r decreases; this redistribution was proposed previously for the level portion of the pH titration curves. It is to be expected that at high PVP concentrations the assumption fails that no PVP molecule is bare (and this is the basis for the calculation of δ according to equation [53]). This explains why the value of δ at $r = 0.429$ falls below the δ versus r curve.

The interaction constant B for the system as a whole (Figure 12) is high at low ionic strengths where intermolecular repulsion, of which B is a measure, is high. At high ionic strengths, where shielding of polyelectrolyte

charges is considerable, B decreases. The variation of B with pH for the system resembles the variation of B with pH for protein solutions, showing a minimum in the neighborhood of the isoelectric point of the protein. This behavior, as a function of pH, is expected for an electrostatic type of interaction between an ampholyte and a charged polymer which by itself is not affected by pH changes. The variation of B with mixing ratio r was recently analyzed by Scatchard, et al. (119), in his osmotic pressure studies of mixtures of serum albumin and globulin in aqueous NaCl solutions, and his calculations show that B is a quadratic function of the mole fraction of either of the components,

$$B_{\text{system}} = B_2 x_2 + B_4 x_4 + (2\beta_{24} - \beta_{22} - \beta_{44}) x_2 x_4 \quad [70]$$

where x_i is the mole fraction of component i , and β_{ij} has the definition given on p. 36. The trend of the results obtained here indicates that B is a quadratic function of weight fraction, in agreement with the prediction of equation [70].

Examination of Figure 13 shows how R_{G6}^2 varies with the molecular weight of the complex when μ , pH, and r , respectively, are varied. It is evident that several tendencies operate within the system. As the molecular weight of the complex increases, the size, and hence R_{G6}^2 , is expected to increase. This increase is magnified when,

in addition to the growth of the complex due to increased binding, there is an extension of the flexible molecule as ionic strength decreases and repulsions between unshielded charges become increasingly important. When pH is increased at constant ionic strength, the size of the complex, as reflected in the value of $R_{G_6}^2$, increases because complexing increases due to the increased number of negative groups of the EA. The rate of increase of $R_{G_6}^2$ with molecular weight, however, is less than under variable ionic strength conditions, since the repulsion forces between PVP chain segments dependent upon the concentration of simple electrolytes are kept constant. On the other hand, neutralization of charges on the PVP molecule with complexing, caused by an increase in the number of bonds between the interacting species, might be sufficient to decrease the repulsion along the PVP backbone, so that the complex would tend to contract. It is to be noted that the amount of binding as measured by M_6 does not indicate the number of bonds formed, and a large number of bonds could explain a tendency to decrease in size even while the molecular weight of the complex increases. If an analogy can be made with simpler systems, it is probable that, as the concentration of one of the components is increased, bonds of lower energy are more likely to form. Such a tendency seems to show up in the plot of $R_{G_6}^2$ versus M_6 at variable r , but the evidence is insufficient at this

time to support this hypothesis.

Ehrlich and Doty (57) have shown that, for polymer fractions of increasing molecular weight for coils R_G increases linearly with molecular weight. Although many additional factors operate in the case of complex formation, it is interesting to note that, in the region studied, $R_{G_6}^2$ is a linear function of the molecular weight of the complex. The particle scattering factor curve for the complex seems to indicate that it is probably a polydisperse coil, and further investigation might show why the $R_{G_6}^2$ versus M_6 relationship is still linear despite attendant charge factors which cause extension or contraction of the molecule.

Work by Foster and his coworkers (11) has indicated that in EA-cationic detergent systems time-dependent unfolding and aggregation of the complex go hand in hand. Light scattering examination of samples of PVP-EA mixtures for a period up to four days at 2° C., and 72 hours at room temperature, showed no change of reduced intensity at various angles. In the light of Foster's work, this could possibly mean that the reacted protein may not have been unfolded. Since similar denaturation studies by Nord and his coworkers (130) have shown that solubilization and other factors may, also, be operating in EA-cationic detergent systems, no conclusion can be drawn at this time as to the physical state of the reacted protein.

The molecular weight of egg albumin after filtration through the Millipore disks was found to be 44,800, in agreement with the accepted value, even though the original stock solution showed visible aggregates on standing for one week at 2° C. Since the concentration change upon filtration was small, this points out that the bulk of the solution is not aggregated, and that the size of the few aggregates must be very large.

Pure PVP in 0.2 N NaCl had a molecular weight of 641,000, and the correlation with viscosity, sedimentation, and diffusion measurements and with light scattering measurements on the parent polymer (see p. 96 and p. 97) supports this value. It was found that, at low ionic strengths, the molecular weight of PVP is about 530,000, the difference between this value and that at high ionic strength being outside experimental error. The same tendency was observed by Fuoss and Edelson (133) in their light scattering studies of PVP. Because the measurements were carried out at very low PVP concentrations, it is believed that ordering effects are not responsible for the lower molecular weight found at low ionic strengths. Pending further investigation along these lines, it is proposed that the decrease in molecular weight may be explained,

(133) R. M. Fuoss and D. Edelson, J. Polymer Sci. 6, 767 (1951).

at least in part, by dissociation of bromide ions at low ionic strengths. Viscosity measurements and consideration of the particle scattering factor indicate that PVP is a polydisperse coil with a value of z between 1 and 2.

VI. SUMMARY

The investigation reported here shows that soluble complexes are formed between a synthetic polyelectrolyte and a protein with net charge of the same sign, and that the interaction can be studied by the angular light scattering method. The salt-like complexes formed, in many respects, resemble those of simpler systems, but the equilibria involved when two macromolecules interact have not as yet yielded to mathematical analysis. In fact, not until very recently has extensive work on the nature of polyelectrolytes themselves and on the light scattering behavior of interacting systems been undertaken. It is hoped that this study may, in some measure, point out some of the factors which must be considered in developing a satisfactory theoretical basis for the treatment of the interactions between polyelectrolytes.

APPENDIX

Reduced Scattered Intensities for PVP, EA,
and PVP - EA Mixtures Measured under the
Experimental Conditions Indicated

TABLE XI
PVP in 0.2 N NaCl

θ	Solvent		$c=0.579 \times 10^{-3}$		$c=1.33 \times 10^{-3}$		$c=2.42 \times 10^{-3}$		$c=5.18 \times 10^{-3}$	
	G_θ	$R_\theta \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^6$	G_θ	$\frac{K_c}{R_\theta} \times 10^6$	G_θ	$\frac{K_c}{R_\theta} \times 10^6$	G_θ	$\frac{K_c}{R_\theta} \times 10^6$
0	65.7 (1234)*		64.0 (1234)		63.0 (1234)		59.0 (1234)		56.3 (1234)	
30	65.0 (1)	2.62	48.0 (41)	2.00	85.0 (41)	2.49	54.6 (42)	3.19	60.0 (42)	5.72
35	67.2	2.71	83.0 (4)	2.00	70.0	2.52	94.8 (41)	3.17	49.8	5.76
40	65.9 (0)	1.25	68.2	2.08	101.0 (32)	2.58	78.8	3.20	88.0 (41)	5.83
45	41.9	.795	99.2 (31)	2.15	85.2	2.62	66.8	3.25	75.0	5.92
50	34.9	.662	84.8	2.18	73.8	2.61	100.4 (32)	3.28	65.0	5.94
60	26.2	.497	63.8	2.26	55.7	2.71	70.8	3.35	90.0 (32)	5.82
70	20.7	.393	50.3	2.35	92.7 (31)	2.86	62.0	3.40	72.2	5.95
80	18.1	.344	88.8 (3)	2.48	78.3	2.97	53.0	3.48	62.1	6.06
90	22.4	.425	81.2	2.61	72.7	3.07	49.1	3.60	58.3	6.18
100	22.9	.435	81.8	2.72	73.2	3.19	50.0	3.71	58.8	6.41
110	26.5	.503	89.7	2.82	79.8	3.33	54.8	3.86	65.0	6.62
120	32.5	.617	49.8 (31)	2.93	94.1	3.46	64.3	4.01	77.0	6.83
130	39.0	.740	60.8	3.07	55.0 (32)	3.55	79.8	4.14	95.3	7.07
135	46.1	.875	69.0	3.12	62.8	3.57	90.4	4.21	60.0 (41)	7.38

*The number of the filter used is indicated in parentheses. Where the filter is not indicated, the one given previously applies.

TABLE XII

PVP at $\mu = .03$, pH = 4.2

Buffer			$c=.889 \times 10^{-4}$		$c=3.09 \times 10^{-4}$		$c=5.43 \times 10^{-4}$		$c=7.29 \times 10^{-4}$	
θ	G_θ	R_θ	G_θ	$\frac{Kc}{R_\theta} \times 10^6$	G_θ	$\frac{Kc}{R_\theta} \times 10^6$	G_θ	$\frac{Kc}{R_\theta} \times 10^6$	G_θ	$\frac{Kc}{R_\theta} \times 10^6$
0	95.6 (1234)		93.5 (1234)		75.3 (1234)		75.0 (1234)		73.8 (1234)	
30	79.3 (1)	2.31	85.8 (3)	2.27	73.8 (31)	3.07	58.0 (4)	3.77	67.0 (4)	4.28
35	46.8	1.36	67.3	2.41	59.5	3.16	82.0 (31)	3.90	54.3	4.36
40	93.2	1.28	54.4	2.49	103.0 (3)	3.26	68.0	3.97	81.0 (31)	4.36
45	60.0	.824	86.0 (2)	2.67	84.0	3.32	57.2	3.96	67.2	4.44
50	42.5	.563	71.0	2.79	70.8	3.42	102.0 (3)	4.08	57.0	4.52
60	32.8	.450	52.2	2.98	52.3	3.61	75.0	4.33	89.0 (3)	4.78
70	27.0	.371	65.1 (1)	3.23	41.0	3.79	59.2	4.51	70.0	5.02
80	23.0	.316	70.0	3.50	72.2 (2)	4.00	50.0	4.68	59.0	5.22
90	24.2	.332	65.5	3.77	65.7	4.28	45.8	4.95	55.0	5.40
100	27.6	.379	65.3	3.97	65.0	4.54	45.0	5.28	55.0	5.66
110	31.7	.435	71.0	4.19	70.8	4.77	49.2	5.51	60.0	5.90
120	39.8	.546	86.2	4.31	82.0	5.06	57.8	5.75	70.0	6.18
130	50.7	.696	50.0 (2)	4.47	100.0	5.35	71.0	6.05	86.5	6.46
135	69.4	.953	59.2	4.51	54.0 (3)	5.49	80.0	6.25	98.0	6.59

TABLE XIII

PVP at $\mu = .004$, pH = 4.60

Solvent*	$C=2.38 \times 10^{-4}$			$C=4.76 \times 10^{-4}$			$C=9.52 \times 10^{-4}$			$C=19.0 \times 10^{-4}$		
θ	$R_\theta \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^5$	G_θ	$\frac{K_c}{R_\theta} \times 10^5$	
0		78.0 (1234)		82.0 (1234)		49.1 (1234)		51.0 (1234)				
30	1.96	75.0 (3)	.560	90.0	.967	53.8 (3)	1.76	60.5	3.53			
35	1.31	38.8	.582	71.8	.981	47.4	1.76	48.7	3.55			
40	1.27	49.6	.600	61.0	1.00	35.6 (2)	1.77	88.1 (2)	3.57			
45	.738	64.1	.616	50.0	1.01	71.4	1.77	73.1	3.56			
50	.568	70.2	.631	90.1	1.01	61.1	1.77	63.1	3.53			
60	.426	52.3	.660	69.0	1.02	47.5	1.77	49.0	3.53			
70	.356	37.0 (1)	.704	55.5	1.05	32.5 (1)	1.78	85.6 (1)	3.57			
80	.312	52.8	.740	47.2	1.09	71.9	1.80	74.5	3.60			
90	.341	66.9	.787	44.6	1.11	68.8	1.80	72.0	3.59			
100	.360	67.2	.836	45.8	1.14	71.5	1.85	74.5	3.66			
110	.440	73.8	.878	51.0	1.18	79.1	1.91	83.7	3.72			
120	.553	87.8	.913	60.2	1.23	95.7	1.93	47.6 (2)	3.75			
130	.705	51.2(2)	.940	75.5	1.25	56.1	1.97	59.3	3.88			
135	.319	58.8	.946	86.1	1.28	64.0	2.00	68.3	3.87			

*These are averages of several determinations, and the same R_θ values were used for all subsequent buffers.

TABLE XIV

EA at $\mu = .001$, pH = 4.62

θ	$c=8.60 \times 10^{-4}$		$c=20.3 \times 10^{-4}$		$c=28.96 \times 10^{-4}$	
	G_θ	$\frac{K_c}{R_{90}} \times 10^5$	G_θ	$\frac{K_c}{R_{90}} \times 10^5$	G_θ	$\frac{K_c}{R_{90}} \times 10^5$
0	74.4 (1234)		75.0 (1234)		79.0 (1234)	
90	69.6 (1)	2.16	65.1 (2)	2.31	48.3 (3)	2.23
45	78.0 (2)		67.3 (3)		50.0 (31)	
135	78.2 (2)		67.2 (3)		49.7 (31)	

TABLE XV

PVP-EA

 $r = 1, \mu = .001, \text{pH} = 4.60$

θ	$C_T = .8 \times 10^{-4}$		$C_T = 2.0 \times 10^{-4}$		$C_T = 3.0 \times 10^{-4}$		$C_T = 3.6 \times 10^{-4}$		$C_T = 4.8 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	95.0 (1234)		95.5 (1234)		72.5 (1234)		95.0 (1234)		92.0 (1234)	
30	92.5 (3)	2.87	77.3 (31)	3.69	65.0 (31)	4.94	85.3	5.93	91.7 (31)	7.03
35	71.0	3.02	60.9	3.81	52.0	5.04	67.9	6.08	74.4	7.07
40	59.2	3.13	50.0	3.98	44.0	5.04	57.4	6.09	63.9	7.00
45	97.5 (2)	3.29	85.7 (3)	4.13	77.1 (3)	5.16	47.9	6.14	53.3	7.07
50	79.0	3.45	71.0	4.26	65.4	5.22	86.5	6.16	95.0 (3)	7.22
60	56.4	3.79	52.0	4.55	48.9	5.43	66.0	6.32	72.1	7.41
70	90.6 (1)	4.17	84.3 (2)	4.87	83.3 (2)	5.51	52.6	6.49	58.4	7.50
80	74.9	4.42	70.0	5.18	70.7	5.71	45.0	6.69	50.0	7.68
90	68.8	4.75	64.2	5.48	65.5	5.96	41.6	6.98	47.8	7.74
100	69.0	5.06	64.2	5.76	60.3	6.19	42.8	7.10	49.0	7.93
110	74.8	5.44	71.0	5.97	72.7	6.47	47.8	7.27	54.4	8.08
120	90.4	5.56			86.5	6.65	57.9	7.35	65.6	8.23
130	51.9	5.84			49.6 (3)	7.04	72.0	7.58	82.9	8.36
135					57.9	6.98	82.7	7.59	94.1	8.53

TABLE XV (Continued)

PVP - EA

 $r = 1, \mu = .001, \text{pH} = 4.60$ $c_T = 9.6 \times 10^{-4}$ $c_T = 14.4 \times 10^{-4}$ $c_T = 19.2 \times 10^{-4}$

θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	95.0 (1234)		95.0 (1234)		95.0 (1234)	
30	88.8(1)	15.0	89.1(31)	22.6	93.9	28.4
35	72.4	15.1	72.2	22.7	76.0	28.7
40	62.0	15.0	62.1	22.4	64.0	28.8
45	52.2	15.0	52.4	22.3	53.1	29.3
50	45.4	14.8	94.5	22.4	96.1	29.4
	(3)		(3)			
60	74.8	14.8	73.9	22.4	74.5	29.6
70	61.4	14.7	60.9	22.3	61.0	29.6
80	54.5	14.5	54.1	21.9	54.0	29.3
90	52.7	14.5	52.0	22.0	52.1	29.3
100	55.1	14.5	54.7	21.9	54.4	29.4
110	63.2	14.4	62.8	21.7	62.7	29.0
120	77.7	14.3	76.0	22.0	77.1	29.0
130	99.3	14.3	98.0	21.9	98.5	28.9
135	54.9	14.7	53.5	21.3		
	(31)		(31)			

TABLE XVI

PVP - EA

 $r = 1, \mu = .0025, \text{pH} = 4.60$

θ	$c_T = 0.4 \times 10^{-4}$		$c_T = 1.8 \times 10^{-4}$		$c_T = 3.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	50.0 (1234)		47.9 (1234)		51.15 (1234)	
30	75.8 (2)	2.09	88.5 (3)	3.04	59.7 (31)	3.67
35	57.0	2.20	69.8	3.13	47.8	3.76
40	46.5	2.38	57.6	3.24	83.7 (3)	3.88
45	77.1 (1)	2.58	47.0	3.34	69.2	3.96
50	58.9	2.76	79.8 (2)	3.59	58.0	4.09
60	87.4 (0)	3.13	58.1	3.85	90.5 (2)	4.28
70	60.0	3.48	44.1	4.18	69.9	4.59
80	53.0	3.92	78.4 (1)	4.44	58.0	4.87
90	49.1	4.26	70.6	4.79	52.9	5.15
100	48.8	4.65	69.9	5.11	52.5	5.46
110	53.4	4.98	75.7	5.41	57.5	5.71
120	63.9	5.15	88.8	5.68	67.5	5.95
130	78.8	5.45	51.0(2)	5.94	83.1	6.22
135	90.1	5.48	58.3	6.00	94.0	6.33

TABLE XVI (Continued)

PVP - EA

 $r = 1$, $\mu = .0025$, $\text{pH} = 4.60$

θ	$c_T = 4 \times 10^{-4}$		$c_T = 6 \times 10^{-4}$		$c_T = 8 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	72.1 (1234)		49.8 (1234)		54.9 (1234)	
30	96.5 (3)	4.22	74.0 (31)	5.61	85.9 (31)	7.14
35	78.0	4.29	61.2	5.66	70.1	7.21
40	64.7	4.40	51.6	5.66	59.0	7.27
45	54.3	4.44	92.0 (3)	5.66	49.4	7.41
50	45.6	4.58	78.5	5.83	90.9 (3)	7.34
60	73.3 (2)	4.66	59.5	6.02	69.0	7.55
70	57.1	4.99	47.4	6.17	55.8	7.69
80	47.4	5.22	84.0(2)	6.42	48.9	7.84
90	43.1	5.49	78.0	6.67	44.2	8.12
100	43.6	5.75	79.4	6.88	45.3	8.38
110	47.6	6.02	87.4	7.09	50.5	8.52
120	55.8	6.29	49.0(3)	7.40	60.0	8.75
130	69.2	6.49	61.0	7.57	75.6	8.94
135	79.0	6.57	69.8	7.63	86.5	9.01

TABLE XVII

PVP - EA

 $r = .1, \mu = .004, pH = 4.60$ $c_T = .800 \times 10^{-4}$ $c_T = 2.0 \times 10^{-4}$ $c_T = 3.0 \times 10^{-4}$

θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	49.5 (1234)		49.2 (1234)		49.0 (1234)	
30	48.3 (3)	2.77	93.0 (3)	3.25	59.4 (3)	3.50
35	78.1 (2)	2.92	73.5	3.36	46.8	3.65
40	64.0	3.11	61.3	3.48	32.5 (3)	3.76
45	50.9	3.23	49.5	3.61	67.3	3.89
50	88.0 (1)	3.40	87.0 (2)	3.73	56.7	4.00
60	63.6	3.70	63.0	4.04	85.5 (2)	4.37
70	48.8	4.00	48.1	4.37	66.7	4.62
80	83.5 (0)	4.42	84.1 (1)	4.71	54.8	4.94
90	77.2	4.68	75.8	5.08	49.3	5.30

TABLE XVIII

PVP - EA

 $r = 1, \mu = .005, \text{pH} = 4.60$

	$c_T = 4 \times 10^{-4}$		$c_T = 6.4 \times 10^{-4}$		$c_T = 9.6 \times 10^{-4}$		$c_T = 12.8 \times 10^{-4}$	
θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	60.0 (1234)		63.0 (1234)		56.5 (1234)	7	54.0 (1234)	
30	66.2 (31)	51.5	95.0	5.93	96.0 (31)	7.87	98.0 (31)	9.77
35	52.4	5.35	75.8	6.10	79.0	7.37	79.8	9.92
40	93.7 (3)	5.45	63.5	6.21	66.8	8.93	67.2	10.0
45	77.2	5.59	52.5	6.40	56.5	7.93	57.0	10.0
50	65.6	5.65	93.6 (3)	6.56	47.6	8.14	48.2	10.2
60	48.6	5.96	70.0	6.85	75.9 (3)	8.30	78.5 (3)	10.3
70	81.0 (2)	6.20	55.5	7.13	60.5	8.73	63.0	10.7
80	68.1	6.48	47.1	7.34	52.3	8.81	54.5	10.8
90	62.9	7.76	43.4	7.66	49.0	8.97	51.1	11.0
100	63.0	7.12	44.0	7.94	49.7	9.40	52.0	11.3
110	69.0	7.43	48.1	8.30	55.9	9.63	58.5	11.5
120	81.9	7.68	50.9	8.63	65.8	9.91	69.8	11.9
130	47.9	7.94	71.1	8.84	82.5	10.1	87.6	12.1
135	55.3	7.97	8.11	8.88	94.7	10.1	100.7	12.1

TABLE XIX

PVP - EA

 $r = 1, \mu = .01, \text{pH} = 4.60$ $c_T = 6.4 \times 10^{-4} \quad c_T = 12.8 \times 10^{-4} \quad c_T = 17.6 \times 10^{-4}$

θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	61.5 (1234)		56.5 (1234)		51.5 (1234)	
30	64.5 (31)	8.79	88.7 (31)	11.4	95.9 (31)	13.1
35	51.2	9.07	72.4	11.5	78.0	13.2
40	91.1 (3)	9.22	61.0	11.6	64.4	13.6
45	75.6	9.36	51.1	11.7	54.5	13.8
50	63.8	9.55	43.5	12.0	46.6	13.9
60	47.9	9.94	69.6 (3)	12.3	73.7 (3)	14.4
70	79.4 (2)	10.4	55.2	12.8	59.8	14.7
80	67.2	10.8	47.1	13.1	51.0	15.0
90	62.5	11.2	44.0	13.5	47.9	15.4
100	63.7	11.6	45.1	13.7	48.4	16.0
110	70.0	12.1	49.9	14.1	54.4	16.3
120	83.6	12.3	59.0	14.8	64.8	16.8
130	49.8	12.6	74.5	14.9	81.8	17.1
135	57.0	12.6	85.3	15.0	93.5	17.0

TABLE XX

PVP - EA

 $r = 1, \mu = .03, \text{pH} = 4.20$

θ	$c_T = 1.427 \times 10^{-4}$		$c_T = 5.95 \times 10^{-4}$		$c_T = 10.24 \times 10^{-4}$		$c_T = 15.36 \times 10^{-4}$		$c_T = 20.48 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	93.0 (1234)		94.0 (1234)		93.4 (1234)		93.5 (1234)		92.0 (1234)	
30	69.2 (3)	6.89	95.0 (31)	3.48	78.6 (4)	9.60	99.3 (4)	12.0	50.2 (41)	13.8
35	53.9	7.21	75.0	6.76	63.1	9.94	77.6	12.0	80.6 (4)	14.0
40	44.5	7.40	63.4	8.83	93.0 (31)	10.0	65.8	12.0	73.6	14.0
45	76.2 (2)	7.59	51.5	9.21	76.1	10.5	55.0	12.2	61.1	14.3
50	61.7	7.88	91.5 (3)	9.49	64.0	10.7	81.4 (31)	12.6	52.0	14.6
60	45.6	8.35	68.0	9.97	48.0	11.1	61.0	13.1	69.9 (31)	14.9
70	75.1 (1)	9.03	53.0	10.5	81.0 (3)	11.5	48.8	13.5	55.4	15.5
80	62.1	9.58	93.5 (2)	11.0	67.2	12.2	41.2	14.0	47.2	15.9
90	58.9	10.1	85.6	11.7	62.2	12.7	38.1	14.5	43.9	16.5
100	59.1	10.7	86.2	12.2	62.1	13.3	39.1	14.9	45.0	16.5
110	64.6	11.3	95.0	12.7	69.0	13.7	42.4	15.5	49.6	17.4
120	76.2	11.9	52.4(3)	13.3	81.0	14.2	51.0	15.9	59.0	17.8
130	44.6(2)	12.2	65.0	13.8	100.3	14.8	63.6	16.4	73.6	18.5
135	50.5	12.2	73.9	13.9	54.0 (31)	14.8	72.1	16.5	83.7	18.6

TABLE XXI

PVP. - EA

 $r = 1, \mu = .004, \text{pH} = 4.20$

θ	$c_T = 2.0 \times 10^{-4}$		$c_T = 3 \times 10^{-4}$		$c_T = 5.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	55.5 (1234)		49.1 (1234)		52.0 (1234)	
30	83.2 (2)	10.1	92.8 (2)	11.7	58.6 (3)	15.0
35	65.2	10.5	72.8	12.0	46.8	15.0
40	55.5	10.9	62.0	12.2	34.2 (2)	15.2
45	42.9	11.4	49.3	12.6	67.7	15.7
50	73.2 (1)	12.2	84.6 (1)	13.5	50.5	16.0
60	54.5	12.8	62.5	14.2	90.4 (1)	16.8
70	91.3 (0)	13.5	49.3	14.8	71.3	17.5
80	74.1	14.6	86.3 (0)	16.0	60.4	18.2
90	70.2	15.5	81.4	16.7	56.4	18.9
100	70.0	16.8	82.0	17.6	56.5	20.2
110	77.0	17.5	89.5	18.6	62.0	21.1
120	90.0	18.7	49.5 (1)	19.6	73.0	22.0
130	53.1 (1)	19.4	61.6	20.1	91.2	22.7
135	60.1	20.0	69.9	20.8	49.9 (2)	22.3

TABLE XXII

PVP - EA

$$r = 1, \mu = .004, \text{pH} = 4.38$$

θ	$c_T = 2 \times 10^{-4}$		$c_T = 3.0 \times 10^{-4}$		$c_T = 5.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	55.0 (1234)		48.9 (1234)		56.6 (1234)	
30	96.0 (2)	8.54	50.0 (3)	9.96	72.6	12.8
35	73.5	9.05	81.8 (2)	10.4	58.0	13.0
40	62.2	9.30	68.2	10.8	48.6	13.3
45	50.0	9.43	55.9	10.9	85.3	13.3
50	37.0	9.90	46.7	11.1	71.9	13.6
60	63.3	10.6	73.0	11.9	53.8	14.1
70	49.5	11.3	57.0	12.6	69.2	15.0
80	87.9 (0)	11.9	47.4	13.4	75.6	15.6
90	81.5	12.7	93.0 (0)	14.2	70.0	16.3
100	81.9	13.5	93.3	15.0	71.0	17.1
110	90.2	14.1	48.3 (1)	15.8	79.0	17.6
120	50.7 (1)	14.7	57.0	16.4	94.0	18.1
130	62.5	15.4	71.0	17.0	55.1	18.6
135	73.6	15.2	81.0	17.3	63.0	18.6

TABLE XXIII

PVP - EA

 $r = 1, \mu = .004, \text{pH} = 4.50$

θ	$c_T = 2.0 \times 10^{-4}$		$c_T = 3.0 \times 10^{-4}$		$c_T = 4.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	63.5 (1234)		58.7 (1234)		54.1 (1234)	
30	64.6 (3)	6.64	74.5 (3)	7.67	82.4 (3)	8.37
35	50.9	6.33	58.6	8.92	64.9	8.70
40	89.1 (2)	7.17	48.9	8.24	53.8	9.03
45	72.7	7.25	83.3 (2)	8.50	43.9	9.23
50	60.0	7.49	69.6 (2)	8.70	78.9 (2)	9.30
60	95.1 (1)	7.91	51.4	9.20	58.7	9.78
70	74.0 (1)	8.37	35.5 (1)	9.77	46.0	10.3
80	60.9	8.97	71.4	10.3	82.0 (1)	11.0
90	56.5	9.52	66.0	10.8	76.0	11.4
100	56.6	10.1	65.8	11.5	76.3	12.0
110	62.0	10.6	72.4	12.0	84.5	12.4
120	72.1	11.3	85.9	12.5	47.0 (2)	13.0
130	90.2	11.6	49.0 (2)	12.9	57.2	13.5
135	47.6(2)	12.0	56.8	13.2	65.0	13.7

TABLE XXIV

PVP - EA

 $r = 1$, $\mu = .004$, $\text{pH} = 4.88$

θ	$c_T = 1.0 \times 10^{-4}$		$c_T = 2.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ
0	54.8 (1234)		56.7 (1234)	
30	71.0 (3)	2.54	55.2 (31)	3.00
35	55.5	2.62	91.6 (3)	3.15
40	48.8	2.75	76.0	3.26
45	78.7 (2)	2.79	62.4	3.33
50	65.1	2.91	52.0	3.45
60	46.9	3.15	82.7 (2)	3.57
70	75.0 (1)	3.49	63.9	3.81
80	61.9	3.76	5.30	4.06
90	56.2	4.03	47.5	4.36
100	56.7	4.25	47.0	4.66
110	61.4	4.50	51.2	4.90
120	7.20	4.76	59.4	5.18
130	87.0	5.02	73.8	5.37
135	100.0	5.12	84.0	5.45

TABLE XXV

FVP - EA

 $r = 1, \mu = .004, \text{pH} = 5.23$

θ	$c_T = 0.5 \times 10^{-4}$		$c_T = 1.0 \times 10^{-4}$		$c_T = 2.0 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	51.0 (1234)		53.0 (1234)	51.6	51.6 (1234)	
30	59.0 (3)	1.42	91.2 (3)	1.83	54.0	2.76
35	46.5	1.48	71.8	1.90	89.7	2.89
40	81.3 (2)	1.53	59.6	1.97	74.1	3.00
45	64.5	1.62	49.1	2.01	61.2	3.05
50	53.0	1.68	35.1 (2)	2.09	51.5	3.13
60	83.0 (1)	1.80	63.0	2.22	79.8	3.36
70	62.7	1.98	47.5	2.43	61.2	3.60
80	50.0	2.11	32.6 (1)	2.64	50.8	3.82
90	46.0	2.34	75.0	2.82	46.0	4.08
100	46.0	2.49	74.3	3.02	45.5	4.56
110	49.8	2.66	81.2	3.16	49.6	4.58
120	60.1	2.72	94.8	3.33	57.5	4.85
130	73.1	2.87	55.0 (2)	3.46	71.4	5.03
135	88.0	2.75	63.0	3.48	81.0	5.12

TABLE XXVI

PVP - EA

 $r = 4.33$, $w_{PVP} = .1875$, $\mu = .004$, $pH = 4.60$

	$c_T = 1.6 \times 10^{-4}$		$c_T = 3.2 \times 10^{-4}$		$c_T = 6.4 \times 10^{-4}$		$c_T = 11.2 \times 10^{-4}$	
θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	62.0 (1234)		48.1 (1234)		51.1 (1234)		42.0 (1234)	
30	89.9 (31)	1.57	61.3 (32)	1.62	64.9 (41)	1.84	73.8 (41)	2.31
35	71.0	1.64	69.0	1.68	52.7	1.88	60.0	2.34
40	59.0	1.68	86.0 (31)	1.75	91.9 (4)	1.95	50.1	2.39
45	48.3	1.74	71.8	1.79	76.8	1.99	88.5 (4)	2.46
50	84.3 (3)	1.83	59.3	1.86	65.0	2.03	75.2	2.52
60	61.8	1.94	43.9	1.96	48.0	2.15	97.0 (31)	2.74
70	47.8	2.07	71.3 (3)	2.12	64.6 (31)	2.32	76.0	2.82
80	82.2 (2)	2.24	59.0	2.24	53.8	2.43	64.0	2.93
90	74.0	2.40	52.0	2.44	48.2	2.60	58.3	3.08
100	73.8	2.53	51.7	2.58	48.2	2.74	58.1	3.23
110	30.0	2.67	55.8	2.74	52.4	2.87	63.3	3.39
120	94.0	2.79	65.7	2.83	61.0	3.02	74.3	3.53
130	54.0(3)	2.96	81.0	2.96	75.8	3.11	93.0	3.61
135	72.2	2.94	92.7	2.96	85.3	3.18	60.3(4)	3.64

TABLE XXVII

PVP - EA

 $r = 1.96$, $w_{PVP} = .337$, $\mu = .004$, $pH = 4.60$

$c_T = 1.66 \times 10^{-4}$		$c_T = 3.32 \times 10^{-4}$		$c_T = 4.98 \times 10^{-4}$		$c_T = 6.64 \times 10^{-4}$	
θ	c/R_θ	θ	c/R_θ	θ	c/R_θ	θ	c/R_θ
0	46.0 (1234)	41.9 (1234)		53.0 (1234)		46.0 (1234)	
30	91.0 (3)	66.9 (31)	2.81	51.6 (32)	3.34	52.0 (32)	3.84
35	72.0	54.8	2.96	89.9 (31)	3.39	90.0 (31)	3.91
40	59.6	45.5	3.05	79.8	3.46	74.8	4.00
45	49.3	78.7	3.16	62.0	3.53	62.0	4.10
50	86.0 (2)	65.4 (3)	3.29	52.4	3.64	53.0	4.20
60	62.3	47.9	3.50	81.6 (3)	3.86	81.0 (3)	4.49
70	48.0	79.6 (2)	3.67	63.4	4.08	63.0	4.78
80	83.3 (1)	65.5	3.91	52.8	4.29	54.0	4.85
90	75.3	60.0	4.18	47.8	4.57	49.0	5.11
100	74.2	58.7	4.42	47.9	4.84	49.3	5.40
110	80.3	63.8	4.57	51.7	5.08	57.0	5.58
120	91.2	74.8	4.85	60.7	5.25	63.0	5.88
130	55.0 (2)	92.3	5.04	75.2	5.47	78.0	6.09
135	62.0	48.9 (3)	5.21	85.8	5.52	89.0	6.15

TABLE XXVIII

PVP - EA

 $r = 0.429$, $w_{PVP} = .700$, $\mu = .004$, $pH = 4.60$

θ	$c_P = 1.60 \times 10^{-4}$		$c_T = 3.2 \times 10^{-4}$		$c_T = 4.8 \times 10^{-4}$		$c_T = 6.4 \times 10^{-4}$	
	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	86.3 (1234)		53.75 (1234)		51.25 (1234)		47.5 (1234)	
30	90.3(3)	5.18	82.0(3)	6.69	94.8(3)	8.14	90.2(3)	10.5
35	70.4	5.33	65.0	6.87	65.6	8.30	73.1	10.6
40	58.1	5.67	55.2	6.97	63.5	8.53	62.2	10.7
45	46.7	5.78	45.1	7.16	53.0	8.53	52.3	10.7
50	31.9 (2)	5.95	79.5 (2)	7.32	45.2	8.62	93.9 (2)	10.9
60	59.7	6.45	59.3	7.69	70.7(2)	9.06	71.6	11.0
70	44.9	7.08	4.67	8.04	56.0	9.43	56.6	11.3
80	80.3 (1)	7.44	81.5 (1)	8.70	47.2	9.80	48.6	11.7
90	74.2	7.92	75.2	9.12	43.8	10.2	45.8	12.0
100	74.2	8.47	75.5	9.64	44.3	10.7	46.0	12.6
110	80.9	8.94	82.9	10.1	48.6	11.1	51.0	13.0
120	94.9	9.41	46.3 (1)	10.4	57.5	11.5	61.2	13.3
130	56.0 (2)	9.58	58.5	10.5	71.9	11.9	76.8	13.6
135	63.1	9.88	66.1	10.8	81.9	12.0	87.4	13.8

TABLE XXIX

PVP - SA

 $r = 1$, $w_{PVP} = .5$, $\mu = .004$, $pH = 5.08$ $c_T = 1.0 \times 10^{-4}$ $c_T = 2.0 \times 10^{-4}$ $c_T = 4.0 \times 10^{-4}$

θ	G_θ	c/R_θ	G_θ	c/R_θ	G_θ	c/R_θ
0	61.5 (1234)		53.9 (1234)		61.25 (1234)	
30	80.2 (3)	2.51	53.0 (31)	2.97	94.0 (31)	3.70
35	61.8	2.64	89.2 (3)	3.07	75.5	3.77
40	51.3	2.75	74.0	3.18	63.0	3.88
45	87.0 (2)	2.86	61.1	3.24	52.5	3.92
50	72.0	2.95	50.8	3.36	44.6	4.00
60	52.0	3.21	79.2 (2)	3.55	69.8 (3)	4.21
70	85.0 (1)	3.47	61.3	3.77	54.8	4.46
80	69.8	3.73	50.2	4.05	45.4	4.70
90	63.8	3.98	45.9	4.28	41.9	4.90
100	63.0	4.31	45.7	4.55	42.0	5.13
110	69.0	4.52	49.4	4.80	45.8	5.38
120	81.0	4.74	58.0	5.04	53.8	5.65
130	100.0	4.95	72.0	5.21	66.7	5.79
135	53.0 (2)	5.13	81.8	5.31	75.7	5.89

AUTOBIOGRAPHY

I, Israel J. Heilweil, was born on May 23, 1924, in Poland, where I received my primary education. After completion of my secondary schooling in Brooklyn, New York, in 1942, I attended The College of the City of New York, from which I obtained the degree Bachelor of Science in 1948. From 1943 to 1946 I served with the United States Army. I received the degree Master of Science from The Ohio State University in 1951, where as a graduate student in the Department of Chemistry, I held the positions of Graduate Teaching Assistant during the 1948-1950 period and Research Assistant on a project sponsored by the United States Public Health Service, The National Institutes of Health, between 1951 and 1954. It was while holding this latter position that I completed the requirements for the degree Doctor of Philosophy.