This dissertation has been 63-4700
microfilmed exactly as received

SEASTROM, Charles Collmar, 1936-
OBSERVATIONS ON THE DISSOLUTION BEHAVIOR
OF IRON WHISKERS.

The Ohio State University, Ph.D., 1962
Engineering, metallurgy

University Microfilms, Inc., Ann Arbor, Michigan

OBSERVATIONS ON THE DISSOLUTION
BEHAVIOR OF IRON WHISKERS

DISSERTATION

Presented in Partial Fulfillment of the Requirements for
the Degree Doctor of Philosophy in the Graduate
School of The Ohio State University

By

Charles Collmar Seastrom, B. S., M. Sc.

* * * * *

The Ohio State University
1962

Approved by

Adviser

Department of Metallurgical
Engineering

ACKNOWLEDGMENTS

The author wishes to express his appreciation to Professor J. P. Hirth, Mr. R. M. Shemanski, and his adviser, Professor F. H. Beck, for their many helpful suggestions. The support of this work by the Advanced Metallurgical Studies Branch, Wright-Patterson Air Force Base, Ohio, is gratefully acknowledged.

CONTENTS

	Page
ACKNOWLEDGMENTS	11
TABLES	v
ILLUSTRATIONS	vi
INTRODUCTION	1
SUMMARY	3
I. LITERATURE SURVEY	7
Whiskers	7
Dissolution of Crystals	26
Use of Etch Pits to Determine Orientation	44
Electrochemical Properties	51
Etch Pit Shape	65
Etch Pits on Iron	67
II. EQUIPMENT AND PROCEDURE	73
III. RESULTS	85
Appearance of As-grown Whiskers	85
Determination of the Preferred Planes of Dissolution	87
Determination of Growth Direction	91
Immersion Etching of Undeformed Iron Whiskers in 1N H ₂ SO ₄ + 0.2N K ₂ S ₂ O ₈	91
Immersion Etching of Deformed Whiskers	121
Determination of the Dissolution Rate	141

	Page
Immersion Etching of Iron Whiskers in 4% picral (e), 4% picral (m), 2% nital and 1N H ₂ SO ₄ + 0.2N K ₂ S ₂ O ₈	158
IV. SUMMARY OF RESULTS	172
V. DISCUSSION	175
Factors Affecting Etch Pit Formation	175
Etch Pit Shape	182
Correspondence of Etch Pits and Dislocation Sites	184
Determination of the Role of the Image Force and Climb	187
Determination of the Angles of Intersection Between the Possible Slip Planes and the Surface for a Deformed Whisker	195
Slip Systems in Operation During the Bending of Iron Whiskers	200
Dislocation Structure of As-grown Whiskers	202
Growth Axis of Iron Whiskers	204
BIBLIOGRAPHY	209
AUTOBIOGRAPHY	213

TABLE

Table	Page
1. Determination of Possible Slip Planes Associated with As-grown Dislocations	193

ILLUSTRATIONS

Figure	Page
1. Influence of an oxidizing agent on the polarization curves for the corrosion of iron in acids	56
2. Polarization behavior of iron in 1N H ₂ SO ₄ + 0.02 N K ₂ S ₂ O ₈	59
3. Polarization behavior of iron in 1N H ₂ SO ₄ + 0.5N (NH ₄) ₂ S ₂ O ₈	60
4. Schematic representation of etch pits	66
5. Whiskers mounted for etching, and for potential measurements and iron analysis	77
6. Electron micrograph of as-grown whisker surface .	86
7. Etch pits at as-grown and deformation-produced dislocations	88
8. Removal of whisker shell	92
9. Whisker core	94
10. Removal of whisker shell	95
11. Removal of whisker shell	97
12. Removal of whisker shell	99
13. Etch pits at as-grown dislocations in shell . . .	100
14. Removal of whisker shell	101
15. Etch pits at as-grown dislocations in shell . . .	103
16. Removal of whisker shell	104
17. Whisker shell	105
18. Etch pits at as-grown dislocations in core . . .	106
19. Shell rotated with respect to core	108
20. Shell rotated with respect to core	109

Figure	Page
21. Shell rotated with respect to core	110
22. As-grown dislocations penetrate whisker	112
23. Removal of whisker shell	114
24. Removal of whisker shell	115
25. Removal of whisker shell	116
26. Etch pits at as-grown dislocations	117
27. Etch pits at as-grown dislocations	118
28. Removal of whisker shell	119
29. Removal of whisker shell	120
30. Etch pits at as-grown dislocations in shell . . .	123
31. Etch pits at as-grown and deformation- produced dislocations	124
32. Etch pits at as-grown and deformation- produced dislocations	125
33. Removal of whisker shell	127
34. Removal of whisker shell	128
35. Removal of whisker shell	129
36. Etch pits at as-grown and deformation- produced dislocations	130
37. Removal of whisker shell	132
38. Etch pits at as-grown and deformation- produced dislocations in core	133
39. Removal of the shell for a deformed whisker . . .	134
40. Removal of whisker shell	136
41. Etch pits at as-grown dislocations in shell . . .	137
42. Etch pits at as-grown and deformation-produced dislocations in core	138

Figure	Page
43. Etch pits at as-grown and deformation-produced dislocations in core	139
44. Etched cross sections of whiskers	142
45. Etched cross section of whiskers	143
46. Potential time traces in 1N H ₂ SO ₄ + 0.2N K ₂ S ₂ O ₈ .	146
47. Etch pits at as-grown dislocations in shell . . .	148
48. Etch pits at as-grown dislocations in shell . . .	149
49. Etch pits at as-grown dislocations in shell . . .	150
50. Etch pits at as-grown dislocations in shell . . .	151
51. Etch pits on undeformed whisker	153
52. Etch pits on undeformed whisker	154
53. Etch pits on undeformed whisker	155
54. Etch pits on undeformed whisker	156
55. Etch pits on undeformed whisker	157
56. Etch pits on shell of undeformed whisker	159
57. Removal of whisker shell	160
58. Etch pits in shell of undeformed whisker	161
59. Etch pits in core of undeformed whisker	162
60. Etch pits in shell of undeformed whisker	165
61. Etch pits in core of undeformed whisker	166
62. Removal of whisker shell	168
63. Etching of whisker core	169
64. Etching of whisker core	170

Figure

65. a. Regions of a unit triangle within which the indicated resolved shear stresses in a b.c.c. lattice is higher than other resolved shear stresses
b. Intersection of slip plane ($\bar{2}11$) with whisker faces ($0\bar{1}1$) and ($01\bar{1}$) 196
66. Traces of slip systems on whisker faces 201

NOMENCLATURE

- (hkl) - can indicate either a given plane or the planes of a form $\{hkl\}$ depending on context
- [uvw] - can indicate either a given direction or the direction of a form $\langle uvw \rangle$ depending on context
- Electrochemical sign convention - the European sign convention has been followed. Potentials active to the reference electrode have been assigned a negative potential
- μ - micron - 10^{-4} cm
- (- -) - placed around a number to designate a particular whisker
- (e) - following an etch, designates that ethyl alcohol was used as the solvent
- (m) - following an etch, designates that methyl alcohol was used as the solvent
- WW - designates a whisker obtained from C. M. Wayman, see text
- Persulfate - refers to the etch, 1N H_2SO_4 + 0.2N $K_2S_2O_8$
- (:) - indicates that the growth axis of the whisker is approximately parallel to the north-south direction on the paper
- (. .) - indicates that the growth axis of the whisker is approximately parallel to the west-east direction on the paper
- SHE - standard hydrogen electrode
- SCE - standard calomel electrode

INTRODUCTION

Small iron whiskers a few microns in diameter are often found to possess unusually high yield strength approaching the theoretical strength of perfect crystals. A wide variation in strength for whiskers of the same diameter is often found, however. Those whiskers which show high strength are thought to contain either no dislocations or to have the dislocations present in some special arrangement. The arrangement of dislocations within a whisker can be determined by using an etch which develops etch pits at dislocation sites.

Several references report the use of solutions of picric acid in alcohol and nitric acid in alcohol for etching of iron whiskers and bulk iron single crystals. The results are not reproducible. In some instances these etches produce pits only at dislocations along which impurity has segregated, while other references indicate that these etches attack only clean dislocations resulting from deformation. The same etch often showed different results from one sample to another.

The purpose of this investigation was to study the dissolution of iron whiskers and from the results formulate a mechanism of dissolution which could explain the

peculiarities observed in the etching of iron whiskers and also, it was hoped, crystals in general.

An etch had to be chosen which would form etch pits only at dislocation sites, produce minimum background attack, and cause the whisker to be reduced uniformly in cross section but not so rapidly that observations cannot be made. These conditions have been satisfactorily met by using the etch $1N H_2SO_4 + 0.2N K_2S_2O_8$. Several whiskers have also been etched in solutions of picric or nitric acid in alcohol in order to better explain the reason for the variation in results reported for these etches.

SUMMARY

The dissolution behavior of iron whiskers has been studied in the solutions: 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$, 4% solution of picric acid in methyl alcohol (picral), and a 2% solution of nitric acid in ethyl alcohol (nital).

The following statements summarize the important contributions found in this dissertation.

1. Most whiskers are composed of a distinct shell or overgrowth surrounding the core. This shell ranged in thickness from less than one micron up to several microns. The as-grown dislocation density in the shell can be either greater or less than in the core. The as-grown dislocations are thought to be attached to nodes formed by a two-dimensional dislocation network parallel to the surface at the shell-core interface.
2. The shell and core do not always have the same orientation. On the (100) face of three rectangular whiskers, the shell was rotated 45° with respect to the core. The shell had a [100] growth axis, while the core was [110]. This was determined by the orientation of the etch pits on two of the whiskers. On the third whisker slip lines present in the shell after deformation agreed with the probable slip systems for a [100] orientation, but not

for a $[110]$, characteristic of a rectangular whisker. This rotation of the shell and core supports the idea of a dislocation network at the shell-core interface.

3. Symmetric etch pits at as-grown dislocations in the shell indicate that these dislocations intersect normal to the surface. The as-grown dislocations in the core of square and rectangular whiskers are also probably aligned normal to the surface. The arrangement of as-grown dislocations in the core of hexagonal whiskers is probably more complex. The alignment of a dislocation normal to the surface can occur if the "image force" pulls the dislocation perpendicular to the surface while it is still in its slip plane, or if the dislocation climbs off its slip plane. Both of these possibilities can operate at the growing temperature. Clean deformation-produced dislocations, introduced by bending the whiskers, intersect at an angle with the surface and etch as asymmetric etch pits.
4. Three requirements have been established for the formation of large well-shaped etch pits in the iron whiskers.
 - a. Presence of an internal poison. Etch pits present in the shell were usually smaller and better-contained than pits in the whisker core. This abrupt variation in the shape of pits in different layers of the whisker, even though etched in the same solution, has

been attributed to a change in the concentration of an internal poison, possibly chlorine in some form. The poison concentration in the shell is usually higher than in the core. The poison probably builds up along the sides of the whisker during growth and at a critical concentration is incorporated into the growing lattice. In a layer with a high poison concentration, well-defined pits are formed at both clean deformation-produced dislocations and as-grown dislocations. In a layer with a low poison concentration, pits at both types of dislocations were wide and shallow. Dissolution is under poison control and the presence or absence of an internal poison determines whether the ledges will be sufficiently retarded so that a pit is observable.

- b. Dissolution rate. The dissolution rate is another important factor affecting pit formation. Better-defined pits are created when the dissolution rate favors pits bound by planes other than the plane of the reference surface. The etch $1N H_2SO_4 + 0.2N K_2S_2O_8$ produces better-contained pits on (100) faces than the 4% picral or 2% nital, while on (110) faces the picral and nital etches produce better-defined pits. The $1N H_2SO_4 + 0.2N K_2S_2O_8$ etch produced pits on (100) faces bound by (110) side faces and having a (100)

bottom. The picral and nital etches produced rectangular pits on (110) planes bound by two (100) faces.

- c. Length of dislocation line. Besides a favorable poison concentration and dissolution rate, large etch pits can form only if the dislocation line is sufficiently long. A pit cannot become deeper than the thickness of the shell.

I. LITERATURE SURVEY

Whiskers

Whiskers in the form of long filaments of copper and silver were observed many years ago growing from copper and silver ores. Recently whiskers were found to possess unusually high strength compared to bulk crystals. Since this discovery much work has been done on whiskers, investigating not only their strength but also magnetic, corrosion, and electrical properties. Whiskers can provide strain free, preoriented, single crystals with smooth crystallographic surfaces and usually improved internal perfection, and therefore are often preferred to larger single crystals.

Brenner (1)* defines a whisker as any fibrous growth of all shapes, both single crystals and polycrystals, the only restriction being a high length to diameter ratio. This definition of a whisker has been used in this discussion, although it should be pointed out that most whiskers are small, single crystals and do show various cross sectional shapes. The term as defined here is not restricted to the very small filaments which show unusually high elastic limits and yield strengths. An excellent summary of the growth and properties of whiskers is provided by Brenner (2).

*Numbers refer to references listed in the Bibliography.

Growth of whiskers

Whiskers have been produced by the following methods:

Proper whiskers--spontaneous growth from the
base metal

Pure vapor deposition

Vapor deposition and subsequent reduction of
metal halide salts

Precipitation of whiskers from solution

It is thought that the growth mechanisms of all four of the methods above possess common characteristics. The four methods will be mentioned briefly; however, the discussion of the methods involving vapor deposition will be presented in more detail since these methods have been employed in growing iron whiskers.

Proper whiskers.--Proper whiskers grow from the base metal with no transfer through the vapor. The material for the whisker comes from within the substrate on which the whisker grows. The mechanism involves the progression of dislocation loops from inside the substrate out to the surface. Each successive loop increases the step height by one more atomic unit (2). Plated metals in general and tin plate in particular are susceptible to proper whisker growth. Stress applied to electroplated tin causes the growth rate of the whiskers to be increased. It is felt that this stress is relieved by means of whisker growth where the stress is not relieved by means of tin extrusion (3).

Pure vapor deposition.--Whiskers of the lower melting metals such as mercury, zinc, cadmium, and silver have been

grown by vaporizing the pure metal at one temperature and condensing it in the form of whiskers at a lower temperature. The difference in temperature provides the supersaturation required. Recently Morelock (4) was able to grow whiskers less than 1μ of chromium, nickel, iron, copper, and gold. Silicon whiskers have also been reported (5). The growth mechanism for these higher melting metals is thought to be similar to that of the lower melting metals.

Pure vapor deposition has proved valuable in studying the mechanism of whisker growth from the vapor because it is a relatively simple system involving only the metal and its transfer through the vapor state. The supersaturation required to form whiskers by this method is rather small. The supersaturation required to grow mercury whiskers is approximately 200, while the supersaturation necessary to nucleate an atomic layer of mercury on a perfect low index plane of mercury is 4×10^6 (7). It has been found that whiskers tend to grow at low supersaturation while growth of bulk crystals occurs at high supersaturation. This discrepancy has been overcome by introducing the concept of a screw dislocation. As atoms are attached to the ledge, the screw continually spirals to provide a continuous low energy site for deposition.

The manner in which a screw dislocation is initiated is not clear. Mercury whiskers were grown on glass by a screw dislocation mechanism. The glass surface is assumed

to have crystallites of ordered glass presenting screw dislocation ends to the mercury vapor. The single screw dislocation postulated for the mercury whisker is considered to be an extension of a screw dislocation already present in the glass (7). More generally, on any real surface there are irregularities present which can act as a source of the growth. An occasional screw which is somewhat separated from its neighbors will form a growth cone out of the center of which a uniform cross section whisker can grow. The growth steps are widely spaced at the base and closely spaced on the whisker. This is based on the assumption that the diffusion of material is the limiting factor for crystal growth. Individual screw dislocations spaced too closely or exposed to an excessive supersaturation will not form growth cones and whiskers, but will cause the surface to advance uniformly (8). Zinc whiskers grown by the use of a temperature gradient showed that a growth cone did form first out of which the whisker grew (9).

Vapor mechanism--halide salts.--High melting metals generally have too low a vapor pressure at moderate temperature to grow whiskers of appreciable size by vaporization and deposition of the pure metal. The normal procedure is to grow whiskers of the higher melting metals by the reduction with hydrogen of a halide salt of the metal. Although there are many variations, normally a boat filled with the halide is pushed into a tube furnace and heated to temperature.

Hydrogen is passed through the tube to reduce the salt.

Brenner (2) lists iron, copper, silver, nickel, silicon, and germanium whiskers grown by the method of halide reduction.

The temperature at which the reduction is carried out can be below or above the melting point of the halide salt. The salt, however, must have an appreciable vapor pressure at the reduction temperature. Molecules of the salt vaporize and either are reduced in the vapor state in which case the metal atoms condense on the growing whisker, or else the salt itself condenses on the whisker and is reduced there. There is no simple method for calculating the supersaturation required, however, as was the case for the pure metal vaporization and subsequent deposition. Also, the temperature at the site of vaporization of the halide salt and those of the growing whiskers is the same. It is more likely that the halide molecules are adsorbed on the growing whiskers and preferentially reduced at the tip (2). When a halide molecule strikes the whisker, it has a high probability of becoming a part of the growing whisker. There is a continuing driving force which attempts to establish the equilibrium vapor pressure of the halide salt around the whisker. Reduction occurs preferentially at the tip because of the ledge provided by a screw dislocation and/or because the sides are covered with adsorbed impurities which prevent an appreciable amount of side thickening. The adsorbed molecules might be FeCl_2 or HCl in the case of iron whiskers grown from ferrous chloride.

The growth tip will usually consist of different kinds of planes and hence be able to attach new atom layers. The end growth is probably a screw dislocation, but the possibility that each new atom layer starts out with a surface nucleus cannot be ruled out by an estimate of the supersaturations (10). Since it is not definitely established where the reduction actually takes place, it is difficult to make any accurate calculations of the supersaturation of metal atoms on the whisker.

Brenner (1)(11) has studied rather completely the formation of copper whiskers by the reduction of CuI. In the first reference it is shown that if the whiskers grow by the condensation of copper vapor the supersaturation of the copper vapor has to be 10^4 to 10^6 to account for the observed axial growth rate. The hypothesis that whisker growth occurs by the adsorption of CuI and its catalytic reduction at the whisker tip presumes, first, the reduction of the CuI in the vapor phase is negligible, and second, the whisker tip has different properties than the sides. Growth below the melting point of CuI is probably the adsorption of CuI and its reduction. There is a rapid increase in growth rate of the copper whiskers above the melting point of CuI and then at still higher temperatures a decrease. This is also observed for iron, where such an increase is also observed at the melting point. It is postulated that the

surfaces of the whiskers become covered with liquid halide which flows to the tip of the whiskers.

Iron whiskers have been grown by the reduction of the ferrous halide with hydrogen (1)(10)(12)(13)(14)(53). Ferrous chloride, both anhydrous and hydrated, is most commonly used; however, ferrous bromide has also been employed. Temperatures between 500° and 760°C have been reported. The hydrogen gas is sometimes diluted with argon before being passed over the halide salt (13).

The size of the whiskers produced appears to be dependent upon the amount of salt used as well as the size of the boat in which the whiskers are grown. Wayman (14), by increasing the amount of salt and the size of the boat, was able to produce single crystals of alpha iron 1 to 2 mm in diameter and up to 80 mm in length. The same boats which contained the large diameter crystals also contained whiskers less than 25 μ in diameter, but of considerable length (greater than 50 mm.). This would suggest that the whiskers first grow to some extensive length, and then thicken into crystals by two-dimensional nucleation and monolayer addition. It has been suggested that the final length of a whisker should be governed by the time of retention of a dislocation which perpetuates the growth steps at the tip. Wayman (14) points out that it is difficult to see how the presence of a greater amount of ferrous chloride would favor the dislocation remaining in the crystal for longer times.

The purity of whiskers is not exceptionally high. The average impurity content as determined by chemical analysis was about 10^{-4} for iron whiskers grown from FeBr_2 (2).

Precipitation of whiskers from solution.--Brenner (2) discusses briefly the growth of whiskers by precipitation. The salt solution is supersaturated by slowly evaporating the water or by changing the temperature. A screw dislocation type growth mechanism has been proposed for whisker growth here also. The screw dislocations for growth in aqueous solutions can come from the impingement of two crystals (15). Another theory postulates that a salt crystallite growing around a nucleated particle could generate a closed loop growth step on a single face which could then advance as a whisker (16).

Strength and perfection of whiskers

Bulk crystals deform plastically at strains much lower than those predicted for perfect crystals. The explanation for this is usually that real crystals contain dislocations which move under the influence of a relatively small stress. Very small whiskers are found to have elastic strains of over 1 percent, while in comparison bulk annealed single crystals yield at elastic elongation of less than 0.01 percent. Since stress is proportional or nearly proportional to strain within the elastic region, the strains associated with small whiskers often correspond to the theo-

retical strength of the crystal. As the result of the high strength of tin whiskers observed by Herring and Galt (17) tremendous interest has been directed toward the mechanical behavior of whiskers in an attempt to ascertain whether the high strength experienced by small whiskers is the result simply of small size or whether whiskers possess a unique perfection.

The mechanical properties of whiskers produced by the four growth mechanisms discussed in the last section have been studied by both bend tests and in direct tensile tests. Small whiskers generally show unusually high strength regardless of the method of growing them.

The mechanical properties of iron whiskers have been studied by Brenner (2)(18), Weik (13), Sears et al. (19), and Emrick et al. (20). The elastic strain was taken as a measure of the strength in the early work. The whisker was bent around a fine wire of known diameter. The maximum strain in bending is equal to the ratio of whisker radius to bending radius. The largest elastic strain for a [100] iron whisker bent in this way was 1.4 percent (19). Young's modulus for alpha iron normal to the (100) plane is 1.9×10^7 psi. The maximum elastic stress is therefore 270,000 psi. The elastic limit for a pure iron single crystal is only 4,000 psi. When the elastic limit is exceeded in a whisker strained by bending, the whisker kinks. The whisker will frequently unkink and recover its original shape if it is

annealed at a high temperature. If the elastic modulus is not known for the orientation of the whisker tested, or if the stress is not proportional to strain throughout the elastic region, the yield strength cannot be accurately computed from the elastic strain calculated in bending.

Tensile tests which record both the load and the elongation provide more accurate data. Brenner (2)(18) considers the strength of the whiskers as the maximum stress the whisker sustained before fracture occurred, which, in this case, was equivalent to the stress at the elastic limit. The iron whiskers snapped without any observable amount of plastic deformation. Within experimental accuracy, Hooke's law is obeyed up to about 2 percent strain. Beyond that the strain increases more rapidly than stress. A maximum elongation of 4.8 percent was noted on a hexagonal 1.6μ diameter whisker. This was equivalent to an elastic strength of about 1,800,000 psi. The highest shear strengths of the whiskers are either close to or above the lower estimate of the theoretical strength of perfect crystals based on rows of atoms sliding over one another without the help of dislocations. There is a wide scatter of strengths observed for whiskers of the same size but with a trend toward increasing strength with decreasing size particularly below 10μ . Generally whiskers grown by halide reduction appear to show a much larger scatter in strength than whiskers grown under

cleaner conditions, such as deposition of pure metal whiskers from the metal vapor.

It is not known whether perfection or small size is the major contributing factor to explain the high strength of small whiskers. A single screw dislocation type of growth should not introduce dislocations during growth, although defects probably enter by the incorporation of adsorbed impurity atoms. In order to possess high elastic strength the whiskers must either have no dislocations other than the one growth screw dislocation, or they must have dislocations which are so arranged that they cannot multiply. Gorsuch (21) shows that the more perfect iron whiskers have dislocation densities below 10^6 dislocation lines per cm^2 . Thus many whiskers which are less than 10μ in diameter would contain at most only a small number of dislocations and should behave as perfect crystals. It is reasoned that in the very small volume comprising the test section of a small whisker it becomes statistically improbable that pinned dislocations will be found which can multiply and cause yielding. Small whiskers are probably more perfect than bulk crystals, but are not free of dislocations. It has often been found that decreasing the size of a bulk sample until it is of comparable size with small whiskers does increase the strength of the specimen. This suggests that it is primarily small size that causes the increase in strength (5). The strength is

also improve by a somewhat lower dislocation density and the smooth surfaces often found on whiskers.

Morphology

Whiskers have been observed with unusual cross sections and odd shapes. Iron whiskers ideally grow in the three principal growth directions: $[111]$, $[110]$, and $[100]$. The cross sections are ideally hexagonal, rectangular, and square, respectively. Coleman (23) suggests that hexagonal type iron whiskers are bound by (110) lateral faces. Rambauske and Gruenzel (22) report analyzing hexagonal whiskers with lateral faces formed by (211) planes. Different growth processes will produce most likely either a (110) or a (211) lateral face. A $[110]$ whisker is bound by two wide (100) planes and two narrow, poorly defined planes, approximately (110) . Ideally the ratio of the widths of (100) (110) is equal to 1.4. A $[100]$ square whisker is bound by four (100) faces.

The ends of ideal whiskers can be visualized by rotating a cube into a similar orientation. The tip of an $[111]$ whisker is ideally bound by three (100) planes; a $[110]$ whisker by two (100) faces; and a $[100]$ whisker by one (100) face. Iron whiskers of all three growth directions have been reported. Most references, however, report a predominance of $[100]$ whiskers.

Ideally the whiskers are straight and do not taper (23). The growth of straight whiskers with uniform cross

sections can be explained by means of a screw dislocation mechanism. The screw dislocation is stable at the center of the whisker. There is an attraction of the screw toward the axis of the whisker. If the screw remains perfectly straight, the final whisker will be straight. The end of the whisker can have the shape of a rotated cube as described above. All end facets will grow consecutively by growth layers initiated at the screw as it moves on its circular path. The probability that this occurs is largest at lower temperatures. When the end of the screw is first on one face and then another, other shapes rather than straight whiskers, perhaps helices, develop (24).

The presence of an axial screw dislocation will introduce a shear stress, causing the whisker to develop a twist about its axis (25). Many investigators have tried to detect the presence of twist by X rays or a goniometer and thereby verify the existence of a screw dislocation. A twist has been observed in alpha Al_2O_3 (6) and SiC (25) but has generally not been observed in metal whiskers.

Rambauske and Gruenzel (22) describe an iron whisker where a detectable twist was observed. Three transmission Laue diffraction photographs were taken along the length of a 4.9μ diameter [100] iron whisker by slightly dropping the goniometer after each exposure while maintaining the same horizontal and vertical rotation positions. A systematic change occurred in the resulting streaked diffraction spots

as the length of the whisker was transversed. This effect confirms the presence of a lattice deformation in the whisker. The twist was found to be a summation of a five degree rotation component about the transmitted beam direction and a three degree rotation component about the crystallographic direction of growth for each 0.5 mm of whisker length. This twist was not observable by optical means.

Treuting (26) found substantial agreement between the observed angle of twist and that predicted for the presence of a screw dislocation in tin whiskers.

Even though a screw dislocation is not normally observable in metal whiskers, it may still be important in metal whisker growth. There may be an even number of parallel cooperating screw dislocations with equal magnitudes of Burger's vectors of each sign which cancel out, or a screw dislocation present during growth could climb out or be forced out through the lateral face of the whisker.

Frequently the whiskers will taper and in some cases severely enough so that the tip goes to a point and a well developed end is not observed. Iron whiskers are normally single crystals if they are reasonably straight and well developed.

Surfaces varied from coarse overgrowth to extremely smooth. Coleman (27) reports that as-grown iron whisker surfaces appear to be extremely smooth in the optical microscope and in many cases the electron micrographs indicate no

structure on large areas of the surface. The electron micrographs do, however, show large numbers of growth steps in certain areas. Growth steps pile up near edges and appear as growth step hills.

Originally the whisker surfaces are highly reflective but tarnish when left in humid air. Overgrown and distorted whiskers invariably show low yield strength when compared to straight well-developed whiskers. Surface defects encountered are pits, overgrowths, whisker branches, spotty corrosion products, and occasionally grain boundaries.

In a boat of iron whiskers, the crystals have a tendency to grow in clumps. Many different crystals appear to radiate from a common nucleus. It appears that oxide nuclei are primarily responsible for whisker branches forming from the original whisker. When oxygen was allowed to enter the tube during the reduction of the ferrous chloride, many of the whiskers were observed to take on a dendritic appearance, indicating that side branches had nucleated at places on the faces which were free of such growths at the time the system was opened to the atmosphere. Some well developed crystals also had very small whiskers growing from their tips (14).

Weik (13) showed that iron whiskers grown from ferrous chloride by reduction in hydrogen and argon atmosphere at 650°C contained a skin of iron (not an oxide or corrosion film), the surface layers of which were iron similar to the

whisker core. This is explained by assuming that growth may occur not only by a screw dislocation but also as a succeeding or simultaneously occurring mechanism by a layer or shell growth perpendicular to the whisker axis.

X-ray investigations (1)(12)(22)(28) have been employed to determine the growth directions of iron whiskers. The orientation of whiskers in all three growth directions was not determined in every case, but none of these references indicate any deviation of growth direction from that suggested by the cross section of the whisker.

Other observations on whiskers. Results show that zinc and cadmium whiskers did not grow perfectly along the c axis as might have been expected but had their axes in a $(10\bar{1}1)$ plane with the axis about 30° from the c axis. As a result of this orientation only two of the side faces of the whisker are prismatic faces. The others are $(01\bar{1}1)$ planes assuming 30° (29). Brenner (1) shows micrographs of a spiral whisker of silver, a twisted shaped whisker of silver, and a whisker of silver which looked as though it were composed of silver plates. Brenner (2) also shows a helical shaped copper whisker. Webb et al. (30) grew silver, palladium, and copper whiskers which occasionally appeared as single crystals in the form of both helices and nominally straight but twisted prisms.

A branch whisker was reported growing on a tin proper

whisker (31). Probably a dual growth mechanism occurs from a single center in the tin plate.

Proper whiskers of zinc, cadmium, and tin are occasionally bent, straight segments being connected by sharp angular bends. Bends at 30° , 60° , and 90° were the most common (32).

Small holes were found in some cross-sectioned tin whiskers. Whisker cross sections generally did not correspond to any regular geometric form (33). A hollow center representing the presence of a screw dislocation was observed in alpha Al_2O_3 whiskers when cross sectioned (34).

Little effort has been made to determine the mechanism of growth of the complex shapes. Since the mechanism of growth of the simplest whiskers has not as yet been completely explained, it is impossible to accurately explain the more complex shapes.

Electrochemical and oxidation properties of whiskers

Copper and silver whiskers grown by hydrogen reduction of their halides show less attack than the bulk metal in nitric acid (35). A 400μ length silver whisker dissolved in two hours in 8N nitric acid, compared with ten minutes taken by a much greater mass of bulk silver. Attack was from the growth tip of the whisker without noticeable reduction in thickness. When the whisker was bent in the acid, which introduced dislocations, it was attacked preferentially at

the bend and broke into two pieces. Potential measurements also predicted that the corrosion resistance of the whisker was better than the bulk metal. A 5μ diameter silver whisker was ten to fifteen millivolts cathodic to a 50μ silver wire in $1/10$ N silver nitrate. Similar results were obtained with copper whiskers in copper bulk crystals.

The corrosion behavior of iron whiskers in 4% picral and 2% nital will be discussed in the sections on Electrochemical properties and Etch pits in iron.

Brenner (2) reports that the rate of oxidation of iron whiskers at 500°C is sometimes only 2 percent of the rate of polycrystalline iron.

Laukonis and Coleman (36) have studied the oxidation of iron whiskers by a process of flash oxidation. Alpha iron whiskers growing along [100] and [111] axes were used to study the oxidation behavior on (100) and (110) surfaces at temperatures from 400° to 700°C and at air pressures from 10^{-6} mm of Hg to 1 atmosphere. Well-defined oxide patterns are observed on clean iron surfaces. Flash oxidation produces square oxide nuclei on (100) and triangles on (110) planes. The whiskers were flash oxidized immediately after growing them, before they were cooled.

Effect of perfection of the metal on the ease of electrodeposition.--Deposition from a solution of cupric sulfate and $0.1\text{N H}_2\text{SO}_4$ does not occur on some very small copper whiskers at an overvoltage of 100 millivolts while

large whiskers grew rapidly at 10 to 15 millivolts. The difference seems to be that the large whisker is growing and the small one is not, even at an overvoltage of 100 millivolts. Once growth has started, strongly adsorbed molecules become part of the deposited layer and this is thought to reduce the overvoltage. Apparently the increased perfection of the small whiskers prevents initial deposition (37).

It is expected that the corrosion and electrochemical behavior of whiskers should be different from a bulk specimen because fewer defects, generally higher chemical purity, and smoother surfaces are often found in the whiskers.

Dissolution of Crystals

Variation in the rate of dissolution of different orientations of metal crystals has long been used in the study of microstructures. Neighboring grains etch at different rates and may be distinguished by the fact that their surfaces have become inclined to each other and are at different levels as a result of differences in rate of corrosive attack. Different inclinations can be distinguished by the amount of light that is reflected from their surfaces (38).

Information on grain orientation can often be provided from the shape of the etch pits which are sometimes found on etched surfaces. Preferential etching along certain planes creates a surface composed of facets formed by the planes which show preferential dissolution. Some etch pits are cone shaped and show no preferred attack along certain planes. Those that show crystallographic shape can often be used to determine the orientation of the plane on which the attack has occurred. When the preferential attack produces isolated holes they are referred to as etch pits. As these pits grow larger or more pits form, they begin to run together, and individual pits are harder to distinguish.

The shape and distribution of the pits are dependent on the solvent, orientation of the surface, the internal structure of the crystal, and the presence or absence of

poisons. The faces of different orientations may possess different degrees of resistance to chemical attack, with the result that the etching of any one form of a crystal will be constant and characteristic of that form, provided the solvent remains the same and the etching has reached the same stage of maturity (39).

Much early work was directed toward relating the shape of etch pits on various minerals to the face on which the attack occurred. More recently it has been shown that etch pits often represent sites of dislocations. Since then a large amount of work has been done on the etching of metals, and ionic and semiconductor type crystals.

Etch pits at dislocations can be used to study the motion of dislocations resulting from mechanical deformation and annealing. The mechanism of dissolution which results in the formation of an etch pit has led to a better understanding of corrosion (40).

In order to produce etch pits at dislocations, dissolution must proceed preferentially at dislocations as opposed to the surface generally. It is insufficient, however, to preferentially create steps at dislocation sites. An inhibitor (poison), which can be present either in the etching solution or in the crystal, must adsorb on the advancing dissolution steps and poison the dissolution reaction. It may be assumed that whenever well-marked etch pits are

formed, an inhibitor or poison is present either by chance or design.

Pits preferentially form on the low index planes (100), (110), and (111), since the high index planes have steps which can more easily result in general attack. Ives (41) in a study of the etching rate of LiF crystals concludes that the etching rate for a close packed surface of a perfect crystal should be zero. Real crystals record a finite rate caused by the formation of etch pits.

Pits which form on low index faces at clean dislocations controlled by poisons ideally have shapes which are related to the crystal symmetry of the face which is etched, i.e., square pit traces on (100) faces, triangular pits on (111), and rectangular pits on (110) faces.

Dissolution kinetics

The surface of a real crystal is not perfect but is thought to consist of low index facets separated by ledges of monomolecular height. The ledges consist of segments lying in close-packed directions separated by kinks of monomolecular offset. These ledges are preferred sites for the removal of atoms from the crystal (42). When etch pitting occurs, preferential attack must be nucleated and restricted to the area surrounding the dislocation line.

Types of control in effect during dissolution.--

Frank (45) has developed a theory that can be used to explain diffusion and poison-controlled dissolution. The theory can be applied in the opposite sense to explain crystal growth. Dissolution is envisioned as the progression of ledges across the surface. The source of ledges on close-packed faces can be crystal edges, pits where a dislocation with a screw component normal to the surface intersects the surface, or holes nucleated in the close-packed surface (42). Atoms enter the solution at these ledges and diffuse into the undersaturated solution.

Frank (45) developed the kinematic theory of dissolution by assuming that the velocity of the steps depends only on the proximity of other steps. The following nomenclature is used.

- k - the step density, the number of steps per unit length in the neighborhood of a particular point
- q - the step flux, the number of steps passing a given point in unit time
- v - the velocity of an individual step
- c - the kinematic wave velocity

If all steps on a crystal surface are moving at the same velocity, their velocity, v, can be found by dividing q by k. The velocity is independent of the width of the ledge. It is usually found, however, that all ledges do not move at the same velocity. In diffusion-controlled dissolution, wide ledges move faster than narrow ledges. The

velocity in this case is called the kinematic wave velocity, c , and is given by the slope $\frac{dq}{dk}$. If the velocity, c , decreases with increasing k , decreasing ledge width, $\frac{d^2q}{dk^2}$ is negative. Narrow ledges then move to the rear of a group of various width ledges and wide ledges move to the front. The profile of such a group of ledges shows the discontinuity of slope at the rear and becomes increasingly rounded at the front.

Ives and Hirth (42) have expanded these ideas and suggest that two variations of diffusion control are possible. The first treatment considers the thickness of the unstirred layer at the solution-crystal interface to be large compared to the steady state ledge spacing, y_0 . This occurs at high undersaturation. Under these conditions, the step velocity, c , continually decreases as the steps become more narrow, in agreement with the ideas expressed by Frank (45). No provision is provided in this analysis for a ledge to change its velocity with time. Ives and Hirth (42) go on to show, however, that if the unstirred layer is only a few angstroms thick, the crystal ledges accelerate at small ledge spacings, y_0 , until a maximum velocity, v_∞ , is attained. At the maximum velocity, the spacing, y_0 , is approximately equal to six times the mean free path of diffusion, $\bar{X}$. It is likely that the motion of ions on the surface, rather than directly into the solution, will be the limiting step in diffusion. This treatment assumes that

surface diffusion is significant and considers dissolution prior to the attainment of the steady state ledge velocity which may never be reached. If y_0 at the ledge source is less than $6\bar{X}$, the ledges will accelerate as dissolution proceeds and the slope of the pit sides will become less steep as the distance from the source increases. If the initial spacing at the source, y_0^0 , exceeds $6\bar{X}$, the ledges will maintain a constant spacing, and the slope of the pit sides will remain constant. A measurement of pit slope is a criterion for distinguishing between volume-diffusion and surface-diffusion control. The slope of a pit at a screw dislocation in which y_0^0 exceeds $6\bar{X}$ is given as

$$\frac{h}{y_0^0} = \frac{hkT \ln(\frac{C_0}{C})}{4\pi \delta' \Omega} \quad \text{Equation 1}$$

- C_0 - concentration at the solution crystal interface which is assumed to be the saturated concentration of the crystal in the solvent
- C - concentration of the dissolving crystal at a point which is removed from the interface
- δ' - interfacial free energy
- Ω - atomic volume of dissolving ions, approximately equal to h^3
- h - height of the monomolecular ledges
- y_0^0 - ledge spacing at the center of the etch pits
- k - Boltzman's constant
- T - absolute temperature

Since no ledges are associated with an edge dislocation, the spacing, y_0^0 , at an edge dislocation depends on the probability for nucleation of a critical size hole. This is based on the conditions necessary to open up any dislocation and form an etch pit when the crystal is placed in an

undersaturated medium. If there is a decrease in free energy caused by dissolution, then the crystal will dissolve (43).

The critical concentration required to open up a dislocation has been expressed as

$$- \ln \left(\frac{C}{C_0} \right) < \frac{2 \pi^2 \gamma^2 \Omega}{k T u b^2} \quad \text{Equation 2}$$

u - shear modulus of crystal

b - magnitude of Burger's vector of a dislocation

The other terms have been previously defined.

Since it is not possible to decrease $\frac{C}{C_0}$ below a certain point, etch pits at dislocations of small Burger's vectors can form only in a medium in which γ is considerably below the value corresponding to the free surface of the crystal (43).

For $\frac{C}{C_0}$ less than $\frac{C}{C_0}$ critical, Equation 2, there is no barrier to nucleation at edge dislocations. Once ledges have been produced in this manner, dissolution can begin. For a concentration ratio greater than $\frac{C}{C_0}$ critical, nucleation of ledges at edge dislocations will not be spontaneous. Nucleation of ledges at the source will be required and the resulting ledge spacing will be too large to produce observable etch pits. It can be seen in Equation 1 for screw dislocations that a small ratio $\frac{C}{C_0}$, large $\frac{C_0}{C}$, will increase the slope of an etch pit at a screw dislocation and make it more observable.

If the ratio of $\frac{C}{C_0}$ is very small in comparison to $\frac{C}{C_0 \text{ critical}}$, nucleation at sites other than at dislocations can occur. There is, therefore, a region of undersaturation in which dissolution pits at dislocations are created with no nucleation barrier, but where nucleation does not occur on a perfect surface at an appreciable rate.

Under part poison part diffusion control, the presence of a poison at the crystal surface affects only two of the parameters, namely the surface free energy, γ , and the effective saturation concentration, C_0 . A poison will lower the surface free energy from γ to some lower value γ' . In like manner the concentration C_0 at the interface will be reduced to some lower value, C_0' .

It can be seen that in Equation 1 a decrease in C_0 and γ have opposite effects on the slope of the pit. The decrease in γ increases the pit slope while a decrease in C_0 would tend to decrease the slope. In this equation, it is felt that the surface free energy term γ is more sensitive to the effect of the poison than is the reduction in concentration at the interface. The addition of a poison, therefore, slows down the ledge velocity and increases the pit slope.

The local concentration of metal ions, C , must be quite small for spontaneous dissolution to occur at dislocations in metal crystals. The difficulty often encountered in obtaining well-shaped etch pits in pure metals has been

attributed to the fact that such small values of C cannot be maintained in the solution. For the dissolution of metal crystals, the crystal edges, screw dislocations, and high index planes provide many steps and sources of steps not involving nucleation processes. Dissolution occurs other than at dislocation sites. When a poison is present, γ is decreased and this permits a higher concentration, C , for the same pit slope.

Frank (45) considers the effect of a poison as a modification of his original kinematic theory of dissolution. The profile of most etch pits on metals shows the slope of the pit face increasing as the distance from the center of the pit increases. This suggests that the narrow ledges are leading and the wide ledges trailing. This is the exact opposite profile from that usually found for dissolution in the absence of an impurity or poison.

There are two ways in which the narrow ledges could lead and the wide ledges trail. Both occur because of the effect of a poison. The poison strongly adsorbs on the surface but because of its low concentration requires time to reach adsorption equilibrium. As it adsorbs, it reduces the velocity of the step. Since the adsorption of the poison is time dependent, the kinematic velocity, c , is no longer simply $\frac{dq}{dk}$ but now depends on the time for adsorption of the poison as well. When a step passes, it leaves a clean surface,

on which the adsorption of a protective poison increases with time. The density of poison met by an oncoming step is an increasing function of the time elapsed since the passage of the previous step. The steps are more impeded by the poison when they are far apart than when they are close together. Ledges which are narrow have been exposed to the solution for a shorter period of time, and therefore have less poison adsorbed on the surface. Narrow ledges are less affected by the poison and travel at a higher velocity. When the slope is small, a very mild impurity effect can suffice to transfer the narrow ledges from the rear to the front of a bunch.

Most etch pits, however, are bound by sides with relatively steep slopes. No ledge can continue to move faster than the leading ledge. In poison control the velocity of the leading ledge will ultimately determine the rate of change of the width of the pit. Since the surface can be considered as a very wide ledge, it has been exposed to the poison for a longer time than any ledges within the pit and, therefore, is the slowest moving. The principal effect of a poison is to slow down the leading pit edge, and pile up ledges formed later, thus increasing the slope of the pit.

Higher ledges or terraces are seen in some etch pits. These are formed when many ledges of atomic height combine. Consider a sequence of steps in which one step lags a little

behind its regular position. The step ahead lengthens, more poison is adsorbed on it, and the step which lagged is retarded still more. Cleaner areas allow steps to advance faster. Larger steps develop when some ledges overtake others as the result of non uniform ledge velocity.

Applications

The original concepts of the theory of dissolution were developed using ionic crystals but in principle apply to metals as well. It is felt that etch pit formation is probably due to the preferential nucleation of unit pits one molecule deep at a dislocation, and the subsequent movement of the monomolecular step across the surface. If the monomolecular step is dissolving slowly, it is likely that the pit will deepen sufficiently to become visible. If the step moves rapidly the surface is uniformly attacked rather than selectively as pitting. The steps on close-packed planes must be crowded together to form a visible pit (46).

When a LiF crystal is immersed in pure water, very wide indistinct pits are formed because the steps are not contained near their point of nucleation (47). Small amounts of ferric fluoride added to distilled water can adsorb on these steps and inhibit their motion so that steeper, more visible pits are produced. The corrosion rate is simultaneously decreased.

A concentration of FeF_3 of about 2×10^{-6} mole fraction was found to be sufficient to poison the steps. When the concentration of poison was increased, a larger proportion of the steps were inhibited and the pit size decreased. The effectiveness of the FeF_3 as a poison resulted from the ferric rather than the fluoride ion.

In certain cases it, therefore, appears that a few parts per million of impurity is sufficient to poison the advancing step. Such small concentrations can also be provided by iron impurities in the lithium fluoride crystal. The impurity can be either in solid solution or as precipitated particles in the parent crystal. It was found that when NaCN was added to distilled water, the surface of the LiF became much smoother. At the same time the weight loss increased. The cyanide reduced the ferric ion concentration in the solution below the value characteristic of the ferric fluoride complex ion. Without the poison available, general attack rather than pitting occurs (48).

Frank (45) suggests that the mechanism of poisoning might be a ferric ion interacting with fluorine ions to make a $[\text{FeF}_6]^{-3}$ complex, with one or perhaps five, of its fluorines forming part of a lithium fluoride crystal. This local excess negative charge would impede the removal of neighboring lithium ions. The complex would dissolve as a complete $[\text{FeF}_6]^{-3}$, ineffective until it decomposes again.

Mendelson (44) obtained etch pits in NaCl crystals using a glacial acetic acid etch with FeCl_3 added. Pure glacial acetic acid produces very wide indistinctly shaped pits. As the concentration of FeCl_3 is increased the pits become smaller and have steeper sides. At the critical concentration of four grams of FeCl_3 per liter the pits have the shape of sharp pyramids. These effects are exactly what was found for FeF_3 additions to distilled water when etching LiF. The concentration of FeCl_3 is, however, several orders of magnitude higher.

Poisons for metals.--Young (40) found that the addition of bromide ion to a ferric chloride hydrochloric acid solution was necessary to form triangular pits on (111) faces of copper. The role of the bromide ion was to reduce the dissolution rate. It was suggested that possibly the bromide ion was acting as a poison. Lovell and Wernick (49) found that conical and then triangular pits formed on a (111) face of copper with increasing addition of bromine to a ferric chloride, hydrochloric acid, acetic acid etch.

Rosenbaum and Saffren (50) found an effect of chlorine, bromine, and iodine on the pits form on the basal plane of zinc. Chlorine, either ionic, atomic, or molecular, most effectively retards the motion of steps which are parallel to $[10\bar{1}0]$ directions while bromine and iodine retard $[11\bar{2}0]$ steps most effectively.

The corrosion rate of iron first decreased and then increased when an increasing amount of CuCl_2 was added to a concentrated hydrochloric acid, water, alcohol solution. It was suggested that small concentrations of CuCl_2 poison the crystal surface, while higher concentrations appear to catalyze the acid attack (53).

In each case the halide ions did appear to influence the dissolution behavior. The halide concentrations were generally considerably higher than the trace impurities often associated with a poison, however.

It is likely that in many cases the poison may be contained in the metal (46). In many cases, a poison of a few parts per million is probably sufficient to poison the steps. It is impossible to reduce the impurities in metals below a level where the effect of trace impurities as possible internal poisons can be safely eliminated.

Etch pits in metals.--Clean and dirty dislocations are found in metals. Clean dislocations contain practically no impurities segregated along the dislocation line, while dirty dislocations have varying amounts of impurities along the dislocation. Dislocations grown-in during the growth of a crystal contain some segregation of impurities along the dislocation line and are considered dirty. Newly produced dislocations resulting from deformation are clean since no diffusion of impurity atoms to the dislocation line has occurred. Even for a poison present in a metal in a few

parts per million, there is probably some segregation of the poison along an as-grown dislocation. There is, however, probably sufficient poison contained throughout the crystal to effectively poison the ledges of newly formed dislocations resulting from deformation. It would be expected for an internally-contained poison that the as-grown and deformation-produced clean dislocations would generally show the same response to the poison. In such a case, provided the etch will attack both clean and dirty dislocations, both types should produce similar etch pits.

For relatively clean dislocations, reagents are needed which are sensitive enough to distinguish the small differences in solution potential between the matrix and the strained metal surrounding the dislocation (49). The presence of impurities decreases the energy of the dislocation. Impurity atoms can increase or decrease the rate of attack at the dislocation line.

If the concentration of impurity at the dislocation is large enough, the dislocation can be considered as a line of the impurity. Decorated dislocations have impurity atoms added to the crystal so there will be considerable segregation along the dislocation line. A galvanic cell can then be set up in the etch between the impurity atoms and the surrounding metal. This type of attack has no relation to step nucleation, and the pits form without regard to crystal face and are conical initially rather than shaped in relation

to the crystal symmetry (40). A conical pit (line of impurity) may subsequently be attacked to form a pit of crystallographic shape, however.

Decorating a dislocation involves diffusing an impurity into a crystal which segregates along the dislocation line and facilitates etching of the dislocation. Dislocations were revealed in zinc by decorating with cadmium and in an iron--3 1/4 wt. % Si alloy by using carbon to decorate the dislocation (50). Young (51) reports that when 0.01 at. % tellurium was added to 99.999% Cu, the dislocations can be revealed as etch pits by electrolytic etching. Etch pits were revealed in both iron bulk crystals and whiskers when decorated with carbon (53).

Etches that reveal clean dislocations generally work only on surfaces nearly parallel to certain crystallographic planes of high atomic density. At present there are etchants which are reported to reliably reveal undecorated dislocations in several metals and on several of the low index crystallographic surfaces (50): copper on (111), (110), and (100); iron on (100) and (110); cadmium on (10 $\bar{1}$ 0); and tungsten on (100) and (112).

The problem of etching metals is complicated by gas evolution and film formation which may increase the potential differences between the matrix and the strained material surrounding a dislocation. Many metals and alloys owe their corrosion resistance to a protective film. At

discontinuities on the surface, such as ledges or the registry of atoms at dislocations, the film is probably weak or incomplete.

Many etches appear to produce a good agreement between etch pits and dislocations, while in others the agreement is often poor.

Screw dislocations and edge dislocations at deformation dislocations can be distinguished by the asymmetry or symmetry of the etch pit bottom in ionic type crystals (47). It is very rare that a difference in reactivity can be observed between edge and screw dislocations on a metal surface. It is reasonable to consider the points where all line defects intersect the surface as reaction sites which are less active than step edges but more active than a perfect surface (52). If the dislocation is moved from the site of the original pit by additional bending or annealing, the pit will no longer etch deeper but will become flat-bottomed as it grows wider during subsequent etching. This behavior has been shown for ionic (47) and metallic (23) crystals.

Effect of dissolution rate on the formation of etch pits.---Jenkins and Stiegler (52) found that the rate of dissolution was closely related to the ability to form etch pits. Anodic polarization of the (100) face of copper crystals in oxygen-free, 0.2M copper sulfate revealed

discontinuities in the curves resulting from a plot of electrode potential versus anodic current density. For current densities up to one microampere/cm², crystal edges and point defects served as nucleation sites for steps rather than areas where line defects intersect the surface. The maximum rate at which such steps can be nucleated determines where this region ends. Between one and five microamperes/cm² anodic current density, both line and point defects were acting as sources for step formation and the steps were being removed at a rate at least equal to the rate at which they were created. This creates a relatively smooth surface. After the maximum rate of step formation is reached, further increase in anodic current resulted in pit formation at points where line defects intersect the surface and at subgrain boundaries. As dissolution continued, the pits grew together to form facets. When the rate of dissolution exceeded the rate at which material could be supplied by the previous sources, reaction sites were apparently nucleated at random on the metal surface. A faceted structure developed rapidly which was not formed by the growth of pits.

The energy required for dissolution is greatest on an idealized flat surface, less where dislocations intersect the surface, and least at step edges located at point defects.

Use of Etch Pits to Determine Orientation

After considerable success with etch pits at dislocations in ionic crystals, recent work has been directed to metals. Additional problems are encountered in metal, however, because of higher dislocation density. Since metals do not cleave similar to ionic crystals, there has been a problem of obtaining deformation-free surfaces.

It was found that when soft iron crystals were mechanically polished through 000 emery paper, they were distorted to a depth of approximately 200 to 300 microns (53). Whiskers possess an advantage in that highly reflective strain-free surfaces are available.

Smith and Mehl (54) suggest the following characteristics of an ideal etch: develop planes of only one crystallographic family (hkl); develop traces (intersections with the surface) which lie accurately in the planes (hkl); develop no re-entrant etch pit planes; develop the bottom of the pit well enough to permit an approximation of the slope of the sides of the pit.

Provided the above requirements are sufficiently met, the orientation of the reference surface can be determined from the etch pits.

Methods of determination of orientation from etch pits

The first general method involves the analysis of the pattern of light produced by reflections from corresponding

faces of all the etch pits on a surface. The light figures produced by such a method can be used to determine orientation. A second method involves a study of individual pits and the measurement of the angles between etch pit faces and the reference surface. A goniometer can be a useful tool in both methods.

Light figure method.--When a narrow beam of parallel light is reflected from the surface of an etched single crystal and projected on a screen, different light figures are obtained (55). Usually the screen is flat, normal to the light beam, and is placed between the light source and the reflecting crystal. The screen can be cylindrical, with the axis normal to the beam and the crystal in the center.

The light figure that is formed will depend on the planes that have been selectively etched. The polygon thus produced by the reflecting light has symmetry equal to that of the crystal because of the anisotropy of etching velocities along the different crystal axes.

The angle of rotation required to obtain a perfect light figure corresponds to the angle between the plane of polish and the low index face. The indices of the original reference surface can then be determined.

This method has been successfully used to determine the orientation of copper (56)(57)(58), iron (56)(58), aluminum (58)(59), zinc (59)(60), nickel (58), and silicon and germanium (55).

Angular relationship of etch pit faces.---The outline of a trace of a representative etch pit is drawn in the center of a stereographic projection and radii drawn perpendicular to the trace of the pit with the surface. The angles of intersection of the faces of the pit with the surface are estimated either with a goniometer or by the use of depth measurements from a microscope combined with the width measurements of the pit. When the angles of intersection of these planes with the reference surface have been determined, the poles of the pit faces can be plotted on the stereographic projection along a line perpendicular to the pit trace. If the (hkl) indices of the pit faces are known, the orientation of the reference surface can be determined. If the (hkl) index of the reference surface on which the pits form is known, then the indices of the pit faces can be determined by the same method. If the reference surface and the pit faces are low index planes, often both can be determined from a stereographic projection on which the poles of the pit faces have been plotted. It is rare that pit faces intersect the reference surface at exactly the theoretical angle between the planes involved. Ideally, however, dissolution follows low index planes, so it is often possible, when the symmetry of the pit is taken into account, to predict the ideal low index planes involved.

Smith and Mehl (54) used etch pits obtained on iron with a copper ammonium chloride etch to determine the orientation of the plane of polish. It was found that pits containing (110) faces generally developed with this etch. A trace is drawn with radii perpendicular. The angle of intersection of the pit planes with plane of polish is estimated and the approximate pole position plotted. A standard projection is then rotated by means of a stereographic net so that (110) poles fall on or very near to the radii and close to the approximate pole positions. The orientation of the plane of polish can be determined.

The previous method required the study of individual pits at high magnification. Barrett (61) measured the angular relationships of etch pit faces by a two rotation goniometer. This method is limited to samples 100 μ and larger in diameter since this method depends on the reflection of corresponding faces of all pits viewed at a relatively low magnification. The difficulties encountered with such angle measurements are in obtaining satisfactory etch pits, in eliminating multiple reflections from two or more faces of the pits, and in distinguishing etch pit reflections from the irregularly scattered light and reflections from etched planes lying nearly perpendicular to the surface of the specimen. The etch pits or facets must have faces accurately parallel to crystallographic planes of low index.

Berlec (46) used a combined approach in recent work on etch pits in tungsten, which is body centered cubic. The faces of the etch pits produced by electrolytic etching are (110) planes. Again an outline of a representative pit trace is drawn in the center of a stereographic projection and the poles of the pit faces are plotted. The orientation of the reference surface can be determined from the resulting stereographic projection.

Mathematical relationships of pit geometry

Tucker and Murphy (62) present a very complete mathematical discussion of the orientation determination of aluminum single crystals using etch pits.

The analysis presented here is for a rectangular etch pit bound by (100) planes and located on or close to a (110) reference surface. The reasoning also applies to (110) planes of body-centered cubic metals such as iron when the etchant preferentially attacks (100) planes. Such etch pits show a line at the base of the pit indicating ideally the intersection of two (100) faces. This bottom line of intersection in the pit is parallel to the reference plane. The Miller indices of this reference plane are the reciprocal of their intercepts. The intercepts are, therefore, $\frac{1}{h}$, $\frac{1}{k}$, $\frac{1}{l}$, where $\frac{1}{h}$ has arbitrarily been selected parallel to the sectioning plane and is therefore infinity. The indices of the reference plane are, therefore, (0kl). The ratio of the

distance of the center line in the bottom of the pit from either side is estimated looking down on the pit. The following relationship has been developed based on similar triangles.

$\frac{x}{x'} = \frac{k^2}{\ell^2}$ where x and x' are the distances from the center line to the edges of the pit seen from above the pit. For example, if the center line appears exactly down the middle of the pit, the ratio $\frac{x}{x'} = 1$ and k and ℓ must be either 1 or $\bar{1}$. The indices of the plane on which the pits are observed must, therefore, be of a form (011). This is shown in Figure 4f.

Other examples of orientation determination by etching

The orientation of planes near (111) in germanium (63) can be determined from etch pits. When a small polished hemisphere is etched in a suitable etchant, the region around each principal pole has a characteristic type of attack associated with it. Using a ferricyanide etch, excellent triangular pits are noted around the (111) orientation. The pits become progressively less equilateral as one moves away from the (111) pole. The shape is sufficiently reproducible so that the rotation from the (111) pole can be estimated from the pit shape, accurate within two degrees.

Etch pits formed by alloying germanium with indium have also been used to determine the orientation of germanium

crystals (64). Liquid indium attacks germanium preferentially along the densely populated (111) planes. After the indium-germanium alloy is etched off, perfect (111) planes are observed on the germanium. These pits were inspected by means of interference fringes. Since exact (111) planes are produced by this method, it serves as a reference for obtaining the orientation of other surfaces.

Electrochemical Properties

The effect of orientation on electrochemical properties

Single and polycrystalline metals have been used to study the variation in electrochemical reactions with change in orientation. Electrochemical processes studied have included deposition, etching, metal displacement, galvanic action, wetting of the surface, and corrosion in specific environments (65). It was concluded that generally the rate of all surface processes depends on the crystal face exposed to the environment.

One of the first investigations on the variation of electrode potential with orientation was conducted by Straumanis (66) in 1929. The potentials of different planes of single crystals of zinc were measured in neutral zinc sulfate solution against a calomel electrode. No difference in potential was found. The surfaces were mechanically polished before testing and this probably smeared the ideal crystallographic planes.

Mears and Brown (67) used a binary alloy 96% aluminum and 4% copper, which was aged to cause precipitation of CuAl_2 . The solution potential varied 51 mv between some of the grains. The orientation of the grains was not established, however.

A study of the solution potentials of different orientations of crystals of high purity aluminum (68) showed that while the differences in solution potential were very

small, the difference in the rate of attack of the different crystal faces was significant. The potential of polished aluminum samples was measured in concentrated hydrochloric acid. A difference of only a couple millivolts was noted between the grains of different orientation. Mechanically polished surfaces were used here also. It was found, however, that even such small differences often establish a trend as to which plane would be attacked most severely. The grain with a (111) plane exposed was anodic to the grain with a (100) plane, although only by a millivolt. The (111) plane dissolved decidedly more rapidly, however.

Measurements on copper crystals showed similar results (69). In one test two copper single crystals were masked off so that on one the (100) surface was exposed and on the other the (111) surface. When connected in a cupric sulfate, sulfuric acid solution the (100) surface was positive to the (111) surface by 6.5 mv but decreased to 5.7 mv after one hour. With an atmosphere of hydrogen above the electrolyte the difference was 2.2 mv. When air was bubbled through the potential difference rose to 5.9 mv. The (111) face of copper was attacked in preference to the (100).

Single crystals of germanium showed a marked variation in dissolution depending upon orientation (70). The rate of attack $(110) > (111) > (100)$, was found after several

minutes in a solution containing HF, H_2O_2 , and H_2O . LiF in distilled water containing 2×10^{-6} mole fraction FeF_3 showed a dissolution rate $(111) > (110) > (100)$, (47).

Orientation was observed to influence the rate of etching of single crystals of iron in 0.2M citric acid and 0.3N H_2SO_4 . The (100) and (321) faces were compared since they represent examples of low and high index faces. In boiling refluxing 0.2M citric acid, the average corrosion rate for the (100) face was $1.4 \text{ mg/cm}^2/\text{hr}$, while for the (321) face $3.0 \text{ mg/cm}^2/\text{hr}$. In 0.3N H_2SO_4 the (100) face corroded at a rate of $0.0091 \text{ mg/cm}^2/\text{hr}$ while the (321) plane corroded at $0.0168 \text{ mg/cm}^2/\text{hr}$. Single electrode potential measurements after 7 to 72 hr in 0.2M citric acid showed that the (100) face was cathodic to the (321) face by 7 to 17 mv. This difference decreased to 3 to 8 mv after immersion for 23 to 92 hr in deaerated citric acid (71).

Iron whiskers etched in 4% picral or 2% nital showed different rates of attack on different crystallographic faces (23). A [100] whisker which has four (100) side faces developed (140) planes at a small angle to the original (100) planes when etched in 4% picral solution. The new surfaces formed were quite rough having facets running perpendicular to the edge of the crystal. The same whisker in a 2% nital solution developed (110) planes on the corners at 45° to the original (100) planes. After continued etching, the newly created faster dissolving planes completely con-

sumed the original (100) faces. The (110) surfaces on the as-grown (111) axial whiskers were generally attacked by the etchants and etch pits could not be resolved.

A very complete study on the effect of orientation on the anodic polarization of iron has been conducted by Engell (72). The polarization curves of α iron single crystals were measured in rapidly stirred dilute sulfuric, perchloric, and nitric acids. Iron in the solution 0.015N nitric acid plus 1N KNO_3 plus 0.2% urea was studied in detail. At 25°C the (100) face had a potential in this solution of -208 mv SHE and a corrosion rate of 14.4 ma/cm^2 . The (110) face had a potential -295 mv SHE and a corrosion rate of 19.2 ma/cm^2 . The (111) face had a potential of -328 mv SHE and a corrosion rate of 12 ma/cm^2 . When these three orientations were cathodically polarized, the polarization curves for the (110) face and (111) face coincided and the combined curve was active to the (100) curve. Other higher order planes were found to fall between these two. The rate of corrosion was greater on the (111) and (110) faces than (100) at a given potential. When sufficient cathodic current density was applied, an active potential was reached where there was no longer significant effect of orientation and the combined (110) - (111) curve coincided with the (100). Engell (72) therefore concludes that iron in an acid under conditions which show little or no effect of orientation can, if anodically polarized, show different polarization behavior

depending upon orientation. For other acids, only the (100) and (111) faces were investigated since it was assumed that these represent the extreme polarization curves and other orientations would fall between them. Iron in sulfuric acid will be discussed in the following section.

The variation of hydrogen overvoltage with orientation has been studied for silver, lead, nickel, tin, and cadmium. It was concluded that the orientation of the metal surface, temperature, and electrolyte employed can change the hydrogen overvoltage on a given metal. Under one set of conditions one set of planes was found to polarize more than the other orientations. Another set of conditions often reversed this order (73).

Characteristics of the active region for iron in acid solution

When iron is placed in an acid solution such as sulfuric, a potential in the active region is established between the iron and the reference electrode. This potential is the result of steady state reactions rather than the establishment of equilibrium conditions. In the active region iron dissolves to form ferrous ions. If the rate of dissolution is increased sufficiently, a critical anodic current density is reached which will cause passivation.

Figure 1 shows schematically the individual polarization curves for the reactions of iron in sulfuric acid.

Figure 1 - Influence of an oxidizing agent on the polarization curves for the corrosion of iron in acids

Figures 1 through 4
adapted in part from
H.-J. Engell, Arch.
Eisenhüttenw., 26, 393
(1955).

E_{corr} = Corrosion potential of iron in acid
 E'_{corr} = Corrosion potential of iron in acid
 with an oxidizing agent added
 $I_{Fe^{+2}}$ = Rate of corrosion of iron found by
 analysing the solution

$I_{\text{Fe}+2}$ represents the dissolution of iron to divalent ions, I_{H} shows the cathodic polarization of the hydrogen evolution reaction on the sample during corrosion in the acid, and I_{Ox} represents the curve for the reduction of an oxidizing agent. When no external current is flowing, the potential of the iron in H_2SO_4 is given by E_{Corr} , which represents the steady state conditions. The anodic current associated with oxidation of the iron to ferrous ions then equals the current associated with the reduction of hydrogen ions to hydrogen gas, $I_{\text{Fe}+2} = I_{\text{H}}$.

An externally applied anodic current will cause the potential to move from E_{Corr} and assume more noble potentials. It can be seen that at a sufficiently noble potential, I_{H} becomes very small and the applied anodic current is approximately equal to the current associated with the oxidation of iron, $I_{\text{Fe}+2}$. An externally applied anodic current is given by the rate of all oxidation reactions minus the rate of the reduction reactions. Similarly an externally applied cathodic current is equal to the rate of reduction minus the rate of oxidation.

A steady state current density of 0.22 ma/cm^2 and a corrosion potential, E_{Corr} , of -250 mv SHE have been reported for (100) and (111) faces of iron in $1\text{N H}_2\text{SO}_4$ at 25°C (72). For a stronger concentration than one normal both $I_{\text{Fe}+2}$ and I_{H} increase but still remain equal. The corrosion potential E_{Corr} changes very little with change

the concentration of the sulfuric acid. $I_{\text{Fe}+2}$ is found by analyzing the solution for ferrous ions and applying Faraday's law.

One way of increasing the rate of oxidation of the iron for the same acid concentration is to anodically polarize the specimen with an external current. Another method is to add an oxidizing agent to the solution. Figure 1 shows the polarization curve for the reduction of the oxidizing agent, I_{Ox} . E_{Corr} moves to a more cathodic potential, E'_{Corr} and the current density associated with iron dissolution is increased. When a large quantity of oxidizing agent has been added, the potential is sufficiently positive so that the evolution of hydrogen as the cathodic reaction is reduced to very small levels. At lower concentrations of the oxidizing agent, all cathodic reactions of corrosion occur simultaneously.

Persulfate has been added as the oxidizing agent in this investigation. In place of the cathodic half reaction

the following reaction now occurs (72).

Figures 2 and 3 show the polarization curves for the corrosion of iron in 1N H_2SO_4 with the addition of potassium and ammonium persulfate at 25°C. $I_{\text{Fe}+2}$ represents the rate of dissolution of iron calculated on the basis of the apparent surface area from the iron content in the solution

Figure 2 - Polarization behavior of iron in 1N $\text{H}_2\text{SO}_4 + 0.02\text{N } \text{K}_2\text{S}_2\text{O}_8$.

Figure-3 - Polarization behavior of iron in 1N H_2SO_4 + 0.5N $(\text{NH}_4)_2\text{S}_2\text{O}_8$.

and Faraday's law. I_c represents the curve of the externally applied cathodic current versus potential. I_{Ox} shows the polarization curve for the cathodic half reaction. In both the 1N H_2SO_4 + 0.02N $K_2S_2O_8$ solution and the 1N H_2SO_4 + 0.5N $(NH_4)_2S_2O_8$ solution described in Figures 2 and 3, the amount of hydrogen liberated is probably quite small and the cathodic reaction is almost completely that of the reduction of persulfate. For the addition of 0.5N $(NH_4)_2S_2O_8$ the curve of I_{Ox} is curved slightly indicating that the limiting current is nearly reached. For the solution of 1N H_2SO_4 + 0.02N $K_2S_2O_8$ the limiting current for the cathodic reaction has been attained at the corrosion potential. The rate of corrosion is then controlled by the diffusion of the persulfate ion to the iron surface.

Figures 2 and 3 show that at a constant acid concentration (in this case 1N H_2SO_4), the current density associated with iron dissolution I_{Fe+2} , is the same for a given potential regardless of the means of achieving that potential. A given current density associated with I_{Fe+2} can be achieved by adding the appropriate amount of oxidizing agent, adding an excess of oxidizing agent and applying a small cathodic current, or externally polarizing the iron anodically until the same potential has been achieved.

The iron crystals described in Figures 2 and 3 were etched before being tested in 10% HNO_3 and polished on 3/0 paper. Finally they were polished using a velvet cloth with

water and placed immediately into the test cell previously purged with nitrogen. If a sample to be tested had a similar roughness, and was tested in 1N H_2SO_4 , it would be possible to read $I_{\text{Fe}+2}$ directly from Figures 2 or 3 provided the potential was measured. The dissolution rates presented in Figures 2 and 3 were obtained by dissolving such a small amount of iron in each case that very little change could be observed on the surface.

The effect of orientation on the rate of dissolution of iron at a constant potential becomes significant only at relatively high rates of attack. This can be seen in Figure 3 for iron in 1N $\text{H}_2\text{SO}_4 + 0.5\text{N}(\text{NH}_4)_2\text{S}_2\text{O}_8$. The polarization curves for orientations other than (100) and (111) are assumed to be between these two. In order to keep the roughness of the surface a constant, a small constant amount of iron was dissolved from each surface. Polarization curves were constructed only for the active region of iron.

In order to interpret the curves, it is assumed that at low current density (no effect of orientation) the passage of the hydrated metal ions from the adsorption state on the metal surface into the electrolyte is current determining. At higher current density the greater field strength in the double layer favors the passage of ions into solution from the double layer. The process of metal from the crystal going into the adsorption position is now current

determining. This part is influenced by the orientation of the crystal face.

Distribution of anodes and cathodes on an actively corroding metal.--The current densities discussed in the previous section were based on the assumption that the entire apparent surface area of the sample acted simultaneously as both an anode and a cathode. Even for uniform attack the surface must be divided into both anodic and cathodic areas even though these may be continually shifting and impossible to define at a given time. When pits or other forms of selected attack are present, it is still more apparent that the anodic current density is not uniformly distributed on the sample. The anodic current density on local anodes is probably considerably higher for a given potential than that indicated in Figures 2 or 3.

It has been shown by Stern and Roth (74) that during corrosion of iron in acid, the major portion of the surface appears to function as a cathode. It is thought that the cathode area increases as the hydrogen ion activity increases, possibly caused by greater hydrogen adsorption. This causes a decrease in the real area of the anode. It is not known whether the reduction of persulfate is similar in this respect to the reduction of hydrogen ions to hydrogen gas.

When a high anodic current density near the passivating current is applied to iron in an acid, the reduction of

hydrogen ions is greatly reduced and the major portion of the iron surface functions as an anode, whereas only a small fraction is an anode without externally applied current.

It has been shown that when iron in 1N H_2SO_4 is polarized anodically to the same potential, first with an applied external current, and secondly with an oxidizing agent such as persulfate, the rate of dissolution of iron $I_{\text{Fe}+2}$ will be identical. Because of differences which may exist in the ratio of cathode to anode area on the surface, the appearance of the corroded surface could perhaps be different. If a different concentration of acid other than one normal were initially used, a different value of $I_{\text{Fe}+2}$ would probably be found when that solution was polarized the same degree.

Etch Pit Shape

Pits show crystallographic shape when dissolution occurs preferentially along low index planes. The following is a partial list of possible pit shapes.

1. Pits on a (100) face

- a. Square pit bound by five (100) faces.

Figure 4a

- b. Pit having a (100) bottom and sides bound by four (111) faces. Figure 4b

- c. Pit bound by four (111) faces. Figure 4c

- d. Pit bound by a (100) bottom and four (110) side faces. Figure 4d

- e. Pit bound by four (110) faces. Figure 4e

2. Pits on a (110) face

- a. Rectangular pit bound by two (100) planes.

Figure 4f

a
Five (100) Planes

b
(100) Bottom, (111) Sides

c
(111) Sides

d
(100) Bottom, (110) Sides

e
(110) Sides

(110) Projection

f
Rectangular
Pit with (100)
Sides.

Figure 4 - Schematic Representation of Etch Pits as Projected on (100) and (110) faces. a through e are (100) projections.

Etch Pits on Iron

Data on etch pits in iron, including the etch used, type of pits produced, and the correlation between etch pits and dislocations are presented in this section.

Distilled water

Distilled water was the simplest etch which reportedly produced etch pits in iron (75). A single crystal of iron was cut to produce planes close to (100), (110), and (111). Samples of these three orientations were mechanically or chemically polished and immersed for three hours in distilled water. It was observed that the (110) plane had the greatest number of pits per unit area. The (100) plane had approximately one-half as many as the (110), and the (111) had only about one-fourth as many as the (110). The results were the same using either the chemically or mechanically polished surface. When a purer sample of iron was used, the general level of pitting attacked decreased. The pits formed were round.

Perchloric acid

Wijk and Dijck (76) used a commercial apparatus, the Disa Electropol, with a bath based on perchloric acid. Etch marks, often small pyramids, were found protruding from the surface. Mild steel was used in this investigation. Projections from the surface are thought to occur because of interstitial atoms present, which concentrate

around the dislocation and lower the rate of attack. Etch pits rather than pyramids usually mark dislocation sites since impurities normally increase, rather than decrease, the rate of attack. The orientation of the plane of polish was not determined. The dislocation density calculated from the etch marks was $10^9/\text{cm}^2$. It is felt that these marks do represent the sites of dislocations. Similar etch pyramids were reported on the (111) face of tungsten when etched electrically in 2% NaOH (46).

Copper ammonium chloride

Svechnikov (77) showed that for a low carbon steel etched in copper ammonium chloride, the etch pits were oriented similarly in the same grain but differently in adjoining grains. The pits appeared to belong to cubes, combinations of cubes with octahedrons, and sections of dodecahedrons. On a steel containing considerable phosphorus, only cube shaped pits were observed. Copper deposits on the sample in the copper ammonium chloride solution, and must be wiped off before the pits can be observed. Smith and Mehl (54), using an electrolytic etch based on copper ammonium chloride, produced large pits with well-developed (110) faces. The density of pits is lower than would correspond to a 1:1 agreement of pits and dislocations on a mechanically polished surface.

Ethyl alcohol - bromine

Small etch pits were produced on an alpha iron single crystal etched in ethanol-bromine solution, 10:1 by volume, for 10 to 30 sec (78). The pits formed contained the (111) planes of octahedrons.

Sulfuric acid

Engell (72) found that the shape of the pits produced on a (100) face of an alpha iron single crystal depended on the rate of dissolution of the face.

Figures 2 and 3 show that if oxidizing agents such as $K_2S_2O_8$ or $(NH_4)_2S_2O_8$ are added to 1N H_2SO_4 the rate of dissolution will increase. The dissolution rates presented in these figures were obtained by dissolving such a small amount of iron in each case that very little change could be observed on the surface. If the iron samples were allowed to dissolve for a considerably longer time, pits were formed which could be related to the speed of dissolution of the different orientations. Large square etch pits bound by five (100) planes were formed on (100) faces without the addition of the oxidizing agents. Figure 4a shows this type of pit, which occurs in the region of the polarization curve in which there is no dependency of orientation. At the high dissolution rate represented by the solution 1N H_2SO_4 + 0.5N $(NH_4)_2S_2O_8$ the pits were bound by either four (111) or four (110) planes, Figures 4c and 43. In a solution of

1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$, pits were formed which combine the dissolution planes favored at the high and low corrosion rate. Pits similar to Figure 4b were found which had a (100) bottom and four (111) side faces.

Citric acid

Square etch pits with pit faces formed by (100) planes were obtained on a (100) plane of polish in boiling 0.2M citric acid (71).

Nitric acid

a 1 part HNO_3 and 4 part H_2O etch is listed by Barrett (61) for producing etch pits in decarborized mild steel. The (100) planes were preferentially attacked.

Picral and nital

Boswell (79) reported etch pits in iron using the following etch.

1. Electropolish in chromic-acetic acid
2. Etch in 1% nitric acid in ethanol for 1 min
3. Rinse in methanol
4. Etch in freshly made 0.5% picric acid in methanol for 5 min.
5. Rinse and dry

Pits were observed at dislocations only in specimens slowly cooled from between 750 and 850°C. It was proposed that some segregation of solute at the dislocation is necessary before the highly selective etching process can occur. The pits formed were round.

Liss (80) used approximately the same etch as Boswell except that ethyl was substituted for methyl alcohol. The pits were again observed to form only in specimens slowly cooled from between 750°C and 850°C . Crystals whose (100) planes were very nearly parallel to the surface showed the greatest concentration of etch pits.

Coleman (23)(27) observed etch pits on alpha iron whiskers using 4% picral and 2% nital solutions. Etch pits were generally not present after etching as-grown (100) surfaces. Etch pits appeared on these same faces immediately following plastic deformation after etching in picral or nital. Usually the etch pits were round. However, certain solutions of 4% picral developed square pits. It is suggested that the purity of the alcohol may determine whether square or round pits are formed. Clean deformation dislocations formed etch pits in picral and nital without intermediate annealing. Pits developed at low angle grain boundaries after annealing the deformed whiskers. Etch pits could not be resolved on (110) surfaces of as-grown [111] whiskers.

Fry's reagent

Gorsuch and Alden (53) used Fry's reagent and a modification of this etch to produce etch pits at dislocations in both bulk iron single crystals and whiskers. The basic composition of Fry's reagent: 40 ml concentrated hydrochloric acid, 30 ml water, 25 ml ethyl alcohol, was modified by

varying additions of cupric chloride. The results for iron single crystals show that segregation of carbon to the dislocations is a necessary prerequisite for etch pit formation on all surfaces except the (100) and (110). In addition, the latter surfaces require markedly different rates of dissolution for revealing clean or undecorated dislocations.

For the etching of iron whiskers, Fry's reagent was modified as follows: 100 ml ethyl alcohol, 8 ml concentrated hydrochloric acid, 1/2 gram cupric chloride, and saturated with picric acid. This etch revealed dislocations decorated with carbon.

II. EQUIPMENT AND PROCEDURE

Source of iron whiskers

All but two of the iron whiskers to be discussed here have been provided by the Advanced Metallurgical Studies Branch, Metals and Ceramics Division, Materials Central, Wright-Patterson Air Force Base, Ohio. The two large whiskers, designated WW, were obtained from C. M. Wayman, Department of Metallurgy, University of Illinois, Urbana, Illinois.

Each whisker has been assigned a number. These numbers are set off by parentheses and dashes, for example (-1), to distinguish them from numbers referring to references. The boats obtained from Wright-Patterson Air Force Base have also been assigned a code designation. After each code number is a list of those whiskers extracted from that boat.

Boat number	List of whiskers extracted (- -) around each number has been omitted
H-69, H-70	38, 39, 40
H-75	4, 5, 6, 34, 35
H-89, H-91, H-92	18, 19, 20, 24, 25, 26, 27, 28, 33
H-121	1, 2, 9, 10, 11, 12, 13, 36, 37
529	7
538	14, 15, 16, 17, 29, 30, 31, 32
540	21, 22, 23

Whiskers numbered (-3-) and (-8-) were obtained from Wayman and will be discussed later.

The following information on growth procedures has been supplied by Wright-Patterson Air Force Base.

H-69, H-70: An iron boat filled with 20 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ was heated up to 710°C in argon and then reduced for 2 hr in hydrogen. Gases were not purified. Specimens were furnace cooled in hydrogen. Flow rate of gases was 225 ml/min.

H-75: A ceramic boat filled with 15 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ was heated up to 710°C in helium and reduced for 2 hr in hydrogen. Gases were passed through a liquid nitrogen trap. Flow rate was 225 ml/min. Specimens were furnace cooled in hydrogen.

H-89, H-91, H-92: Conditions were the same for the three boats. Iron boats with approximately 20 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ were heated up to 690°C in helium. They were held for 2 hr in hydrogen. Flow rate of the gases was 225 ml/min. Gases were passed through a liquid nitrogen trap. Specimens were furnace cooled in hydrogen.

H-121: A boat containing approximately 15 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ was heated in helium to 675° , then the hydrogen was turned on and the temperature raised to 700°C . The reaction was held for 2 hr at 700° . Flow rate was 330 ml/min. Gases were passed through a liquid nitrogen trap. Specimens were furnace cooled in hydrogen.

529: A fused silica boat was filled with 6.4 grams of anhydrous FeCl_2 . The reaction tube was evacuated with an aspirator, heated and flushed with helium. Then the FeCl_2 was moved into the hot zone and the hydrogen flow started. The temperature was 660° and the flow rate was 170 ml/min. Time held at temperature was 2 hr. Specimens were furnace cooled in hydrogen.

538, 540: Ceramic boats were filled with 12 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$. The samples were heated to 660°C in helium, then the hydrogen flow was started. The temperature was raised to 710°C . The boats were held at temperature for 3 hr. Flow rate was 500 ml/min.

for the helium and hydrogen until 710°C was reached. Upon reaching 710°C the hydrogen flow was reduced to 145 ml/min. Time held at temperature was 3 hr. Specimens were furnace cooled in hydrogen. Gases were passed through a liquid nitrogen trap.

The two large whiskers received from C. M. Wayman are assumed to have been grown in a manner similar to that described in reference (14). An iron boat filled with 30 or 600 grams of $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ was heated to 731°C under helium and reduced for 12 hr in hydrogen. A larger amount of salt, slightly higher reduction temperature, and a longer reduction time are the principal differences.

Extraction and mounting of the iron whiskers

All whiskers were removed from the boats with micro forceps, the ends of which were ground to increase the fineness of the point. Whenever possible the whiskers were extracted by pinching them at the base end with the forceps and then pulling them loose.

The extraction of all whiskers, as well as all mounting and other fine operations, was carried out under an American Optical Co., Spencer stereoscopic microscope with magnifications of 9 X, 27 X, and 54 X.

Mounting whiskers for immersion etching.--Two types of mounting procedures were used depending on the type of test to be conducted. Most of the whiskers were etched by dipping them in the etchant. These whiskers were mounted by suspending them between two pieces of black vinyl electri-

cal tape which were glued adhesive-side up to a glass slide with epoxy resin. The epoxy came in separate tubes for resin and activator, and appears commercially under the trade name Epoxe. The top slide in Figure 5 shows a whisker mounted in this manner. The space between the two sections of tape was varied depending upon the length of the whisker to be mounted. In some cases another piece of tape was placed adhesive-side up onto the first layer in order to increase the distance between the mounted whisker and the glass slide.

After a whisker had been pulled loose from the boat, there was usually sufficient magnetic attraction to hold the whisker to the forceps while the whisker was positioned above the tape. The whisker was then lowered face up until the ends touched the adhesive and were held in position. This method of mounting has the advantage that a given whisker can be located quickly on the metallograph. It also permits many whiskers to be etched simultaneously. Whiskers mounted in this manner are held rigidly and are less susceptible to damage. They can be reduced considerably in cross section and still not break.

Only one face of the whisker can be examined by this method. This has the disadvantage that the progressive attack on other faces cannot be observed. The fact that the same face is always up can be an advantage, however.

Figure 5. Whiskers mounted for etching (top), and for potential measurements and iron analysis (bottom).

After extensive etching, the surface can change significantly. Growth or etch patterns present at one stage of etching may no longer be present later on. This method assures that the orientation of the surface being viewed has not changed, and any changes that are seen are the result of etching patterns on planes approximately parallel to the original surface farther down into the whisker.

The most representative portion of the whisker mounted in this way is the section spanning the gap between the two pieces of tape. The etching and rinse solutions can flow easily around this portion of the whisker. Since the span is being attacked on all sides, it usually is reduced in cross section faster than portions mounted on the tape. Unless the portion of the whisker which is fastened to the tape possesses an unusual etching behavior, photographs presented here show that portion of the whisker which is part of the span.

Mounting whiskers for potential measurements and calculation of corrosion rate.--A modification of the above mounting method was employed when the surface area of the whisker was measured. A method which masked off both ends of the whisker and exposed the center portion is most desirable. The base end of the whisker is often scratched or slightly deformed as the result of extracting it from the boat. Whiskers often taper, sometimes to nearly a point at the end. On others, the end is poorly formed. The difficulty

in attempting to calculate the area of such a surface is apparent. In order to measure the single electrode potential of a corroding whisker, an electrical connection must be made with the whisker, and this connection must be insulated from the etchant.

A whisker mounted for such tests is shown at the bottom of Figure 5. The whisker is mounted on the tape in the same manner as that previously described. A 5 mil platinum wire was taped to the glass slide and fastened to one end of the whisker with silver print, a silver paint used in electrical printed circuits. When the silver paint had hardened, all the portions of the whisker not part of the span and any portions of the platinum wire which would later be immersed in the etchant were coated with epoxy. The epoxy was placed over one end of the whisker at a time and allowed to harden before coating the other end. The whisker was stored vertically so that the epoxy would not run over the span while curing. Finally the entire mount, except for the span portion of the whisker, was coated with Glyptal red enamel and allowed to dry. A slight film occasionally covered the span portion of whiskers mounted in this way. However, rinsing in water always removed all traces of any film present. The span portion of a whisker mounted in this manner is usually of a reasonably constant cross section. The length and width of the top face of the span can be used to compute fairly accurately the total

surface area of the span for hexagonal and square whiskers. In addition the thickness of the span must be measured independently for rectangular whiskers.

This method does not provide a perfect answer to the problem since with extended etching there is some attack through the epoxy at the epoxy-metal-solution interface at each end of the span. Also the Glyptal dissolves in alcohol, which limits this method of mounting to etching in water base solutions.

Etchants employed

Four etching reagents were employed in this investigation.

1. 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. This solution was prepared in the following proportions: 11 ml concentrated sulfuric acid (reagent grade), 10.8 gr of $\text{K}_2\text{S}_2\text{O}_8$ plus approximately 385 ml of double distilled water. A fresh solution was prepared about once a week. For the sake of brevity, this solution will be referred to in the text as the persulfate etch.
2. 4% picral (ethanol) by weight. Four gr of picric acid plus approximately 125 ml of absolute ethyl alcohol. This solution will be abbreviated 4% picral (e).
3. 4% picral (methanol) by weight. Four gr of picric acid plus approximately 120 ml of methyl alcohol. This solution will be abbreviated 4% picral (m).
4. 2% nital (ethanol) by volume. Two ml of concentrated nitric acid plus 98 ml of absolute ethyl alcohol.

During etching the slide was placed upside down in a small petri dish so that the whisker was positioned on the

underneath side. This permitted any corrosion products to settle to the bottom of the solution rather than accumulate on the whisker surface. The whiskers were less inclined to show stain using this method. Approximately 5 to 15 ml of solution were used. The solutions were changed frequently. After etching, the whiskers were rinsed in tap water, methyl alcohol, and finally dried in a blast of hot air.

Those whiskers mounted for iron analysis and potential measurements were rinsed in distilled water after etching and dried in an air blast.

Equipment for polarization measurements

The single electrode potential was recorded with time for several whiskers in a 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ solution. A saturated calomel half cell was employed with a saturated KNO_3 agar agar salt bridge. The potential of this electrode is 242 millivolts cathodic to the standard reversible hydrogen electrode. The recording circuit consists of a Curtiss-Wright electrometer model NA 100, having an internal resistance of greater than 10^{15} ohms and a Brown recording potentiometer. The solution was exposed to the atmosphere during the measurement of potential.

Analysis of iron content in solution

Whiskers mounted as in Figure 5 (bottom) were etched for a predetermined length of time in 20 ml. of the solution 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. The slide containing the whisker was

carefully washed with distilled water at the conclusion of the test and these washings returned to the solution for analysis.

A Coleman spectrophotometer has been used for the iron analysis. The method is based on the quantitative application of absorption spectra. The absorption is proportional to the number of molecules of the absorbing substance through which the light passes. If the absorbing substance is dissolved in a non absorbing medium, the absorption will then be proportional to the concentration, in this case, of iron in the solution.

The following procedure has been employed for iron in the solution of $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. The additions listed below are based on a final solution volume of 50 ml. In addition to the unknown, 20 ml of unused etching solution were also processed simultaneously as a blank.

- Add 10 ml of $NH_2OH \cdot HCl$, hydroxylamine-hydrochloride (prepared 10 gr to 100 cc of water) to each solution and heat for about 3 hr. This addition reduces the potassium persulfate present.
- After heating add $1/2$ ml of $NH_2OH \cdot HCl$.
- Then add 1 ml of tartaric acid to each solution.
- Several drops of nitrophenol are added as an indicator and the solution taken to yellow with concentrated NH_4OH and then brought back to clear with 1:1 HCl . When the solution has cleared, one additional drop of 1:1 HCl is added.
- Five ml of 1, 10 phenanthroline are then added. This addition gives the solution an orange color, which deepens as the amount of iron present in the solution increases.
- Distilled water is added to each sample until a total volume of 50 ml is reached.

The per cent light transmitted through the unknown is measured on the spectrophotometer against the blank which contains some iron as an impurity from the reagents used. Accompanying charts can be used to read the amount of iron dissolved during etching of the whisker by knowing the per cent of light transmitted, wave length 508μ .

Electron microscopy

The electron microscope was used initially to study the as-grown and etched surfaces. The difficulty in preparing replicas of such small samples, and the destruction of the whisker during the processing, made this method generally impractical.

Replicas for use in the electron microscope were prepared in one of the following two ways:

Collodion method. The whiskers were mounted by floating them on epoxy. The epoxy used here is Armstrong C-1 Resin with activator "A." After the epoxy was hard, successive layers of collodion were built up on the surface. The collodion film was then stripped off under water. This was followed by a carbon evaporation shadowed with platinum. The collodion layer was then dissolved, using amyl acetate, and the final carbon replicas were mounted for examination on copper grids.

Lucite method. The whisker was mounted directly in lucite. After polishing approximately one-half of the

whisker away lengthwise, the remaining portion was pulled from the lucite, leaving an imprint of the whisker surface. This was followed by a carbon evaporation shadowed with platinum. In both the collodion and lucite methods the stage was rotated during the carbon evaporation, in order to insure that all re-entrant angles were filled and a strong replica was produced. After evaporation, the lucite mount was dissolved in chloroform and the carbon replicas mounted on grids for examination.

An RCA electron microscope model 2B was used to examine the replicas.

Photomicrographs

All photomicrographs shown here were taken on a Bausch and Lomb Balphot metallograph. With a few exceptions 5" x 7" Kodak contrast process ortho film was employed.

III. RESULTS

Appearance of as-grown whiskers

Many whiskers with unusual shapes and as-grown surfaces have been observed and photographed. The discussion here, however, is limited mainly to those whiskers which were later etched. Their as-grown appearance will be discussed along with their response to etching.

Growth steps are a fairly common occurrence on whisker surfaces. Most whisker surfaces at 1000 X do not show such steps, although in several cases this phenomenon was found. Figure 6 shows an electron micrograph of an as-grown whisker at 20,000 X showing growth steps. This replica was prepared using the collodion method. The black band in the upper left hand corner is the intersection of two crystal faces. This edge appears to be composed of many closely spaced, well-defined growth steps. As the distance from the intersection of the faces increases, the growth steps become less pronounced until they fade out in the lower right hand corner of Figure 6. Growth steps are probably not present on all areas of a whisker face, but large patches of such steps are probably present on most whiskers if a high enough magnification could be used. Coleman (27) suggests that liquid halide is transported to the growth

Figure 6. Electron micrograph of as-grown whisker surface. 20,000 X

(-38-)

steps and reduced. Such steps could provide a method whereby whiskers could thicken after reaching their final length. Each step is probably composed of many small ledges, which can provide many sites for iron atoms to become a part of the growing lattice.

Determination of the preferred planes of
dissolution for the etch
1N H₂SO₄ + 0.2N K₂S₂O₈

In order for etch pits to be used to determine the reference plane and growth axis of a whisker fairly large, well-shaped etch pits must be formed. The angle of intersection of a pit face with the surface can be determined accurately only if the depth and width dimensions of the pit are accurately known. At 1000 X, which is the maximum feasible magnification for viewing the whiskers, pits should be of the order of several microns, both wide and deep, for the pit angles to be accurately measured. The schematic pit outlines shown in Figure 4 can be used to suggest the likely planes composing a pit. Such an approach can be used for pits too small to accurately measure the angle of intersection of a pit face with the reference surface.

Figure 7a shows the (100) face of a rectangular whisker etched for 1 1/2 min in 1N H₂SO₄ + 0.2N K₂S₂O₈. This etch will be referred to as the persulfate etch. Large clearly defined etch pits have been produced at as-grown dislocations. These pits resemble Figure 4d and on this basis

Figure 7. Etch pits at as-grown and deformation-produced dislocation.

{-1-} Rectangular whisker,
{100} face

- a. Etched for 1 1/2 min in
1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
- b. Deformed after the 1-1/2
min etch, then etched for
1 additional min. Total
etch 2-1/2 min in 1N H_2SO_4
+ 0.2N $K_2S_2O_8$. 1000 X

it would be concluded that these pits are bound by four (110) planes on the sides with the bottom face a (100) plane. Figure 7b shows a larger view of this whisker after 2 1/2 min etch. This whisker was deformed after the 1 1/2 min etch. The small pits in the background are etch pits produced at deformation dislocations. The subject of the deformation of whiskers will be discussed later in an independent section.

The angles of intersection between the surface and the pit faces were determined for its numbered 2, 3, 4, 5, 8, 9, and 10. Beside each pit are lines which indicate the faces of that pit which were measured. Angle measurements were not made after etching for 1 1/2 min. After etching for 2 1/2 min the traces of the pits with the surface were often not as clear. Attack along the edge of the whisker in some cases destroyed part of the pit faces and prevented angle measurements from being made on every face. The pit bottoms at 1 1/2 min all appear to be symmetrical. The pits are still etching symmetrically at 2 1/2 min although some pits on Figure 7b appear to be asymmetric because one or more of their sides has been partially etched away.

The tangent of the angle of intersection of a pit face with the surface is equal to the ratio of the pit depth divided by the distance from the edge of the pit trace to the bottom of the pit projected on the reference surface. This width dimension was measured on micrographs taken at

1000 X such as Figure 7b. Every pit had its bottom and trace in focus on at least one negative. This problem resulted since the whisker was no longer flat after it was deformed. Depth measurements from the reference surface to the base of the pit were made using the focusing knob on the metallograph. Because of the difficulty in determining exactly when the surface and the base of the pit were in focus, four depth measurements were made for each face and averaged. Depth measurements made in this manner often showed considerable variation from reading to reading. Therefore, it is thought that even with an average of four depth measurements there is likely to be considerable error in the determination of any given angle of intersection.

Since the etch pits are symmetrical, the angles of intersection of all the pit faces with the reference surface can be averaged in order to minimize the error in any one calculation. The average intersection angle for the seventeen faces indicated in Figure 7b was equal to approximately 43° with a spread from 39° to 48° .

The broad face of a rectangular whisker ideally is a (100) plane. Four (110) planes are each theoretically found at 45° to a (100) plane. The average angle of 43° calculated above is in good agreement. Based on this, it is concluded that on (100) faces the persulfate etch develops etch pits bound by four (110) planes with a bottom composed of a (100) plane.

Determination of growth direction from etch pits

If it is assumed that the 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ etch creates (110) planes, then the growth direction of the whisker can be determined from the etch pits. Again, it is reasoned from Figure 7b that if four (110) planes are each located at approximately 45° to a surface, that surface is a (100) plane. If the trace of a representative pit in Figure 7 is drawn in the center of a stereographic projection and the poles of the four (110) planes plotted at 45° along normals to the sides of this trace, then a [110] direction lies parallel to the growth axis of the whisker. Diagonals of the etch pits point in [110] directions. Normals to the trace of the pit point in [100] directions.

Once it has been established that the etch 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ preferentially creates pits bound by (110) planes, then whisker faces containing fairly small but well-shaped pits can be oriented by a visual examination of the pitted surface.

Immersion etching of undeformed iron whiskers in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$

Figure 8a shows an example of large well-shaped etch pits present on a (100) surface of a rectangular whisker after etching for 1 1/2 min. Pit angles were not measured in this case, but the pits are apparently again bound by four (110) faces with a (100) bottom. The rotation of these

Figure 8. Removal of whisker shell.
(-2-) Rectangular whisker, (100) face
a. Etched for 1 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
b. Same as a. except etched for 2 1/2 min

pits again indicates that the growth axis is approximately parallel to the [110] direction. Most of the surface at 1 1/2 min was composed of interlocking pits similar to those shown at the bottom of Figure 8a. The pits appear to etch to a uniform depth and then expand. As the pit sides move back they intersect neighboring pits and in many instances appear to etch away the common wall between them. The pit bottoms unit to form larger flat-bottomed areas.

This observation was verified by continued etching. Figure 8b shows an area of this whisker after 2 1/2 min. No individual pits are present. It is assumed that the pits continued to expand rapidly until the original surface was almost completely removed. A few remaining portions of the top layer can still be seen. Additional etching of this whisker is shown in Figures 9 and 10. Another area of this whisker, Figure 9a, still shows pieces of the outside layer of the whisker remaining after 2-3/4 min etching. After etching for 5 min most of the surface comprising the span portion of the whisker contained no remains of the outside layer.

This type of etching can occur only if the outside layer is of uniform thickness and in some manner dissimilar to the inside core of the whisker. It is concluded that whiskers can be composed of an outside shell region and an inside core region. Based on the pits in Figure 8a this shell is estimated to be about 2μ thick. Figure 10 shows the

a

b

Figure 9. Whisker core.
(-2-) continuation of Figure 8

- a. Etched for 3-3/4 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
b. Same as a. except etched for 5 min

a

b

Figure 10. Removal of whisker shell.
(-2) continuation of Figure 9

- a. Etched for 6-1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
b. Same as a. except etched for 7-1/2 min

progressive removal of the whisker shell and the formation of a surface composed of former pit bottoms. This portion of the whisker was fastened to the tape during etching.

No well-formed etch pits developed in the core region of the whisker. An examination of Figure 9a, however, shows many small black specks which are very likely etch pits formed at as-grown dislocations in the core. These pits are too small to determine if they show crystallographic shape.

The etch pits formed in the shell of whisker (-2-), Figures 8, 9, and 10, were well spaced and fairly large. The thickness of the shell is a major factor in determining the length of dislocation line and therefore the depth of an etch pit which can form in the shell.

On some whiskers the shell forms a very thin veneer as is shown in Figure 11, again a (100) face of a rectangular whisker. As-grown, the surface contained many black specks which could be either pits or raised projections. Etching for one minute produced many small pits, too small to determine their shape. The lower portion of Figure 11b shows the core already partially exposed. Another portion of this same face at one minute, Figure 11c, shows the shell completely removed. Figure 11d shows the same view as Figure 11b except after 2 1/2 min. A clear distinction can be seen between the etching which is characteristic of the shell and that of the core. Etch pits formed in the shell are small,

a

b

c

d

Figure 11. Removal of whisker shell.
 (11-) Rectangular whisker, (100) face

- a. As-grown. 1000 X
- b. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- c. Different view also after 1 min. 1000 X
- d. Same as b. except etched for 2-1/2 min

but well-defined. Dislocations in the core etch as very wide shallow pock-like pits.

The same type of behavior is shown in Figure 12. The etch pits are very small but well-contained in the shell, Figure 12a. No clearly resolvable pits appear to be present in the underlying core. Dislocations are probably still present but the pits are likely too shallow to be observed.

While the existence of a shell and a core is thought to be a common growth defect, the rate of removal of the shell during etching can vary greatly. Very small but well-contained pits can be seen in Figure 13a after etching for 1 min. These pits after 2 min are only slightly larger and growing very slowly.

Up to this point whiskers have been described in which fairly well-formed etch pits have been seen in the shell. Pits in the core were either very small or more commonly very wide shallow pocks. Pits with crystallographic shape can, however, form in the core and poorly shaped pits in the shell. Figure 14 b shows etch pits in the shell after etching for 2 1/2 min. A very high density of very small pits has formed along the edges. Larger pits have formed in the center of the face but these are more rounded in appearance and do not show definite crystallographic shape. Upon removal of this outer shell, pits showing crystallographic shape have etched in the core. These pits are correctly oriented for a [110] growth axis. After

Figure 12. Removal of whisker shell.
(-23-) Rectangular whisker, (100) face

- a. Etched for 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. Same as a. except etched for 1 min

a

b

Figure 13. Etch pits at as-grown dislocation in shell.
(-14-) Rectangular whisker, (100) face

- a. Etched 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
b. Same as a. except etched for 2 min

a

b

c

Figure 14. Removal of whisker shell.
(-13-) Rectangular whisker, (100) face

- a. As-grown. 1000 X
- b. Etched for 2 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- c. Same as b. except etched for 4 1/2 min

6 1/2 min, pits with large flat bottoms had formed. This suggests that this whisker was perhaps composed of two independent shell layers over the core.

Figure 15b shows etch pits in the shell which are very similar in appearance to those in Figure 14b. The pits are definitely round, shaped like a cone. It is felt that in both examples, an impurity has segregated along the dislocation line in an amount sufficient to produce a galvanic cell type of etching similar to a decorated dislocation.

For most whiskers the density of as-grown dislocations appears to be greater in the shell than in the core. Figure 16 shows an example of a higher etch pit density in the core than in the shell. Since there are very few dislocations present in the shell, Figure 16b, dissolution is nucleated at the edge and progressively moves inward, stripping away the shell. The exposure of the core, Figure 16c, shows a very high pit density present.

Another type of shell and core is shown in Figures 17 and 18 for a large rectangular whisker obtained from Wayman, abbreviated WW. This long whisker has been cut into several pieces. The first section was immersion etched. Figure 17b shows a representative view as-grown of the poorly defined side faces of this whisker. Coarse growth steps were often observed on these faces. The ratio of the width of the broad (100) face to the side face is 3.25, which is considerably larger than the ideal ratio of 1.4. In general

Figure 15. Etch pits at as-grown dislocations in shell.

(-21-) Rectangular whisker, (100) face

a. As-grown. 1000 X

b. Etched for 2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

a

b

c

Figure 16. Removal of whisker shell.
 (-9-) Rectangular whisker, (100) face
 a. As-grown. 1000 X
 b. Etched 2 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
 c. Same as b. except etched for 6 1/2 min 1000 X

Figure 17. Whisker shell
(-3-) WW. Rectangular whisker

- a. (100) face, as-grown. 200 X
- b. Side face as-grown. 200 X
- c (100) face etched for 1 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$.
(:). 1000 X

a

b

c

Figure 18. Etch pits at as-grown dislocations in core.
(-3-) continuation of Figure 17.

- a. Etched for 3 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. (:).
1000 X
- b. Same as a. except etched for 5 min (:)
- c. Same as a. except etched for 1 hr 35 min (:)

the rectangular whiskers were more plate-like than ideal.

The shell of this whisker is thin and composed of a very high pit density. After 3 min of etching this shell has been removed, and with continued etching, the dislocations etch as very wide shallow pits. The density of the pits decreases and the width of the individual pits increases with greater penetration into the whisker, Figure 18. The dislocation density is very high in the shell and then drops off progressively.

Several examples have been given so far of well-formed etch pits bound by (110) sides and a (100) bottom. In each case the whisker was rectangular and the face (100). The pits were found aligned correctly to suggest a [110] growth axis for the whiskers. Figures 19, 20, and 21 show examples of two rectangular whiskers which appear to have pits in the shell rotated in a [100] orientation. The pits formed in the shell of (-10-), Figure 19b, suggest a [100] orientation. The density of etch pits in the shell is not uniform, with the major portion being grouped in a patch. After etching for 4 1/2 min the shell has been removed in the area of high pit density, and small pits can be seen in the core. The large pits still present in the shell are definitely oriented in the [100] direction. Figure 20 b shows the etch pits in the core and a few remaining portions of the shell on the rightside. The thickness of this whisker was not measured as-grown. However, after etching for 11 1/2 min both width

a

b

Figure 19. Shell rotated with respect to core.
(-10-) Rectangular whisker, (100) face

a. As-grown. 1000 X

b. Etched for 1 min in 1N H₂SO₄ + 0.2N K₂S₂O₈. 1000 X

a

b

Figure 20. Shell rotated with respect to core.
(-10-) continuation of Figure 19

- a. Etched for 4 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$.
1000 X
- b. Same as a. except etched for 11 1/2 min

Figure 21. Shell rotated with respect to core.
 (-15-) Rectangular whisker, (100) face

- a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. Etched for 2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. Shows section of whisker on the tape. 1000 X
- c. Same as b. except showing a portion of the span after 2 min of etching

and thickness were measured and the (100) face was approximately twice the thickness.

A similar rotation of the shell is shown in Figure 21. Figure 21b shows a portion of this whisker fastened to the tape while Figure 21c shows a view of the span. The portion on the tape still contains some of the remaining shell. The pits in the shell suggest a [100] orientation. Careful examination of Figure 21c, which shows only the core, reveals pits in the [110] orientation.

The core of the whisker determines its cross section. Both rectangular whiskers just described probably have cores oriented in the [110] direction. The shell surrounding this core on most whiskers probably has the same orientation as the core. Two examples have been shown, however, where the shell on rectangular whiskers was a (100) plane, but rotated 45° to the [100] orientation.

Not every whisker has a shell and core. Figure 22 shows two very thin plate-like whiskers which appear to have as-grown dislocations extending entirely through the whisker, perpendicular to the broad face. After etching for one minute pits had etched through whisker (-4-). One large pit etched through whisker (-6-) after etching 5 min. Assuming (110) dissolution planes in the pit, the thickness of the plate shown in Figure 22b is about 3μ . Adjacent to the pits which etched through are many pits with wide bottoms suggesting a shell and core in this portion.

a

b

Figure 22. As-grown dislocations penetrate whisker.
 (-4-) Rectangular plate-like whisker, (100) face

- a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 200 X
 b. Same as a. except at 1000 X. (:))

(6-) Rectangular plate-like whisker, (100) face

- c. Etched for 5 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. (:))
 1000 X

Rectangular whiskers possess the widest surface based on the cross sectional area. The original surface can, therefore, be examined for a longer time during etching before it is destroyed by the formation of new planes nucleated along the edges.

Etching of square and hexagonal whiskers.--The (100) face of a [100] whisker is shown in Figure 23. In Figure 23a, small but well-contained pits have formed in the shell. With increased etching the shell was etched away and pock-like surface developed in the core along with the same smaller pits.

The square whisker in Figure 24 shows as-grown surface defects in the form of lines approximately parallel with the axis. They were found to etch selectively in the form of ridges. Figures 24b and 25a show the progressive removal of the shell layer. The (100) face characteristic of the core is shown down the middle of Figure 25b. Many small shallow pock-like pits have formed. Along either side, planes have etched at a low angle to the (100) surface.

A three micron square whisker is shown in Figure 26a after etching of 1 min. A high dislocation density is revealed by the large number of small etch pits. Etching for an additional 1/2 min caused this whisker to thin to slightly over one micron. The same type of pitting was still present.

Figure 23. Removal of whisker shell.
(-7-) Square whisker

- a. Etched for 2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. (:). 1000X
- b. Same as a. except etched for 6 min
- c. Bent after etching for 6 min (:). 1000 X

a

b

Figure 24. Removal of whisker shell.
(-8-) WW. Square whisker

- a. As-grown. 500 X
- b. Etched in 1N H₂SO₄ + 0.2N K₂S₂O₈ for 1/2 min. (:).
1000 X

a

b

Figure 25. Removal of whisker shell
(-8-) continuation of Figure 24

- a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
b. Same as a. except etched for 25 min

Figure 26. Etch pits at as-grown dislocations
(-16-) Square whisker

a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

(-17-) Hexagonal whisker

b. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

Figure 27. Etch pits at as-grown dislocations.
(-22-) Hexagonal whisker

- a. Etched for 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
b. Same as a. except etched for 1 min

Figure 28. Removal of whisker shell.
(-18-) Hexagonal whisker with approximately 150μ (110) face
a. As-grown. 1000 X
b. Etched for $1/2$ min in $1N H_2SO_4 + 0.2N K_2S_2O_8$. 1000 X
c. Same as b. except etched for 14 min

Figure 29. Removal of whisker shell.
(-19-) Hexagonal whisker

- a. As-grown. 1000 X
- b. Etched for 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- c. Same as b. except etched for 5 min
- d. Same as b. except etched for 14 min

Figures 26b, 27a, and 27b show small hexagonal whiskers etched in the persulfate solution. Etch pits formed in both hexagonal whiskers but were too small to determine the shape.

Growth steps visible at 1000 X are shown in Figure 28a on a (110) face of a hexagonal whisker. The hexagonal whiskers are assumed to be bound by (110) rather than (211) planes. Etching revealed a very high dislocation shell, Figure 28b, which etched away, leaving a surface which appears to be free of etch pits. A similarly smooth surface resulted after etching hexagonal whisker (-19-), Figure 29. The as-grown surface contained many black specks along with numerous growth ridges. Etching removed these layers and produced a surface, Figure 29c, with only the slightest suggestion of very shallow pits present. Continued etching produced new planes at a slight angle to the original (110) surface. Figure 29d shows that well-contained etch pits were formed farther down into the whisker.

Immersion etching of deformed whiskers
in 1N H₂SO₄ + 0.2N K₂S₂O₈.

All of the whiskers which are described in this section were bent sometimes during the etching. Generally the characteristics previously found for the as-grown dislocations apply to the as-grown dislocations in these whiskers as well.

Rectangular whiskers.--Rectangular whisker (-1-) is shown in Figure 7. Angle measurements on the pits at as-grown dislocation sites of this whisker were used to calculate the preferred dissolution planes of the etch $1N H_2SO_4 + 0.2N K_2S_2O_8$. After etching for 1 1/2 min this whisker was deformed by loosening one end from the tape and bending it in an arc. The whisker was then straightened as well as possible and fastened again to the tape. All the whiskers were bent so that the radius of the arc made by the deformed whisker was approximately perpendicular to the surface being examined. Figure 7b shows this whisker after etching for 1 min following deformation. The small pits in the background have etched at the clean newly-formed deformation dislocations. On this particular whisker, as-grown and deformation dislocations can be easily distinguished by the size of the etch pits. Figure 30 shows views of the end of the whisker which remained on the tape during deformation. This portion was not deformed and no small etch pits were formed in the background.

During etching both as-grown and deformation dislocations grew in size. When the pits at as-grown dislocations reached the bottom of the shell, a large flat bottom developed as the sides moved out. The expansion of the bottom of pit number four can be seen in Figures 7a, 7b, and 31a. The group of pits labeled number six in Figure 7 appear as a continuous flat bottom in Figure 31c.

Figure 30. Etch pits at as-grown dislocations in shell.

(-1-) Rectangular whisker, (100) face, continuation of Figure 7

- a. Etched for 2 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. This portion of the whisker was not deformed after 1-1/2 min etch. 1000 X
- b. Same as a. except etched for 3-3/4 min

a

b

6

c

Figure 31. Etch pits at as-grown and deformation produced dislocations.

(1-) continuation of Figure 30

- a. Etched 3 min in $1N H_2SO_4 + 0.2N K_2S_2O_8$. 1000 X
- b. Same as a. except etched $3-3/4$ min
- c. Same as a. except etched $6-1/2$ min

Figure 32. Etch pits at as-grown and deformation produced dislocations.
(-1-) continuation of Figure 31

- a. Etched for 3-3/4 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$.
1000 X
- b. Same as a. except etched for 5 min
- c. Same as a. except etched for 6-1/2 min

There is no evidence to suggest that the as-grown dislocations moved during deformation. Impurity atoms segregated along the as-grown dislocations pin these dislocations and prevent them from moving under a stress sufficient to cause the movement of clean dislocations.

The etching sequence of deformation-produced dislocations is shown in Figure 32. After 3-3/4 min, the pits at deformation dislocations appear also to have formed flat-bottomed pits which, upon additional etching, interlock and remove any suggestion of individual pits. Perhaps dislocation loops were nucleated at the surface and do not extend to a greater depth.

Etch pits at deformation dislocations were very similar to those at the as-grown dislocations. The as-grown dislocations were much larger, but this is probably because of a longer dislocation line. Both types of dislocations formed well-contained pits rather than large shallow pocks.

The etching of a plate-like whisker is shown in the sequence Figures 33, 34, 35, and 36. This whisker was etched for nine minutes before it was deformed. Pits with crystallographic shape were formed in the shell. Figure 34 shows that these pits soon etched to the shell-core interface and formed flat-bottomed pits. A large flat-bottomed area developed by the interlocking of these pits.

After removal of the shell, the pits formed at as-grown dislocations in the core were large shallow pocks,

Figure 33. Removal of whisker shell
(-5-) Rectangular plate-like whisker, (100) face
a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 200 X
b. Same as a. except etched 2 min
c. Same as a. except etched 7 min

a

b

Figure 34. Removal of whisker shell
(-5-) continuation of Figure 33

- a. Etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
b. Same as a. except etched² for 2 min

a

b

Figure 35. Removal of whisker shell
(-5-) continuation of Figure 34

- a. Etched for 9 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. Another view after 9 min etching showing a remaining patch of well-defined pits. 1000 X

a

b

Figure 36. Etch pits at as-grown and deformation produced dislocations.

(-5-) continuation of Figure 35

Etched 9 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$, then deformed

- a. Etched for 1 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$ following bending. Total etching time 10 min. (··). 1000 X
- b. Same as a. except etched for 8 min following bending. (:)

totally different from the pits with crystallographic shape produced in the shell, see Figures 33c and 35a. After etching for 9 min the shell was completely stripped off except for a small patch of pits shown in Figure 35b.

This whisker was then deformed by bending it in a manner similar to that previously described. No slip lines were visible after deformation. Figure 36 shows the deformed surface after additional etching. The deformation dislocations etched as very small shallow pocks. It is interesting that in this case also, excluding the size of the pits, the as-grown and deformation dislocations produce similarly shaped etch pits. When the pits of as-grown dislocations are shallow without crystallographic shape, it is found that the pits at deformation dislocations are also shallow pock-like pits.

Another fairly similar example is shown in Figures 37 and 38 for rectangular whisker (-12-). An unusual growth band appeared on the as-grown surface. This band contained a high dislocation density as shown by the large number of etch pits after a 1 min etch. This band was apparently located entirely in the shell since with continued etching this defect was removed, leaving a smooth core. The etch pits produced at as-grown dislocations in the core are so wide and shallow that they are barely visible, Figure 38a.

This whisker was then deformed and etched for an additional 5 min, Figure 38b. The etch pits formed at the

Figure 37. Removal of whisker shell.
 (-12-) Rectangular whisker, (100) face

- a. As-grown. 1000 X
- b. Etched 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- c. Same as b. except etched for 2-1/2 min

Figure 38. Etch pits at as-grown and deformation produced dislocations in core
(-12-) continuation of Figure 37

- a. Etched for 6-1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$.
1000 X
- b. Deformed after 6-1/2 min and etched for 5 additional min. Total etch 11-1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$.
1000 X

Figure 39. Removal of the shell for a deformed whisker.

(-3-) WW. Rectangular whisker, (100) face

The section of whisker (-3-) shown here was deformed before etching.

- a. As-grown, after bending. 1000 X
- b. Etched for 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- c. Same as b. except etched for 2 min
- d. Same as b. except etched for 15 min. (:))

deformation-produced dislocations are slightly better defined than the pits at as-grown dislocations. At best the pits are very shallow, however.

The final illustration of the deformation of a rectangular whisker is shown in Figure 39. This is another section of whisker (-3-) which was shown undeformed in Figures 17 and 18. Slip bands were present along two orientations prior to etching. The shell then consisted of an exceedingly high dislocation density which produced an almost unresolvable mass of etch pits in the shell. After the shell was removed, a mixture of large and small shallow pocks were present, representing pits at as-grown and deformation-produced dislocations.

Hexagonal whiskers.--It should be recalled that the persulfate etch produces etch pits on the (110) plane of undeformed hexagonal whiskers but these pits were never as clearly defined as those produced on square and rectangular whiskers. Two hexagonal whiskers have been deformed at some stage during etching in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. Whisker (-24-), Figure 40, was etched for 1-1/2 min prior to deformation. By this time the shell was removed and as-grown dislocations in the core appeared as very shallow etch pits. Etch pits at deformation produced dislocations can be seen in Figure 40c. The surface shown in Figure 40d is a face at

a

b

c

d

Figure 40. Removal of whisker shell.
(-24-) Hexagonal whisker

- a. Etched for 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
- b. Same as a. except etched 1 1/2 min. Deformed after etching for 1-1/2 min
- c. Etched 1 min after deformation. Total time 2-1/2 min in 1 N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
- d. Same as c. except etched 4 min after deformation. Total etching time 5 min

Figure 41. Etch pits at as-grown dislocations in shell.

(-20-) Hexagonal whisker with approximately 100 μ wide (110) face

a. As-grown. 1000 X

b. Etched for 1/2 min in 1N H₂SO₄ + 0.2N K₂S₂O₈. (:). 1000 X

Figure 42. Etch pits at as-grown and deformation-produced dislocations in core.
(-20-) continuation of Figure 41

- a. Etched 4 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. (:). 1000 X
Deformed after 4 min etching
- b. Etched 1 min following deformation. Total etch
5 min. (:). 1000 X
- c. Etched for 10 min following deformation. Total
etching time 14 min. (:). 1000 X

Figure 43. Etch pits at as-grown and deformation-produced dislocations in core.
(-20-) continuation of Figure 42

- a. Etched for 16 min following deformation of whisker. Total etching time in 1 N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ 20 min. (:). 1000 X
- b. Etched for 21 min following deformation. Total etching time 25 min. (:). 1000 X

a low angle to the (110) face and is characteristic of smaller pits which are better contained.

A more convincing example of this is shown in Figures 41, 42, and 43. Small well-contained pits were formed in the shell. When the shell was removed, the surface appeared very smooth except for a few large pits adjacent to the span section at one end, Figure 42a. Deformation and subsequent etching produced a mass of pock-shaped pits at deformation dislocations, Figure 42b. As-grown dislocations were probably present in this region as well, but the deformation-produced dislocations probably have a longer dislocation line and tend to produce more visible etch pits. After etching for 10 min following deformation, Figure 42c, the central portion of the face still contained pock-like pits. The pit bottoms are asymmetric, indicating that the dislocation lines are not perpendicular to the surface. Deeper down within the whisker, pits with crystallographic shape were again formed, Figures 43a and 43b. The reference surface is now at a low angle to the original (110) orientation. The pits are again decidedly asymmetric. Certain regions within the whisker apparently favor the formation of pits with crystallographic shape, while in others round pock-like pits are formed. Deformation dislocations are etching in both regions. The smaller better-contained pits were produced on the low angle faces and not on the (110) face of the core.

Variations in the type of etch pits produced from whisker to whisker and with depth within a given whisker can be explained in part by assuming changes in concentration of an internal poison located within the whisker. However, for a given poison content it appears that the poison is less effective in containing pits occurring on the (110) face of hexagonal whiskers when etched in $1N H_2SO_4 + 0.2N K_2S_2O_8$. Figure 42 c shows large pock-like pits on the center surface which has a (110) orientation. Along the left side of this micrograph is a region showing a face at a low angle to the (110) face. The pits on this face are well-contained. These pits, however, are much smaller than those found on low angle faces farther down within the whisker.

Determination of the dissolution rate
of whiskers in a solution
 $1N H_2SO_4 + 0.2N K_2S_2O_8$

The gross change in cross sectional shape during etching provides an indication of the corrosion rate. The analysis of the solution for iron following etching provides another method. Both methods have been applied to sections of whiskers (-3-) and (-8-) supplied by Wayman. The etching of other sections of these same two whiskers has already been discussed in Figures 17, 18, 24, and 25.

Change in cross sectional shape.--The cross sectional shape of the as-grown whiskers was estimated either by cross sectioning the whisker or by measuring the width of the faces.

Figure 44. Etched cross sections of whiskers.
 (-3-) WW. Rectangular whisker

- a. Cross sections as-grown and then etched for 1 hr 20 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 200 X. Dark field
- b. Another piece of the same whisker that was etched for 1 hr 40 min before cross sectioning and then 20 min following cross sectioning. 200 X

The very light line in a. marks the as-grown cross section.

Figure 45. Etched cross section of whiskers
(-8-) WW. Square whisker

Etched for 25 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$, then
cross sectioned and etched for an additional 15 min.
1000X

After the cross section was measured, either the same section or an adjacent segment of the whisker was etched, and the etched whisker then cross sectioned. The change in shape of the cross section during etching was used to determine the corrosion rate.

A comparison of Figures 44a and 44 b reveals that approximately 32.5μ was removed perpendicular to each broad (100) face in 1 hr 40 min. This corresponds to a rate of penetration of $0.33\mu/\text{minute}$. Applying Faraday's law, it was found that this corresponds to a corrosion current density of approximately $15 \text{ ma}/\text{cm}^2$.

In a similar manner Figures 24a and 45 show that approximately 7.5μ was removed from each (100) face of square whisker (-8-) in 25 min. This corresponds to a corrosion rate of $14 \text{ ma}/\text{cm}^2$. The dimensions in each case are made from the center of the face so that the rate on a (100) rather than a low angle face to a (100) plane is measured.

It was found that when a whisker cross section is etched, a deep trough invariably follows the outline of the whisker-lucite interface. This behavior has also been observed on cross sections of hexagonal whiskers etched in 2% nital. When an as-grown whisker is cross sectioned and then etched, perhaps the shell layers dissolve preferentially, causing the initial attack to be restricted to the surface of the whisker. When a previously etched whisker is cross sectioned, perhaps this outer layer is again favored because

of previous etching of the surface. Another possible explanation for the trough is crevice corrosion. This behavior was not observed on the cross section of a 240 μ iron wire etched in the same manner, however.

Based on Figure 3, a corrosion rate of 15 ma/cm² on a (100) face corresponds to a corrosion potential, E'_{Corr} , of -164 mv SHE or -406 mv SCE. The measurement of the single electrode potential of an iron whisker corroding in 1N H₂SO₄ + 0.2N K₂S₂O₈ should indicate how close the dissolution rate of the whiskers agrees with the results found for large iron single crystals. As a check, the iron content of the solution was determined after etching.

Figure 46 shows the potential time graphs for both rectangular whisker (-3-) and square whisker (-8-). These whiskers were mounted as shown in Figure 5 (bottom). Whisker (-3-) reached a steady state potential of about -411 mv SCE (-169 mv SHE) which corresponds to a corrosion rate of 12ma/cm², Figure 3. In like manner, the square whisker (-8-) reached a steady state potential of -407 mv SCE (-165 mv SHE) corresponding to a corrosion rate of 14.5 ma/cm².

The rate calculated from the change in cross section perpendicular to a (100) face agrees very well with the corrosion rate corresponding to the measured potential as determined from Engell's graph. These two whiskers have a corrosion rate very similar to that found for large bulk iron single crystals. It should be noted, however, that the

a

b

30, 40, 50 correspond to -300, -400, -500 millivolts active to the saturated calomel electrode (SCE).

Figure 46. Potential time traces in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$.

a. Rectangular whisker (-3-)

b. Square whisker (-8-)

The initial instability in b. resulted from a loose connection in the measuring circuit.

etch pits were very shallow on both of these whiskers. The calculation of corrosion rate in this manner cannot be applied directly to a surface containing large well-shaped pits, such as Figure 7.

Iron analysis.--The two solutions described in Figure 46 were analyzed for their iron content after the measurement of potential. Based on the iron analysis, rectangular whisker (-3-) had a corrosion rate of 21 ma/cm^2 and square whisker (-8-) a corrosion rate of 39 ma/cm^2 . A somewhat higher dissolution rate was expected because the dissolution of the corners creates higher order planes which dissolve at a faster rate. In the case of the rectangular whisker the poorly defined side planes probably dissolve at a higher rate. The initial dissolution rate during the removal of the shell might also be faster than the rate of penetration in the core. Some error in the measurement of surface area might also have occurred. Even taking the above possibilities into account, the dissolution rate calculated from the iron content in solution is higher than expected, especially the 39 ma/cm^2 calculated for square whisker (-8-).

Immersion etching of iron whiskers in
4% picral and 2% nital

The solutions used were:

4% picral (e). Ethyl alcohol used.
4% picral (m). Methyl alcohol used.
2% nital. Ethyl alcohol used.

Figure 47 shows examples of very small pits formed on

Figure 47. Etch pits at as-grown dislocations in shell.

(-33-) Hexagonal whisker

a. Etched for 45 min in 4% picral (e). 500 X

(-36-) Square whisker

b. Etched for 3 hr in 4% picral (e). 500 X

Figure 48. Etch pits at as-grown dislocations in shell.

(-39-)

Electron micrograph of hexagonal whisker showing etch pits formed after 20 min in 4% picral (●). 5300 X

Figure 49. Etch pits at as-grown dislocations in shell.
(-40-)

Electron micrograph of hexagonal whisker showing etch pits formed after 20 min in 4% picral (e).
5300 X

Figure 50. Etch pits at as-grown dislocations in shell.

(-29-) Rectangular whisker

a. As-grown. 1000 X

b. Etched for 5 min in 4% picral (m). 1000 X

a hexagonal and a square whisker when etched in 4% picral (e). It is not known whether the large black spots on Figure 47b are also etch pits or perhaps a stain. It is assumed in both of these whiskers that the pits have etched in the shell and that no core has been exposed. Figures 48 and 49 show two electron micrographs of very small etch pits present after 20 min in 4% picral (e). The dislocation density is quite high in both cases, but does vary markedly between the two. The pits are small, but round and well-contained. It is assumed that the pits have etched in the shell and that the shell is probably thin, which does not provide sufficiently long dislocation lines to create larger pits.

Figure 50 shows small etch pits on a rectangular whisker, (100) face, when etched for 5 min in 4% picral (m). The pits are not clearly enough defined to provide an indication of the preferred planes of dissolution.

Figure 51a shows a square whisker etched for 2 min in 2% nital. The center white band is all that remains of the (100) face. The formation of (110) planes has removed the corners and almost consumed the original face. Figure 51b shows etch pits on a (100) face of a rectangular whisker.

The formation of etch pits on a (100) face with 4% picral (e), Figure 47b, does not usually occur. Most very small whiskers show very little or no indication of any attack when etched in 4% picral (e). Figure 52a shows a

Figure 51. Etch pits on undeformed whisker
(-30-) Square whisker
a. Etched for 2 min in 2% nital. 1000 X
(-31-) Rectangular whisker, (100) face
b. Etched for 2 min in 2% nital. 1000 X

Figure 52. Etch pits on undeformed whisker.
(-37-) Square whisker

- a. Etched for 3 hr in 4% picral (e). No pitting produced. 500 X
- b. Etched for 3 hr in 4% picral (e) followed by 1 min etch in 2% nital. 500 X

Figure 53. Etch pits on undeformed whisker.
(-35-) Square whisker

- a. Etched for 2 hr in 4% picral (e) which produced no pitting. The growth spirals were present as-grown. 500 X
- b. Etched for 2 hr in 4% picral (e) followed by 1 min etch in 2% nital (e). 500 X

Figure 54. Etch pits on undeformed whisker.
(-34-) Square whisker

- a. Etched for 1-1/2 hr in 4% picral (e) which produced no pitting. This view is after 1 min in 2% nital following the 4% picral (e) etch. 500 X
- b. Etched for 1-1/2 hr in 4% picral (e) followed by a 2-1/2 min etch in 2% nital (e). 500 X

Figure 55. Etch pits on undeformed whisker.
(-32-) Rectangular whisker, (100) face

- a. Etched for 12 min in 4% picral (e) followed by 10 min in 4% picral (m). 1000 X
- b. Etched as stated in part a. followed by an etch of 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

square whisker after 3 hr in 4% picral (e). The growth spirals on Figure 53a were present as-grown and appear to have remained intact after etching in 4% picral (e). Some slight dissolution of the whisker is undoubtedly occurring but no pits are formed. Dislocations were, however, present because etch pits were produced when these whiskers were etched for a short period in 2% nital, Figures 52, 53, and 54.

Immersion etching of iron whiskers
Immersion etching of iron whiskers
in 4% picral (e), 4% picral (m), 08
2% nital, and 1N H₂SO₄ + 0.2N K₂S₂O₈—

It was found in the last section that a 4% picral (e) solution was usually ineffective in forming pits at as-grown dislocations on (100) faces of iron whiskers. Figure 55 shows a rectangular whisker where no pits were formed after exposure to both 4% picral (e) and 4% picral (m), but a high as-grown dislocation density was revealed by a subsequent 1 min etch in 1N H₂SO₄ + 0.2N K₂S₂O₈. It appears that the dissolution rate of 4% picral is so low that planes of dissolution are not favored that would produce etch pits at as-grown dislocations on (100) faces.

A 4% picral (m) solution was found to produce pits with crystallographic shape on certain hexagonal whiskers, Figure 56b and 56c. The pit faces intersect along a line running down the center of the pits.

Figure 4f suggests that these pits might be formed ideally by the intersection of two (100) faces. Theoretically

a

b

c

d

Figure 56. Etch pits on shell of undeformed whisker.
 (-26-) Hexagonal whisker

- a. As-grown. 1000 X
- b. Etched for 4 min in 4% picral (m). 1000 X
- c. Etched for 5 min in 4% picral (m). 1000 X
- d. Etched for 30 min in 4% picral (m). 1000 X

a

b

c

Figure 57. Removal of whisker shell.
(-26-) continuation of Figure 56

- a. Etched for 45 min in 4% picral (m). 1000 X
- b. Etched for 45 min in 4% picral (m) followed by 1-1/2 min etch in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X
- c. Etched for 45 min in 4% picral (m) followed by 5 min etch in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X

Figure 58. Etch pits in shell of undeformed whisker.
 (-27-) Hexagonal whisker

- a. As-grown. 1000 X
- b. Etched for 2 min in 2% nital. 1000 X
- c. Etched for 4 min in 2% nital. 1000 X
- d. Etched for 10 min in 2% nital. 1000 X

Figure 59. Etch pits in shell of undeformed whisker.
 (-27-) continuation of Figure 58

- a. Etched for 10 min in 2% nital followed by 1/2 min etch in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. 10 min in 2% nital, 1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ followed by 2 min etch in 2% nital. 1000 X
- c. Following the etching described in b. this whisker was etched for 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

two (100) planes are each located at 45° from a (110) surface. No pits were found that were deep enough to measure this angle of intersection, however. The line of intersection at the base of the pits should make an angle of 54.7° with the [111] growth axis if the pit faces are (100) planes. The agreement is found to be reasonably close. Therefore, base on these observations, it has been assumed that a 4% picral (m) solution favors pits bound by (100) planes. This hexagonal whisker is bound by (110) rather than (211) planes since a (211) stereographic projection shows no poles of low index faces properly aligned to produce the pits shown in Figure 56.

Figures 56 and 57 show the progressive etching of a hexagonal whisker in 4% picral (m). After etching for 45 min the surface showed considerable background etching, Figure 57a, which may or may not be individual dislocation sites. The shell showed no sign of being removed. However, when this whisker was subsequently etched for 1-1/2 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ the shell was completely removed. The core was very smooth with only a faint suggestion of very wide shallow pits. However, continued etching in the persulfate etch again resulted in the formation of well-contained etch pits. These small pits again occurred after two low angle faces removed the original face with a (110) orientation.

Figure 58b and 58c suggest that 2% nitral solution also favors the formation of pits with (100) faces. The pits again appeared to be bound by two faces intersecting along a

straight line at the base of the pit and oriented similarly to those formed in 4% picral (m). The dissolution rate in 2% nital is somewhat greater than in 4% picral, however, based on the etching time required to form the pits.

The surface of this whisker, Figure 58a, was tarnished, as-grown. Etching in the 2% nital solution removed this layer and produced etch pits with crystallographic shape. After 10 min the surface was one mass of pits and background etching, Figure 58d. A 1/2 min etch in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ removed most of the shell layer and left the surface reasonably smooth. This whisker was then re-etched in 2% nital to determine the etching behavior of the nital on the whisker core. Figure 59b shows that many small very shallow pits were produced in the same core that showed only a faint suggestion of pits in the persulfate etch. This was verified by placing this whisker back in the 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ solution. All the tiny pits disappeared again.

A similar example is shown in Figures 60 and 61. The pits produced in the shell with the 2% nital are too small and close together to determine whether they have crystallographic shape. The severely etched shell resulting from 10 min in 2% nital was removed by a 1/2 min etch in the persulfate solution. Neither the 4% picral or 2% nital solutions appeared to have a sufficiently high dissolution rate to remove the shell. Figure 61b again shows that the

Figure 60. Etch pits in shell of undeformed whisker.
(-28) Hexagonal whisker

- a. As-grown. 1000 X
- b. Etched for 2 min in 2% nital. 1000 X
- c. Etched for 10 min in 2% nital. 1000 X

Figure 61. Etch pits in core of undeformed whisker.
(-28-) continuation of Figure 60

- a. 10 min etch in 2% nital followed by 1/2 min etch in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. Etched as stated in a. followed by 2 min in 2% nital. 1000 X
- c. Etched as stated in a. and b. followed by 1 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

2% nital solution reveals the as-grown dislocations in the core which were not shown by the persulfate etch.

The etching characteristics of 4% picral (m), 2% nital, and 1N H₂SO₄ + 0.2N K₂S₂O₈ are summarized in the etching of the hexagonal whisker shown in Figures 62, 63, and 64. The whisker was etched initially in 4% picral (m). Very small but well-contained pits were produced in the shell. After etching for 45 min, Figure 62c, there was still no indication that the shell was being removed. A 1-1/2 min etch in the persulfate solution completely removed the shell, however. After etching for 5 min in the persulfate the relatively smooth middle section shown in Figure 63a was produced. This core was then etched in 4% picral (m) for an additional 4 min which produced no pits. Many as-grown dislocations present in the core were revealed, however, with a short etch in 2% nital. Again a light etch in 1N H₂SO₄ + 0.2N K₂S₂O₈ removed these pits. Some etch pits were present, however, on the side faces at a low angle to (110).

It should not be inferred that every whisker has as-grown dislocations intersecting the surface and that these pits will invariably etch in one of the four etches just described. One 2.5μ square whisker was etched for 12 min in 4% picral (e), 10 min in 4% picral (m), and then 10 min in 1N H₂SO₄ + 0.2N K₂S₂O₈. No etch pits and very little attack of any type was observed. Probably no dislocations

Figure 62. Removal of whisker shell.
 (-25-) Hexagonal whisker

- a. As-grown. 1000 X
- b. Etched for 4 min in 4% picral (m). 1000 X
- c. Etched for 45 min in 4% picral (m). 1000 X
- d. Etched for 45 min in 4% picral (m) plus 1-1/2 min
 in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X

Figure 63. Etching of whisker core.
(-25-) continuation of Figure 62

- a. Etched for 45 min in 4% picral (m) and then 5 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$. 1000 X
- b. Following the etch for 45 min in 4% picral (m) and 5 min in 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$, the whisker was etched for an additional 4 min in 4% picral (m). 1000 X

Figure 64. Etching of whisker core.
(-25-) continuation of Figure 63

- a. Etched for 45 min in 4% picral (m), 5 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$, 4 min in 4% picral (m), and finally 3 min in 2% nital. 1000 X
- b. Same as a. except following the 3 min etch in 2% nital, the whisker was etched for an additional 1/2 min in 1N H_2SO_4 + 0.2N $K_2S_2O_8$. 1000 X

intersected the surface of this whisker which was observed. This, of course, does not preclude the intersection of an occasional dislocation with the other faces of the whisker, nor even the possible existence of a less perfect core surrounded by a highly perfect shell.

IV. SUMMARY OF RESULTS

The following list of conclusions is a summary of the important observations presented in the section on Discussion of Results.

1. Growth steps on the as-grown whisker suggest a mechanism for whisker thickening.
2. Etch pits large enough to measure the angles between the pit faces and the whisker face were found on one rectangular whisker when etched in a 1N H_2SO_4 + 0.2N $K_2S_2O_8$ solution. This etch produces pits on (100) faces bound by four (110) sides and having (100) bottom.
3. Etch pits were used successfully to determine the growth axis of the whisker.
4. Almost all whiskers contain a distinct shell and core region.
5. The thickness of the shell is a major factor in determining the depth of an etch pit which can form in the shell.
6. Etch pits at as-grown dislocations in the shell are symmetrical.
7. As-grown dislocations intersect normal to the low index faces of the whiskers and appear to remain perpendicular to the surface, at least to the depth of the shell-core interface.
8. On most whiskers the shell forms only a thin veneer over the core, often less than 1μ . Several rectangular whiskers were found, however, which apparently had a shell several microns thick.
9. The shell and core can usually be distinguished by the difference in the appearance of the etch pits at dislocations in both regions.

10. The dislocation density based on the number of pits was usually greater in the shell. Occasionally whiskers were found with a higher dislocation density in the core.
11. The shell and the core are probably the same orientation for most whiskers. Etch pits on two rectangular whiskers suggest that the shell was a (100) plane rotated 45° to the [100] orientation.
12. Two plate-like whiskers several microns thick had as-grown dislocations extending completely through the whisker perpendicular to the surface.
13. The etch $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ usually formed well-contained pits in the shell and large pock-like pits in the core. However, whiskers with better-defined pits in the core were found, and in some cases fairly well-defined pits were found in both layers.
14. The $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ etch usually produced better-formed etch pits in the shell of square and rectangular whiskers than on hexagonal whiskers.
15. The core of hexagonal whiskers was usually smoother than the core of rectangular and square whiskers when etched in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. Etch pits at as-grown dislocations in the core were sometimes so shallow that the surface took on a polished appearance.
16. When the core of a hexagonal whisker was etched in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$, well-contained etch pits usually formed on the faces at a low angle to the (110) plane rather than on the (110) plane itself.
17. Clean dislocations resulting from deformation usually produced etch pits similar to those at as-grown dislocations. If the as-grown dislocations etched as well-defined pits, it was usually found that deformation dislocations were also well contained. Similarly a region that produced shallow pocks at as-grown dislocations usually produced round shallow pits at deformation dislocations as well. Since the length of the dislocation line of deformation dislocations can be longer or shorter than that of as-grown dislocations in the same layer, the size of the pits at as-grown and deformation dislocations under the same etching conditions is often different.
18. Etch pits at clean dislocations resulting from deformations were found to be asymmetric whenever the pits were large enough to determine their shape.

19. The rate of dissolution of the (100) face for two large iron whiskers etched in $1N\ H_2SO_4 + 0.2\ K_2S_2O_8$ was found to be approximately equal to that previously found for alpha iron single crystals, which had an analysis similar to mild steel. This etch created a rate of penetration of about $0.33\mu/min$ perpendicular to the (100) face of two large whiskers calculated from the reduction in thickness of the whiskers during etching. The etch pits formed on these whiskers were shallow so that the surface was relatively level. The calculation of corrosion rate in this manner cannot be applied directly to a surface containing large well-shaped pits, such as Figure 7.

20. Solutions of 4% picral and 2% nital appeared to ideally create rectangular etch pits bound by two (100) faces on the shell of hexagonal whiskers.

21. The 2% nital etch was best for revealing as-grown dislocations on (110) faces, 4% picral (m) was next best, while $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ was poorest. Only the persulfate etch was capable of removing the shell, however.

22. The $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ etch was best able to reveal as-grown dislocations on (100) faces, 2% nital was next best, while 4% picral was poorest. Again only the persulfate etch was capable of removing the shell layer. On [100] whiskers the 2% nital was unsatisfactory since (110) faces were created at the corners of these whiskers, and the (100) face often was consumed before significant penetration perpendicular to the (100) face had occurred.

23. The newly created planes which formed and consumed the original corners of the whiskers during etching were not the same as those which ideally comprised the etch pit faces. For example, etch pits bound by (110) planes were found on (100) faces of iron whiskers when etched in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. The low angle faces at the corners of the square whisker shown in Figure 45 are approximately 4° to 6° from the (100) face and have an index approximately (10,10).

24. Regardless of whisker growth direction the $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ etch was particularly suitable for studying the whisker interiors. The new faces formed at the corners during etching were at low angles to the original reference surface. This provided a longer opportunity to view the surface since the newly created faces were generally in focus with the original surface orientation. The side faces produced by the persulfate etch were relatively smooth and etch pits could be observed on these planes as well.

V. DISCUSSION

Explanations will be discussed for the following:

1. An abrupt variation is found in the shape of pits at as-grown and clean deformation dislocations in different layers of the whisker, even though etched in the same solution. The pits are usually better contained in the shell than in the core.
2. The etch $1N H_2SO_4 + 0.2N K_2S_2O_8$ produces better-contained pits on (100) than 4% picral or 2% nital, while on (110) the picral and nital etches produce better-defined pits.
3. As-grown dislocations intersect normal to the whisker faces, while deformation-produced dislocations intersect at an angle.
4. A dislocation structure of the as-grown whisker is suggested which explains the observations on as-grown dislocations including the existence of a shell-core interface.
5. The shell and core are not always the same growth direction.

Factors affecting etch pit formation

Effect of an internal poison.--Etch pits probably form by the preferential nucleation of ledges at dislocation sites. If these ledges are contained near the dislocation line, the pit will develop a sufficient depth to width ratio to be observed. If the ledges move rapidly away, the surface will develop a smooth polished appearance and individual etch pits will not be observed. It is assumed that whenever well-contained pits are present, a poison is also present to slow down the ledges.

Several examples have already been mentioned in the Literature Survey where halide ions appeared to act as a poison. The poison in these cases was added to the solution.

Berlec (46) suggests that in many cases the poison may be contained in the metal. It is impossible to reduce the impurities in metals below a level where the effect of trace impurities as internal poisons can be safely eliminated.

Sears (48) found that the iron required to poison the ledges of LiF could be provided by iron impurities either in solid solution or as precipitated particles in the parent crystal.

The abrupt change in the shape of etch pits observed in different layers of the whisker is attributed to a variation in the amount of internal poison present. Most whiskers have one concentration of poison in the shell and another in the core. While this is shown in almost all the whiskers, it is particularly striking in Figure 35. Well-shaped pits are present in the shell and very large shallow pock-like pits in the core. As-grown dislocations are present in both shell and core. Since the etch in both cases is the same, the poison cannot be in the etching solution. A considerably higher concentration of poison is present within the shell than is apparently present in the core. The poison is thought to adsorb on steps very close to the spot where it dissolves.

The effect of the poison appears to be quite localized since the poison in the shell retard only pits in the shell.

The concentration of poison in the shell in Figure 14b is so high that the pits appear to be etching as cones similar to decorated dislocations. Deeper within the whisker, Figure 14c, the poison is correct to form pits with crystallographic shape.

This same reasoning applies to clean deformation-produced dislocations as well as as-grown dislocations. A layer within the whisker which produces well-contained pits at as-grown dislocations should also produce well-contained pits at deformation dislocations. Figure 7 shows pits with crystallographic shape at as-grown dislocations. The etch pits at deformation dislocations, even though small, are well defined. Many illustrations have been shown where wide shallow pits have formed at both as-grown and deformation-produced dislocations in the same layer, for example, Figures 35a and 36. In Figure 38a the poison content is apparently so low in the core that as-grown dislocations are barely visible. After deformation, Figure 38b, shallow pock-like pits are present. The poison content is the same but the deformation dislocations show up slightly better, either because of a longer dislocation line or because the deformation dislocations have higher energy.

The impurity which is acting as a poison is unknown. The poison content of the shell was usually found to be

than the core. The poison probably builds up along the sides of the whisker during growth and at some concentration is incorporated into the growing lattice. Wiedersich (10) shows that an equilibrium exists between gaseous H_2 , HCl , and $FeCl_2$, and the solid $FeCl_2$ and Fe during growth of the whiskers. Adsorbed $FeCl_2$ and HCl molecules are present on the whisker during growth and could easily be incorporated into the whisker. Since it has already been shown that halide ions and halogen molecules appear to act as poisons when present as additions to the solution, it is very likely that they could also act as an internally contained poison.

Chlorine in some form is very likely serving as the poison in this case. The concentration of poison required as an internal poison is probably considerably lower than would be required as an addition to the solution. The reagents used in preparing the $1N H_2SO_4 + 0.2N K_2S_2O_8$ etch contain a maximum chloride impurity of 0.00002% in the sulfuric acid and 0.001% in the potassium persulfate. Apparently a chloride concentration of this magnitude in the solution is not sufficient to poison the ledges. A very small chloride concentration contained internally very likely could build up sufficiently at the solution-whisker interface during etching to cause poisoning of the ledges. It should be pointed out, however, that no chemical analysis was made of either the solution or the whisker, and that the

choice of poison was made solely on the basis of chlorine in some form being the most likely contaminant.

Effect of dissolution rate on pit formation. An internal poison is only one requirement for forming large etch pits with crystallographic shape on iron whiskers. A solution designed for etching iron whiskers should have a dissolution rate high enough to favor dissolution on planes that produce well-shaped pits, and on the other hand not have a rate of attack so high that the whiskers dissolve in too short a time. The rate of removal of the corners of the whiskers should be slow enough so that the original whisker face can be examined in depth.

It is usually found that the best etch pits are produced when dissolution is favored on planes other than the plane of the reference surface. An etch with a dissolution rate which favors creation of (110), or (111) planes is more likely to produce well-defined etch pits on a (100) face than is an etch which favors dissolution on (100) planes. An etch which favors dissolution on (100) planes is more likely to produce well-defined pits on a (110) face, however.

The solution: $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ establishes a corrosion rate intermediate between the solutions $1N\ H_2SO_4 + 0.02N\ K_2S_2O_8$, and $1N\ H_2SO_4 + 0.5N\ (NH_4)_2S_2O_8$, discussed in Figures 2 and 3. Engell (72) found pits bound by four (110) or four (111) planes when etched in $1N\ H_2SO_4 + 0.5N\ (NH_4)_2S_2O_8$. Pits bound by four (111) side faces and

having a (100) bottom formed on (100) planes when etched in $1N\ H_2SO_4 + 0.02N\ K_2S_2O_8$. Pits produced on (100) faces of iron whiskers should, therefore, contain some combination of the planes (110), (111), and (100) when formed by $1N\ H_2SO_4 + 0.2n\ K_2S_2O_8$. This etch was found to produce pits bound by (110) side faces and having a (100) bottom. It is not known why the (110) rather than (111) side faces are favored. Both of these orientations have a rate of attack higher than (100).

The $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ etch is not as well suited to forming etch pits on hexagonal whiskers, which are assumed to be bound by (110) planes. The etch favors general removal of the surface rather than selective attack as pitting. In the shell where the poison content is greatest, etch pits are visible when etched in the persulfate etch. These pits were not as clearly defined as etch pits formed on (100) faces, however. In the core where the poison content is lower, the persulfate etch was unsatisfactory for revealing as-grown dislocations on (110) planes.

An etch which preferentially removes the reference surface causes the poison to be less effective. If the dissolution is assumed to be under poison control, the rate of enlargement of the pit will be determined by the velocity of the leading ledges. This velocity is governed by the amount of adsorbed poison on the reference surface just ahead of the advancing discontinuity. Since the persulfate etch

favors the removal of the (110) face, the poison must continually be readsorbed and is less effective in containing the ledges near the dislocation line.

The effectiveness of the poison depends markedly on orientation. Several examples have been shown where wide pock-like pits were formed on (110) planes, while better-contained pits were formed on adjacent faces at a low angle to the (110) orientation. This is probably caused by the preferred removal of the (110) face by the persulfate etch which restricts the adsorption of the poison.

The picral and nital etches favor the creation of (100) pit faces. These etches would, therefore, be expected to form better-contained pits on (110) than on (100) faces. This was found generally to be correct. The (110) face is no longer preferentially attacked and therefore, the poison can more effectively adsorb on the surface. The picral and nital appear to have a lower corrosion rate normal to both the (100) and (110) faces. The (100) pit faces are apparently favored at the lower corrosion rate. These etches are usually not satisfactory on (100) faces since the plane of preferred attack is the same as the reference plane. The picral etches often produce no etch pits on (100) whisker faces.

Length of dislocation line and dislocation density.--

Provided the dissolution rate and poison content are favorable, a large etch pit can form only if the dislocation line

is sufficiently long. Pits such as those shown in Figures 7 and 8 require that the shell be several microns thick. The shell on most whiskers is often less than one micron, which in itself prevents the formation of larger pits.

The dislocation density should be low enough so that the pits can grow without interlocking. The as-grown dislocation density shown in Figure 7 is about 4×10^5 dislocations/cm² while it is about 2×10^6 dislocations/cm² in Figure 8a.

Etch pit shape

Two conflicting ideas have been advanced concerning the formation of etch pits. In the first idea ledges are nucleated at a source and move back as atoms dissolve from the ledges. In poison controlled dissolution, poison on the reference surface just ahead of the leading ledges slows down these front ledges and piles up steps formed later. On the other hand, it has been stated that the persulfate etch preferentially creates (110) planes and the picral and nital (100) planes. Apparently the dissolution rate of the persulfate modified by the poison present must be such as to cause the leading ledges to move slowest in the (100) directions, and cause pits bound approximately by (110) side faces to develop on a (100) reference surface. Once the pit has been formed the pit sides continue to move back, retaining approximately (110) side faces, even when the dislocation is no longer present in the base of the pit.

Many large etch pits at as-grown dislocations show terraces within the pit, Figures 7, 8a, 20a, 22b, 32a, 34, 35, and 36. These terraces have probably been formed by bunching (45), where some atomic ledges overtake others and form steps of larger height. It is not known whether these terraces are bound by (100) type planes forming a profile which would look like a set of steps or whether the terraces are slanted and bound by segments of perhaps (110) and (100) type planes. The same type of analysis can be applied to the formation of pits bound by (100) planes on hexagonal whiskers.

Round cone-shaped pits form either because the poison is so high that the dislocations behave like decorated dislocations or because the dissolution rate and/or poison content are not correct for restricting the ledges so that pits with crystallographic shape are produced.

For convenience the various etches have been described as preferentially creating pits bound by certain crystallographic faces. Actually such pits are created because the leading pit ledges are restricted the right amount and along the right directions by the etch and poison. This piles up later formed ledges and creates pits which appear to be bound by certain crystallographic faces.

Correspondence of etch pits and dislocation sites

The agreement between the number of as-grown and deformation-produced dislocations intersecting a whisker face, and the number of etch pits formed, is discussed for the etches 4% picral (e), 4% picral (m), 2% nital, and 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$.

The results already presented indicate that the internal factors within the whisker determine to a large degree whether pits are observable at dislocation sites. The etches were generally found not to produce equally well-defined pits on both (100) and (110) whisker faces.

The 1N H_2SO_4 + 0.2N $\text{K}_2\text{S}_2\text{O}_8$ etch is ideally suited to the etching of (100) faces of both rectangular and square whiskers. The agreement between etch pits and dislocations in the shell where the poison content is higher is probably quite good. Whisker (-1-), Figures 7, 30, 31, and 32, shows no change in the number of large pits at as-grown dislocation sites during etching. When the pits are small and the density high, this is more difficult to determine, but the number appears to remain constant. The existence of a shell and core on most whiskers prevents the number of pits from remaining constant over extended etching, however. The shell is removed and the underlying core often has a completely different dislocation density and amount of internal poison present. The persulfate etch normally develops observable

etch pits in the core of square and rectangular whiskers. These pits were commonly shallow pocks since the amount of poison in the core is usually less than the shell. If the poison content of the core is very low, neither as-grown nor deformation-produced dislocations will etch as well-defined pits, Figure 38.

The persulfate etch is less satisfactory for etching hexagonal whiskers. The agreement of dislocations and etch pits is good in the shell, but the pits are less clearly defined. On (110) planes in the core where the poison content is usually lower, the persulfate etch is unsatisfactory for revealing as-grown dislocations.

The persulfate etch produces a good agreement between etch pits and deformation dislocations. Figure 7b shows small pits at deformation dislocation sites. No small pits were present on the section of the whisker which was not deformed, Figure 30. Figure 42 shows that deformation dislocations are revealed on hexagonal whiskers. The pits are better contained when the poison content is high.

It is felt that the persulfate etch produces pits only at dislocation sites. In unfavorable conditions of orientation and poison content, no etch pits were observed at as-grown dislocation sites. There is no indication, however, that etch pits have formed at sites other than where dislocations intersect the surface.

The picral and nital etches were used to etch only undeformed whiskers. The picral etches were usually found unsuitable for revealing as-grown dislocations on (100) faces, even in the shell where the poison content is higher. The 4% picral (m) etch produces well-defined etch pits in the shell of hexagonal whiskers, however. The etch pits observed after several minutes etching in 4% picral (m) are very likely located at dislocation sites, Figures 56b and 62b. The agreement between dislocation sites and etch pits is probably good. With extended etching in 4% picral (m) considerable background attack is observed, Figures 56d and 57a. These pits are probably not located at dislocation sites. On (110) planes in the core of hexagonal whiskers where the poison is lower, the 4% picral (m) etch was unsatisfactory for revealing dislocation sites, Figure 63b.

The 2% nital etch produces etch pits at as-grown dislocations on (100) and (110) planes. The pits produced on hexagonal whiskers after several minutes of etching probably agree well with the dislocations present, Figures 58b, 58c, and 60b. Etching for 10 min produced considerable background etching probably not associated with dislocations, Figures 58d and 60c. The 2% nital etch was the only etch suitable for revealing as-grown dislocations on (110) planes in the core of hexagonal whiskers, Figures 59b, 61b, and 64a. Since the core was etched in the nital 3 min or less in each case, it is felt that the pits revealed in the core by the nital do

represent as-grown dislocation sites. Square and rectangular whiskers etched for a relatively short time in 2% nital usually showed pits which are probably at dislocation sites, Figures 51b, 52b, 53b, and 54a.

The creation of (110) faces on the corners of square whiskers often removes the original (100) face before etch pits on the (100) face can be observed, however, Figures 51a, and 54b.

The dissolution rate, length of the dislocation lines, and poison present all influence the formation of well-shaped etch pits. The etch establishes the dissolution rate. In the case of iron whiskers, the poison is present internally within the whiskers and must be present at a high enough level or none of the etches discussed here will produce satisfactory etch pits.

Determination of the role of the image force and climb in causing as-grown dislocations to be drawn perpendicular to the surface

As-grown dislocations intersect perpendicular to the whisker faces. This can occur either if the image force pulls the dislocation perpendicular to the surface while it is still in its slip plane, or if the dislocation climbs off its slip plane.

A dislocation near a free surface is acted upon by a force which tends to pull it to the surface. It has been shown that this force is equal to the force between the real

dislocation and an "image dislocation" which is considered to be located in free space the same distance above the surface as the real dislocation is below. The two are mirror images across the surface. Read (81) presents the following equation for the force between two parallel screw dislocations for the isotropic case.

$$F = \frac{Gb^2}{2\pi r}$$

- F - the force on one dislocation per unit length due to the presence of a second dislocation
- G - torsion or shear modulus
- b - Burger's vector
- r - distance between the dislocations

The force between parallel screw dislocations is therefore central and varies inversely as their separation, just like the force between parallel charged wires. In this analogy, the charge and Burger's vector are equal in magnitude and sign and the dielectric constant is proportional to $\frac{2\pi}{G}$.

The above equation can be modified to estimate the magnitude of the image force. The Burger's vectors of the real and image dislocations are equal. If L is the distance from the real dislocation perpendicular to the surface, then $2L = r$.

$$F = \frac{G}{2\pi} \left(\frac{1}{2L} \right) b^2$$

The following values have been used:

- G - 1.13×10^4 kg/mm² (16×10^6 psi) for iron along the [100] direction
- L - arbitrarily picked at 1μ (10^{-3} mm)
- b $\sim 2.5 \times 10^{-7}$ mm which is the distance of closest approach of iron atoms

Using the above values, $F_{\text{image}} \cong 5.6 \times 10^{-8} \text{ kg/mm}$.

For comparison the critical resolved shear stress has been calculated along the slip system $(1\bar{1}2) [\bar{1}11]$ which is favored for a $[001]$ tensile axis, see Figure 65a. The yield strength along the $[001]$ direction is approximately 10 kg/mm^2 (14,200 psi) (82) for a bulk iron single crystal.

$$\tau_{[\bar{1}11]} = \frac{F}{A} \cos \lambda \cos \phi$$

λ - angle between the $[\bar{1}11]$ direction and the tensile axis. $[001] - [\bar{1}11]$ is 54.7°

ϕ - angle between the normal to the slip plane and the tensile axis. $[001] - [1\bar{1}2]$ is 35.3°

Using the above values $\tau_{[\bar{1}11]} = 4.7 \text{ kg/mm}^2$

Critical resolved shear stress/unit = $4.7 \text{ kg/mm}^2 \times b$
dislocation length

Critical resolved shear stress/unit = $1.2 \times 10^{-6} \text{ kg/mm}$
dislocation length

The yield strength used is that of bulk iron crystals not the high strength observed for some small whiskers. Only short dislocation segments are considered here and their slipping to positions perpendicular to the surface rather than actual yielding of the whisker. This yield strength for dislocation movement may well not be the same as the critical resolved shear strength based on the total yielding of the specimen.

Based on the above calculations the critical resolved shear stress is 21 times the force available from the image force. The magnitude of the image force calculated above is only an approximation, however, since the calculation is

based on the hypothetical case of two parallel screw dislocations in an isotropic medium. Also, the image force was calculated for a dislocation at a depth of 1μ . Figures 7 and 8 show pits symmetrical to a depth of several microns. This indicates that the dislocation can be drawn perpendicular to the surface over at least this distance. The image force is less on dislocations farther from the surface. It is quite possible, however, that the dislocation line is drawn perpendicular to the surface as the whisker thickens. The distance from the surface to the dislocation is then very small and the dislocation is affected by a larger image force than that calculated above.

The yield strength and the image force are temperature dependent. The image force might be larger with respect to the critical resolved shear stress at the growing temperature of 700°C .

It appears quite possible for the dislocation line during growth of the whisker to glide in its slip plane until it is perpendicular to the surface. This does not occur, however, to deformation-produced dislocations at room temperature. These dislocations are restricted to the available slip systems.

Besides the possibility of whiskers gliding within the slip plane until perpendicular to the surface, it is also possible for the dislocations to climb off their slip

plane. An excess of vacancies is the driving force for climb. The recrystallization temperature of iron is 200° to 300°C . Therefore, climb of dislocations can and does occur at the growing temperature of 700°C . The image force also acts on these dislocations and could draw these dislocations perpendicular to the surface by a combination of climb and glide. A dislocation line at a given point normally contains both a screw and edge component. The motion of a screw dislocation is always glide. The edge component, however, is available for glide, and climb also, if the crystal is heated to a temperature where appreciable diffusion of vacancies can occur.

Based on the above discussion, glide and climb at the growing temperature can produce dislocations which intersect perpendicular to the (100) and (110) whisker surfaces. Glide of the dislocation line can, independent of climb, result in dislocations perpendicular to the surface. Certain of the (110) type slip planes can intersect normal to a (100) face while certain (110) and (211) planes can intersect normal to a (110) whisker face. In these cases the dislocations can glide until they are perpendicular to the surface without leaving the slip plane. Climb and glide must occur simultaneously for dislocations associated with slip planes not perpendicular to the surface. It is felt that both of these mechanisms can operate during growth of the whiskers.

Pits, associated with as-grown dislocations which have slipped but remained in a slip plane perpendicular to the surface, should be aligned along traces of these planes with the surface. Most of the whiskers examined had such a high as-grown dislocation density that it was impossible to tell.

Table 1 lists several illustrations where the pits appear to be aligned along straight lines, which suggest possible traces of the slip planes with the surface. Three examples were found which suggest pits at dislocations located normal to the surface in a (110) type slip plane. It should be noted that these slip planes do not have to be the slip planes which would be favored during deformation of the whisker at room temperature.

In several other cases the pits appeared to be associated with dislocations on the same slip plane but the traces did not correspond to the intersection of one of the slip planes with the surface. Four illustrations are shown in Table 1 where the line of pits was oriented at an angle between 9° and 13° with a [100] axis.

No information is provided on the slip plane associated with a given dislocation for those pits not aligned along traces of slip planes normal to the surface. Since there are many parallel slip planes of each orientation, it is entirely possible for the dislocations to be randomly located on the slip planes and show no preference for certain

TABLE 1

DETERMINATION OF POSSIBLE SLIP PLANES ASSOCIATED WITH AS-GROWN DISLOCATIONS

Whisker face	Growth axis	Fig. no.	Pits studied	Approximate angle between the row of pits and the growth axis	Possible slip plane trace
(001)	[110]	7a	The three pits labeled #6	32° with [110] growth axis, 13° with [010] axis	None
(001)	[110]	7a	Pits labeled a, b, c, and d	Parallel with [110] growth axis, 45° with [100] axis	$\begin{pmatrix} \bar{1}\bar{1}0 \\ \bar{1}10 \end{pmatrix}$
(001)	[110]	8a	Pits appearing along traces with a positive slope	56° with [110] growth axis, 11° with [110] axis	None
(001)	[110]	14c	Row of pits with negative slope	36° with [110] growth axis, 9° with [010] axis	None
(001)	[110]	16b	Row of pits with negative slope	58° with [110] growth axis, 13° with [100] axis	None
(011)	$[\bar{1}\bar{1}\bar{1}]$	56b	Parallel rows of pits having a negative slope	55° with $[\bar{1}\bar{1}\bar{1}]$ growth axis	$(01\bar{1})$ at 54.7°
(011)	$[\bar{1}\bar{1}\bar{1}]$	58b	Parallel rows of pits having a negative slope	57° with $[\bar{1}\bar{1}\bar{1}]$	$(01\bar{1})$ at 54.7°

of the parallel planes. The pits could still glide in the individual slip planes normal to the surface and intersect perpendicular to the surface.

It is much more likely that climb as well as glide is occurring. The rows of pits are then similar to low angle tilt boundaries resulting from polygonization. The stable dislocation array is the tilt boundary. In the illustrations listed in Table 1, the pits were generally fairly well spaced. The angle of tilt along such a boundary is probably a very small fraction of a degree rotation. A polygonized structure was reported on undeformed iron whiskers by Gorsuch and Alden (53).

It is impossible to determine whether as-grown dislocations are always normal to the whisker surface. Symmetric etch pits at as-grown dislocations in the shell indicate that these dislocations intersect normal to the surface. Several examples have been shown where as-grown dislocations penetrate a shell several microns thick and remain perpendicular to the surface. The as-grown dislocations in the core of square and rectangular whiskers are probably also aligned normal to the surface. The alignment of as-grown dislocations in the core of a hexagonal whisker is probably more complex.

Etch pits at deformation-produced dislocations were usually small or shallow and it was impossible to determine whether or not the pits were symmetric. Figures 42 and 43

show the only examples of larger pits and in these cases they are asymmetric, indicating that the dislocation intersects the surface at an angle.

The following analysis shows theoretically that it is never possible for deformation dislocations to intersect normal to the (100) faces of square or rectangular whiskers. They can intersect normal to a (110) face of a hexagonal whiskers only as a special case.

Determination of the angles of intersection between the possible slip planes and the surface for a deformed whisker

A dislocation on a slip plane can intersect normal to the surface only if the slip plane itself intersects normal to the surface. This fact has been used to determine whether it is ever theoretically possible for a deformation-produced dislocation to intersect normal to a whisker face as has been found for as-grown dislocations.

For alpha iron the (110), (211), and (321) planes can all slip under favorable conditions of orientation. Figure 65a shows a unit triangle derived by Opinsky and Smoluchowski (82) which indicates the preferred slip systems for each orientation based on the critical resolved shear stress. Following the nomenclature used in this triangle, the growth axis of a square whisker is designated [001], a rectangular whisker [011] and a hexagonal whisker $[\bar{1}11]$. The radius of bending of the whiskers is always normal to the whisker axis

(a) Regions of a unit triangle within which the indicated resolved shear stresses in a b. c. c. lattice is higher than other resolved shear stresses

(b) Intersection of slip plane $(\bar{2}11)$ with whisker faces $(0\bar{1}1)$ and $(01\bar{1})$

Figure 65

and approximately perpendicular to the face which is being examined. The bending is such that compressive stresses are induced in this face initially and then tensile stress as it is again forced back down onto the tape.

Square whisker.--Figure 65a shows that the slip systems $(1\bar{1}2)$ $[\bar{1}11]$ and $(2\bar{1}3)$ $[\bar{1}11]$ are favored. From the zone axis law, the four faces of the whisker must obey $Oh + Ok + \ell = 0$. The four whisker faces are therefore (010) , $(0\bar{1}0)$, (100) , and $(\bar{1}00)$. The angle between the slip plane and each of these faces can be found by using the following relationship.

$$\cos \phi = \frac{h_1 h_2 + k_1 k_2 + \ell_1 \ell_2}{\sqrt{h_1^2 + k_1^2 + \ell_1^2} \sqrt{h_2^2 + k_2^2 + \ell_2^2}}$$

The angles calculated are:

$\begin{Bmatrix} 2\bar{1}3 \\ 2\bar{1}3 \end{Bmatrix}$	$- \begin{Bmatrix} 0\bar{1}0 \\ 0\bar{1}0 \end{Bmatrix}$	74.5°	$\begin{Bmatrix} 1\bar{1}2 \\ 1\bar{1}2 \end{Bmatrix}$	$- \begin{Bmatrix} 0\bar{1}0 \\ 0\bar{1}0 \end{Bmatrix}$	65.9°
$\begin{Bmatrix} 2\bar{1}3 \\ 2\bar{1}3 \end{Bmatrix}$	$- \begin{Bmatrix} 100 \\ 100 \end{Bmatrix}$	57.7°	$\begin{Bmatrix} 1\bar{1}2 \\ 1\bar{1}2 \end{Bmatrix}$	$- \begin{Bmatrix} 100 \\ 100 \end{Bmatrix}$	65.9°
$\begin{Bmatrix} 2\bar{1}3 \\ 2\bar{1}3 \end{Bmatrix}$	$- \begin{Bmatrix} \bar{1}00 \\ \bar{1}00 \end{Bmatrix}$	57.7°	$\begin{Bmatrix} 1\bar{1}2 \\ 1\bar{1}2 \end{Bmatrix}$	$- \begin{Bmatrix} \bar{1}00 \\ \bar{1}00 \end{Bmatrix}$	65.9°

Since it is found that the slip planes do not intersect perpendicular to any of these faces, deformation dislocations cannot intersect normal to the face of a square whisker.

Rectangular whisker, (100) face.--Figure 65a shows that the slip systems $(2\bar{1}1)$ $[\bar{1}11]$ and $(3\bar{1}2)$ $[\bar{1}11]$ are favored. A rectangular whisker with axis $[011]$ is bound by parallel faces (100) and $(\bar{1}00)$.

The angles are calculated as indicated above.

$$\begin{array}{ll} \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 100 \\ 100 \end{array} \right\} & 35.3^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 100 \\ 100 \end{array} \right\} & 36.7^\circ \end{array}$$

Hexagonal whisker.--The slip systems $(\bar{3}12)$ $[111]$ and $(\bar{2}11)$ $[111]$ are again favored for a hexagonal whisker with axis $[\bar{1}11]$. The six planes bounding such a whisker are: (110) , $(\bar{1}10)$, (101) , $(\bar{1}01)$, $(0\bar{1}1)$, and $(01\bar{1})$. The angles of intersection are:

$$\begin{array}{ll} \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 110 \\ 110 \end{array} \right\} & 67.8^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 110 \\ 110 \end{array} \right\} & 67.8^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 101 \\ 101 \end{array} \right\} & 79.1^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 101 \\ 101 \end{array} \right\} & 79.1^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 0\bar{1}1 \\ 0\bar{1}1 \end{array} \right\} & 79.1^\circ \\ \left\{ \begin{array}{l} \bar{3}12 \\ 312 \end{array} \right\} - \left\{ \begin{array}{l} 0\bar{1}1 \\ 0\bar{1}1 \end{array} \right\} & 79.1^\circ \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 110 \\ 110 \end{array} \right\} & 73.2^\circ \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 110 \\ 110 \end{array} \right\} & 73.2^\circ \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 101 \\ 101 \end{array} \right\} & 73.2^\circ \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 101 \\ 101 \end{array} \right\} & 73.2^\circ \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 0\bar{1}1 \\ 0\bar{1}1 \end{array} \right\} & 90^\circ* \\ \left\{ \begin{array}{l} \bar{2}11 \\ 211 \end{array} \right\} - \left\{ \begin{array}{l} 0\bar{1}1 \\ 0\bar{1}1 \end{array} \right\} & 90^\circ* \end{array}$$

The above calculations indicate that no slip planes intersect normal to the (100) type faces of either a square or rectangular whisker. Dislocation lines lying in these slip planes, therefore, can never intersect normal to the (100) type faces no matter what the relative magnitude of the edge and screw components.

The slip plane in two cases for hexagonal whiskers can intersect normal to a (110) type face. These two cases are marked with an asterisk above. Figure 65b shows the intersection of the slip plane $(\bar{2}11)$ with whisker faces $(0\bar{1}1)$ and $(01\bar{1})$. The line BD represents the slip direction $[111]$. A pure edge dislocation in this slip system has been represented by the line AC. The Burger's vector lies along

*See text.

BD. The extra plane of atoms is perpendicular to the $(\bar{2}11)$ plane, ADC. In this unique orientation it can be seen that the dislocation line AC intersects normal to the $(0\bar{1}1)$ and $(01\bar{1})$ faces. An etch pit at such a dislocation would be symmetric. A pure edge dislocation is the limiting case for this system, however. Dislocations normally nucleate and move out as loops. Such a dislocation is represented by the arc A'BC' which has both an edge and a screw component and does not intersect normal to the surface. An etch pit at such a dislocation would be asymmetric. It can be assumed that deformation-produced dislocations do not intersect normal to the faces of iron whiskers. These dislocations would etch as asymmetric etch pits, provided conditions were correct to produce a well-defined pit.

Figures 42 and 43 show the only example where pits formed at clean deformation-produced dislocations were large enough to verify that the pits are asymmetric. Both the round pits in Figure 42c and those showing crystallographic shape in Figure 43 show asymmetry. In the other examples of whiskers that were bent and then etched, the pits at deformation dislocations tended to be so small and usually shallow that no information could be obtained concerning the symmetry of the pits.

Slip systems in operation during the bending of iron whiskers

Figure 65a shows the most probable slip systems in operation during the deformation of whiskers of each of the three growth directions. The creation of etch pits at newly created deformation-produced dislocations does not in itself indicate the slip planes, since the density of pits is usually too high, and the pits usually are randomly scattered.

While most of the whiskers when deformed did not produce slip lines on the surface, one square and one rectangular whisker did show slip lines after deformation, see Figures 23c and 39a. The slip system or systems causing these slip lines can be determined from a consideration of the most probable slip systems based on the critical resolved shear stress. Based on the conventions in Figure 65a, the $(1\bar{1}2)$ $[\bar{1}11]$ or $(2\bar{1}3)$ $[\bar{1}11]$ are the most probable slip systems for a $[001]$ whisker.

The slip bands shown in Figure 23c result from two slip systems. The angles of intersection of these lines with the $[001]$ whisker axis are shown in Figure 66a. Figures 66c and 66d show the theoretical angles of intersection of the $(1\bar{1}2)$ and $(2\bar{1}3)$ planes with the (100) whisker surface. The angle of 62° agrees very closely with the angle of 63.4° for the $(1\bar{1}2)$, while 70° agrees very well with the 71.6° for a $(2\bar{1}3)$ plane. The slip systems in operation were those predicted from Figure 65a.

Figure 66 - Traces of slip systems on whisker faces

Slip lines on the (100) face of rectangular whisker (-3-), Figure 39a, also appear to belong to two slip systems. One set has a positive slope, the other a negative. The angles measured from the whisker axis are shown in Figure 66b. Figure 66e shows the theoretical angles of intersection of the $(\bar{2}11)$ and $(\bar{3}12)$ slip planes, which are favored for a [011] whisker axis. The angles observed do not agree with either of these slip systems. These angles agree with the slip systems $(1\bar{1}2)$ $[\bar{1}11]$ and $(2\bar{1}3)$ $[\bar{1}11]$, however, assuming a [001] rather than [011] growth axis. It is felt that this is probably another example of a whisker in which the shell and the core do not have the same orientation. The rectangular shape probably results from a [011] growth axis of the core. The very thin shell over this core is apparently still a (100) face but rotated 45° to a [001] orientation. Two examples of rectangular whiskers have already been presented in which the pits in the shell appeared to be rotated to the [001] orientation.

Dislocation structure of as-grown whiskers

Nearly all whiskers appear to have a distinct shell and core region. The as-grown dislocation density in these two regions is usually considerably different. Because of the difference in poison content, pits at as-grown dislocations are usually shaped differently in each region. Symmetric etch pits at as-grown dislocations in the shell

indicate that dislocations intersect normal to the surface. The as-grown dislocations in the core are very likely also aligned normal to the surface. It has been shown that the image force and/or climb causes these dislocations to be drawn perpendicular to the surface.

The nature of the shell-core interface can only be postulated. As-grown dislocations perpendicular to the surface in the shell are probably attached to some type of two-dimensional dislocation network along the shell-core interface. Amelinckx (83) revealed dislocation networks in sodium chloride crystals by decorating the dislocations. The dislocations in the shell are probably attached to dislocation nodes formed where two or more dislocation lines lying along the interface intersect each other. These dislocations lie parallel to the reference surface and cannot be observed during etching. The fact that the shell and core can be of different orientation supports the idea of such a dislocation network.

The dislocation network at the shell-core interface probably resulted from the incorporation of impurity atoms into the growing lattice, forming growth defects. Frank (45) shows that the effect of impurities during crystal growth is similar to the effect of a poison during dissolution. The impeding impurity is not desorbed to make way for the advancing growth step, but is buried into the growing crystal. Cabrera and Vermilyea (34) give several examples to show that

such impurity incorporation actually can occur. The concentration of impurity atoms builds up on the surface of the whisker during growth and finally reaches a concentration where it is incorporated into the growing lattice. The shell is usually richer in the poison atoms than is the core.

It can be seen that the number of as-grown dislocations in the core, which are attached to nodes at the shell-core dislocation network, bear no relationship to the number of dislocations in the shell attached to nodes from the other side. The dislocation density in the shell can be greater or lesser than that found in the core.

Less is known concerning the dislocations in the core because pits with crystallographic shape usually do not etch at these dislocations. Except for the poison concentration, which is usually less, these dislocations are probably similar to those in the shell. The dislocation density apparently can decrease with penetration within the core, see Figure 18. This can occur if dislocation networks exist at varying depths and not only at the shell-core interface.

Growth axis of iron whiskers

Unless proven otherwise, square whiskers are assumed to have a $[100]$ axis, rectangular whiskers $[110]$, and hexagonal whiskers $[111]$. Three rectangular whiskers have been observed which had a shell rotated to the $[100]$ orientation. This was determined from the rotation of etch pits on two of

the whiskers, and from the slip bands present on a third. The shell-core interface takes on new meaning since, in these cases, it has the properties of a grain boundary.

Laue X-ray patterns have been used in the past to determine the growth axis of iron whiskers. Since most whiskers have a shell and a core, it is very important to establish how deep a whisker is being examined by the X-rays.

The intensity of the incident beam does not suddenly become zero at any one depth, but rather decreases exponentially with distance below the surface. The method used has been suggested by Cullity (85). The depth of penetration has been calculated, which will account for 90% of the intensity of a hypothetical transmission Laue spot formed in the following manner. The incident beam makes a 10° angle with the whisker face. Assume that the reflecting planes are parallel to the surface. The reflected beam then also makes a 10° angle with the surface, which corresponds to a Laue spot at slightly over 1 cm from the center of the film based on a specimen-film distance of 3 cm. The results show that the above conditions are fulfilled for a depth of penetration of 0.8μ for Cu $K\alpha$ and 2.2μ for Cr $K\alpha$. A lower angle of either the incident or reflected beam with the whisker face decreases the depth of penetration. Other target materials and wave lengths also give different depths of penetration.

The possibility has been demonstrated that the depth of penetration corresponding to 90% of the observed intensity

is often approximately the same as the thickness of the shell. Laue transmission patterns of iron whiskers are primarily patterns of the shell. Since it has been shown that the shell is not always representative of the entire cross section, X rays must be used with discretion in determining the growth axis and other properties of iron whiskers.

FUTURE WORK

1. Etches with different dissolution rates can be made by varying the $K_2S_2O_8$ concentration in the basic $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ etch. It might be possible, by using less $K_2S_2O_8$, to develop an etch which would produce better-contained pits on (110) planes. An increase in concentration above $0.2N\ K_2S_2O_8$ might result in pits on (100) faces bound by other combinations of low index planes. If all etching could be done with a $1N\ H_2SO_4$ solution with varying amounts of potassium persulfate added, it would provide an excellent test of the effect of dissolution rate on pit formation.
2. More whiskers should be bend and the slip lines analyzed. Slip lines are not produced on every whisker after bending, but when present they can be used to study the growth axis of both the shell and the core.
3. It is felt that many structural defects, such as tilt boundaries, reported in iron whiskers, are probably present in the shell only. The whiskers could be X-rayed as-grown and again after removing the shell by etching in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. Phenomena peculiar to the shell could then be isolated. It would be interesting to X-ray a whisker known to contain a shell with a growth axis different from the core, to determine whether the Laue patterns from the separate orientations can be distinguished from each other.
4. None of the whiskers reported in this dissertation were deformed and then etched in picral or nital. While such procedures have already been reported in the literature, it would be interesting to repeat these experiments in the light of the existence of a shell and a core as well as the commonly found variation in internal poison concentration.
5. The shell on several hexagonal whiskers reported in this dissertation was etched with picral or nital and the shell then removed with the etch $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. These whiskers were then re-etched in either picral or nital to determine the effect of these etches on the core. This same procedure could now be applied to square and rectangular whiskers.

6. The dissolution rate of one square and one rectangular whisker in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$ was calculated by measuring the single electrode potential and comparing it with data previously obtained, by measuring the change in cross sectional shape during etching, and by analyzing the solution for iron. These methods could be applied to other square and rectangular whiskers as well as hexagonal whiskers.
7. The change in cross sectional shape during etching can be used to measure the dissolution rate for whiskers etched in picral and nital. This would help verify the effect of dissolution rate on pit formation.
8. Etch more whiskers in $1N\ H_2SO_4 + 0.2N\ K_2S_2O_8$. Considerable variation exists between whiskers. The possibilities can be found only if a sufficient number of whiskers are studied.

BIBLIOGRAPHY

1. S. S. Brenner, Acta. Met., 4, 62 (1956).
2. S. S. Brenner, Science, 128, 569 (1958).
3. R. R. Hasiguti, Acta. Met., 3, 200 (1955).
4. C. R. Morelock, Acta. Met., 10, 161 (1962).
5. G. L. Pearson, W. T. Read, Jr., and W. L. Feldman, Acta. Met., 5, 181 (1957).
6. R. D. Dragsdorf and W. W. Webb, J. Appl. Phys., 29, 817 (1958).
7. G. W. Sears, Acta. Met., 1, 457 (1953).
8. S. S. Brenner and G. W. Sears, Acta. Met., 4, 268 (1956).
9. G. W. Sears and R. V. Coleman, Acta. Met., 5, 131 (1957).
10. H. Wiedersich, J. Electrochem. Soc., 106, 810 (1959).
11. S. S. Brenner, Acta. Met., 7, 519 (1959).
12. A. W. Cochardt and H. Wiedersich, Naturwissenschaften, 42, 342 (1955).
13. H. Weik, J. Appl. Phys., 30, 789 (1959).
14. C. M. Wayman, J. Appl. Phys., 32, 1844 (1961).
15. J. C. Fisher, R. L. Fullman, and G. W. Sears, Acta. Met., 2, 344 (1954).
16. J. B. Newkirk and G. W. Sears, Acta. Met., 3, 110 (1955).
17. C. Herring and J. K. Galt, Phys. Rev., 85, 1060 (1952).
18. S. S. Brenner, J. Appl. Phys., 27, 1484 (1956).
19. G. W. Sears, A. Gatti, and R. L. Fullman, Acta. Met., 2, 727 (1954).

20. J. E. Emrich and H. L. Gegel, A Tensile Testing Apparatus for Short Fine Filaments with Optical Mechanical Strain Measurements, ASD Technical Report, 61-68.
21. P. D. Gorsuch, J. Appl. Phys., 30, 837 (1959).
22. W. R. Rambaueske and R. R. Gruenzel, X-ray Diffraction Investigations on Iron Whiskers, Technical Documentary Report No. ASD-TDR-62-331 (1962).
23. R. V. Coleman, J. Appl. Phys., 29, 1487 (1958).
24. S. Amelinckx, Phil. Mag., 3, 425 (1958).
25. D. R. Hamilton, J. Appl. Phys., 31, 112 (1960).
26. R. G. Treuting, Acta. Met., 5, 173 (1957).
27. R. V. Coleman in Growth and Perfection of Crystals (John Wiley and Sons, Inc., New York, 1958), p. 239.
28. R. G. Treuting and S. M. Arnold, Acta. Met., 5, 598 (1957).
29. R. V. Coleman and N. Cabrera, J. Appl. Phys., 28, 1360 (1957).
30. W. W. Webb, R. D. Dragsdorf, and W. D. Forgeng, Phys. Rev., 103, 498 (1957).
31. E. C. Roberts and S. C. Lawrence, Acta. Met., 5, 335 (1957).
32. G. S. Baker, Acta. Met., 5, 353 (1957).
33. E. E. Thomas, Acta. Met., 4, 94 (1954).
34. W. W. Webb and W. D. Forgeng, J. Appl. Phys., 28, 1449 (1957).
35. J. F. Green and A. A. Woolf, Research, 11, 38 (1958).
36. J. V. Laukonis and R. V. Coleman, J. Appl. Phys., 30, 1364 (1959).
37. D. A. Vermilyea, J. Chem. Phys., 28, 717 (1958).
38. W. K. Boyd and A. M. Hall, Metals Engineering Quarterly, August, 1961, p. 15.

39. A. P. Honess, The Nature, Origin, and Interpretation of the Etch Figures on Crystals (John Wiley and Sons, Inc., New York 1927).
40. F. W. Young, Jr., J. Appl. Phys., 32, 192 (1961).
41. M. B. Ives, J. Appl. Phys., 32, 1534 (1961).
42. M. B. Ives and J. P. Hirth, J. Chem. Phys., 33, 517 (1960).
43. N. Cabrera, M. M. Levine, and J. S. Plaskett, Phys. Rev., 96, 1153 (1954).
44. S. Mendelson, J. Appl. Phys., 32, 1579 (1961).
45. F. C. Frank in Growth and Perfection of Crystals (John Wiley and Sons, Inc., New York, 1958), p. 411.
46. I. Berlec, J. Appl. Phys., 33, 197 (1962).
47. J. J. Gilman, W. G. Johnston, and G. W. Sears, J. Appl. Phys., 29, 747 (1958).
48. G. W. Sears, J. Chem. Phys., 32, 1317 (1960).
49. L. C. Lovell and J. H. Wernick, J. Appl. Phys., 30, 590 (1959).
50. H. S. Rosenbaum and M. M. Saffren, J. Appl. Phys., 32, 1866 (1961).
51. F. W. Young, Jr., J. Appl. Phys., 29, 760 (1958).
52. L. H. Jenkins and J. O. Stiegler, J. Electrochem. Soc., 109, 467 (1962).
53. P. D. Gorsuch and T. H. Alden, Research on the Behavior on Nearly Perfect Crystals, Final Report, Contract No. AF-33(616)-6181 (1961).
54. D. W. Smith and R. F. Mehl, Metals and Alloys, 4, 31 (1933).
55. G. A. Wolff, J. M. Wilbur, Jr., and J. C. Clark, Z. Electrochem., 61, 101 (1957).
56. G. Tammann and A. A. Botschwar, Chemical Abstracts, 23, 317 (5) (1929).
57. M. Yamamoto and J. Watanabe, Chemical Abstracts, 54, 203 (c) (1960).

58. M. Yamamoto, Chemical Abstracts, 41, 4987 (g) (1947).
59. B. Fujita, Chemical Abstracts, 23, 4660 (2) (1929).
60. M. Yamamoto and J. Watanabe, Chemical Abstracts, 46, 807 (d), and 46, 3362 (c) (1952).
61. C. S. Barrett, Structure of Metals (McGraw Hill, New York, 1952), p. 192; also C. S. Barrett and L. H. Levenson, Trans. AIMME, 137, 76 (1940).
62. C. E. C. Tucker and P. C. Murphy, J. Inst. Metals, 81, 235 (1953).
63. P. J. Holmes, Acta. Met., 7, 283 (1959).
64. R. Dreiner and R. Garnache, J. Appl. Phys., 33, 888 (1962).
65. A. T. Gwathmey, H. Leidheiser, Jr., and G. P. Smith, Chemical Abstracts, 42, 8040 (1) (1948).
66. M. Straumanis, Nature, 124, 56 (1929).
67. R. B. Mears and R. H. Brown, Ind. Eng. Chem., 33, 1001 (1941).
68. C. S. Walton, Trans. Electrochem. Soc., 85, 239 (1944).
69. H. Leidheiser, Jr. and A. T. Gwathmey, Trans. Electrochem. Soc., 91, 95 (1947).
70. P. R. Camp, J. Electrochem. Soc., 102, 586 (1955).
71. W. R. Buck III, and H. Leidheiser, Jr., J. Electrochem. Soc., 104, 474 (1957).
72. H.-J. Engell, Arch. Eisenhüttenw., 26, 393 (1955).
73. R. Piontelli, L. P. Bicelli, and A. La Vecchia, Research on Hydrogen Overvoltage on Metallic Single Crystals, WADD Technical Report 60-769 (1961).
74. M. Stern and R. M. Roth, J. Electrochem. Soc., 104, 390 (1957).
75. J. Kruger, J. Electrochem. Soc., 106, 736 (1959).
76. F. Van Wijk and J. A. B. Van Dijk, Acta. Met., 4, 657 (1956).

77. M. V. N. Svetchnikoff, Revue de Metallurgie, 27, 404 (1930).
78. S. Yamaguchi, Bull. Chem. Soc., Japan, 24, 237 (1951).
79. F. W. C. Boswell, Metal Progress, 72, 92, December, 1957.
80. R. B. Liss, Acta Met., 7, 231 (1959).
81. W. T. Read, Jr., Dislocations in Crystals (McGraw-Hill Book Company, Inc., New York, 1953), p. 127.
82. A. Opinsky and R. Smoluchowski, Carnegie Institute of Technology Symposium on the Plastic Deformation of Crystalline Solids, Office of Naval Research, 1950, p. 216.
83. S. Amelinckx, in Dislocations and Mechanical Properties of Crystals (John Wiley and Sons, Inc., New York, 1957), p. 3.
84. N. Cabrera and D. A. Vermilyea, in Growth and Perfection of Crystals (John Wiley and Sons, Inc., New York, 1958), p. 393.
85. B. D. Cullity, Elements of X-ray Diffraction (Addison-Wesley Publishing Co., Inc., Reading, Massachusetts, 1956), pp. 270 and 466.

AUTOBIOGRAPHY

I, Charles Collmar Seastrom, was born in Easton, Pennsylvania, April 30, 1936. I received my secondary-school education in the public schools of Easton, Pennsylvania, and my undergraduate training at Lafayette College, which granted me the Bachelor of Science degree in 1958. From The Ohio State University, I received the Master of Science degree in 1959. My doctoral program was under the guidance of Professor F. H. Beck. I have held positions as research assistant and University Fellow while completing my graduate work.

I have accepted employment with the Organic Chemicals Division, E. I. duPont de Nemours and Co., Inc., Wilmington, Delaware.