INFORMATION TO USERS

This manuscript has been reproduced from the microfilm master. UMI films the text directly from the original or copy submitted. Thus, some thesis and dissertation copies are in typewriter face, while others may be from any type of computer printer.

The quality of this reproduction is dependent upon the quality of the copy submitted. Broken or indistinct print, colored or poor quality illustrations and photographs, print bleedthrough, substandard margins, and improper alignment can adversely affect reproduction.

In the unlikely event that the author did not send UMI a complete manuscript and there are missing pages, these will be noted. Also, if unauthorized copyright material had to be removed, a note will indicate the deletion.

Oversize materials (e.g., maps, drawings, charts) are reproduced by sectioning the original, beginning at the upper left-hand corner and continuing from left to right in equal sections with small overlaps. Each original is also photographed in one exposure and is included in reduced form at the back of the book.

Photographs included in the original manuscript have been reproduced xerographically in this copy. Higher quality 6" x 9" black and white photographic prints are available for any photographs or illustrations appearing in this copy for an additional charge. Contact UMI directly to order.

University Microfilms International
A Bell & Howell Information Company
300 North Zeeb Road, Ann Arbor, MI 48106-1346 USA
313/761-4700 800/521-0600

Order Number 9411989

Dilatometric study of low profile unsaturated polyester resins

Kinkelaar, Mark Richard, Ph.D.

The Ohio State University, 1993

U·M·I
300 N. Zeeb Rd.
Ann Arbor, MI 48106

**DILATOMETRIC STUDY OF LOW PROFILE UNSATURATED
POLYESTER RESINS**

DISSERTATION

Presented in Partial Fulfillment of the Requirements for

the Degree Doctor of Philosophy

in the Graduate School of The Ohio State University

By

Mark Richard Kinkelaar

The Ohio State University

1993

Dissertation Committee:

Jeff Chalmers

Kurt Koelling

L. James Lee

Approved by

A handwritten signature in cursive script that reads "L. James Lee". The signature is written over a horizontal line.

Adviser
Department of Chemical Engineering

To my wife, Karin

Acknowledgments

I would like to express my gratitude to Dr. L. James Lee, my adviser, for his support and guidance throughout this project and the Engineering Research Center for Net Shape Manufacturing at The Ohio State University for financial support during my graduate studies. I would like to acknowledge Mike Kukla, Roy Renshaw and Bob Ashcraft for the technical support and machine work performed during the design stages of this project and Bing Wang for his assistance and insight offered as a visiting scholar towards the last year of the project. I wish to express my appreciation to Ken Atkins, Donnell Gilliam, Gary Rex and Rob Seats of Union Carbide Corporation for performing the BMC molding work. I would like to thank Rachel Gooding, Paul Clark and Dr. Umit Ozkan for assistance with the BET equipment, Debbie Chiu and Y. C. Chou for some assistance on the SEM work and Henk Colijn for training on the SEM technique. I wish to thank Drs. Jeff Chalmers and Kurt Koelling as members of the dissertation committee. Finally, I wish to thank my family for their support throughout the years of my college life and most of all I wish to thank my wife, Karin, for her understanding and support throughout this endeavor.

Vita

November 26, 1965.....Born – Parma, Ohio

1988.....B.S., The Ohio State
University, Columbus,
Ohio

1990.....M.S. The Ohio State
University, Columbus,
Ohio

Publications

- Kinkelaar, M. R., Hsu, C. P. and Lee, L. J. “Interactions of Reaction, Rheological Changes, Microstructure Formation and Volume Change in the Cure of Low Profile Unsaturated Polyester Resins”, SAMPE Quarterly, **21**(4), 1990.
- Hsu, C. P., Kinkelaar, M. R. and Lee, L. J., “Effects of Thermoplastic Additives on the Cure of Unsaturated Polyester Resins”, Polymer Engineering and Science, **31**(20), 1991.
- Kinkelaar, M. R. and Lee, L. J., “Development of a Dilatometer and Its Application to Low Shrink Unsaturated Polyester Resins”, Journal of Applied Polymer Science, **45**, 1992.

Fields of Study

Major Field: Chemical Engineering

Development of a dilatometer with application to low shrink unsaturated polyester resins.

Table of Contents

Dedication	ii
Acknowledgments.....	iii
Vita.....	iv
Table of Contents.....	v
List of Tables	vii
List of Figures	viii
Chapter	Page
I. Introduction	1
1.1 Problems Caused by Resin Shrinkage in Composite Processing.....	1
1.2 Methods Used to Address Molding Problems	5
1.3 Materials Common to Unsaturated Polyester Compounds	10
1.3.1 Unsaturated Polyester Resin	12
1.3.2 Initiators and Inhibitors	17
1.3.3 Low Profile Additive and Its Mechanism.....	20
1.3.4 Thickeners.....	33
1.3.5 Filler.....	36
1.3.6 Fibers	37
1.3.7 Other Additives	37
1.4 Objective of Study.....	38
II. Literature Review of Dilatometry	42
2.1 Dilatometry Introduction.....	42
2.2 Capillary Dilatometers.....	44
2.3 Plunger Dilatometers	54
2.4 Bellow Dilatometers.....	61
2.5 Miscellaneous Dilatometers.....	63

III. Instrumentation	67
3.1 Introduction	67
3.2 The Dilatometer	68
3.2.1 Overview	68
3.2.2 Hardware Specifics.....	76
3.3 Dilatometer Calibration.....	84
3.3.1 Isothermal Calibration.....	85
3.3.2 Ramping Calibration	91
3.4 Design History.....	100
IV. Volumetric Studies of Low Profile Unsaturated Polyester Resin	107
4.1 Overview	107
4.2 Materials and Formulation.....	109
4.3 Isothermal Studies.....	110
4.4 Ramping Studies.....	121
4.4.1 8°C/Minute Ramping Series.....	121
4.4.2 16°C/Minute Ramping Series.....	131
4.5 Overall Comparison	138
4.6 Shrinkage and Conversion	141
4.7 Change in Morphology/Opacity During Cure	145
4.8 Effect of Pressure on Shrinkage Control	155
4.9 Effect of Filler.....	157
4.10 Effect of Thickener	166
4.11 LPA Mechanism	177
V. Molding and Shrinkage Control	186
5.1 Introduction to Molding.....	186
5.2 D-sight Results.....	189
5.3 Molding Shrinkage	197
5.4 Morphology of Molded Panels.....	199
5.5 Surface Area of Molded Panels.....	207
VI. Conclusions and Recommendations.....	211
References.....	217
Appendices	
A. Dilatometer Operating Procedure.....	225
B. Results from a Different Dilatometer	233
C. Dilatometric Application to Other Materials.....	239

List of Tables

Table	Page
1. Various peroxide initiators and their 10 hour half life temperature data.	18
2. Specifications of the current dilatometer system	84
3. Summary of the formulations used in this study.....	110
4. Percent final shrinkage measured for various LPA concentrations	115
5. Comparison of final shrinkage and color/opacity for the pressure series	157
6. Summary of the thickened sample final shrinkage data	168
7. Summary of BET surface measurement experiments.....	180
8. Molding formulations	188
9. D-sight index of molded panels	196
10. Molding shrinkage data	198
11. Surface area data of molded parts.....	209

List of Figures

Figure	Page
1. Summary of processes which commonly use unsaturated polyester resin as a matrix. Included are standard reactive conditions	2
2. Cut away view of molded boss. Note fiber direction and resin rich area	3
3. Surface profile of an SMC panel, note the difference between long term and short term waviness	4
4. Profilometer reading over a rib (a) conventional molding and (b) two stage pressure molding.....	8
5. Sink mark depth as a function of second stage pressure release time	9
6. Example of polyesterification reaction.....	14
7. Polyesterification with 1:1 ratio of maleic anhydride and propylene glycol. This is the resin most commonly used by the automotive industry	15
8. Structure of the unsaturated polyester reins / styrene copolymerization network	16
9. Plot of typical half life data as a function of temperature. The peroxide used to generate this data was t-butyl perbenzoate.....	19
10. Structures of some of the commonly used initiators (a) dibenzoyl peroxide, (b) t-butyl perbenzoate and (c) t-butyl peroxy-2-ethyl hexanoate (PDO).....	19
11. Molding shrinkage as a function of LPA molecular weight.....	22
12. Surface profile of a part compression molded without the use of a low profile additive	24

13. Surface profile of a part compression molded with the use of a low profile additive	24
14. Dilatometer (shrinkage) profile of (top) resin cured with low profile additive and (bottom) resin cured without low profile additive.....	25
15. Typical SEM micro-graph of unsaturated polyester resin cured with 15% PVAc LPA. This sample was etched to remove the LPA phase.....	26
16. Schematic of LPA mechanism based on local incompatibility	27
17. Schematic demonstrating the roles of microgel formation and LPA in the gelation of UPE resins	28
18. Example of the mechanical loss data as a function of temperature for pure PVAc, UPE with PVAc LPA and UPE without LPA. The peak corresponds to the glass transition temperature of each distinct phase of the material	29
19. LPA and resin concentration as a function of position in the part.....	31
20. Thickening reaction (a) metal ion with carboxylic group [63], (b) complex aggregate structure.....	35
21. Typical thickening viscosity plot.....	36
22. Proposed flow diagram of study	39
23. Improvements in surface waviness of SMC moldings	41
24. Simple bulb and capillary dilatometer	44
25. Dilatometer used by Starkweather to study polymerization shrinkage and kinetics	46
26. Dilatometer used by Braun and Disselhoff to study copolymerizations.....	47
27. Dilatometer used by Hunter to measure polymerization shrinkage.....	48
28. First automatic recording dilatometer.....	50
29. Recording dilatometer used by Bartkus and Kroekel to study polymerization shrinkage and low profile additives	52
30. Ruben and Stochdopole's dilatometer used an optical method to follow the meniscus movement	54
31. Simple plunger dilatometer as described by Tung	56

32. Syringe dilatometer used by Mitani, Shiraishi, Honda and Owens for SMC pastes.....	57
33. Dilatometer based on pneumatic cylinder	60
34. Space flight dilatometer	61
35. An example of a bellows dilatometer design.....	63
36. Schematic of a TA Instruments Thermomechanical Analyzer	64
37. Dilatometer attachment for a TMA	65
38. Dilatometer schematic	69
39. Photograph of the unassembled dilatometer	70
40. Photograph of the assembled dilatometer	70
41. Dilatometer pressure system.....	72
42. Dimensions of upper copper disc	77
43. Dimensions of lower copper disc	78
44. Temperature profile, isothermal calibration.....	86
45. Position data, isothermal calibration.....	87
46. Percent volume change and $(-1) \times \text{conversion}$, isothermal calibration	89
47. Temperature profile, ramp calibration	93
48. Position data, ramping calibration	94
49. Percent volume change and $(-1) \times \text{conversion}$, ramp calibration	97
50. DSC reaction rate data and $(-1) \times \text{derivative percent volume change}$	98
51. Comparison of dilatometer and DSC temperature profiles.....	99
52. Schematic of older dilatometer system used very early in this study	103
53. Overview of LPA mechanism study.....	108
54. Plot of percent volume change versus time for isothermally cured samples and various low profile additive concentrations.....	112
55. Example of isothermal temperature profile used, 15% LPA sample.....	113

56. Plot of percent final shrinkage as a function of low profile additive concentration, cured isothermally at 80°C.....	116
57. Isothermally cured sample morphology, (a) no LPA, (b) 2.5% LPA, (c) 5% LPA, (d) 6% LPA, (e) 10% LPA and (f) 15% LPA.....	117
58. Plot of percent volume change versus time for samples cured at 8°C/minute and various low profile additive concentrations	124
59. Example of 8°C/minute cure temperature profile, 15% LPA sample.....	125
60. Plot of percent final shrinkage as a function of low profile additive concentration, cured at 8°C/minute.....	127
61. 8°C/ minute cured sample morphology, (a) 2.5% LPA, (b) 6% LPA, (c) 10% LPA and (d) 15% LPA.....	128
62. Plot of percent volume change versus time for samples cured at 16°C/minute and various low profile additive concentrations.....	132
63. Example of 16°C/minute cure temperature profile, 15% LPA sample	133
64. Plot of percent final shrinkage as a function of low profile additive concentration, cured at 16°C/minute	135
65. 16°C/ minute cured sample morphology, (a) 2.5% LPA, (b) 6% LPA, (c) 10% LPA and (d) 15% LPA.....	136
66. Overall comparison of the final shrinkage data obtained at isothermal, 8°C/minute and 16°C/minute cure temperature profiles.....	140
67. Comparison of DSC rate data and polymerization shrinkage for the 2.5% LPA sample isothermally cured at 80°C.....	143
68. Cross plot of polymerization shrinkage and conversion, 2.5% LPA sample cured isothermally at 80°C	144
69. Comparison of 2.5% LPA samples cure isothermally at 80°C, demonstrating change in materials with age, inhibitor level and preparation ..	147
70. Morphology of 2.5% LPA samples isothermally cured, (a) original, (b) mix and use after 20 minutes, (c) mix, let set overnight and use and (d) 50 ppm pBQ added.....	148
71. Plot demonstrating point where the reaction was stopped and sample appearance and morphology were observed.....	152
72. Change in morphology during cure, (a) 26 minutes, (b) 50 minutes and (c) 150 minutes in the experiment.....	153

73. Effect of pressure, 2.5% LPA sample isothermally cured at 80°C.....	158
74. Effect of pressure, 6% LPA sample isothermally cured at 80°C	159
75. Effect of pressure on sample morphology (a) 2.5% LPA cured at 0.69 MPa, (b) 2.5% LPA cured at 2.55 MPa, (c) 6% LPA cured at 0.69 MPa and (d) 6% LPA cured at 2.55 MPa.....	160
76. Comparison of filled and unfilled 2.5% LPA samples cured isothermally at 80°C.....	163
77. Comparison of filled and unfilled 6% LPA samples cured at 8°C/minute.....	164
78. Comparison of cure temperature profile for filled and unfilled 6% LPA samples cured at 8°C/minute.....	165
79. Comparison of percent volume change versus time data of thickened samples with various LPA concentrations cured isothermally.....	170
80. Comparison of percent volume change versus time data of thickened samples with various LPA concentrations cured at 8°C/minute	171
81. Percent volume change versus time data of a thickened 15% LPA sample cured at 16°C/minute.....	172
82. Morphology of thickened samples, (a) 6% LPA isothermal, (b) 10% LPA isothermal, (c) 15% LPA isothermal, (d) 6% LPA 8°C/minute, (e) 10% LPA 8°C/minute, (f) 15% LPA 8°C/minute and (g) 15% LPA 16°C/minute	173
83. SEM micro-graphs demonstrating fissure formation (a) 6% LPA sample cured isothermally and (b) 6% LPA sample cured at 8°C/minute	181
84. D-sight output, (a) no LPA, (b) 2.5% LPA, (c) 6% LPA, (d) 10% LPA, (e) 15% LPA, (f) 20% LPA, (g) 25% LPA, (h) 15% LPA thickened and (i) 15% LPA cured at 150°C.....	190
85. Comparison of D-sight index and molding shrinkage as a function of LPA concentration	200
86. SEM micro-graphs of panel morphologies, (a) no LPA, (b) 2.5% LPA, (c) 6% LPA, (d) 10% LPA, (e) 15% LPA, (f) 20% LPA, (g) 25% LPA, (h) 15% LPA thickened and (i) 15% LPA cured at 150°C	201
87. Comparison of D-sight index and BET surface area as a function of LPA concentration	208
88. Comparison of measured temperature profiles using the dilatometric technique described in Figure 33.....	236

89. Comparison of the percent volume change data obtained using the dilatometric technique described in Figure 33	237
90. Plot of percent final shrinkage versus low profile additive concentration, as measured by the dilatometer described in Figure 33.....	238
91. Plot of temperature profile used for BMI study	242
92. Percent volume change data for BMI resin	243
93. Plot of percent volume change as a function of time for a vinyl ester resin with (Derakane 790) and without (Derakane 780) LPA, cured isothermally at 80°C.....	244

Chapter I

Introduction

1.1 Problems Caused by Resin Shrinkage in Composite Processing

Low shrink unsaturated polyester (UPE) resins are commonly used in several reactive processing manufacturing techniques, such as sheet molding compound (SMC) compression molding, bulk molding compound (BMC) injection and compression molding, resin transfer molding (RTM), pultrusion, hand lay-up and resin casting processes. These processes operate at different reaction conditions with temperatures ranging from room temperature for hand lay-up and resin casting to over 150°C for compression, injection and pultrusion, and pressures ranging from atmospheric for casting and hand lay-up to over 7 MPa for injection molding. This is summarized in Figure 1. Descriptions of the various processes are available in the literature [1 - 7].

As these processes share a common matrix, they also share some common manufacturing problems which have hindered growth in their respective markets [8 - 15]. These problems include surface flaws such as sink marks and part surface waviness, and dimensional control problems such as warpage and the inability to accurately reproduce the mold (mold shrinkage or dimensional control). All these

problems are due to, at least in part, the unsaturated polyester resin polymerization and thermal shrinkages. Other factors important to surface quality include porosity, fiber orientation, resin rich areas, a large coefficient of thermal expansion for the matrix and molding problems such as blistering and delamination.

Figure 1. Summary of processes which commonly use unsaturated polyester resin as a matrix. Included are standard reactive processing conditions.

Sink marks are a surface defects which develop on the cosmetic surface of the part, opposite a substructure (rib or boss). Sink marks are caused partly by flow induced fiber orientation as the compound flows into a substructure [7]. The flow causes the fibers to curve or bend into the rib and leaves a resin rich area near the cosmetic side as shown in Figure 2. Two factors lead to sink formation; higher polymerization shrinkage of the resin rich area during cure (the fibers prevent some of the polymerization shrinkage in the surrounding areas) and a larger coefficient of

thermal expansion (COTE) of the resin rich area causing the sink to become larger during cooling [16]. During molding, polymerization shrinkage may cause the part to pull away from the mold yielding a sink and this sink is further developed as the part cools to room temperature because of a larger COTE in the resin rich area.

Figure 2. Cut away view of a molded boss. Note fiber direction and resin rich area [7].

In the literature, surface waviness is divided into long term and short term defects [8, 10]. Short term waviness is associated with surface defects which provide an orange peel like texture. These defects could be caused by fiber pattern readout [7, 17], the part pulling away from the mold locally during cure due to polymerization shrinkage or other molding problems such as porosity and cracking. Short term waviness causes reflections to appear fuzzy, but not distorted. Long term waviness, however, is associated with a distorted visual reflection, similar to old glass window panes. Long term waviness is due to polymerization shrinkage and fiber positioning through the part thickness, as well as residual stresses due to polymerization shrinkage. Figure 3 is a surface profile of an SMC panel measured with a Bendix

Profilometer [18]. A profilometer is a device which uses a probe similar to a phonograph needle to measure surface details. The “needle” is pulled over the surface, measuring peaks and valleys of the part surface. From Figure 3, the local surface noise is shown everywhere and a large depression exists on the right, which corresponds to short term waviness and long term waviness of a part, respectively.

Figure 3. Surface profile of an SMC panel, note the difference between long term and short term waviness [18].

Part warpage is due to residual stresses in the part caused by both thermal and polymerization shrinkage [19]. One scenario that could lead to part warpage is if the resin cures (shrinks) differently or at different times at different positions of the part [20]. In SMC, the molding compound contacts the lower hot mold first and therefore the lower half of the part should react first. Similarly, thick sections react from outside in, causing stress, cracks and voids in bosses and ribs. The same occurs in

pultrusion, where the material being pulled through the die reacts from the outside in [21]. As another example, if one makes a part in which the fibers are concentrated on one surface, leaving one surface resin rich and one surface fiber rich, the part will curve or curl such that the resin rich side is concave. The reason is that during cure, the side of the part with the fiber resists shrinkage because of the fiber orientation; however the side without the fibers will shrink its full amount.

Finally, mold reproducibility is the part dimensional control, or, the ability to exactly reproduce the cold mold cavity dimensions. This is especially important for part design. “Molding shrinkage” or the difference in part and mold dimensions is related to the coefficient of thermal expansion of both the mold and the part material as well the polymerization shrinkage and warpage. The coefficient of thermal expansion (COTE) for a composite is a function of the fiber orientation. With the fibers in plane, the composite COTE is small because the fiber COTE is small, however, transverse to the fibers the composite COTE is more dependent on the resin COTE and is therefore much larger [22]. If there exists preferential fiber orientation in a part, there may be problems with dimensional control, residual stress and warpage.

1.2 Methods Used to Address Molding Problems

There are several techniques available to address surface quality and shrinkage related problems:

- Inclusion of a low profile additive (LPA) in formulation
- In-mold coating (IMC)
- Secondary and finishing operations
- Part and tool design
- Modification of the molding process

A low profile additive is (usually) a non-reactive additive included in the formulation to aid in controlling polymerization shrinkage. The LPA is generally a compatible or partly compatible thermoplastic dissolved or dispersed in the formulation. On cure, the thermoplastic becomes incompatible and localized phase separation occurs, causing a characteristic morphology and compensating volumetrically for the polymerization shrinkage. More will be said later about the use and mechanism of the LPA.

In-mold coating (IMC) is a method used exclusively with SMC molding [7, 14, 16, 23]. After the part is cured, the mold is partly opened and a resin is injected into the cavity. Vinyl ester or a blend of polyether urethane and a small amount of polyester resin are commonly used as IMC resins. The resin flows to form a film on the part and the mold is reclosed until the IMC resin is cured. This provides a resin rich layer which covers and fills porosity, sink marks, fiber readout, micro-cracks and other surface flaws and, depending on IMC resin formulation, may provide a conductive coating for electrostatic painting [7, 16, 23].

Secondary and finishing operations include sanding and use of putty to fill damaged areas, similar to the techniques used in an automotive body shop. These operations are used when the surface is damaged, but the structural integrity is intact. A review of some of the techniques is available [9].

Often when structural integrity and a cosmetic surface are required, the part is divided into several smaller parts and adhesively bonded together [16]. Examples of this are Chevy Corvette hood, some Navistar truck hoods and the spoiler on the 1993 Pontiac Trans Am [23, 24, 25]. For instance, the Corvette hood is manufactured in two parts; the cosmetic skin and the reinforcing structural member. The structural member is then adhesively bonded to the outer skin, providing the desired rigidity and strength while avoiding the use of ribs and the corresponding sink marks. However, part consolidation is one of the advantages of using a composite material and therefore the current manufacturing technique does not take advantage of all the benefits of using a composite material. Much research is being done on the effect of rib geometry to reduce sink mark formation and potentially provide a process in which acceptable parts can be made [16, 26]. Important factors include rib depth and width and the ratio between them, the radius of the corner into the rib [16], and the friction coefficient and surface roughness of the mold just outside the rib [26]. These variables can be adjusted to minimize sink marks; however, the sink marks are still obvious enough to prevent the use of ribbed parts in most cosmetic applications.

Finally, modification of the molding process to improve surface quality is a current issue [27, 28, 29]. The two key modifications include vibrating the mold during part cure [28] and staging (varying) the pressure in compression molding [27]. When molding a part, high pressure is initially required to fill the mold. This will prevent short shot or incomplete mold filling problems. However, it has been shown that reducing the pressure by approximately 75% at some time during the cure can reduce sink mark severity by up to 70% [27], as demonstrated with a profilometer reading in Figure 4 [29], and improve overall surface quality [27]. Furthermore, there is an optimum release time as shown in Figure 5 [27] which is a function of cure conditions. The mold movement during the pressure cure cycle has been measured

by some researchers [27, 29]. It has been used to explain the pressure release effect, but a limited understanding as far as the mechanism is concerned is prominent feature in the work and most data are found by trial and error molding. One study [27] has shown that the optimum release time corresponds to a peak in the material expansion (due to heating) and the onset of reaction exotherm. This study has also shown that sink mark severity decreased with decreasing the second stage pressure; however, surface waviness increased with decreasing second stage pressure posing an optimization problem. It has been proposed that optimum pressure release time is related to gel time and LPA mechanism [29]; however, the phenomenon still requires study.

Figure 4. Profilometer reading over a rib (a) conventional molding and (b) two stage pressure molding [29].

From the discussion of all the above methods used for enhanced surface quality and dimensional control, one can see that all the methods, except the inclusion of LPA in the formulation, are equipment or labor intensive. In addition, the pressure

staging requires the use of LPA for best performance. If the LPA could be used to solve or minimize all the problems, labor and equipment costs could be reduced markedly.

Figure 5. Sink mark depth as a function second stage pressure release time [27].

Unfortunately, the LPA mechanism is not well understood and much of the work in this area relies heavily on trial and error moldings. This is very costly in terms of materials, equipment and labor, and provides only limited understanding of the LPA mechanism. The purpose of this study is to provide a better, more analytical method of determining LPA performance as well as providing a better understanding of the LPA mechanism. The direction and motive of this study will be discussed later

in this chapter. Before that, a review of the compounding materials and the current understanding of the LPA mechanism will be presented.

1.3 Materials Common to Unsaturated Polyester Compounds

As mentioned in the first section, unsaturated polyester compounds are used in a wide variety of reactive processes and applications. Though these applications are quite different in cure conditions and final product requirements, many of the material aspects are quite similar. The optimum formulation changes slightly for each process and application, however, most UPE compounds include:

- Unsaturated polyester resin and a diluting monomer
- Initiator and sometimes an inhibitor
- Low profile additive
- Thickening agent
- Filler
- Glass or other reinforcing fiber
- Other additives such as mold release, viscosity reducing agents, etc.

A brief discussion of each material is in the sections to follow. But first, an overview of the material roles in the compounding is given.

The unsaturated polyester resin and styrene are the only reactive polymeric materials in the formulation. The initiator is used to start or initiate the free radical copolymerization by decomposing to provide a free radical. This can be done either thermally, as is the case most of the time, by redox reaction (use of a promoter) or photochemically. An inhibitor is sometimes used to postpone reaction (solidification) of the compound by consuming the free radicals until all the inhibitor is consumed. Ideally, the inhibitor / free radical reaction is much faster than the initiation of polymerization, therefore the inhibitor is first consumed then polymerization occurs. The low profile additive is a compatible or partially compatible thermoplastic added to the compound to control polymerization and molding shrinkage. The LPA does not, in general, participate in the free radical polymerization. The LPA mechanism will be discussed later in this section. The thickening agent is used to increase the viscosity of the material before molding. It may take several days in a controlled environment to get to the desired viscosity. Thickening is most often done for SMC and BMC, where it is important to be able to easily handle the material. In addition, thickening provides the viscosity necessary to carry fibers during compression molding and minimizes fiber orientation [10]. The key role of the filler is to stretch material costs. It also has some interesting effects in compounding that will be discussed later. Glass or other fiber is used to enhance strength and stiffness of the part. It also controls the coefficient of thermal expansion. Other materials used in compounding include mold release agents to aid in part removal after cure, viscosity reducing agents to temporarily reduce compound viscosity during compounding, pigment and other materials used to enhance fire properties, cure behavior, etc.

1.3.1 Unsaturated Polyester Resin

The first record of unsaturated polyester resins dates back to a researcher named Vorlander in 1894 [30]. The material was not used to any significant degree, though, until after World War II when styrene, the copolymerization monomer of choice, started to be produced on a large scale and the material could easily be cross-linked [30]. The first applications in the 1940's were a form of BMC called premix. The material was compounded with styrene, peroxides, filler and fiber and rolled into a log shape [7]. The premix log was then cut to the desired size and compression molded. From here all the other processes were developed.

The current market demand in America for unsaturated polyester resin is now over 1.4 billion pounds annually [30] and has a large degree of diversity in both application and chemistry. Consequently, the intention here is to introduce the basics of the material and its chemistry and not to cover the material exhaustively. A much more detailed description of the material and its manufacturing are available elsewhere in the literature [5, 7, 9, 10, 30-32].

Unsaturated polyester resin is a prepolymer produced by the condensation polymerization of an unsaturated diacid or anhydride and a glycol. This produces a prepolymer backbone with several unsaturated or $C=C$ bond sites. The $C=C$ bond sites are then used to cross-link the unsaturated polyester resin, producing a thermosetting network when copolymerized with styrene.

A saturated diacid is sometimes substituted for some of the unsaturated diacid in the polyesterification reaction to modify or engineer the final (thermoset reaction)

product properties. Figure 6 is an example of the polyesterification reaction used to produce an unsaturated polyester resin. Note that, in this case, some saturated diacid is substituted for some of the unsaturated anhydride [10, 31]. Here, one mole of maleic anhydride and one mole of isophthalic acid are reacted with 2 moles of propylene glycol to produce water and the unsaturated polyester resin. One mole of the saturated isophthalic acid is used instead of using two moles of unsaturated maleic anhydride. The resultant resin is known as an isophthalic unsaturated polyester or iso resins [30].

The reaction is usually carried out using a two step procedure when working with a less reactive saturated diacid [9, 31]. In the case shown in Figure 6, the isophthalic acid and propylene glycol are charged into a reactor and reacted at 190°C until a low acid number is obtained, implying that all the isophthalic acid has reacted. Then the reactor is cooled to 160°C and the maleic anhydride is added. This provides a better distribution of the isophthalic acid group in the unsaturated polyester chain, as the glycol will react preferentially with the maleic anhydride if both are charged at the same time. The reaction proceeds until the desired acid number, which corresponds to the desired prepolymer molecular weight, is obtained [7, 10]. On average, the desired value of X in Figure 6 (the number of repeating groups) is 6 - 20 [7].

Finally, when the desired unsaturated polyester is obtained, the resin is diluted in (usually) styrene and shipped as a solution. This makes it easier to handle and compound. A more detailed explanation of the reaction procedure as well as some of the equipment required are available in the literature [7, 9, 31, 32].

Figure 6. Example of polyesterification reaction [10].

The anhydride, diacid and glycol are selected to provide the desired final product properties; larger constituent materials as well as the use of large saturated diacids generally provide a more flexible product with better impact properties whereas smaller constituent materials provide a more rigid and brittle product with a better heat deflection temperature [9, 10]. The material most commonly used in automotive applications [7] and used in this study is produced by reacting a 1:1 ratio of maleic anhydride and propylene glycol. This is known as a polypropylene fumarate resin. This resin is produced [7] as outlined in Figure 7. First maleic anhydride and a small excess of propylene glycol are reacted at $>60^\circ\text{C}$, which is slightly above the melting point of the maleic anhydride (the first two steps in Figure 7). Then more glycol is added and the system is heated to over 140°C . The resulting unsaturated polyester is shown in Figure 7. Since both are relatively small molecules

and no saturated diacids are used, this provides a cross-linked product with good stiffness and heat deflection properties [7].

Figure 7. Polyesterification with 1:1 ratio of maleic anhydride and propylene glycol. This is the resin most commonly used by the automotive industry [7].

So far the isophthalic resins and the polypropylene fumarate resins (or sometimes known as maleate resins) were discussed. There are other commonly used resins available commercially. These include resins based on phthalic anhydride and maleic anhydride called orthophthalic resins, bisphenol A fumarates based on propoxylated bisphenol A and fumaric acid and chlorendic polyester resins based on chlorendic anhydride and maleic anhydride [30, 32]. In addition, vinyl ester resins are sometimes used in conjunction with or in place of unsaturated polyester resins [33, 34]. The benefits and weaknesses of several of the constituent materials are covered at length in Burns [9]. As stated earlier, most of the commercial resins are shipped as a solution in styrene, generally around 60% - 70% resin by weight (30% - 40% styrene) [7].

The resin chemistry discussed up to this point occurs at the resin manufacturing facility. Now let us discuss the reaction that occurs in the mold. Generally, the unsaturated polyester resin is further diluted to 40% - 55% based on the total weight of the styrene, unsaturated polyester resin and LPA [35]. Too much styrene will result in an excessively brittle part, too little and the viscosity would be prohibitive to good fiber wetting and high filler loads could not be obtained [7, 36, 37]. There are several other copolymerization monomers available which are used in combination or as the sole diluting monomer, including alpha-methyl styrene, chlorostyrene, vinyl toluene, divinyl benzene, vinyl acetate and methyl methacrylate [7, 38, 39]. Assuming that styrene is used to copolymerize the unsaturated polyester resin, Figure 8 [7] demonstrates the final, cross-linked chemical structure [7, 10]. The free radical polymerization reaction occurs between the styrene C=C and the unsaturated polyester resin C=C sites. Recall there are, depending on resin manufacturing, 6 to 20 C=C bond sites per unsaturated polyester molecule. These sites are connected by a chain of 1 to 5 styrene groups, as shown by x in Figure 8 [7].

Figure 8. Structure of the unsaturated polyester resin / styrene copolymerization network [7].

1.3.2 Initiators and Inhibitors

The initiator is used to start or initiate the free radical polymerization by decomposing to provide two free radicals. This can be done either thermally, as is the case most of the time, by redox reaction (use of a promoter) or photochemically. The resultant free radical attacks the unsaturated polyester C=C bonds, starting a chain reaction.

Most initiators are some form of organic peroxide, however, some azo and dibenzyl compounds are also used less frequently [9]. There are several peroxides available on the market, all varying in decomposition half life. Table 1 is a brief list of some common initiators and the 10 hour half life temperature [7, 9, 40] determined in benzene. The half life data can be affected by the type and polarity of the solvent it is in as well as peroxide concentration [40, 41]. Transition metals, strong acids or bases, reducing agents and amines will also affect decomposition rate data [40].

The 10 hour half life temperature is a commonly provided characteristic of an initiator and it is a good indication of its reactivity. As a rule of thumb, the useful molding or curing temperature for an initiator is approximately 40°C over the 10 hour half life temperature [7], though this may have to be adjusted to account for mold filling times, part thickness and compound characteristics. If the temperature is too low, the reaction is unnecessarily slow and if it is too high, side reactions could occur minimizing the degree of cure [7]. A typical relationship between half life and temperature is shown in Figure 9 [32] for *tert*-butyl perbenzoate. Note the region in which decomposition half life is very small (near zero); that is the useful operating temperature range [32]. Finally, Figure 10 gives the chemical structures of the more

commonly used peroxides. Most important here is PDO (t-butyl peroxy-2-ethyl hexanoate) and TBP (t-butyl perbenzoate) as they were used in this study.

There is one final method of producing the free radicals that requires review. That is the use of promoters for low temperature applications. Several promoters are available to induce or catalyze the decomposition of initiators into radicals, including cobalt salts for ketone peroxides, vanadium salts for peresters, perketals and hydroperoxides and amines for diaryl peroxides [32, 41]. The metal salts are actually catalysts working on the redox reaction principles [32, 41], however, the amines react with the peroxide and form the radical. As a word of warning, the metal salts and peroxides will react violently if mixed together at high concentration, therefore, care must be taken to ensure that this does not occur while formulating.

Table 1. Various peroxides and their 10 hour half life temperature data [7,9, 40].

Peroxide	10 Hour Half Life Temperature (°C)
Di-(sec-butyl) peroxydicarbonate	40
Dibenzoyl peroxide	73
t-Butyl peroxy-2-ethyl hexanoate (PDO)	73
t-Butyl peracetate	102
t-Butyl perbenzoate	105
Dicumyl peroxide	115
2,5-Di(t-butylperoxy)-2,5-dimethyl-hexyne-3	128

Figure 9. Plot of typical half life data as a function of temperature [32]. The peroxide used to generate this data was t-butyl perbenzoate.

Figure 10. Structures of some of the commonly used initiators (a) dibenzoyl peroxide, (b) t-butyl perbenzoate and (c) t-butyl peroxy-2-ethyl hexanoate (PDO).

An inhibitor is sometimes used to postpone reaction (solidification) of the compound by consuming or absorbing the initiator produced free radicals until the inhibitor is consumed. This is very useful if mold filling takes a long time, as for complicated or large parts. The inhibitor / free radical reaction is much faster than the initiation of polymerization, therefore the inhibitor is consumed before polymerization. Like initiators, there are several inhibitors available to the industry. The two most common are p-benzoquinone and hydroquinone. Oxygen is also known to be an (often overlooked) inhibitor, forming a stabilized species which does not propagate polymerization [41].

1.3.3 Low Profile Additive and Its Mechanism

The purpose of the low profile additive is to compensate for the thermal and polymerization shrinkage of the UPE resin at a minimum cost to other cure properties, such as strength and stiffness, reaction rate, etc. For non-cosmetic applications the low profile additive is often omitted from the formulation. In this section, first the LPA material characteristics will be covered, including material characteristics which are believed to be important to low profile activity. Following the materials aspect is a presentation of the current understanding of the low profile additive mechanism including some of the experimental techniques used to investigate it.

The LPA is a thermoplastic material which is compatible or partially compatible with the styrene and unsaturated polyester resin mixture before cure and becomes incompatible at some time during the cure. Except for a few unusual cases,

the low profile additive does not participate in the free radical polymerization [42]; however, it is known to have an effect on compound viscosity and thickening [10, 43 - 46].

Standard low profile additives include polyethylene (PE) [7, 10], polystyrene (PS) [7, 10, 36, 37], poly(vinyl acetate) (PVAc) [35 - 39], poly(methyl methacrylate) (PMMA) [10, 43], polymers prepared from ϵ -caprolactones [9, 35, 39], poly(styrene-co-butadiene) [7, 45], polyurethanes [10, 42, 47], co-polymers with acrylates [10, 37] and other less common thermoplastics. The amount of LPA used in the formulation is dependent on the application and is usually determined by trial and error. The acceptable limits vary in the literature, some say 7% - 20% by weight range [10], others 5% - 25% [35] based on organic content of the compound. The optimum amount varies for different LPAs and reactive conditions.

Other factors to consider in picking an LPA are LPA molecular weight, dipole moment and glass transition temperature. The molecular weight of the LPA has been shown to have a useful range which is LPA specific. For the case of PVAc, the useful range is 10,000 - 250,000, and preferably between 25,000 and 175,000 [37]. Another study has determined LPA molecular weight effect on molding shrinkage (comparison of cold mold and cold part dimensions, a method of determining mold reproducibility) as shown in Figure 11 [7]. The material used as an LPA in Figure 11 was a polyester urethane.

Figure 11. Molding shrinkage as a function of LPA molecular weight [7].

Good shrinkage control has been correlated with a large dipole moment in the LPA [48]. In that study, the dipole moment of uncured polyester resin was estimated at 2.0 - 2.5, decreasing to an estimated 0.2 to 0.8 on cure. The dipole moment was determined to be 1.6 for poly(vinyl acetate) and only 0.3 for polystyrene. It was hypothesized that an LPA with a large dipole moment would be very compatible with the highly polar unreacted resin, however, on cure the LPA would become increasingly incompatible due to the large developing difference in polarity. In essence, the difference in dipole moment would act as a driving force for phase separation [10, 48]. For the case of PVAc, this seems to be true. For a less polar LPA, one would expect that the driving force for phase separation to be less and that LPA performance should decline, as has been shown by polystyrene LPA performance [10].

Finally, the LPA glass transition temperature and LPA bulk thermal expansion coefficient were determined to be important for LPA performance [10, 48]. As the material is heated it expands. The more it expands on heating, the more volume it will occupy on gelation and the more it will compensate cure shrinkage.

With all that is known about what variables affect low profile activity, it is surprising to learn that the LPA mechanism is still not well understood. The first significant work in the area was by Bartkus and Kroekel [18, 49]. They molded a few parts, some with LPA, some without, and reported that the surface quality (as measured by a profilometer) of molded parts improved with the addition of LPA. This is shown in Figure 12 and Figure 13. In addition, they built a dilatometer (see Chapter 2 for a literature review of dilatometry) and measured polymerization shrinkage with and without LPA as shown in Figure 14, showing that LPA controlled the polymerization shrinkage. Finally they proposed a mechanism to explain the LPA effect, known as the optical heterogeneity theory in the literature now [10, 49, 50], which involved the observation that the neat resin with LPA will turn white on cure whereas the resin without LPA will remain transparent. They speculated that some phase separation occurred and showed some photos to that effect [49]. Furthermore, they believed that either during cure or just due to emulsion like behavior, the styrene was collecting in these LPA rich regions and on a large heat of reaction exotherm (over the atmospheric pressure boiling point) the styrene vaporized and styrene vaporization compensated volumetrically for polymerization shrinkage [49]. Other researchers claimed that this was not possible as at 200°C (above most process operating and exotherm temperatures) the vapor pressure of styrene was 50 psig, which, when compared to most molding conditions described in Section 1.1, is very low [50]. It is interesting to note, however, that if one cures the neat low profile resins at atmospheric pressure and higher temperature, as the cure proceeds the material foams, which is possibly what the early researchers observed.

Figure 12. Surface profile of a part compression molded without the use of a low profile additive [18].

Figure 13. Surface profile of a part compression molded with the use of a low profile additive [18].

The work of Bartkus and Kroekel started a large flow of studies in low profile additive mechanism [4, 7, 9, 10, 12, 29, 33 - 35, 43 - 48, 50 - 66]. However, the mechanism and some of the key variables are still topics of controversy. Perhaps the most common aspect of the studies is the use of microscopy (optical and scanning electron) to study the resin - LPA morphology.

Figure 14. Dilatometer (shrinkage) profile of (top) resin cured with low profile additive and (bottom) resin cured without low profile additive [18].

Most of the microscopy studies are of the final cured resin, however, studies of morphology as function of gelation have been accomplished [56, 57]. Figure 15 is a sample scanning electron microscopy (SEM) micro-graph of an unsaturated polyester resin cured with 15% PVAc LPA. The sample was prepared by first fracturing the material and then etching it with dichloromethane to remove the thermoplastic (LPA) phase. Therefore, the material one sees in Figure 15 is the cured unsaturated polyester phase topography.

Figure 15. Typical SEM micro-graph of unsaturated polyester resin cured with 15% PVAc LPA. This sample was etched to remove the LPA phase.

It is important to realize that the characteristics of the morphology does change greatly for different low profile additives [10, 48, 52, 57, 58, 61, 64, 66], however, a particulate structure is common to most of them. This particulate structure led to the conclusion that the low profile additive separated out locally on

cure, as shown in Figure 16 [56, 57]. It was determined that when the polymerization started (initiated), the LPA quickly became incompatible. This caused the LPA to phase out of the locally cured area, providing a spherical structure which was locally UPE rich inside and surrounded or encapsulated by a locally LPA rich layer.

Figure 16. Schematic of LPA mechanism based on local incompatibility [57].

This concept was further developed with the aid of light scattering to handle the possibility of microgel formation [56, 57], as shown in Figure 17. In Figure 17 (a) the induction of polymerization occurs and monomeric radicals are formed. This quickly leads to the microgel formation stage in Figure 17 (b) in which the monomeric radicals link a few of the unsaturated polyester and styrene molecules. As the reaction progresses more microgels are formed and clusters of microgels, connected by chemical bonds start to form. If an LPA is present, this is the stage in

which LPA phase separation occurs, as shown in Figure 17 (c, ii). If no LPA is present, both microgels and clusters are formed but the phase separation does not occur as shown in Figure 17 (c, i). Finally, macro-gelation occurs by both chemical cross-linking, as shown in Figure 17 (d, i and ii) and phase inversion or physical cross-linking as shown in Figure 17 (d, iii).

Figure 17. Schematic demonstrating the roles of microgel formation and LPA in the gelation of UPE resins [56, 57].

There are other experimental methods available to prove the existence of a two phase system. A less common approach is to use dynamic mechanical analysis (DMA, sometimes known as torsional pendulum) to get $\tan \delta$ or mechanical loss

spectra as a function of temperature [10, 48, 52]. An example of such a plot is shown in Figure 18 [48]. Mechanical loss spectra provides a peak corresponding to the glass transition temperature of each distinct phase of a material [10]. In Figure 18, the dotted line is the cured polyester resin without an LPA, the dashed is the polyester resin cured with PVAc LPA and the solid line is the neat PVAc response. Note the two peaks in the LPA/UPE curve which correspond to the peaks of the constituent materials. This is proof of two phases. All the morphology and mechanical loss spectra help to explain what occurs on cure, however, they do not clearly explain how exactly the polymerization shrinkage is reduced.

Figure 18. Example of mechanical loss data as a function of temperature for pure PVAc, UPE with PVAc LPA and UPE without LPA. The peak corresponds to the glass transition temperature of each distinct phase of the material [48].

The most common industrially used method of determining LPA performance is to mold several parts and measure molding shrinkage and surface quality. As previously mentioned, molding shrinkage is the comparison of cold mold and cold part dimensions [7, 9, 10, 35, 48, 53, 55] and has units in length shrinkage per length part or in percentage. Generally a square or rectangular shaped part is used and the molding shrinkage is determined by [35, 37, 46]

$$\text{Shrinkage (inch / inch or mils / inch)} = \frac{a - b}{a}$$

where

$a = \sum$ lengths of four sides of the cold mold

$b = \sum$ lengths of four sides of the cold part

Surface quality is measured by various methods including reflection of a grid pattern off the part [10], profilometers [18, 49], LORIA [7, 10, 67] and Diffracto D-Sight [10, 27, 68]. LORIA is a laser light technique developed by Ashland Chemical Company. Lines of laser light are reflected at a low angle off of a 10" by 10" section of the part to be analyzed. The light reflecting off the part is projected on a reflective screen and this reflection is picked up with a video camera. The images of the reflected light amplify the surface defects of the part and these images are analyzed by a computer routine to give an unbiased index [10, 67]. Diffracto is another reflective method. Light from a single white source is reflected off the part to a retro-reflective screen, back to the part and into a solid state camera. This image is sent to a computer for analysis and hard copy. Diffracto also gives an index value, which

correlated well with LORIA data [68]. The advantages of Diffracto and LORIA are that these methods provide an index or unbiased number to compare a large number of parts and only require about half a minute [68]. Profilometers take up to 15 minutes per line and visual inspection tends to be biased and less repeatable.

Finally, one study used microscopy and infrared analysis to determine LPA and UPE concentration as a function of depth into the part. Figure 19 is a plot of this data [69]. This study showed that the LPA and resin migrate to the surface of the part and that the LPA migrates preferentially over the resin. The study also showed that the part was fiber deficient in the top 125 μm .

Figure 19. LPA and resin concentration as a function of position in the part [69].

Given this battery of tests and the corresponding data, the current LPA mechanism theory in the literature for controlling polymerization shrinkage varies slightly, but is generally a variation of the following [9, 10, 48, 50, 56, 57]:

1. As the material is heated it expands thermally.
2. The rise in temperature causes initiator decomposition and cure starts.
3. The once compatible thermoplastic becomes incompatible and starts to form a second phase, possibly by the mechanism described in Figure 17.
4. Unreacted styrene and UPE resin starts to collect in the thermoplastic phase.
5. Temperature and degree of polymerization continue to increase. As the degree of polymerization increases, the UPE phase will shrink. As the temperature increases, the volume occupied by the LPA and unreacted monomer increases, compensating for polymerization shrinkage.
6. The monomer in the LPA phase starts to react, creating micro voids in that region due to the polymerization induced stress. Alternatively, some researches propose that the polymerization shrinkage in the UPE phase causes a large stress to occur in the LPA phase which leads to micro voids in the LPA phase [47].
7. Finally, part cooling occurs. Above the T_g of the UPE resin phase (approximately 170°C as shown by the UPE peak in Figure 18) the bulk coefficient of thermal expansions of the LPA phase and the UPE phase are about the same. Below the T_g of the UPE phase, the UPE phase will shrink much less on cooling than the LPA phase. This difference in

cooling shrinkage will cause more micro voids to occur in the LPA phase as more stress is applied over the LPA phase and will continue until the T_g of the LPA phase has been reached (approximately 45°C from Figure 18).

This mechanism does not take into account a number of key observations. The role of LPA migration under molding conditions intuitively seems important, but is not explained. Nor does the proposed mechanism explain the need for a large reaction exotherm for best LPA performance as observed in the literature [50]. In addition, the role of molding shrinkage and surface quality and how they are controlled by LPA are not very clear from the model. Finally, it has been shown that larger than normally needed amounts of styrene (compared to systems without LPA) are best for LPA performance [50].

1.3.4 Thickeners

Thickeners are additives used in compounding to increase compound viscosity which in turn provides for ease of handling and fiber carry during molding [7, 9, 10, 39, 44, 55, 70 - 77]. The use of thickeners is almost exclusively limited to SMC and some BMC applications [9]. SMC is manufactured in sheet form and is often cut by hand and hand placed in the mold. On thickening the sticky resin loses its tackiness and becomes a pliable solid, similar in consistency to leather and much easier to handle than the unthickened resin [7]. In addition, the use of a thickener enables the compounder to use a less viscous system to compound, providing for a higher glass fiber and filler loads. Finally, the thickening behavior enables the resin to better carry

the fiber during compression molding (SMC, BMC), enhancing fiber distribution and preventing, to some degree, fiber orientation [7, 10]. Typical concentrations of thickener are between 0.5 and 5 part per hundred resin (phr) depending on the thickener and resin system used [9].

There are two basic thickening methods: the use of alkaline earth oxides or hydroxides and the use of isocyanate [7, 10, 77]. Combinations of the two methods, called dual maturation, are also sometimes used [7]. The isocyanate method or interpenetrating network (IPN) uses the reaction between the hydroxyl groups in the resin and the isocyanate groups to increase molecular weight and therefore viscosity [77]. More commonly, and the method of interest here, are use of the alkaline earths thickeners, especially magnesium and calcium oxide and hydroxide. The exact reaction mechanism is still a topic for debate [7, 9, 10, 70, 74]; however, the literature agrees that the acid groups in the resin reacts with the alkaline earth. The reaction is shown in Figure 20 (a) [70]. According to polymerization theory, the rise in viscosity is too large for such a limited increase in molecular weight, therefore it has been proposed that some sort of ionic orientation or aggregation plays an important role in thickening, as shown in Figure 20 (b) [7].

During the early development of low profile additives, it was found that the low profile resin became sticky or tacky on thickening due to the LPA becoming incompatible with the thickened resin [10]. To counteract the undesired separation, carboxyl groups were added to the low profile additive thermoplastic. This causes the LPA to participate in the thickening reaction and prevents separation before cure [10, 46]. What is not clear is the effect this has on the LPA mechanism.

Figure 20. Thickening reaction, (a) metal ion with carboxylic group [70], (b) complex aggregate structure [7].

Depending on the thickening additive or agent, the material may have to age or mature at approximately 27°C for several days before it is moldable [74]. Figure 21 is a plot of viscosity versus time for an alkaline earth thickening system [74]. There are typically three stages. The first stage, (1) in Figure 21, is the induction period. This is followed by a rapid rise in viscosity (2). Finally, a stable viscosity (moldable zone) is obtained after one to four days of aging (3). Once thickened, the material has a shelf-life of up to six months or more [73] but it is usually molded after three or four days.

Moisture content in the compound, thickener particle size distribution and thickener concentration all play important roles in the thickening rate of alkaline earth oxides and hydroxides [9, 73]. Moisture has been shown to increase the thickening rate in the induction period [9] and, as one would expect, the more thickener used, the faster the thickening behavior and the higher the final viscosity [73].

Figure 21. Typical thickening viscosity plot [74].

1.3.5 Filler

Several materials are available for use as a filler, including calcium carbonate, talc, clays, aluminum trihydrate [7, 9, 72], hollow glass spheres [7, 72] and ground SMC [78, 79]. As the name implies, one of the key purposes of a filler is to extend the resin and reduce costs. However, there are several other advantages to using a filler. Some fillers have a specific purpose, such as the aluminum trihydrate. Aluminum trihydrate is used for improved fire properties [7, 9]. Other advantages in general include lower polymerization shrinkage based on compound volume and less cracking due to shrinkage [7], better surface quality [7], increased Young's modulus with little cost to the composite strength [80 - 82], increased thermal conductivity [83], decreased coefficient of thermal expansion [22, 82], increased impact properties [7, 82] and reduced permeability to liquids and gasses [82]. In most cases a mixture of fillers is used and the filler load is varied for the optimum of properties and cost.

1.3.6 Fibers

Fibers are used in a composite to enhance strength and stiffness properties; they are the load bearing constituent of the fiber-matrix composite. In addition to strength and stiffness, fibers reduce coefficient of thermal expansion (reduce molding shrinkage), increase heat distortion temperature and provide better impact properties. By the nature of fiber reinforcement, one is free to design a part with directional properties.

Types of fibers used in composites include several varieties of glass fibers, carbon fibers, aramid fibers (Kevlar), quartz fibers, boron fibers, thermoplastic fibers, etc. [22, 82, 84, 85]. By far, the most common fiber used is E glass. Fibers are used in a variety of forms including random, bi-directional, unidirectional, chopped, continuous, milled or in any combination of orientation and form. The different fibers and orientations provide different physical properties which are used to design the part properties. Composite design is beyond the scope of this work, however, several texts and review articles are available to the reader [22, 82, 84, 86, 87].

1.3.7 Other Additives

There are several other additives used in composite processes which are used with a specific purpose and often with a specific process. They do not, in general, affect composite mechanical or cure properties. A mold release agent is one such additive [7, 9, 10]. Mold release is added to a compound to aid in part removal from

the mold. Without mold release, part removal is difficult if not impossible; however, the use of mold release often causes problems with paint application. Viscosity reducing agents are another such additive. They are used to decrease viscosity during compounding, which aids in fiber wetting and permits a higher filler load [35, 36]. Other additives include pigments [38, 46, 60], air release agents [88, 89], styrene monomer emission reducing agents [90] and conductive additives used for EMI shielding [72].

1.4 Objective of Study

In the previous sections of this chapter, some of the key issues of unsaturated polyester resin materials and composite processing were covered. From the discussion, it is evident that the role of polymerization shrinkage in the processing of this material is important and not well understood. Based on this lack of understanding in the literature, this study was designed as shown in the flow diagram in Figure 22. The first step in studying polymerization shrinkage was to develop an analytical method to measure polymerization shrinkage during cure (not just final shrinkage data as is available by density determination). Traditionally, a piece of equipment used to measure the pressure - volume - temperature relationship of a material is called a dilatometer. This study is a special case of dilatometry in that conversion is also a variable, so we need to measure the pressure - volume - temperature - conversion (reaction) relationship. The next chapter is a literature

review of dilatometry techniques and their limitations and applicability. Chapter 3 is a description of the dilatometry technique developed for this study and its calibration.

Figure 22. Proposed flow diagram of study.

After development of the dilatometer, the LPA mechanism required investigation in a more refined manner than previously available in the literature. Varying the material type was not considered as important here as understanding the effect of heating conditions, pressure, LPA concentration and the effect of specific key compound constituents such as filler and thickener. The goal is to answer the

question “What are the important variables and how do they affect polymerization shrinkage and LPA mechanism?”. This work is covered in Chapter 4.

Once the LPA mechanism and all the variables related to it are understood, the polymerization shrinkage and molded part properties need to be correlated. To accomplish this a method similar to that described as “the critical shrinkage control test” was used [10, 51]. The test entails a molding process similar to compression molding of BMC using a compound with minimum fiber content (on the order of 10% by weight).

The desired results of this study include:

- Demonstration of a method to measure polymerization shrinkage and low profile activity.
- A better understanding and quantification of some of the important variables in LPA mechanism.
- Demonstration of a method to optimize reaction conditions or material to provide better shrinkage control.
- A better understanding of the relationship between shrinkage control and molded part surface quality and dimensional control.

One might ask then, what is the applicability of this work? To answer this, consider the development/improvement of SMC over time. Figure 23 is a plot of the surface waviness of parts produced as a function of year [91]. From the plot, one can see that the improvements are marked, however, considering the amount of time involved (almost 30 years) improvement timing could be accelerated. It will be up to industry to use the understanding, data and trends developed here to develop or

modify resin design and improve the molding technology. With the understanding developed in this work, molders and material producers could better design a compound or resin system for a specific application and, hopefully, eliminate at least part of the trial and error involved. This is especially important to researchers in the newer composite process areas, such as RTM, casting or other less developed methods where LPA technology is not well defined [59, 62].

Figure 23. Improvements in surface waviness of SMC moldings [91].

Chapter II

Literature Review of Dilatometry

2.1 Introduction to Dilatometry

A dilatometer is a device used to measure the pressure-volume-temperature (or PVT) relationship of materials. Examples of traditional dilatometry data include coefficient of thermal expansion (COTE) or specific volume data from a steam table. As a special case and more applicable to this study, dilatometry has also been applied to reacting systems. Reaction adds several degrees of complexity to the technique, including:

- Temperature control problems due to heat of reaction exotherm.
- Require the ability to distinguish thermal effects from reactive volume change.
- Need for a sample environment which will not interfere with, catalyze, inhibit or modify reaction kinetics.
- Require repeatable and often quick heating and both isothermal and ramping modes.
- May need to handle both liquids and solids during the same experiment as the material reacts.

Coupled with these difficulties is the fact that reaction creates a path specific process whereas non-reactive dilatometry data is a state function and therefore not path specific. As an interesting aside, before the development of thermal analytical techniques, such as differential scanning calorimetry (DSC) and differential thermal analysis (DTA), a simple form of dilatometry was used to measure polymerization kinetics. However, in light of the relative ease of thermal analytical techniques and the difficulties and limitations of the simple dilatometry techniques, reactive dilatometry has almost completely disappeared in the current literature. Most dilatometers were not designed for use with reactive systems and the ones that were are generally not current technology.

Reactive dilatometry is of the greatest interest for this study, however, dilatometers for both reactive and non-reactive systems will be presented for completeness. Most of the dilatometers used in the literature were in-house made devices. For presentation organization, they are divided into three categories: (i) capillary type (ii) plunger type and (iii) bellow type. A section will follow on each of the types, concluding with some of the industrially available dilatometers. The ideal or desired dilatometer characteristics for this study include the ability to operate at a variety of temperatures and pressures, handle isothermal and ramping modes, accuracy to a fraction of a percent, have a quick thermal response (heat of reaction dissipation) and not interfere with the reaction mechanism. Several interesting attempts have been made in the literature, but all are limited one way or the other. Most systems are designed for and applicable to only specific situations.

2.2 Capillary Dilatometers

Capillary dilatometers use a small tube or capillary to measure fluid volume change. They were the first dilatometers used. Early designs were similar to that of a thermometer, consisting of a bulb and a graduated capillary [92 - 95] as shown in Figure 24 [93]. They were originally used to measure the bulk coefficient of thermal expansion of both liquids and solids at the beginning of the century [93]. Liquid sample data was easy to obtain. Knowing the amount of liquid charged, all one had to do was measure fluid level in the capillary as a function of temperature. To measure solid material coefficient of thermal expansion, however, required that the bulb be charged with a known amount of solid and a known amount of encapsulating liquid. The same experimental procedure was followed, however, the encapsulating liquid thermal response was back calculated.

Figure 24. Simple bulb and capillary dilatometer [93].

Starkweather [96] was the first investigator who used a similar type of system to study polymerization shrinkage and kinetics in 1930, as shown in Figure 25. He modified the dilatometer shown in Figure 24 such that the monomer could be distilled under vacuum directly into the bulb. As demonstrated in Figure 25, the monomer was placed into bulb B and chilled with liquid air or dry ice while a vacuum was pulled at E. After degassing, E was closed, bulb C was chilled, and B was heated to room temperature. The light fraction was collected in C, and D was then closed. The monomer was distilled from B into bulb A, leaving the heavy fraction in B, and F was then closed. Bulb A was placed into a boiling liquid (water, benzene or toluene depending on desired constant temperature) and the volume change of the reacting system was monitored by following the liquid level in the capillary [96].

This dilatometric technique was limited to low viscosity monomers and to the early part of polymerization due to viscosity rise limitations. As the viscosity rose, the material pulled away from the glass, formed voids in the bulb and prevented volumetric measurement in the capillary. In addition, it required a slow reaction rate due to the heat of reaction exotherm and the system's inability to dissipate heat. Finally, any temperature changes (either from fluctuations in bath temperature or heat of reaction) seriously affected the results, as this bulb and capillary system was essentially a thermometer.

Figure 25. Dilatometer used by Starkweather [96] to study polymerization shrinkage and kinetics.

A similar, but more refined model of the bulb and capillary dilatometer was used by Braun and Disselhoff [97] and is shown in Figure 26. The reactive system was quite large, therefore a fast or highly exothermic reaction was not possible as thermal runaway would most certainly occur. Again, polymerization could not be carried out to completion due to the viscous effects described earlier. The benefits of the system included safer and better controlled heating and sample mixing during cure.

Figure 26. Dilatometer used by Braun and Disselhoff [97] to study copolymerizations.

Hunter [98] and Rees and Jacobsen [99] used a capillary system similar to the one shown in Figure 27. First, a polymer resin was placed in a flask. Then, the rest of the flask and half of a calibrated capillary stoppered onto the flask were filled with mineral oil. The system was then submersed into a constant temperature bath and the volume change was monitored by following the height of the liquid in the column. With this dilatometric system the heat of reaction and viscosity problems found in Starkweather's dilatometer were avoided but new problems were introduced. Since the resin was in direct contact with the mineral oil [98] (or any other encapsulating liquid), parts of the resin would dissolve if soluble. Even if they did not dissolve, contamination may be a problem. As an example, for styrene-based unsaturated polyester resin systems like the ones used in this study, some of the soluble constituents, such as styrene and maybe the initiator, would dissolve whereas some of

the heavier constituents (e.g. unsaturated polyester and the low profile additive) would not. This would obviously affect the reaction mechanism, LPA mechanism and kinetics.

With some modification to the design, mercury could be used as the encapsulating fluid instead of mineral oil. Most materials will float in mercury, so a U shaped bulb is required. Most organics are not soluble in mercury and several investigators have used systems similar to this with mercury [92, 93, 96]. One must be certain, however, that the mercury does not catalyze or promote the reaction. Furthermore, it is not a good idea to heat mercury open to the atmosphere, as the vapor could be dangerous to the investigator.

Figure 27. Dilatometer used by Hunter [98] to measure polymerization shrinkage.

Several automatic recording capillary dilatometers have been presented in the literature. There are several ways to automatically follow a meniscus in a capillary, four of which are described below. The advantage of an automatic recording dilatometer system is that the investigator is not subjected to a harsh environment (radiation, mercury vapors, etc.) and slow polymerizations may be addressed more easily.

Perhaps the first automatic recording dilatometric system was used by Burnett in 1950 [93, 100, 101] as shown in Figure 28. Reactants were contained in a bulb and mercury was used as the encapsulating fluid. Mercury is denser than the reactants, thus this dilatometer was designed accordingly in a U shape configuration (see Figure 28). A piano wire, ground to a pointed tip, was aligned in the capillary and mounted to a precision worm screw. A current was passed through the piano wire and the mercury. When the mercury level decreased due to reaction shrinkage, the circuit was broken. This caused a solenoid to rotate the worm screw that the piano wire was mounted on and the piano wire was then pushed back into the mercury, completing the circuit once more. The solenoid could be set to turn either one quarter, one half or one complete turn. By monitoring the solenoid's rotations, the volume change was followed. Volume changes on the order of 1 part in 30,000 were reported.

Though very accurate, the system was limited to only one direction at a time (shrinkage or expansion) which could be a problem for studying low profile systems or accounting for thermal expansion during shrinkage (especially for ramp heating). In addition, high viscosity and heat of reaction effects limited performance and heated mercury was exposed to the atmosphere. A more current version of this dilatometer was developed at N.I.S.T. and applied to the study of liquid-crystals [102]. Instead of employing the wire/screw technique to follow mercury level, a linear variable

differential transformer (LVDT) with a floating core was use. This provided for an automated system which could handle expansion and contraction, but still had sample size problems.

Figure 28. First automatic recording dilatometer [101].

The conductive properties of mercury were used differently by the dilatometer designed by Bartkus and Kroekel [18], a schematic of which is shown in Figure 29. The sample and a thermocouple were sealed into a poly(vinyl alcohol) tube. The filled tube was then placed in the lower part of the assembly as shown in Figure 29, and the system was filled with mercury to the midpoint of the capillary in the upper half. Heating tapes were wrapped around the lower half of the assembly and used to

heat the system and sample. As the sample was heated and cured, its volume changed and the mercury level in the upper half responded accordingly. A thin graphite rod (pencil lead) was installed in the capillary in the upper half of the assembly from the top into the mercury. Graphite acts as an electrical resistor; the longer the rod, the higher the resistance. As the mercury level changed, the effective graphite rod length changed and thus the resistance changed. A current was passed through the graphite, system and mercury and the resistance was recorded. The resistance, after calibration, was correlated to volume change. With this dilatometric system, a wide temperature and pressure range was possible, but isothermal conditions were not. In addition, it is not clear how the thermal effects of mercury were accounted for.

It is interesting to note that this system was used to study the low profile additive effect in unsaturated polyester resin. Only two sets of data obtained from this system were published (in 1968), both of which were presented in Chapter 1 (Figure 14). There were no further data in the literature to confirm their findings.

There are other potential problems with Bartkus' and Kroekel's system. Based on the work of Kiaee [103], the graphite quickly absorbs mercury, affecting its resistance and repeatability. Consequently, it would be difficult for experiments to run a long time and to determine if fouling had interfered with mercury meniscus position measurement. Bernatchez [104] reported an automatic recording device similar in principle to Bartkus' and Kroekel's except that a thin nichrome wire was used instead of a graphite rod. Fouling was avoided and she reported a measured accuracy of ± 0.007 cm.

Figure 29. Recording dilatometer used by Bartkus and Kroekel [18] to study polymerization shrinkage and low profile additive.

Several investigators used an optical system to follow fluid meniscus position [105, 106]. In essence, a light was focused onto the transparent capillary and a photocell was mounted on the other side. If the photocell registered a bright light, the capillary was empty. If the photocell registered a dimmer light, the capillary is full. This could be applied to most any containing fluid in the capillary – transparent, colored or opaque. Similar to Burnett's system previously discussed, as the meniscus position of the fluid in the capillary changed, the entire optical system, mounted on a worm screw, moved to follow it [105, 106]. Niezette [105] used this type of automatic recording system on a simple bulb and capillary dilatometer, similar to the

one depicted in Figure 24, for radiation polymerization studies. Accuracy on the order of 0.04 mm was reported [105].

Another optical meniscus following dilatometric system, designed by Ruben and Skochdopole, is shown in Figure 30 [106]. The sample was contained in a poly(vinyl fluoride) bag, which was found to be inert to the system of interest. The bag was placed in a cavity honed into two stainless steel plates, sealing the last edge of the bag with the O-ring seal between the plates. The system was filled with mercury (half way up the capillary) and the entire system was submersed into a heated water bath. Again the column height was followed photo electrically. One disadvantage of this dilatometric system was that the sample temperature was not monitored, thus heating rate and heat of reaction exotherm could have unknowingly effected the results. Furthermore, it would be difficult to fill the system such that all the air was removed, due to the fact that a vacuum technique would cause air bubbles to form in the sample (or cause the sample to vaporize) and without vacuum or circulation of some sort, small air bubbles could be entrapped.

The final method of following a meniscus was demonstrated by Cundall, et. al. [107]. They claimed that if a tube containing the meniscus of the confinement fluid passed between two parallel metal plates, the capacitance measured across the plates would be linearly proportional to the meniscus position.

This system was used to monitor photopolymerizations. Photopolymerization is a special situation in that, the reaction does not start until the UV lamp is turned on. This made the reaction easier to study, as the UV lamp was not turned on until all the variables had stabilized and temperature control would be easier.

Figure 30. Ruben and Stochdopole's dilatometer [106] used an optical method to follow the meniscus movement.

2.3 Plunger Dilatometers

Plunger type dilatometers are characterized by their use of some sort of piston and cylinder apparatus to pressurize the material of interest and its containing fluid (if any) and monitor volume change. There are several advantages to using a plunger design versus a capillary design, one of which is that it is much easier to vary the sample pressure. From the previous section, only a few of the capillary type dilatometers were capable of high pressures and temperatures. With the use of pressure, higher temperatures could be obtained without the disturbance of sample volatilization which would be highly detrimental to volume measurement. In

addition, high pressure lessens the importance of air bubble entrapment in the system, as percent air volume decreases markedly with increasing pressure. Some of the plunger systems were designed to handle very small samples (as is mentioned later in this section) thus insuring isothermal conditions and quick temperature response. Unfortunately, the plunger type of dilatometer was used infrequently compared to the capillary type in the literature.

The first plunger type dilatometer design, reported by Tung [108] in 1967, is illustrated in Figure 31. The sample, in the 3 mg range, was placed in the sealed tip of a U-tube. The rest of the tube was filled with mercury and the plunger was installed using standard vacuum techniques. The plunger and the cylinder were precision ground to match and had a diameter of 0.32 cm (0.125 in). As the sample volume changed, the plunger responded accordingly. Plunger movement was followed using an LVDT (linear variable differential transducer). This system was applicable to both reactive and non-reactive systems, however, with reactive systems the U-tube had to be thoroughly cleaned with a solvent after each use. Results have been shown to be reproducible to 2×10^{-6} ml. Larger versions of this dilatometer [93] as well as similar designs for highly viscous systems [109] were also described in the literature. Some of the limitations of this type of system include the limitation of pressure to atmospheric conditions, the inability to measure sample temperature profile and the possibility of volatilizing part of the sample during assembly due to the use of vacuum.

Five years later, Hojfors, et al. [110] reported that the dilatometer described by Tung [108] could be used in pairs, one with a sample and one containing only the confining fluid. The LVDT signal from the confining fluid was subtracted from that of the samples using a measuring bridge. Thus, the recorded output was only the

response of the material of interest (provided that the same amount of confining fluid was used in each). This technique, called differential dilatometry, was only applied to melt and crystallization data [110], though the system could be applied to reactive materials.

Figure 31. Simple plunger dilatometer as described by Tung [108].

A similar plunger type dilatometer was employed by Mitani, Shiraishi, Honda and Owens [64] and is shown in Figure 32. It was used to monitor the volume change of SMC pastes on cure. The sample was placed into a 10 ml ethylene-tetrafluoroethylene vial and capped using a vacuum technique. The vial was rigid at room temperature, but at operating conditions the plastic became soft and pliable. Furthermore, it was chemically unaffected by and insoluble in any of the constituents of the SMC resins. The filled vial was placed into a 30 ml glass syringe, the syringe was filled with silicone oil, capped (at the needle port) and was placed into a holding

ring, which was connected to an angle iron stand. Weights (providing on the order of 50 psi in the syringe) were placed onto the plunger of the syringe and a dial gauge was mounted onto the stand and placed on the weights. To heat the system, a beaker filled with silicone oil and a mixing hot plate were placed under the syringe. The beaker and hot plate were elevated into place by a lab jack which sat on the base of the stand. As the resin and oil expanded or contracted due to reaction or thermal response, the syringe plunger moved accordingly. The plunger movements were recorded via the dial gauge with respect to time and the volume change was later calculated.

Figure 32. Syringe dilatometer used by Mitani, Shiraishi, Honda and Owens [64] for SMC pastes.

In this system, the pressure was provided by balancing weights on top of a glass syringe plunger, so high pressures could not be expected. In addition, the vial

required a minimum temperature of about 110°C to become soft enough to respond, but could not be subjected to too high a temperature or the vial material would flow and styrene would start to volatilize. Thus the range of possible temperatures was small. Vials made of different material could be used for differing the temperature range, but there are not too many materials which will not swell or dissolve in styrene.

Since the nominal volume of the vial was large (10 ml), isothermal conditions could not be expected either. Exotherms on the order of 100°C were measured. Since the vapor pressure of styrene at 200°C is approximately 50 psig [50] reaction exotherm could possibly lead to a potentially dangerous situation when using this dilatometer. If the styrene vaporized quickly during the reaction exotherm, the sample might expand to the point in which the plunger was no longer in the syringe, causing the weights and plunger to plummet.

One plunger dilatometer system was developed without the use of encapsulating fluid and is shown in Figure 33 [24]. This apparatus was used to study low shrink unsaturated polyester resins. The system consisted of a pneumatic cylinder mounted on a stand (such that the rod was pointing down) and a cylindrical cavity in a heated steal block where the material was cured. The sample was approximately 5 cm (2 in) long and 1.25 cm (0.5 in) in diameter. To operate the equipment, the rod was lowered into the sample cavity and the steal block was preheated to the desired temperature. Once the desired temperature was obtained, the rod was lifted from the sample cavity (by toggling the lever on the three way pneumatic valve, see Figure 33) and the sample was poured into the cavity. With the sample in place, the rod was pneumatically lowered on to the sample and thereby pressurizing the sample to nine times the air pressure used in the pneumatic cylinder.

The sample chamber was sealed at both ends with an O-ring and the sample temperature was measured during the cure via a thermocouple in the sample. The position of the cylinder rod was monitored as the resin cured and this position data was used to calculate the resin shrinkage. When the cure was complete, the system had to be disassembled to remove the sample and prepare for the next one.

Some of the key disadvantages of using the system in Figure 33 include highly non-isothermal conditions (temperature peaks of over 100°C are common), limited to higher pressures (over 1 MPa) due to the pneumatic system, large scale stress cracking in some samples and the possibility of the sample pulling away from the wall during cure, yielding a measured shrinkage less than the true shrinkage. Furthermore, there is a strong possibility that air will be trapped in the sample during assembly (there was a small vent which was designed to permit air and extra resin to escape, but it was still possible to trap some air). Furthermore, the sample viscosity had to be reasonable low, as the sample was poured into the chamber, making thickened samples difficult to study. The key advantage to this system is that it is very straight forward and quick.

Finally, included for the sake of completeness, a space-flight dilatometer was produced [111] for the Space Shuttle Orbiter. The authors labeled their apparatus as a "diaphragm dilatometer", however it's characteristics are very similar to a plunger type dilatometer. This dilatometer was designed to monitor the curing of a monodispersed emulsion of styrene/polystyrene. A schematic of the space flight dilatometer is shown in Figure 34.

Figure 33. Dilatometer based on pneumatic cylinder [24].

Figure 34. Space flight dilatometer [111].

2.4 Bellow Dilatometers

Bellow dilatometer designs are characterized by the use of a metal, collapsible bellow to contain the sample, based on the Bridgman bellows technique [112, 113]. They were used for non-reactive systems, partly due to the fact that design limits quick heating and polymer cure interferes with operation. They were used to measure the PVT relationships of either liquids [114, 115] or solids in a confining liquid. Both mercury and silicon oil were used as confining liquids [116] and even though silicon

oil is safer, mercury is most often used because the PVT data for mercury is available at high pressures and temperatures [115, 117, 118]. Bellow dilatometers are capable of extreme pressures; a maximum pressure of 700 MPa was reported by Quarch and Simha [118]. Bellow dilatometers have reportedly been used to monitor phase separations of copolymers [119] and determine the PVT data of liquid water [120] over a wide range with good agreement to accepted values.

A schematic of a bellow dilatometer is shown in Figure 35 [117]. The bellows were made from either stainless steel [118] or nickel [114] and end pieces were welded onto each end of the bellow. On one end piece a piston was mounted. A plug was installed at the other end which was used to fill the bellow with the sample, or in the case of a solid sample, the sample and a confining liquid. The bellow was installed into a pressurized cavity as shown in the diagram. As the sample expanded or contracted, the bellow expanded or contracted, causing the piston to move. The piston, in turn, pushed a rod in a pressurized shaft that caused an LVDT core to move.

One must be careful when using this dilatometric method while studying thermoplastic or semisolid materials. If mercury is used as the confining liquid, the sample will float to the top and, on melting and re-solidification, will prevent the mercury from completely surrounding the material. This would interfere with cooling studies and possibly cause an artificial hysteresis in the heating/cooling data.

A company by the name of Gnomix Research [121, 122] has started to market a bellow dilatometer under the trade name Gnomix PVT apparatus. It is capable of up to 200 MPa and requires a 1-2 gram sample [120].

Figure 35. An example of a bellow dilatometer design [118].

2.5 Miscellaneous Dilatometers

Industrially, there are no dilatometers available for thermosetting polymers similar to those used in composite manufacturing. The closest to this would be a

TMA (Thermomechanical Analyzer) from TA Instruments or other thermal analytical manufacturers, as depicted in Figure 36 [123]. TMAs are commonly used to measure coefficients of thermal expansion and glass transition temperatures (T_g) of polymers. A sample is placed onto a platform next to a thermocouple in the sample holder and a quartz probe is placed onto the sample. The probe is attached to a very accurate linear variable differential transducer (LVDT), which measures the change in position of the probe as the sample is heated or cooled. The entire sample holder is then placed into a heater and an insulating dewar and is subjected to a heating routine, usually a temperature ramp of 5°C per minute or less. From this, linear coefficients of thermal expansion and glass transitions are found.

Figure 36. Schematic of a TA Instruments Thermomechanical Analyzer [123].

Some TMAs offer an optional dilatometer attachment. Figure 37 [124, 125] depicts a standard dilatometer attachment for a TMA. It is essentially the bulb part of a capillary dilatometer with a plunger. The encapsulating fluid used is a fluidized bed of quartz. The probe and the dilatometer cell are also constructed out of quartz, so that the thermal expansion of the tube, probe and encapsulating fluid cancel each other out yielding a level baseline. The baseline is level over a temperature range of sub zero temperatures to over 500°C. Unfortunately these dilatometers are limited to solid samples or liquid samples with a viscosity of above 15,000 poise. Due to the particulate nature of the quartz fluidized bed, a sample with a viscosity lower than 15,000 poise would flow into the voids of the quartz particles, causing a false shrinkage measurement [125]. Furthermore, TMAs are limited to operate at atmospheric pressure and very slow heating rates (0.005°C - 3°C per minute) are recommended for the dilatometry attachment [124].

Figure 37. Dilatometer attachment for a TMA [124].

An industrially available dilatometer does exist for thermoplastic polymer melts [126]. A polymer melt is placed into a cylinder and pressure is applied from above with a plunger. The system is heated to the desired temperature and, when steady state is achieved, volume, temperature and pressure are recorded. This is very similar to the dilatometer based on a capillary rheometer and Instron machine system reported by Hsiao, et. al. [127].

Chapter III

Instrumentation

3.1 Introduction

Three key analytical techniques were applied in this study to characterize the low profile additive mechanism in low shrink unsaturated polyester resins. These techniques included:

- Dilatometry
- Scanning Electron Microscopy (SEM)
- Differential Scanning Calorimetry (DSC)
- BET surface area measurement

The differential scanning calorimeter used was a TA Instruments DSC 10. All samples were reacted in an aluminum volatile sample pan, which was capable of withstanding an internal pressure of 0.2 MPa (2 atm) when sealed. Sample sizes were on the order of 10 mg and an empty pan was used as a reference. The scanning electron microscope used was a Hitachi S-510 with 25 KeV power. Most SEM samples were prepared either by fracturing the sample, etching in dichloromethane and gold coating or fracturing and gold coating without etching. All micro-graphs presented here are 6000x unless stated otherwise. BET surface area measurement was performed with a Micromeritics 2100E Accusorb system.

BET, SEM and DSC are standard analytical techniques and consequently require no further description or explanation. However, the dilatometer used in this study was designed and built in-house and therefore will be presented in detail. The remainder of this chapter will cover the dilatometer developed. First, the current dilatometer hardware and a brief discussion of the methodology will be covered. After the hardware description, dilatometer calibration and an introduction to the type of data obtainable with the dilatometer will be described. Finally, a small section will be devoted to a brief look into the development process for this piece of equipment.

3.2 The Dilatometer

3.2.1 Overview

A cut-away view of the current dilatometer configuration is shown in Figure 38, and Figure 39 and Figure 40 are photographs of the unassembled and assembled dilatometer, respectively. The sample was enclosed in a heat sealed sample pouch much like a ketchup pouch. The sample geometry was disc shaped, approximately 9 cm in diameter with a thickness which depended on the desired sample size (volume). The sample pouch was prepared by heat sealing (with a T-Bar Plastic Sealer, Model T-7 Harwil Co.) a circle onto a double layer of laminated plastic film (Dazey Micro-Seal Film, 0.0051 cm (2 mils) thick), leaving one gap for the sample and one gap for a thermocouple. A 28 gauge K type bare thermocouple was sealed into the sample pouch at this time with the leads passing through the heat sealed edge, allowing for sample temperature measurement.

Figure 38. Dilatometer schematic.

Figure 39. Photograph of the unassembled dilatometer.

Figure 40. Photograph of the assembled dilatometer.

To fill the pouch, the empty pouch weight was measured, the sample was poured into the last remaining break in the pouch edge seal, all the air was forced out of the pouch and the last edge was sealed. Once the pouch was filled the full pouch weight was obtained and the sample weight was calculated by the difference between the full and empty pouch weights.

The pouch material had to be inert to and insoluble in styrene or whatever material under investigation. To test this, a pouch of pure styrene was made and permitted to age. No change in the pouch or smell of permeating styrene could be detected for six months. If the pouch material was soluble or swelled in styrene, a breach in the sample containment would occur during the experiment, causing sample contamination and possibly damage to the dilatometer. Furthermore, if the pouch was soluble in unsaturated polyester resin / styrene compounds, it might have acted as a low profile additive.

The sample pouch was located in the lower half of the dilatometer in the sample chamber, as shown in Figure 38. The sample chamber was a cavity honed between two copper discs and was connected to the lower half of a small hydraulic cylinder via a nipple. The upper half of the hydraulic cylinder was connected to a constant pressure source as shown in Figure 41 and was used to pressurize the lower half of the dilatometer.

Figure 41. Dilatometer pressure system.

The lower half of the dilatometer was filled with degassed silicon oil (Dow Corning 550 fluid) as the encapsulating fluid. It was filled by continuously pumping the silicon oil into the lower valve and out of the top valve (labeled in Figure 38) while working the cylinder piston until all the air was removed. A bellow pump (5 cm diameter bellow, Gorman Rupp Co.) was used for this procedure to provide a pulsating flow which aided in bubble removal. The oil flowing out of the system was monitored for air bubbles.

To confirm air-free conditions, pressure was applied to the rod of the hydraulic cylinder with all valves closed; if it felt “spongy” there was some air entrapped in the system, if it felt firm the lower half was air-free. The upper half of the dilatometer and part of the tube leading into the cylinder was filled with silicon oil (not degassed).

With the top and lower valves closed, the lower half of the dilatometer (sample cavity and lower part of the hydraulic cylinder) was a closed system. Therefore, any volumetric response (thermal or cure induced) would be registered by the movement of the hydraulic cylinder piston position. By following the cylinder rod position with an LVDT (linear variable differential transformer), the volumetric response of both the oil and the sample were followed.

The dilatometer was heated by four 150 watt, 120V cartridge heaters (Watlow Firerod, E1A53), two in the upper copper disc and two in the lower. The cartridge heaters were located such that the two on the same disc were 180° from each other and the cartridge heaters on the upper disc were offset by 90° from the cartridge heaters on the lower disk. Two modes of heating were available, isothermal and ramping.

In the isothermal mode, the dilatometer was heated to a set point and controlled. Two PI controllers (Omega CS5001) were used to control the dilatometer temperature, one for the lower disc and one for the upper. During the initial heating, the set point of both controllers was set to 150°C until approximately 2°C below the desired operating condition. At approximately 2°C below the desired isothermal temperature, the set point was adjusted to the desired value and control was established. The purpose of this operation was to provide full power to the heaters up to the set point, establish stable control as quickly as possible and avoid a temperature over-shoot. On average, approximately 10 minutes of heating time was required to establish isothermal conditions. Once isothermal conditions were obtained, control was stable and no oscillatory temperature behavior was observed.

In the ramping mode, constant voltage was applied to the cartridge heaters by means of a Variac. By varying the voltage across the heaters various heating rates were obtained. Since $\text{volt} = \text{power} * \text{resistance}$, by varying the voltage and knowing that the resistance of the cartridge heaters is constant, one varies the power into the system and thus the heating rate. For a better temperature distribution, it was important that the power applied to the upper heaters was the same as that applied to the lower heaters. Therefore, all the heaters were connected to one Variac. Finally, it is important to realize that by using this method of ramp heating, linearity was not necessarily obtained. For slow heating rates (less than approximately 5°C/minute) the heating profile was curvilinear due to system heat loss, even though the system was insulated. For faster heating rates (8°C/minute or more) the system heat loss was not as large compared to heat in and therefore nearly linear heating was obtained.

Given the description of the apparatus above, the following is a brief description of the operating procedure. A more detailed procedure is available in Appendix A.

- The sample was prepared and the sample pouch was made. The apparatus was assembled as illustrated in Figure 38 and mounted in the stand as illustrated in Figure 41. The LVDT and thermocouple connections were made to the data acquisition system and the system was pressurized.
- A cooling bath was applied to the system until a constant temperature and a corresponding constant cylinder rod position was measured. Once the initial temperature and position were recorded, the cooling bath was removed and the heating system and insulation were installed.
- The desired heating cycle, either isothermal or ramping mode, began. During the heating cycle, temperature and position data were measured. The temperature recorded was the actual sample temperature, however, the position data obtained actually corresponded to the thermal volumetric response of both the silicon oil and the sample thermal and cure volumetric responses.
- On completing the heating cycle (when cure was complete), the heating system was removed and the dilatometer was cooled to its initial temperature and final position. Cooling was by air down to approximately 100°C and by use of the cooling bath system from 100°C to the initial temperature. This was done to avoid quench cooling which might warp parts or cause minor leaks.
- Since the system was cooled exactly (within 0.1°C) to the initial temperature, the volumetric difference in the sample was the difference in the rod final and initial position (Δh) times the piston area $\pi D^2/4$ where D is the cylinder diameter, 1.9 cm

(nominally 0.75 inch). To obtain the dynamic volumetric response (volume change as a function of time) the thermal response to the encapsulating oil must be subtracted. To do this, the thermal cycle was repeated (heating and cooling), without disassembly of the apparatus, using the final position of the cure as the initial position of the second heating cycle. This second cycle is referred to as the baseline. A second advantage of using a baseline is that it is a good indication of a complete cure and a leak-free system. If the baseline did not return to the initial position when cooled either more reaction or a leak occurred and the run was repeated. The volume change as a function of time was obtained by subtracting the cure position curve minus the baseline (accounting for the cylinder diameter as previously discussed). This does not change the final volume change data as the baseline returns to zero for a successful run. Note that the volumetric response was not purely due to cure. By subtracting cure minus baseline, the monomer minus the polymer thermal expansions were also incorporated in the volumetric response.

3.2.2 Hardware Specifics

Figure 42 and Figure 43 are diagrams illustrating the dimensions of the upper and lower discs as machined, respectively. Both parts were machined out of 12.7 cm (5 inch) round, 1.9 cm (0.75 inch) thick copper discs. Both the upper and lower discs had a 10 cm (4 inch) diameter, 0.32 cm (0.125 inch) deep cavity machined in them which, when the parts were bolted together, combined to form the sample chamber, as shown in Figure 38.

Figure 42. Dimensions of upper copper disc.

Figure 43. Dimensions of lower copper disc.

Both discs had eight evenly spaced holes around the perimeter which were used to bolt the parts together. The eight holes in the lower plate were tapped to accommodate a 0.32 cm (0.125 inch) diameter, 20 thread bolt. The eight holes in the top plate were machined a little larger and were not tapped as the bolts used had an unthreaded collar (see Figure 38).

The lower disc had one hole drilled and tapped, as shown in Figure 43, to accommodate the lower valve (Whitney B-OVM2, brass needle valve), as shown in Figure 38. In addition, an O-ring groove was machined into the lower disc, between the sample cavity and the threaded holes.

The O-ring groove was machined to a width of 0.483 cm and a depth of 0.284 cm to accommodate a #243 O-ring. O-ring material was either standard Nitrile rubber for low temperature applications (less than 100°C) or Viton for up to 200°C. The groove dimensions are very important and were designed to provide approximately a 18% to 20% compression with metal to metal contact. If the groove was too small, metal to metal contact would not have occurred when the parts were bolted together. If this happened, the O-ring would permanently collapse on heating, which would have caused a small decrease in sample chamber volume and result in a corresponding (artificial) measured expansion in the sample volume. If the groove was too large, the O-ring would not compress enough and leakage would occur, resulting in the measurement of an artificially large sample shrinkage.

The upper plate had two (1/8 inch NPT) holes drilled and tapped in it, as shown in Figure 42. The hole in the center was used to connect the hydraulic cylinder via a (1/8 inch NPT) nipple and the hole near the edge was used to accommodate a (1/8 inch NPT) to 0.476 cm (3/16 inch) tubing male connector for the sample thermocouple. The area between the bolt holes and the sample cavity were used as

the sealing edge, corresponding to the O-ring seal in the bottom plate. Any scratches in this area had to be removed by occasionally re-machining this surface.

Finally, both the lower and upper halves had two holes drilled into the side to accommodate the cartridge heaters, as shown in Figure 42 and Figure 43. The cartridge heaters were 0.635 cm (0.25 in) in diameter, 2.54 cm (1 in) long and had a 1.27 cm (0.5 in) long thick protective sleeve over the wire near the heater. Due to the sleeve, it was necessary to drill the holes 1.27 cm deeper than the heater length and mill out a groove for the protective sleeve, as shown in Figure 42 and Figure 43.

The heating system employed the use of Watlow Firerod 150 watt, 120 volt cartridge heaters (part # E1A53). As previously mentioned, two heaters were used for each disc and, for isothermal operation, two controllers were used (Omega CS5001 controllers with type J thermocouple adaptation), one for the upper disc and one for the lower disc. The controller thermocouples were placed in a small hole (2.54 cm deep) drilled into each copper disc at approximately a 45° offset from the heaters (not shown in Figure 42 and Figure 43).

The hydraulic cylinder used was a 1.91 cm (0.75 in) bore, 5.08 cm (2 in) stroke, dual acting brass cylinder manufactured by Cylinder and Valves (Strongsville, Ohio, Part No. UC 700). A small cylinder was chosen so that a larger measured response (rod position) to small volume changes and therefore better resolution and smaller sample size requirements were possible. In addition the smaller thermal mass provided for faster heating of the cylinder. All seals in the cylinder were Viton rubber O-rings. Due to the materials of construction, the upper pressure limit of the cylinder was 3.45 MPa (500 psi) and upper temperature limit was 200°C. As manufactured, there was one (1/8 inch NPT) hole drilled and tapped from the side in both the top and bottom cylinder heads. Connected to the upper head was the pressure system and

connected to the lower head was the top valve (Whitney, B-OVM2 brass needle valve) as shown in Figure 38. An extra (1/8 inch NPT) hole was drilled and tapped in the bottom of the lower head for the nipple connection to the sample chamber, also shown in Figure 38.

The cylinder rod was 0.635 cm (0.25 in) in diameter, therefore, the pressure in the sample cavity was 88% of the pressure applied to the top half of the dilatometer. For example, if the pressure in the pressure system (see Figure 39) was set to 0.69 MPa (100 psig), the pressure in the sample cavity would be $(0.88)(0.69 + 0.10) = 0.695$ MPa or approximately 0.69 MPa (100 psi). The 88% was calculated using a force balance on the piston and was based on the ratio of piston area on the top (with the rod) to the piston area on the bottom (no rod).

The pressure system was made from all stainless steel components and is illustrated in Figure 41. All tubing was 0.635 cm (0.25 in) O.D. A nitrogen cylinder was used as the pressure source. To pressurize the system, the dilatometer was installed and all valves except the one closest to the cylinder (between the regulator and the tee to the dilatometer as shown in Figure 41) were closed. The regulator was opened and the pressure was monitored with the pressure gauge (0 - 6.9 MPa range) until the desired pressure was obtained. Once the system was at the desired pressure, the valve between the regulator and tee was closed. This was done to avoid variations in pressure due to regulator activity and to test for pressure system leaks. In order to help stabilize the pressure and lessen pressure fluctuations due to room temperature changes, a small gas cylinder was added to the pressure system line, as shown in Figure 41. With this extra tank, pressure does not change measurably during the course of a full day experiment. A valve to the atmosphere was included to drain the system when an experiment was completed and a relief valve (Swagelok, SS-4R3A)

set at 3.45 MPa (500 psi) was added as a safety precaution (the hydraulic cylinders upper pressure limit was 3.45 MPa). Finally, a small trick was required to provide hydraulic pressure to the dilatometer from a pneumatic source. The line leading from the pressure system into the upper half of the hydraulic cylinder was a flexible metal hose. Before a run, the metal hose was filled with the same oil as the cylinder, preventing nitrogen from entering the cylinder and providing the necessary conversion between pneumatic and hydraulic systems.

The cylinder rod position was followed by a Schaevitz LVDT system, consisting of an LVDT (with spring, ± 2.54 cm, part number GCA-121-1000) and an analog transducer amplifier (part number ATA-101). The voltage produced was ± 10 volts (adjustable) for the ± 2.54 cm travel. Calibration of the LVDT was performed by moving the LVDT rod at 0.2540 cm increments and reading the voltage. A first or second order polynomial curve was fit to the data to calculate position data.

Reading sample temperature required that the thermocouple wire pass through the sample chamber without a breach in the system seal. To accomplish this, a thermocouple encased in a 0.476 cm (3/16 inch) packed tube was run through a (1/8 inch NPT) to 0.476 cm (3/16 inch) tube male connector in the top disc. The part of the encased thermocouple that entered into the sample chamber was stripped to the bare wires and the packing was sealed with a high temperature epoxy resin. Recall that the thermocouple was sealed into the sample pouch with wire leads running out the side. The wire leads from the sample pouch were twisted onto the bare wires leading out and the inter spring of a wire nut was used to assure good electrical and mechanical contact.

The data acquisition system used was either a DianaChart 16 channel system connected to an IBM PC or an ADC-1 16 channel system with a 40 gain amplifier on

the first 8 channels (Remote Measuring Systems) connected to a Macintosh SE/30. Both sample temperature and cylinder rod position were measured by the data acquisition system.

To summarize and conclude the discussion of the dilatometer hardware, Table 2 is a list of some of the dilatometer specifications and limitations. As mentioned, the maximum temperature was approximately 200°C, due to the Viton O-rings used as the dilatometer and cylinder seals. The maximum pressure was 3.45 MPa (500 psi) (3.05 MPa sample side) due to the upper pressure limit of the brass hydraulic cylinder. If a similar cylinder made of a stronger metal were available this limit could be easily raised. The heating rate was limited by the power rating of the cartridge heaters to a maximum of approximately 20°C/minute. At higher heating rates (over 15°C/minute) it was necessary to apply a heat dissipation material (Thermal Compound, Wakefield Engineering Inc., Part # 120-2) to the heaters before inserting into the holes in the dilatometer in order to avoid damaging the heaters.

The sample size could be varied depending on the material and heating conditions used. For materials with a slow reaction or small reaction exotherm, a larger sample was used, corresponding to a larger change in rod position during cure and increased accuracy based on percent volume change. However, for more reactive systems, such as unsaturated polyester resins, it was necessary to use a smaller sample to avoid excessive temperature rise during reaction exotherm. Finally, the resolution of the LVDT / data acquisition system was 0.001 cm (0.0004 inches) which corresponded to a volumetric resolution of 0.003 cm³.

Table 2. Specifications of the current dilatometer system.

Specification Item	Value/Limit	Reason/Comment
Maximum Pressure	3.45 MPa	Hydraulic cylinder
Maximum Temperature	200°C	O-ring material
Maximum Heating Rate	~20°C/minute	Power rating of the cartridge heaters
Sample Size	3 to 10 grams	Depends on reaction rate
Resolution	LVDT - 0.001 cm Volume - 0.003 cm ³	Limited by LVDT signal and data acquisition system

3.3 Dilatometer Calibration

Dilatometer calibration was performed to demonstrate that the dilatometer data is correct for both the final shrinkage and the reaction trend. The reaction of styrene to polystyrene was used to calibrate the dilatometer because it is known to shrink linearly with conversion and the final polymerization shrinkage is known (14.5%) [92]. In fact, as discussed in the previous chapter, early researchers used thermometer-like dilatometers to study polymerization kinetics before the thermal analytical techniques were available. The dilatometer was calibrated in both isothermal and ramping modes and both methods will be presented in the sub-sections to follow.

3.3.1 Isothermal Calibration

For isothermal calibration, styrene with 6% by weight PDO was used. The initiator level was tuned to the dilatometer knowing the amount of heating time required by the dilatometer to reach isothermal conditions and using various levels of initiator in isothermal DSC. The dilatometer isothermal operating temperature was arbitrarily chosen to be approximately 80°C.

The temperature profile of the isothermal dilatometer calibration is shown in Figure 44. The corresponding position data for isothermal calibration is shown in Figure 45. As discussed in Section 3.1, after assembly the dilatometer was placed in the cooling bath and time, temperature and position data were taken until isothermal conditions and constant position data were obtained. Temperature was measured both in the cooling bath and inside the sample to assure isothermal conditions. The constant temperature and position data were taken to be the initial data (time = 0 in Figure 44 and Figure 45 and position = 0 in Figure 45). Once initial data was obtained, the cooling bath was removed and the heating system was installed. The heat was applied and the data acquisition was turned on at the same time and the system began to heat. Once operating conditions were obtained the temperature was controlled at 80°C until reaction was complete. Reaction was monitored by following the cure position data as shown in Figure 45 (solid line). Completion of reaction was determined by the leveling off of the cure position line. Once reaction was complete, the heating system was turned off and removed and the cooling system was again installed.

Figure 44. Temperature profile, isothermal calibration.

Figure 45. Position data, isothermal calibration.

Time, temperature and position were monitored until a level response at the same temperature as the initial temperature was measured. The position data indicated a net difference (shrinkage) of approximately 0.32 cm (0.12 inch). This difference was the sample polymerization shrinkage response only, as the initial position and final position data were obtained at the same temperature and pressure, negating the thermal effects of the encapsulating oil.

To obtain the data corresponding to the cure shrinkage as a function of time, the oil response had to be removed or subtracted from the cure position data. To do this, the final position data was taken to be the initial position (zero position) for the baseline and the entire heating cycle was repeated without disassembly or disturbance of the equipment, as shown by the gray line in the position data plot, Figure 45. There are additional advantages to running a baseline. Note in Figure 45 that the baseline returned exactly to the zero position after cooling. If this did not occur, either the reaction was incomplete during the cure cycle or a leak had developed in the dilatometer. Either way, it is a good method of testing the validity of an experiment.

The sample percent volume change can be calculated, as shown by the gray line in Figure 46. To calculate the percent volume change, the baseline was subtracted from the cure line and the sample size (volume) and the hydraulic cylinder geometry was accounted for.

Figure 46. Percent volume change and -1*conversion, isothermal calibration.

The calculated percent volume change was not exactly the pure polymerization shrinkage response. As shown in Figure 46, the sample expanded thermally before cure. This expansion was the monomer (styrene) thermal expansion minus the cured polymer (polystyrene) thermal expansion. The pure monomer expansion was actually larger than that shown in Figure 46. At the completion of the reaction and on cooling to the initial temperature, polymer was subtracted from polymer, so no differences due to the thermal expansion were encountered. The percent volume change was not plotted for the cooling section in Figure 46. The cooling rate was uncontrolled and percent volume change calculated over the cooling region was noisy and of little interest. Therefore, to avoid confusion, percent volume change over the cooling region was not plotted.

A problem not illustrated in Figure 46 is the possibility of a shift in the percent volume change curve. The isothermal experiments can take quite a while to complete, in this case 290 minutes for the cure alone. During that time, it is common for the room temperature to change and, even though the system is controlled and insulated the same way for both cure and baseline, the baseline temperature may still be slightly different than the cure temperature. This slight difference in temperature may cause shifts in the data between the final shrinkage and the shrinkage versus time curve. If the baseline runs too hot, too much is subtracted from the cure line and the percent volume change curve shifts downward. If the baseline runs too cold, not all of the thermal effects of the oil and cured sample are subtracted from the cure line and the percent volume change line shifts upward. The shift in the data does not affect the validity or trend in the data, however, it may affect the initial expansion value.

Using the sample temperature profile measured in the dilatometer, the DSC was used to follow the polymerization conversion. The temperature profile of the

dilatometer was modeled in the DSC using first a ramp (approximately 14°C/minute, see Figure 44), followed by isothermal operation at 80°C. Using this temperature profile, an estimation of the conversion as a function of time was obtained and negative conversion is plotted as the solid line in Figure 46. Negative conversion (or $-1 \times \text{conversion}$) is shown instead of conversion for easier comparison. From Figure 46, one can see that the trends compare nicely.

The final shrinkage as measured by dilatometry and shown in Figure 46 by the gray line around 325 minutes was approximately 13.47%, based on a sample size of 5.914 grams and a sample density of 0.910 grams/cm³ (as measured). From the DSC modeling of the dilatometer run, a final conversion of 95.2% was estimated. This assumed that the heat of reaction measured in a scan (10°C/minute) was the equivalent of 100% conversion and the heat of reaction measured isothermally divided by the scanning heat of reaction was the final conversion. To compare with the literature data, the final shrinkage for complete polymerization of styrene to polystyrene is 14.5% [92]. Since shrinkage and conversion are linearly and inversely related, the equivalent literature value of the final shrinkage at 95.2% conversion is 95.2% of 14.5 or 13.80%. Therefore, final percent volume change measured compared quite favorably with the literature data.

3.3.2 Ramping Calibration

For ramping calibration, again 5% PDO in styrene was used. The initiator level was tuned for the operating conditions of the dilatometer based on the DSC results. For scanning mode calibration, the major concern was that the reaction must

be completed before the upper limit of the dilatometer (200°C) was reached while maintaining a linear heating rate.

Figure 47 is a plot of the ramping dilatometry temperature profile (both cure and baseline) as measured from the thermocouple in the sample and Figure 48 is a plot of the corresponding position data. As was the case in isothermal operation, an initial temperature and corresponding position was obtained by applying the cooling system to the assembled dilatometer system. Once the initial data was obtained, the cooling system was removed and the heating apparatus was installed. Recall that the heating rate for ramping mode was adjusted by the use of a Variac to supply constant voltage to the heaters. Power to the heaters and the data acquisition were started at the same time and time, sample temperature and position data were recorded.

From Figure 47, the temperature started from the initial temperature and rose at approximately 3°C per minute until the dilatometer neared the upper temperature, at which point the power to the heaters was terminated. At this point, the heating equipment was removed and the system was cooled to the initial temperature. As with the isothermal run, the entire heating cycle was repeated to obtain a baseline response. The baseline in Figure 47 is the gray line and the cure line is the solid (black) line. Comparing the cure and baseline temperature profiles, temperature repeatability was quite good. If the cure and baseline temperatures did not overlap this nicely, a shift in the corresponding percent volume change data would occur, as discussed in the isothermal sub-section. The only discrepancy between cure and baseline temperature profiles occurred during a slight reaction exotherm, as illustrated in Figure 47.

Figure 47. Temperature profile, ramp calibration.

Figure 48. Position data, ramp calibration.

The temperature profile in Figure 47, though repeatable, is not quite linear. Due to increased heat losses at increased temperatures, the temperature ramp rate decreased at increased temperatures leading to this non-linear heating. This is only a problem when trying to compare dilatometer data with other analytical equipment, such as DSC. To avoid this non-linearity, either a faster heating rate or a ramping controller is required. A faster heating rate may lead to a larger heat of reaction exotherm (again making comparison with other equipment more difficult) and possibly incomplete reaction, therefore care in picking the appropriate heating rate is required, especially for calibration.

As shown in Figure 48, the position data for ramping dilatometry was quite different in appearance as compared to isothermal data, however, the concept is still the same. From the initial zero position, the position data continually expanded on heating until the power to the heaters was terminated. The position data showed the polymerization shrinkage as a change in slope or a slowing in expansion rate. The thermal expansion of the oil and the sample are in competition with the sample polymerization shrinkage and the volume of the oil is significantly more than the sample volume.

On cooling to the initial temperature, the final position of the cure data is approached. Again, from the difference in initial and final position (approximately 0.23 cm) the final shrinkage was calculated to be 14.2%, which compares favorably to the literature value of 14.5% [92]. This was based on a sample size of 3.9370 grams and a measured density of 0.910 grams/cm³. Unlike the isothermal calibration, there was no need to account for the DSC final conversion when comparing literature and measured final shrinkage, as it is usually assumed that 100% conversion is obtained in a scanning experiment.

The final position of the cure line was taken to be the initial position of the baseline. Once more, the purpose of the baseline was to account for the thermal expansion of the oil. The baseline should return to the zero position or either the reaction did not go to completion during the cure cycle or the system leaked. The baseline did return to the zero position as shown in Figure 48 and therefore the run was valid.

Continuing on the same lines as the isothermal calibration, percent volume change and negative conversion are plotted in Figure 49. For further comparison, Figure 50 is a plot comparing the derivative of the percent volume change and the DSC rate data. The conversion data in Figure 49 was obtained by integration of the DSC rate data shown in Figure 50. Figure 51 is a comparison of the dilatometer temperature profile and the DSC temperature profile used to model the dilatometer. Again, the cooling segment is not included in Figure 49 and Figure 50 as cooling rate was not controlled until the final temperature was obtained.

The percent volume change data (gray line in Figure 49) showed an expansion up to the point at which polymerization started to occur. The initial expansion was caused by the differences in thermal expansion of the monomer and the polymer, since percent volume change was calculated by subtraction of the polymer (baseline) from the reacting monomer. Once polymerization started, the difference in the coefficients of thermal expansion between curing monomer and cured polymer lessened and polymerization shrinkage became the dominant factor. As shown in Figure 49, the percent volume change from the dilatometer compared nicely with the negative conversion data measured by DSC, even showing the change in slope due to the gel effect.

Figure 49. Percent volume change and $-1 \times \text{conversion}$, ramp calibration.

Figure 50. DSC reaction rate data and $-1 \times$ derivative percent volume change.

Figure 51. Comparison of dilatometer and DSC cure temperature profiles.

Figure 50 is simply a different way of viewing the data in Figure 49. The conversion data shown in Figure 49 was obtained by integration of the DSC rate data (times -1) shown in Figure 50, therefore the derivative of percent volume change (times -1) should compare to the DSC rate data and it does as shown in Figure 50. The data in Figure 50 highlights several features not as clearly seen in Figure 49. The gel effect is much easier to see as the secondary peak or shoulder toward the end of the reaction in this form of the data. In Figure 49 this was simply a slight change in slope. Figure 50 shows a slight difference in peak time, indicating that the DSC data led the dilatometer data by approximately 3 minutes. The reason for this lead-lag is the inability to exactly model the dilatometer temperature profile with the DSC as shown in Figure 51. As mentioned earlier, the dilatometer temperature profile is not exactly linear, therefore the DSC temperature profile must be chosen to best model the dilatometer. For lack of a better method, linear regression was used to model the dilatometer temperature profile. This obviously is not the best fit possible; however it is not possible to break the temperature profile into two slopes (as done for isothermal dilatometry) as that would cause a shift in the DSC baseline which could not be accounted for mathematically during integration and the DSC does not accept a second order temperature profile.

3.4 Design History

The current dilatometer design was the product of several generations of designs and refinements. This section will describe briefly this series of refinements

and is included for completeness and general interest as well as to provide some insight into the development process. A more in-depth discussion is available elsewhere [128, 129].

The first dilatometer built in this study was based on the dilatometer used by Mitani et. al. shown in Figure 32 [64]. Recall, that dilatometer employed a 30 cm³ syringe as the sample chamber and used a plastic vial to contain the sample. The position data was measured by a dial gauge and a small oil bath was used to heat the system. Weights were balanced on the syringe plunger to apply pressure to the sample.

After building this apparatus for study, it was found that the sample vial, though satisfactory for rough material comparison, was too limiting for analytical studies. The sample was too large for good temperature control in the sample, a large reaction exotherm coupled with limited pressure caused styrene in the sample to boil leading to large voids and the high temperature required to make the vial pliable limited the equipment to high temperatures and fast reactions. Therefore the search for a replacement started.

Since the reaction of interest in this study was the copolymerization of styrene and unsaturated polyester, the material used to contain the system had to be insoluble in and unaffected by styrene. To avoid limiting the sample size to that of available vials, a pouch was determined to be the best method to contain the sample. Therefore, the material had to be heat sealing as well. Two materials were found to be satisfactory, laminated aluminum foil and laminated polyethylene (the cooking pouch material currently used). The laminated PE was chosen for two reasons: it was easier to obtain and it was transparent. Transparency made it easier to confirm that all bubbles were removed from the sample before sealing the last edge.

The new sample pouch (similar in size and shape to a ketchup pouch) was used in the syringe dilatometer and the smaller sample was a marked improvement. However, there was still a significant reaction exotherm as demonstrated by a large thermal expansion followed by large thermal shrinkage. The sample geometry was still somewhat limiting. The best way to avoid the large exotherm was to provide a larger surface area for the sample to dissipate the heat, which led to a disc shaped sample geometry.

To accommodate a disc shaped geometry, the dilatometer sample chamber needed to be disc shaped. Therefore the syringe was cut and two aluminum plates with a cavity honed between them were adhesively affixed to the cut syringe (with the aid of aluminum sleeves), as shown in Figure 52. The two plates bolted together, forming a cavity between them. An O-ring around the perimeter was used to seal the system. The aluminum plates also provided faster heating for the sample as more surface area was exposed to the heating oil and the thermal conductivity of aluminum is much greater than glass.

This design also provided a possible method of obtaining the sample temperature profile, which was not available up to this point and could only be estimated by bath temperature. The pouch could easily accommodate a thermocouple simply by heat sealing it into the sample with the leads passing through the seal. The sample pouch seal was not breached if the wire was of a small enough gauge.

Figure 52. Schematic of older dilatometer system used very early in this study.

All that was required to get the thermocouple into the sample chamber was to put a small diagonal slice in the O-ring seal between the aluminum discs for each wire and run the wires through the seal. The compression of the O-ring from bolting the plates together assured a good seal. One thermocouple was placed inside the sample and one was placed outside the sample but inside the sample chamber. Any discrepancy between the two readings during reaction was attributed to reaction exotherm during isothermal conditions.

Around this time, the concept of using a baseline was developed. Recall from the previous section that the baseline was used to remove the thermal effects of the encapsulating oil. The baseline was also very helpful in determining if a leak had occurred or the sample reaction was complete during the cure cycle.

The new design made assembly of the equipment slightly more complicated though. A vacuum technique could not be used to fill the system with oil, as the sample would either out gas or volatilize under vacuum, or both. Therefore, the plunger of the syringe was worked until all the air bubbles were removed. A screen on either side of the sample was needed to force the sample into the center of the sample cavity and prevent it from blocking the holes in the discs while working the plunger.

This design was closer to the desired equipment needed to study low shrink unsaturated polyester cure. In fact, this dilatometer was calibrated isothermally and was applied to the study of low shrink UPE resins [128, 129]. However, several undesirable limitations existed, including a limited and dangerous pressure supply (supplied by balancing weights on the syringe plunger). All data was taken manually

and poor temperature control due the use of an undersized oil temperature bath system.

These concerns led to the next generation dilatometer, which was very similar in appearance to the one currently used. The syringe from the first design was replaced with the hydraulic cylinder currently being used. However, instead of pressurizing the upper half of the hydraulic cylinder as done in the current design, a larger pneumatic cylinder was used to push down on the rod of the dilatometer cylinder to pressurize the sample. The sample chamber had to be redesigned to accommodate the higher pressures now possible with the cylinder. Copper was chosen for this task for better heat transfer. To aid in faster heating, a larger oil bath was acquired and in addition to using the heating bath, heating coils were run into the lower half of the sample chamber providing heat directly to the sample at the turn of a valve. Finally, data acquisition was obtained for the system. The rod position was monitored by an LVDT and thermocouples could still be run through the O-ring seal.

After working with this design for a short time, it was discovered that the pressure system had a serious hysteresis problem due to the compressibility of the air in the pneumatic cylinder and a frictionally induced slip-stick situation in the upper (pneumatic) cylinder. This caused irreproducible errors in the position data and at that time it was decided to eliminate the upper cylinder and to directly pressurize the upper half of the hydraulic cylinder.

Running the sample thermocouple through the O-ring quickly became unacceptable due to leaks occurring at the higher pressures and damage being done to the sealing face. At that time the Swagelok seal and tubing encased thermocouple system was developed.

Finally, after several successful but slow experiments, the heating system was redesigned for all electric heating. The oil system was too slow and the coil next to the sample made it more difficult to assure a bubble free sample chamber on assembly. After experimenting with various heating arrangements, the current heating method was chosen as the most appropriate, fastest and easiest to control.

All the above mentioned changes led to the final design of the dilatometer discussed in detail earlier this chapter. And though there may still be improvements to be made, the current design has been proven through calibration and is adequate for studying the low profile behavior in unsaturated polyester resin.

Chapter IV

Volumetric Studies of Low Profile Unsaturated Polyester Resin

4.1 Overview

The first chapter of this document discussed some of the key material aspects of low profile unsaturated polyester resins, including a review of the low profile additive mechanism. From this discussion, it was evident that the LPA mechanism is complicated and, as of yet, not clearly understood. Therefore, it would be valuable to study the LPA mechanism in a clear, logical method in a more analytical and controlled environment. Such a study has been carried out, and the presentation of this study is to follow. However, before the details of the study are presented, an overview of the study is provided in Figure 53. The best way to study LPA shrinkage control was to be able to measure polymerization shrinkage during cure, i.e. dilatometry. With that in mind, dilatometry experiments were performed to study the interactive effects of LPA concentration, pressure, some key additives (thickener and filler), and thermal history on shrinkage control. From these experiments the final polymerization shrinkage and shrinkage trends were obtained, and sample appearance (opacity) was observed. Sample morphology was obtained from the cured samples as well. Finally the results of these experiments were used to provide some insight into the LPA mechanism and propose some modifications to the mechanism outlined in Chapter 1.

Figure 53. Overview of LPA mechanism study.

4.2 Materials and Formulation

Typical unsaturated polyester resin compounds often include the unsaturated polyester resin, styrene, low profile additive, initiator, inhibitor, filler, thickener, fiber, mold release, etc. To minimize the amount of variables and to avoid confusing and unnecessarily complicated results, only the unsaturated polyester resin, styrene, low profile additive, and initiator were included in the formulation (unless studying the effect of a key additive). Only one unsaturated polyester resin and one low profile additive were used; both of them were industrially available.

The unsaturated polyester resin used was Q6585 (Ashland Chemical Co.). Q6585 was manufactured from a 1 to 1 ratio of maleic anhydride and propylene glycol with an average of 10.13 carbon-carbon double bonds per unsaturated polyester molecule. The unsaturated polyester had an average molecular weight of 1580 grams/mole, which worked out to be approximately 156 grams/mole of C=C. The resin was used as received and was shipped as a 65% solution of unsaturated polyester in styrene. The low profile additive used was LP40A (Union Carbide), which was a 40% solution of acrylic modified poly(vinyl acetate) in styrene. The compounds were formulated to provide a styrene C=C to unsaturated polyester C=C ratio of 2.0. The low profile additive concentrations reported later in this chapter were solids weight percent based on the total weight of the unsaturated polyester resin, styrene and low profile additive. One percent PDO (a 50% solution of t-butyl peroxy-2-ethyl hexanoate) was used in the formulation as the initiator and no inhibitor was used, unless indicated otherwise. To summarize the formulations used, Table 3 provides the compositions.

Table 3. Summary of the formulations used in this study.

Formulation	Q6585 (grams)	LP40A (grams)	Styrene (grams)	PDO (grams)
No LPA	65.9	0.0	34.1	1.0
2.5% LPA	64.25	6.25	29.5	1.0
5% LPA	62.6	12.5	24.9	1.0
6% LPA	61.9	15.0	23.1	1.0
10% LPA	59.3	25.0	15.7	1.0
15% LPA	56.0	37.5	6.5	1.0

4.3 Isothermal Studies

Isothermal dilatometry experiments were performed on all of the samples listed in Table 3. Reaction conditions were 80°C and 0.69 MPa (100 psi). Figure 54 summarizes the percent volume change data as a function of time for this series of experiments, and Figure 55 is an example of the temperature profile used. The 15% LPA experiment temperature profile was used as the example in Figure 55; however, all the experiments had very similar temperature profiles. From Figure 55, there was a small (0.5°C) heat of reaction peak during cure.

By studying the trends in Figure 54, clearly the sample without low profile additive exhibited the most polymerization shrinkage. Interestingly enough, the best isothermally cured shrinkage control performance was the sample with the least amount of low profile additive, the 2.5% LPA sample. The 2.5% LPA sample showed an initial expansion (as did all of them) followed by a sharp polymerization shrinkage up to approximately 35 minutes. At about 35 minutes into the run, the sample polymerization shrinkage had stopped. The sample then expanded slightly, and at approximately 100 minutes, the sample resumed shrinkage again at a rate comparable to the other samples in the same time region. The expansion/plateau region was from 35 to 100 minutes for a total of approximately 65 minutes.

The 5% LPA and 6% LPA percent volume change data in Figure 54 also exhibited a plateau region; however, no expansion was measured for these samples, and the shrinkage control performance was less than that of the 2.5% LPA sample. The plateau region for the 5% LPA sample was from 65 to 120 minutes for a total of 55 minutes, and the plateau region for the 6% LPA sample was from 110 minutes to 135 minutes or only about 25 minutes. By adding more low profile additive, the plateau region was lost all together, as shown by the 10% LPA and 15% LPA percent volume change data in Figure 54. Consequently, isothermal low profile additive performance corresponded with a plateau region and better yet a slight expansion.

Figure 54. Plot of percent volume change versus time for isothermally cured samples and various low profile additive concentrations.

Figure 55. Example of isothermal temperature profile used, 15% LPA sample.

The timing of the plateau region seemed to be important too-- the earlier the plateau, the better the shrinkage control. However, the earlier appearance of the plateau region does not necessarily mean that the plateau region occurred at a lower degree of cure. The reaction rate may not be the same for all samples. Recall that the initiator concentration was always 1 gram per 100 grams of the unsaturated polyester resin, styrene and low profile additive; therefore, the samples with more LPA have a higher concentration of initiator based on unsaturated polyester resin and styrene (the 15% LPA samples had 1 gram initiator to 85 grams unsaturated polyester resin and styrene whereas the 2.5% LPA sample had 1 gram initiator to 97.5 grams unsaturated polyester resin and styrene). It has been shown that a higher initiator concentration should produce a slight increase in reaction rate [130]. In competition with this was the effect of concentration of the reactive materials (unsaturated polyester resin and styrene) on kinetics -- a higher concentration of reactive materials (and thus a lower LPA concentration such as 2.5% LPA or no LPA) should react faster. Therefore, very little about the plateau region as a function of conversion can be said without the conversion data. A brief discussion of the relationship between polymerization shrinkage and conversion will be covered later in this chapter.

Figure 56 is a plot of the percent final shrinkage measured as a function of the low profile additive concentration. The no LPA sample demonstrated the highest shrinkage and the 2.5% LPA sample provided the best shrinkage control (or least shrinkage). Table 4 is a summary of the exact final shrinkage measured. Assuming densities were the same, the 10% LPA and 15% LPA samples had final shrinkage almost exactly 10% and 15% less than the no LPA sample (90% of the final shrinkage of the no LPA sample (11.28%) is 10.15%, and 85% of that is 9.59%). This implies that at a higher concentration, the LPA simply acted as a non-reactive filler with no

“low profile activity.” Similarly, Table 4 contains an estimate of the low profile effect observed.

Table 4. Percent final shrinkage measured for various LPA concentrations.

Percent LPA	Final Shrinkage	Low Profile Effect
0	11.28%	0%
2.5	6.89%	4.11%
5	8.76%	1.96%
6	9.91%	0.69%
10	10.14%	0%
15	9.77%	0%

Both the plot in Figure 56 and the plot in Figure 54 show that there was clearly an optimum LPA concentration for best shrinkage control. One could imply from this data that, for a manufacturing process with conditions similar to the isothermal temperature used here (such as hand lay-up or casting), less low profile additive would be desirable and even necessary for best polymerization shrinkage control.

Figure 57 is the SEM micro-graphs of the final (cured) morphology for all the isothermal dilatometry samples. Figure 57(a) is the SEM micro-graph of the sample without LPA. The literature has shown this to be a flake-like structure [56, 57] without any particulate indications and Figure 57(a) confirmed this. From Figure 54, the optimum shrinkage control was found to be at a 2.5% LPA. The corresponding morphology is shown in Figure 57(b). Compared to the other sample micro-graphs in Figure 57, this morphology showed a particulate nature of the unsaturated polyester phase which was very irregularly shaped and loosely packed-- almost peanut shaped.

Figure 56. Plot of percent final shrinkage as a function of low profile additive concentration, cured isothermally at 80°C.

(a)

(b)

Figure 57. Isothermally cured sample morphology, (a) no LPA, (b) 2.5% LPA, (c) 5% LPA, (d) 6% LPA, (e) 10% LPA and (f) 15% LPA.

Figure 57. Continued.

(c)

(d)

Figure 57. Continued.

(e)

(f)

The 5% LPA and 6% LPA samples also exhibited a plateau region shown in Figure 50. Their SEM micro-graphs are shown in Figure 57(c) and Figure 57(d) respectively. The addition of more low profile additive caused the particles to develop in a more spherically shaped and tightly packed morphology. The particle sizes for the 2.5% LPA, 5% LPA and 6% LPA samples were all about the same.

With a higher LPA concentration in the formulation, the plateau region in the percent volume change versus time plot was lost as was shrinkage control; the LPA acted as a non-reactive filler. The corresponding SEM micro-graphs (10% LPA in Figure 57(e) and 15% LPA in Figure 57(f)) show that the particulate structure became smaller, more spherical, and more tightly packed. This result has some interesting implications. The occurrence of phase separation does not necessarily indicate shrinkage control. More than mere phase separation occurred to control the polymerization shrinkage. Therefore, dilatometric experiments were required to study the low profile additive mechanism correctly; SEM studies alone are not enough. The “boiling styrene theory” obviously does not apply to this data as styrene boils at 146°C at atmospheric conditions and well above that at 0.69 MPa (100 psi). These findings do not eliminate, however, the possibility of micro-void or fissure formation in the low profile additive phase, as the low profile additive was etched away for SEM studies. In fact, the data presented here do not conflict with the accepted low profile mechanism. Yet, in light of these data, the accepted low profile mechanism should be scrutinized and perhaps expounded upon.

Summarizing, there was an optimum low profile additive concentration for shrinkage control that corresponded to a loosely packed irregularly shaped morphology. For this system and reactive conditions, 2.5% LPA was optimum, 5% LPA and 6% LPA exhibited some low profile activity, and 10% LPA and 15% LPA

acted as a non-reactive filler. All samples had a particulate morphology; however, the best shrinkage control sample had a larger, irregularly shaped, loosely packed morphology. In contrast, the poor shrinkage control samples had a smaller, spherically shaped, tightly packed morphology.

4.4 Ramping Studies

Using the same materials described in Table 3, two series of ramping dilatometry experiments were performed, one at approximately 8°C/minute, and one at approximately 16°C/minute. All experiments in this series were performed at a sample pressure of 0.69 MPa (100 psi). The thought behind doing two different ramping series was two fold. First, it was meant to provide a trend for studying the effect of heating rate on low profile additive performance. Second, depending on the manufacturing process the compound was used in, one or the other heating rate may be closer to industrial molding condition and, therefore, more closely modeling or approaching the manufacturing process.

4.4.1 8°C/Minute Ramping Series

Figure 58 summarizes the percent volume change as a function of time results for the 8°C/minute ramping series of experiments, and Figure 59 is an example of the temperature profile used in this series. This temperature profile approached the RTM heating cycle or other slower, limited production manufacturing techniques. The

temperature profile of the 15% LPA experiment was used as the example; however, all the experiments had similar temperature profiles. As stated in Chapter 3, the temperature profile was only an approximation of a linear ramp. Comparing the ramp data and the isothermal data, in the 8°C/minute series, the heat of reaction temperature peak is clearly much more of a prominent factor, being approximately 45°C at 10 minutes into the experiment in Figure 59. This was due to the large amount of heat produced during the reaction coupled with the short reaction time. During isothermal dilatometry, the system had several hours to dissipate the heat, yielding only an approximate 0.5°C temperature peak. Since heating time was only 22 minutes at 8°C/minute, the system could not dissipate the heat quickly enough to avoid this peak. Preliminary experiments with slower heating rates showed that the heat of reaction peak could be avoided; however, this would not be close to the molding conditions in industry. In addition, there was speculation in the literature that the temperature rise due to reaction exotherm may be required for good low profile activity [50].

There are a couple of key features in Figure 58 that require some attention. Comparing the percent volume change data in Figure 58, one can clearly see that all samples with low profile additive exhibited some low profile activity, unlike the isothermal dilatometric series. For comparison, the solid line is the percent volume change data for the sample without low profile additive. All the samples expanded during the heating cycle before reaction. However, note that both the 2.5% LPA and the 6% LPA samples showed a secondary expansion peak just before the polymerization shrinkage section of the curve which corresponded to the reaction exotherm peak. It is interesting that all samples had a similar exotherm peak, but only the samples with low concentrations of low profile additive showed this secondary peak activity. In addition, the 6% LPA sample turned out to be the best for shrinkage

control, so secondary expansion activity may be important to good low profile additive performance. One study of two pressure stage molding [27] (a molding technique used with SMC in which the molding pressure is reduced at some time during the part cure cycle for better surface quality and sink mark reduction,. See Chapter 1.) showed that the optimum release time was right before any polymerization shrinkage or reaction exotherm was detected. Since this corresponded to the timing of the secondary peak time, one might think that the release of pressure here may have caused an even larger secondary peak and resulted in less overall polymerization shrinkage.

One final point about the 10% LPA and 15% LPA samples in Figure 58 is that towards the end of the heating cycle, both these samples started to expand. This may have continued if the temperature continued to rise, providing better shrinkage control performance for these samples. However, the heating had to be stopped to avoid exceeding the dilatometer upper temperature of 200°C.

Figure 60 is a plot of the percent final shrinkage as a function of low profile additive concentration. As previously stated, all samples with low profile additive exhibited some low profile activity unlike the isothermal data. Recall that during the isothermal studies at high concentrations, the low profile additive acted simply as a non-reactive filler, similarly, with the isothermal data, an optimum low profile additive concentration was observed. However, the minimum had shifted to a higher LPA concentration of 6% LPA as compared to 2.5% LPA for isothermal cure. Moreover, the minimum region was much broader, implying that some insensitivity or room for error on formulating and compounding the material was available for ramp curing.

Figure 58. Plot of percent volume change versus time for samples cured at 8°C/minute and various low profile additive concentrations.

Figure 59. Example of 8°C/minute cure temperature profile, 15% LPA sample.

The SEM micro-graphs of the dilatometer cured samples are shown in Figure 61. Several interesting differences can be seen between the morphologies of the isothermally cured samples and the morphologies of the 8°C/minute cured samples. The 2.5% LPA, 8°C/minute cured sample morphology is shown in Figure 61(a). Note that it did not have the particulate structure shown in Figure 57(b) for the isothermally cured 2.5% LPA sample. Instead the morphology was less clear and only a slight particulate structure was observed. Final shrinkage data for the 2.5% LPA sample showed a marginal increase in shrinkage control with the ramping cure, demonstrating that the particulate morphology was not entirely essential to low profile activity or mechanism.

The 6% LPA sample provided the optimum shrinkage control at the 8°C/minute cure conditions. The corresponding morphology is shown in Figure 61(b). Note the clear, loosely packed particulate structure. The particles appeared to be somewhat irregular in shape. Comparing the morphology of the 6% LPA, 8°C/minute cured sample to the morphology of the 6% LPA isothermally cured sample in Figure 57(d), the morphology of the 8°C/minute cured sample exhibited a much looser packing and a significantly smaller particle size.

The morphology of the 10% LPA, 8°C/minute cured sample is shown in Figure 61(c). Compared to the 6% LPA, 8°C/minute cured sample, the particles seemed to be more closely packed and smaller. The shrinkage control performance for this sample was slightly less than the 6% LPA, 8°C/minute cured sample, implying again that the loosely packed morphology was important. Compared to the morphology of isothermally cured 10% LPA sample shown in Figure 57(e), again the ramping cure produced a smaller particle size and a less tightly packed network.

Figure 60. Plot of percent final shrinkage as a function of low profile additive concentration, cured at 8°C/minute.

(a)

(b)

Figure 61. 8°C/minute cured sample morphology, (a) 2.5% LPA, (b) 6% LPA, (c) 10% LPA and (d) 15% LPA.

Figure 61. Continued.

(c)

(d)

Finally, the morphology of the 15% LPA, 8°C/minute cured sample is shown in Figure 61(d). Note that a clear particulate morphology did not develop in this sample, yet shrinkage control existed as shown in Figure 60. Compared to the isothermally cured 15% LPA sample in Figure 57(f), which showed a tightly packed particulate structure, the 15% LPA, 8°C/minute sample morphology looked somewhat underdeveloped.

From the morphology-shrinkage control comparison, clearly morphology is not necessarily a good indication of shrinkage control. Comparing the isothermal and 8°C/minute cured sample data, the best shrinkage control for both series exhibited a sample morphology that was loosely packed and well developed. The morphology that corresponded to the optimum isothermal shrinkage control had large, irregularly shaped particles whereas the 8°C/minute cured morphology correlating to optimum shrinkage control had slightly larger particles compared to other 8°C/minute samples but had smaller, more spherical particles compared to the isothermally cured samples. Furthermore, the 8°C/minute data demonstrated that shrinkage control can occur without the particulate structure, and the isothermal data showed that the particulate structure does not necessarily indicate shrinkage control.

4.4.2 16°C/Minute Ramping Series

The final series of ramping experiments was performed at approximately 16°C/minute. Figure 62 is a plot summarizing the percent volume change data for this series, and Figure 63 is an example of the temperature profile used. Again, the temperature profile of the 15% LPA sample was used as the example; however, all the experiments had similar temperature profiles. There was a large (60°C) reaction exotherm peak at approximately 6 minutes into the experiment. This was due to the large amount of heat produced during the reaction coupled with the short reaction time.

Comparing the percent volume change data in Figure 62, one can clearly see that, again, all samples exhibited some low profile activity. As was the case in the 8°C/minute series, all the samples expanded during the heating cycle before reaction. This time all samples showed a secondary peak, but not all of the peaks were the same size. The 6% LPA sample provided the largest secondary peak and the best shrinkage control. The 15% LPA sample provided the smallest secondary peak which was more like a shoulder after some polymerization shrinkage had occurred.

Figure 64 is a plot summarizing the percent shrinkage as a function of low profile additive concentration. As was the case for the previous two series, a minimum in percent final shrinkage was observed; this time it was at 6% LPA again. The 10% LPA final shrinkage was close to the minimum, and both the 2.5% LPA and 15% LPA data were the poor shrinkage control performers of the series.

Figure 62. Plot of percent volume change versus time for samples cured at 16°C/minute and various low profile additive concentrations.

Figure 63. Example of 16°C/minute cure temperature profile, 15% LPA sample.

Figure 65 is a collection of the SEM micro-graphs showing the morphologies of the samples used in this series. Figure 65(a) was the 2.5% LPA, 16°C/minute cured sample. As was the case in the 2.5% LPA, 8°C/minute cured sample, the 16°C/minute cured sample morphology was not clearly particulate in nature. Furthermore, the 8°C/minute and the 16°C/minute 2.5% LPA sample morphologies look very similar. Figure 65(b) is the SEM micro-graph of the 6% LPA, 16°C/minute cured sample morphology. Compared to the 8°C/minute counterpart, the particle size of the 6% LPA, 16°C/minute cured sample was slightly smaller; even though packing seemed comparably loose between the two morphologies.

Figure 65(c) is the SEM micro-graph of the 10% LPA, 16°C/minute cured sample. Again, compared to the 8°C/minute counterpart, the particle size of the 10% LPA, 16°C/minute cured sample was slightly smaller and comparably packed. Finally, Figure 65(d) is the SEM micro-graph of the 15% LPA, 16°C/minute cured sample morphology. Compared to the 8°C/minute cured sample morphology, the 15% LPA, 16°C/minute cured sample started to show a particulate structure though not as clear as the 6% LPA and 10% LPA, 16°C/minute cured sample morphologies.

Figure 64. Plot of percent final shrinkage as a function of low profile additive concentration, cured at 16°C/minute.

(a)

(b)

Figure 65. 16°C/minute cured sample morphology, (a) 2.5% LPA, (b) 6% LPA, (c) 10% LPA and (d) 15% LPA.

Figure 65. Continued.

(c)

(d)

4.5 Overall Comparison

In the previous sections of this chapter, all three series of dilatometer experiments were, for the most part, considered separately. Comparisons of some of the sample morphologies were made, even though actual shrinkage control performance was not. It is informative to compare the three series and to develop an understanding of the effect of the heating rate on low profile additive activity.

Figure 66 is a plot summarizing the percent final shrinkage for all three series of experiments. For comparison, a line representing the calculated filler effect (assuming all densities the same) is included in Figure 66. Several interesting trends are shown in this figure. First, note that increasing heating rate always improved the ability to control polymerization shrinkage. This was observed regardless of the low profile additive concentration. Additionally, the effect was most dramatic for the 6% to 10% LPA range.

From Figure 66, it is also clear that the optimum low profile additive concentration, as defined by minimum percent final shrinkage, shifted to higher low profile additive concentration when heating rate was increased. This has some implications to industrial applications. If one were to formulate for a slow reactive process, one should design a formulation with a lower amount of low profile additive. This process is what is being done industrially [131]. Examples of such techniques include hand lay-up or spray-up techniques and resin casting.

For somewhat higher reaction rates, such as the RTM process, one might expect to see an optimum low profile additive concentration of perhaps 6% to 10%. Extrapolating the trend in Figure 66 for even higher reaction rates such as the SMC or BMC molding processes which have cycle times of less than 2 minutes, more low profile additive would be required for best shrinkage control. Again, this agrees with current industrial technology; the optimum low profile additive concentration in SMC applications is on the order of 15%. Industry has been aware of the trend in Figure 66 for a while; however, all information of this trend was obtained by trial and error molding using techniques such as part visual inspection. Furthermore, the trends in Figure 66 were never quantified nor were they discussed in the literature to any significant extent. Finally, note that as the heating rate increased, the width of the minimum increased. That is, at higher heating rates (faster processes), one may obtain the same shrinkage control from 6% and 10% LPA. From the molding point of view, this may appear to show that after some critical LPA concentration, further addition of LPA has no effect on part quality.

Comparing the percent volume change as a function of time data for the three series, several features tended to correlate to good shrinkage performance. Isothermally, a plateau region was found to indicate low profile activity. Plateau length and expansion during the plateau region correlated to better shrinkage performance. In temperature ramping studies, the existence of a secondary peak correlated with optimum shrinkage control; however, the secondary peak was not required for the existence of low profile activity.

Figure 66. Overall comparison of the final shrinkage data obtained at isothermal, 8°C/minute and 16°C/minute cure temperature profiles.

Finally, some comparisons of the sample morphology were already made. To summarize, optimum shrinkage control correlated with a more loosely packed, clear particulate network. Optimal isothermal morphology showed a very irregular shaped particle whereas optimal shrinkage control in ramping mode showed a slightly irregular particle shape. Particle size correlating to optimum shrinkage control decreased with an increased heating (or reaction) rate. However, within a specific series, larger particle size and irregular particle shape correlated to better shrinkage control. Furthermore, it was found that a clear particulate structure was not required for shrinkage control as was the case with the 2.5% LPA sample in the ramping studies. Moreover, particle formation does not necessarily indicate the existence of shrinkage control as shown by the 10% LPA and 15% LPA samples cured isothermally. It would be safe to say that even though morphology helps to explain the low profile additive mechanism, it is not a good indication of how well a particular formulation will perform in an application. Determining the polymerization shrinkage control ability of a compound still requires a dilatometer.

4.6 Shrinkage and Conversion

To introduce the relationship between polymerization shrinkage and conversion, both the reaction rate data and polymerization shrinkage data were measured for the 2.5% LPA isothermal sample. The reaction rate data was measured with a DSC. Modeling the dilatometer temperature profile in the DSC was done in

the same way as the dilatometer calibration described in Chapter 3. Figure 67 is a plot of both the shrinkage data and the DSC rate data versus time.

The DSC rate data was integrated to get conversion data. Conversion at time, t , was found by calculating the integral of the rate data up to time t and dividing by the total heat of reaction, which was estimated by a separate ramp DSC experiment. Figure 68 is a cross-plot of the polymerization shrinkage versus conversion. The shrinkage data plotted in Figure 68 was shifted so that zero shrinkage is at the peak of the initial expansion of the percent volume change data shown in Figure 67. Thus, the data in Figure 68 starts at the origin. From Figure 68, the relationship between shrinkage and conversion appeared to be linear before the plateau region (within experimental error) as is the case with traditional polymerization. However, during the plateau region, conversion continued but shrinkage stopped. After the plateau region, the polymerization shrinkage continued but at a different slope. This may be attributed to the tail on the DSC curve. In the tail or later region of the cure, the dilatometer was more sensitive. Summarizing, polymerization shrinkage and conversion were found to be linearly related before the plateau region producing a backwards “s” shaped curve. Similar result can be expected for other samples which exhibited a plateau region and samples with which the plateau should show a linear relationship between conversion and shrinkage. This type of comparison could not be successfully made for the ramp cured samples due to the inability to model the large temperature peak found in the dilatometer cure with the DSC.

Figure 67. Comparison of DSC rate data and polymerization shrinkage for the 2.5% LPA sample isothermally cured at 80°C.

Figure 68. Cross plot of polymerization shrinkage and conversion, 2.5% LPA sample cured isothermally at 80°C.

4.7 Change in Morphology/Opacity During Cure

After developing an understanding of the effect of LPA concentration, heating rate, and sample morphology on shrinkage control, it was deemed instructive to find how morphology changed during cure, especially before, during, and after the plateau region shown in the isothermal data. To accomplish this, the dilatometer experiment had to be stopped, the hot dilatometer disassembled, and the sample removed and etched first in a solution of dichloromethane and p-benzoquinone (an inhibitor) and then in clean dichloromethane. It would also be possible to quench the dilatometer to stop reaction; however, that may warp the system and take longer. Thus, it was avoided. Clearly, the best sample to use for this study was the 2.5% LPA sample as it had the longest plateau region.

With that in mind, the next step was to affirm that the 2.5% LPA isothermal data could be repeated because about 6 months had passed since the three series previously discussed were performed, and the styrene source had changed (from Ashland Chemical Co. to Aldrich). Unfortunately, because the material had changed over the 6 months, shrinkage control was lost to some extent. Furthermore, the sample had become very sensitive to preparation methods as shown in Figure 69. Figure 69 shows the percent volume change data for the original 2.5% LPA (presented in Section 4.3) and for two runs of 2.5% LPA prepared from the old material. The two repeated run samples were from the same vial yet exhibited markedly different shrinkage control as shown in Figure 69.

The first of the repeated samples was mixed for 20 minutes (at high rate) and permitted to set 20 minutes before placing into the pouch and run. This sample showed a sharper initial shrinkage before the plateau region and a sharp expansion before the region. The other sample was mixed the same way but was permitted to set overnight before it was used. This sample demonstrated very good reproducibility with the initial part of the cure shrinkage (as compared to the original sample) but also showed a diminished shrinkage control and poor reproducibility of the plateau region. Furthermore, the sample morphologies of the two attempted repeated samples were very similar to each other but very different compared to the original sample as shown in Figure 70. Figure 70(a) shows the original 2.5% LPA sample morphology, Figure 70(b) shows the morphology of the sample used immediately after mixing, and Figure 70(c) shows the morphology of the sample aged overnight. Clearly, the particulate morphology was diminished yet some shrinkage control was measured.

Several experiments were performed to try to explain this odd phenomenon. First, experiments were performed to see whether the trends in Figure 69 were repeatable, especially the occurrence of the sharp expansion. Having found that the trend in Figure 69 was repeatable, it was then thought that perhaps the sample was styrene deficient since styrene could have easily volatilized from the sample as it aged. A sample with 5% extra styrene by weight was prepared, set overnight and run. The results showed an even larger expansion than the previous sample did. Thus, it is possible that while mixing the sample twice to get the results in Figure 69, enough styrene was lost to account for the difference in the expansion and plateau. That still did not explain the difference between these findings and the original data. A sample of all fresh material was prepared, and it yielded slightly better results, but shrinkage control was still somewhat less than the original sample and a non-particulate sample morphology similar to Figures 70(b) and (c) was still observed.

Figure 69. Comparison of 2.5% LPA samples cured isothermally at 80°C, demonstrating change in materials with age, inhibitor level and preparation.

(a)

(b)

Figure 70. Morphology of 2.5% LPA samples isothermally cured, (a) original, (b) mix and use after 20 minutes, (c) mix, let set overnight and use and (d) 50 ppm pBQ added.

Figure 70. Continued.

(c)

(d)

It was finally discovered that the inclusion of 50 ppm p-benzoquinone (pBQ, an inhibitor) in the sample formulation yielded the same shrinkage control as originally measured (shown in Figure 69). Furthermore, the particle formation was repeated in the pBQ sample, only bigger, as shown in Figure 70(d). In hindsight, this makes some sense. The inhibitor definitely would change the reaction conditions during the very initial stages of polymerization, which in turn would affect the particle formation and, therefore, the whole shrinkage mechanism. Ideally, it is thought that the inhibitor consumes all the free radicals produced by the initiator until all of the inhibitor is consumed; however, in reality, this is not true. Some polymerization does occur during this time, apparently enough to affect the phase separation and particle formation. The last question to answer would then be how did the inhibitor level change? Small amounts of inhibitor were included in the styrene, LPA and unsaturated polyester resin used in this study by the manufacturer of these materials, and it was not removed before use. The inhibitor could have been slowly consumed over the course of the 6 months aging between the attempts to repeat the original data and the original series. Furthermore, by changing the source of the styrene, as previously mentioned, one clearly could change the inhibitor level. Therefore, the phenomenon demonstrated in Figure 69 and Figure 70 can be explained, however, it could not have been avoided. The old material was used for the rest of this study, and when comparisons to original data were desired, they were made to repeats of the original series using the aged materials.

Figure 71 is a plot demonstrating the effort to determine morphology change during reaction of a 2.5% LPA sample cured isothermally at 80°C, 0.69 MPa (100 psi). The reaction was stopped three times during the cure, at 26 minutes, 50 minutes, and 150 minutes into the experiment as shown in Figure 71, and the sample

appearance (opacity) and morphology were observed. Again, the system was disassembled hot, and the sample was placed in a solution of dichloromethane and p-benzoquinone to stop the reaction. The entire process took approximately five minutes from cutting the power to the heater to placing the sample into the dichloromethane solution. The sample morphologies of the three points of interest are shown in Figure 72.

The first sample (26 minute) corresponded to the region of large shrinkage before the plateau region. The 26 minute sample was observed to be a slightly cloudy gel (solid). After etching, the sample turned stark white (opaque). The morphology of this sample is shown in Figure 72(a) and appeared slightly deflated but nonetheless fully developed. This could be due to the removal of unreacted unsaturated polyester and styrene from the sample during etching, which is analogous to letting some of the air out of a balloon.

The 50 minute sample, which corresponded to the beginning of the plateau region, was observed to be an opaque (stark white) solid. The corresponding morphology is shown in Figure 72(b) and is not markedly different from the 26 minute sample.

Finally, the 150 minute sample representing a point after the plateau region was also found to be an opaque solid, and the corresponding morphology, which was not unlike the 26 and 50 minute sample morphologies, is shown in Figure 72(c).

Figure 71. Plot demonstrating points where the reaction was stopped and sample appearance and morphology were observed, 2.5% LPA cured at 80°C, 0.69 MPa (100 psi).

(a)

(b)

Figure 72. Change in morphology during cure of 2.5% LPA sample, (a) 26 minutes, (b) 50 minutes and (c) 150 minutes in the experiment.

Figure 72. Continued.

(c)

In summation, the sample morphology did not change markedly after gelation had occurred early on in the reaction, and this is in agreement with some of the findings in the literature [56, 57]. Opacity did change during the reaction, and shrinkage control as demonstrated by the plateau region corresponded to an opaque sample. After observing this trend, the samples from the three previous series discussed in Section 4.3 and Section 4.4 were observed, and this trend was confirmed. The samples that demonstrated shrinkage control were opaque (or stark white), and the samples that acted as no more than a filler were a cloudy translucent white. Furthermore, the 2.5% LPA isothermal repeated samples from Figure 69 showed regions that were opaque where the sample was the thickest and cloudy where the sample was thin. This implied that the thick regions in the sample pouch experienced shrinkage control, and the thin regions in the pouch did not. An attempt to explain this phenomenon is postponed until later in this chapter.

4.8 Effect of Pressure on Shrinkage Control

The effect of pressure was investigated by the comparison of the high pressure and low pressure cure shrinkage profiles of two of the formulations in Table 3, the 2.5% and the 6% LPA formulations. Both samples were cured isothermally at 80°C in the dilatometer and had 0.69 MPa (100 psi) and 2.55 MPa (370 psi) as a sample pressure. Figure 73 is a plot comparing the percent volume change versus time for the 2.5% LPA sample cured at high and low pressures, and Figure 74 is the same only with the 6% LPA. When comparing the data in Figure 73 and Figure 74, one must understand that a hysteresis problem occurred at high pressure with the current

dilatometer design. The effect of this hysteresis is that the high pressure data obtained were somewhat compressed. That is, the high pressure data shown in Figure 73 and Figure 74 should have shown a larger expansion before cure (during heating) and shown more shrinkage at the end of the heating cycle aligning the high temperature and low temperature final shrinkage data. Nonetheless, the trends in the data and the final shrinkage measured are correct as the baseline returned to the zero position for these experiments. Recall from Chapter 3 that the baseline could be used to indicate the validity of an experiment. If the baseline returned to the zero position no leakage occurred and the results were valid, if not, either more cure or a leak occurred.

Comparing the high and low pressure experimental results, the final shrinkage is markedly higher for the high pressure samples for both LPA concentrations. Furthermore, the plateau region was not observed at high pressure as shown in Figure 73 and Figure 74. The sample colors matched the trend previously discussed, too. The low pressure samples were stark white (opaque) in appearance, and the high pressure samples were cloudy (translucent) in the case of the 2.5% LPA sample and a blotchy translucent for the 6% LPA sample. Etching in dichloromethane turned the 6% LPA, high pressure sample stark white but had no effect on the 2.5% LPA high pressure sample color. Table 5 summarizes the pressure effect results. From these results, clearly pressure had a negative effect on shrinkage control.

Figure 75 is a comparison of the sample morphologies for the pressure studies. Figure 75(a) and Figure 75(b) are the 2.5% LPA samples cured at 0.69 MPa (100 psi) and 2.55 MPa (370 psi) respectively and Figure 75(c) and Figure 75(d) are the 6% LPA samples cured at 0.69 MPa (100 psi) and 2.55 MPa (370 psi) respectively. From these micro-graphs, pressure did not have a large effect on morphological

difference visible was that the particles formed at higher pressure were slightly smaller.

Table 5. Comparison of final shrinkage and color/opacity for the pressure series.

Sample	Appearance	Appearance After Etch	Final Shrinkage
2.5%, 0.69 MPa	Two Regions, Stark white and Translucent	No Change	7.8%
2.5%, 2.55 MPa	Translucent	No Change	12.5%
6%, 0.69 MPa	Stark White	No Change	8.8%
6%, 2.55 MPa	Blotchy Translucent	Stark White	11.0%

4.9 Effect of Filler

The effect of filler was investigated for both isothermal and ramp cure conditions. Camel Wite, an industrially available, 3 micron calcium carbonate powder was used as the filler at a loading of 200 parts per hundred resin (phr) by weight. All other aspects of the formulation and sample preparation were unchanged and all reactions were performed at 0.69 MPa (100 psi).

Figure 73. Effect of pressure, 2.5% LPA sample isothermally cured at 80°C.

Figure 74. Effect of pressure, 6% LPA sample isothermally cured at 80°C.

(a)

(b)

Figure 75. Effect of pressure on sample morphology (a) 2.5% LPA cured at 0.69 MPa, (b) 2.5% LPA cured at 2.55 MPa, (c) 6% LPA cured at 0.69 MPa and (d) 6% LPA cured at 2.55 MPa.

Figure 75. Continued.

(c)

(d)

The 2.5% LPA sample was used for the isothermal study and was again cured at 80°C. Figure 76 is a plot of the percent volume change data as a function of time for both the filled and unfilled samples. In addition, the calculated (effective) shrinkage based on resin volume alone for the filled sample is shown in Figure 76. The resin volume was back-calculated knowing the filled sample size and the filler loading. From Figure 76, clearly the inclusion of filler decreased the overall resin shrinkage with a final shrinkage of about 5.5% for the filled sample compared to about a 7.8% shrinkage for the unfilled sample. However, comparing on a resin only basis, the filler had a somewhat negative affect on shrinkage control as final shrinkage of the filled sample based on resin volume only was approximately 9.5%.

The 6% LPA sample was used to study the effect of filler in a ramping cure situation. The heating rate used was approximately 8°C/minute. Figure 77 is a plot of percent volume change for the unfilled sample, filled sample, as well as the filled sample based on resin volume only analogous to Figure 76. The secondary peak common to the ramp cure studies was observed for both samples; however, it was much larger for the unfilled sample. Also, the timing for the secondary peak was different. The filled sample showed some shrinkage before the secondary peak, and the unfilled sample almost expanded before any shrinkage was detected. For comparison, Figure 78 is a plot of the cure temperature profile for both the filled and unfilled samples.

Figure 76. Comparison of filled and unfilled 2.5% LPA samples cured isothermally at 80°C.

Figure 77. Comparison of filled and unfilled 6% LPA samples cured at 8°C/minute.

Figure 78. Comparison of cure temperature profile for filled and unfilled 6% LPA samples cured at 8°C/minute.

The temperature profiles in Figure 78 correspond again to the secondary peak measured in the percent volume change data. Clearly the sample without filler showed a larger temperature rise, and therefore, a larger secondary peak in Figure 77. However, the final shrinkage data for these samples was not significantly different. The final shrinkage for the unfilled sample was 2.7% while the final shrinkage for the filled sample was 1.7% which based on resin volume alone was approximately 3.0%. This implies that the effect of the secondary peak and the magnitude of the reaction induced temperature peak are minimal on shrinkage control, and that the effect of filler in a ramp cure situation is insignificant as far as shrinkage control is concerned.

4.10 Effect of Thickener

The effect of thickening on shrinkage control was investigated both isothermally and with a ramp heating profile. As discussed in Chapter 1, thickening is the ionic reaction between alkaline earth oxides and hydroxides, and the carboxyl groups in the resin and sometimes in the LPA. In the case of the formulations used in this study, both the LPA and the unsaturated polyester resins used had carboxyl groups and, therefore, participated in the thickening reaction. The 6%, 10% and 15% LPA formulations in Table 3 were used with the addition of 3% MgO by weight, and no filler was used to study shrinkage control of thickened samples.

Careful sample preparation was required to get repeatable results and a well-mixed sample. The thickened sample did not flow easily; therefore, some of the viscosity rise had to occur in the sample pouch. Sample preparation consisted of first formulating the resin and mixing it well for approximately 20 minutes. Then the

MgO was added mixing it first with a small amount of the resin and then blending that into the rest of the batch. The sample was then mixed, first at a high shear to provide good mixing, then slowly to prevent separation until the sample viscosity started to rise. The amount of time the resin took to start to thicken was highly dependent on LPA concentration; the 15% LPA sample started to thicken in about 2 hours, and the 6% LPA sample required over 6 hours. This is not surprising since the LPA molecular weight and viscosity was significantly higher than that of the unsaturated polyester resin. Furthermore, formulations with more LPA provided the most uniformly thickened sample. The 6% and 10% samples would separate in the pouch if permitted to set; therefore, they were strapped on to a high speed shaker mixer (Thermolyte Type 50000 Maxi Mix III) to help prevent separation in these samples during the completion of thickening in the pouch. However, the 15% LPA sample, even without the mixer, still thickened more uniformly and, therefore, reacted slightly differently than the 6% and 10% LPA samples.

Figure 79 is a plot of percent volume change versus time for the thickened samples isothermally cured at 80°C, 100 psi. Again, the difference in the 15% LPA sample and the 10% and 6% LPA samples may be attributed to sample uniformity. By comparing the 6% thickened sample to the 6% unthickened ones, clearly shrinkage control was lost by the inclusion of thickener. Furthermore, the samples were translucent in appearance, indicative of poor shrinkage control.

Figure 80 and Figure 81 summarize the findings for the ramp cured thickened samples. Figure 80 is a plot of percent volume change versus time for the thickened samples cured at approximately 8°C/minute, and Figure 81 is the same for the 16°C/minute sample. The secondary peak was not observed for any of these samples, and the corresponding temperature peak was somewhat smaller compared to the

unthickened samples (approximately 10°C less). Some shrinkage control was observed for the ramp cured samples though the shrinkage control was substantially less than the unthickened samples. Correspondingly, the samples were observed to be opaque in appearance.

Table 6 is a summary of the final shrinkage measurements for the thickened samples. Some of the scatter in the shrinkage data should be attributed to sample non-uniformity, and direct comparison to the unthickened samples would be incorrect. However, shrinkage control was reduced with the inclusion of the thickener.

Table 6. Summary of the thickened sample final shrinkage data. Numbers in parenthesis is unthickened final shrinkage measured.

LPA content	Isothermal Final Shrinkage	8°C/minute Final Shrinkage	16°C/minute Final Shrinkage
6%	11.6/(9.9)	8.9/(3.5)	-
10%	11.4/(10.1)	9.8/(4.7)	-
15%	12.1/(9.8)	8.4/(5.0)	9.3/(4.8)

An explanation for the reduced shrinkage control can be found in the sample morphologies shown in Figure 82. Figure 82(a), Figure 82(b), and Figure 82(c) are the 6%, 10% and 15% LPA isothermally cured thickened samples, respectively. The particulate micro-structure was not developed for these samples though some micro-

structure was visible. The thickening reaction ionically coupled the unsaturated polyester resin and LPA molecules, changing the compatibility and the ability to develop the particulate unsaturated polyester morphology during cure. This, in turn, prevented the needed micro-structure formation and, therefore, the shrinkage control.

Comparing the morphology of the 6%, 10% and 15% LPA thickened sample cured at 8°C/minute in Figure 82(d), Figure 82(e), and Figure 82(f) respectively, a particulate morphology was observed. The thickened sample morphology observed showed a much smaller particle size and a tighter packing structure when compared to the non-thickened counter part which would explain the reduced shrinkage control. In the literature, it has been reported that the viscosity of thickened samples breaks down at approximately 100°C [132] implying that at least some of the ionic bonds that caused the thickening split at around 100°C. The reaction temperature peak was observed to start around 110°C. Therefore, shortly before the reaction, some of the ionic thickening bonds split permitting some phase separation to occur and, thus, a somewhat particulate morphology to develop. Looking at the 15% LPA 16°C/minute thickened sample in Figure 82(g), the particulate morphology was not as developed as the 8°C/minute sample, and shrinkage control decreased accordingly as shown in Table 6. At a faster heating rate, the time between splitting the ionic bond and gelation was reduced; therefore, particle formation may have been limited by lack of time.

In conclusion, thickening had a negative effect on shrinkage control. It made particle formation difficult above the temperature in which the ionic bonds split, it made it impossible below that point. This, in turn, reduced the shrinkage control.

Figure 79. Comparison of percent volume change versus time data of thickened samples with various LPA concentrations cured isothermally.

Figure 80. Comparison of percent volume change versus time data of thickened samples with various LPA concentrations cured at 8°C/minute.

Figure 81. Percent volume change versus time data of a thickened 15% LPA sample cured at 16°C/minute.

(a)

(b)

Figure 82. Morphology of thickened samples (a) 6% LPA isothermal, (b) 10% LPA isothermal, (c) 15% LPA isothermal, (d) 6% LPA 8°C/minute, (e) 10% LPA 8°C/minute, (f) 15% LPA 8°C/minute and (g) 15% LPA 16°C/minute.

Figure 82. Continued

(c)

(d)

Figure 82. Continued.

(e)

(f)

Figure 82. Continued.

(g)

4.11 LPA Mechanism

From the data presented in this chapter, clearly the sample morphology was important to the LPA mechanism, but in itself, morphology did not fully explain the shrinkage control mechanism. This implies a two step mechanism, requiring that micro-structure formation occurs first. The literature has proposed the formation of fissures or voids in the weaker LPA phase; however, little conclusive evidence for fissure formation was available. Fissure formation could explain why the samples with good shrinkage control (as measured by the dilatometer) are opaque or stark white in appearance whereas the samples with poor shrinkage control (LPA acting as a non-reactive filler) were cloudy or translucent in appearance.

To investigate the occurrence of fissures in systems exhibiting shrinkage control, BET surface area analysis was performed on samples with various levels of shrinkage control. As LPA shrinkage control increased, fissure formation should have increased. If fissure formation is the second step in the LPA mechanism surface area should have increased. Therefore, shrinkage control and surface area should correlate nicely.

BET [133, 134], named after Brunauer, Emmett and Teller, is a technique used to measure surface area any clean, non-volatile material, but most often a catalyst. The technique required that the samples be outgassed entirely (overnight) preferably while being heated. Once all the gas adsorbed on the surface of the sample was removed, the samples (in glass vials) were placed in liquid nitrogen, and a known amount of adsorbate gas was released into the sample chamber. Several gases were

available as the adsorbate, including argon, nitrogen and krypton. Krypton was used for this study as it was most applicable to the surface area range of interest (less than 2 square meters per gram). The technique assumes that the first layer molecules to adsorb onto the sample surface were attracted by van der Waal forces whereas additional layers were added by condensation. The amount of adsorbate gas was incrementally increased, measuring the equilibrium pressure for each known amount of gas. At equilibrium, the rate at which gas condensed and evaporated from the surface was equal. By equating the rates and summing over an infinite number of layers [133, 134]:

$$V_a = \frac{V_m C P}{(P_s - P)[1 - (C - 1)(P / P_s)]} \quad (1)$$

where

V_a = Volume of gas adsorbed at pressure P

V_m = Volume of gas adsorbed when surface is covered with a monolayer

C = constant based on adsorbing gas type and temperature

P_s = saturation pressure.

Rearranging

$$\frac{P}{V_a(P_s - P)} = \frac{1}{V_m C} + \frac{C - 1}{V_m C} \frac{P}{P_s} \quad (2)$$

So a plot of $P/V_a(P_s - P)$ vs. P/P_s provided V_m , and from V_m , the surface area of the material was found by knowing the area covered by one krypton molecule ($21\text{\AA}^2$) [133, 134].

Ideally, one might want to use 2.5% LPA samples isothermally cured along various regions of the shrinkage profile (before, during, and after the plateau region) as was done for determining change in morphology during cure. However, this would not be possible due to the enormous amount of unreacted styrene in the sample. Therefore, the BET technique was applied to the 2.5% LPA isothermally cured high pressure sample, the 2.5% LPA isothermally cured low pressure sample, and the 6% LPA sample cured at 8°C/minute. The 2.5% high pressure sample was chosen because no shrinkage control was observed, and the 2.5%, low pressure and 6%, 8°C/minute samples were chosen to represent various levels of shrinkage control.

The results of the BET studies are summarized in Table 7. Clearly shrinkage control and surface area correlated nicely. Comparing the data in Table 7, a shrinkage control of 9.8% provided a 38 fold increase in surface area (between the high pressure 2.5% LPA sample and the 6% ramp cured sample), and a shrinkage control of approximate 3.5% provided a 2.5 fold increase in surface area (comparing the 2.5% low and high pressure samples). Note that the relationship between the surface area and shrinkage control is not linear. Studying the morphology of the low pressure 2.5% LPA sample (with the non-particulate morphology as shown in Section 4.7), it was evident that fissure development could not be well developed; therefore, quite a few “blind pores” should be expected. That is, all the fissures were not connected internally, and pores existed in the center of the sample, which were not accessible to the BET technique used.

Table 7. Summary of BET surface measurement experiments

	2.5% LPA 2.55 MPa Iso. Cure (80°C)	2.5% LPA 0.69 MPa Iso. Cure (80°C)	6% LPA 0.69 MPa Scan (8°/minute)
Final Shrinkage	12.5%	9.0%	2.7%
Surface Area	0.028 m ² /gram	0.070 m ² /gram	1.074 m ² /gram

Figure 83 is SEM micro-graphs of samples that were not etched and had visible fissures. Figure 83(a) is the morphology of the ramp cured 6% LPA sample used in the BET series of experiments, and Figure 83(b) is the morphology of a 6% LPA sample cured isothermally at 80°C and 0.69 MPa (100 psi). Comparing the two, the fissures seemed to have developed in the LPA phase between the unsaturated polyester particles as expected. However, the size and number of the fissures seem to be different. The isothermally cured sample showed a much larger, long and wide fissure through the particles where the ramp cured sample showed many much smaller, shorter and narrower fissures. This was a direct result of the particulate morphology for the samples. Large particles provided fewer weak (LPA) regions in which fissure could grow, but the larger particle also provided a larger weak region so larger and wider fissures could develop. Unfortunately, SEM provided only a two dimensional view of the fissure formation. BET analysis provided indirect insight into the three dimensional aspect of fissure formation.

(a)

(b)

Figure 83. SEM micro-graphs demonstrating fissure formation (a) 6% LPA sample cured isothermally and (b) 6% LPA sample cured at 8°C/minute.

Given that the LPA mechanism is a two stage process including particle formation and, subsequently, fissure formation, the mechanism or cause behind fissure formation still requires some explanation. Clearly, fissure formation did not occur in all of the samples as some samples were translucent, and, thus, shrinkage control was not observed. Fissure formation must have occurred because of internal stresses developed by the polymerization shrinkage, and the level of stress necessary to develop the fissures must be different for different samples.

Reviewing the data in the previous sections of this chapter, the two step mechanism can be applied to explain the shrinkage control observations. The relationship between LPA concentration and reaction temperature profile showed an optimal morphology which was more loosely packed and, within a particular series, showed larger and irregularly shaped particles. The larger irregularly shaped particles and the looser packing structure provided the largest continuous weak phase that the fissures could initiate and propagate. The faster reaction in the ramp cure cycle provided a higher level polymerization and induced internal stress due to the fast reaction. Therefore, even though the weak phase was on a smaller order of magnitude, the internal stress developed could still cause the development of fissure formation. Furthermore, the ramp cured filler studies showed that the stress produced internally was predominately due to polymerization instead of the thermal effects as the shrinkage control was about the same but the temperature peak was suppressed for the filled sample. A slow reaction, as demonstrated by the isothermally cured samples, could permit stress-relaxation to occur making fissure formation more difficult even though the larger morphology would make fissure propagation easier.

The large expansion observed before the plateau region in some of the isothermal samples described in Section 4.7 can also be explained by fissure

formation. As the stresses developed, a metastable situation developed, and when a fissure formation initiated, propagation through the sample was fast and quickly relieved the stress. This, in turn, caused the material to spring back and expand on the macro scale. In contrast, the plateau regions without a sharp expansion were caused by fissure propagation that grew slowly to compensate shrinkage; thus, polymerization shrinkage occurred on the micro-scale but was not observed on the macro-scale.

The effect of pressure on shrinkage control can also be explained by fissure formation. Intuitively, it would be more difficult to form a fissure with the sample under pressure. Therefore, even though the sample morphology was not changed markedly by high pressure, fissure formation was more difficult and did not occur. This may help to explain, at least in part, the benefits of using a two stage molding process in compression molding. Initially, a high pressure in the mold and good, intimate contact between the molding compound and the mold would be required for mold filling. However, once the material had gelled and before the reaction exotherm (as indicated by the secondary peak in the ramp data), it would be beneficial to release the mold pressure to help develop the fissures and control shrinkage.

Finally, the thickened sample data showed an underdeveloped morphology due to the formation of ionic bonds during thickening. Even though the internal stress developed during the cure, the LPA phase did not develop as well as the unthickened samples, and shrinkage control was affected accordingly. Both the development of the morphology and the development of internal stress induced fissures were required.

On the basis of the findings of this study, a proposed LPA mechanism is:

1. As the material is heated, it expands thermally as indicated by the initial expansion observed.
2. The rise in temperature causes initiator decomposition and cure starts.
3. The once compatible thermoplastic becomes incompatible and starts to form a second phase. The unsaturated polyester resin develops the characteristic particulate morphology and the LPA forms a layer around and in between the UP particles. Morphology does not change markedly once developed. If the sample was thickened, most of the ionic bonds must first be split before morphology can develop.
4. The material becomes increasingly rigid as polymerization continues and internal stresses develop. At some critical internal stress value, fissures form along the weak LPA region and propagate. Two possible methods of fissure development are possible: (1) fissures can grow to compensate shrinkage or (2) metastable situation could develop in which when the fissures develop they grow very quickly causing the material to “spring back” or expand somewhat.

Several points highlighted in the literature were not observed in this study.

They include:

1. Volume correction between the phases: As the degree of polymerization increases, the UPE phase will shrink. As the temperature increases, the volume occupied by the LPA and unreacted monomer increases compensating for polymerization shrinkage.

2. Fissure formation due to cure in the LPA phase: The monomer in the LPA phase starts to react creating micro-voids in that region due to the polymerization induced stress. (The LPA phase should be higher in styrene content which should react slowly compared to the unsaturated polyester phase. Furthermore, the higher styrene content in the LPA phase should weaken the phase and make fissure formation easier by the unsaturated polyester phase polymerization shrinkage.)

Summarizing the key points, the LPA mechanism is a two stage process; first, the weak phase (morphology) must develop, and then the stress induced fissures must develop. Without the two phase morphology, shrinkage would not be possible, and without the micro-structure formation, fissure development could not occur on the micro-scale. The LPA phase separation/micro-structure formation sets the stage for shrinkage control but does not, in itself, control shrinkage. Fissure formation is required for shrinkage control to develop. Optimum morphology will provide the largest continuous weak regions for fissure development to occur; however, fissure formation requires the development of internal stresses. Therefore, optimum shrinkage control is a function of both morphology and reaction induced stresses.

Chapter V

Molding and Shrinkage Control

5.1 Introduction to Molding

Several of the common molding problems experienced in industry are to some extent caused by polymerization shrinkage. To investigate the role of shrinkage control in molded part surface quality and dimensional control, a series of BMC compression molding experiments was performed using a formulation very similar to that used in the dilatometer. To better understand the relationship between LPA mechanism, shrinkage control, and molded part surface quality and dimensional control, comparisons between molded part surface quality, molding shrinkage, morphology and BET surface area as a function of LPA concentration were made. The effect of thickener and higher reaction temperature was also briefly studied.

All moldings were performed by the Specialty Chemical Division of Union Carbide Corporation at the South Charleston, West Virginia location. Two series of unthickened BMC compression moldings were performed, one series at 3.45 MPa (500 psi) molding pressure using 45.7 cm (18 in. by 18 in.) square mold and one series at 0.69 MPa (100 psi) molding pressure using a 30.5 cm (12 in. by 12 in) square mold. The larger panels were molded on a Lawtomatic 200 ton press (C. A. Lawton Co.,

De Pere, Wisconsin) using a 1200 gram charge, and the smaller panels were molded on a 100 ton variable pressure press (Erie Mill and Press Co., Erie, Pennsylvania) using a 550 gram charge. The 30.5 cm square mold was smooth on one side and textured on the other, and the larger press was smooth on both sides and of higher surface quality than the smaller mold. The panel surface quality from the smaller mold was poor due to the low pressure used; therefore, the surface quality data from those parts was not considered, and only molding shrinkage for those parts is reported. All samples were molded for 4 minutes at 120°C except for one sample which was molded at 150°C to compare the effect of temperature on molding and simulate a “fast cure” application.

The formulations in Table 3 had to be changed slightly for molding. These changes included doubling the initiator concentration and including filler, glass fiber and zinc stearate as an internal mold release agent into the formulation. Glass content was kept low (10% by weight) in order to exaggerate the molding shrinkage as discussed in Chapter 1. The filler used was Huber W4, which was a 4 micron calcium carbonate powder. The glass used was Vetrotex P-276, which was a 1.25 cm (0.5 in.) chopped fiber. 20% and 25% LPA samples were also prepared for the larger panel molding series. These formulations required that a special LPA formulation containing 50% by weight poly(vinyl acetate) be prepared. In addition, one 15% LPA high temperature formulation and one 15% LPA thickened formulation was prepared. The high temperature formulation was prepared with 1 phr TBPB instead of the PDO, and the thickened sample was prepared by the inclusion of 2.0 phr of a MgO suspension (Plasticolors PG-9033) which worked out to be about 0.8 phr MgO overall. Table 8 summarizes the formulations used for molding.

The charges were prepared by first mixing the unsaturated polyester resin, styrene, LPA, mold release, and initiator with a cowel mixer at high speed for 3

5.2 D-sight Results

A D-sight Audit Station-2 (Diffracto Co.) was used to quantify the molded part surface quality. A brief description of the D-sight technique was provided in Chapter 1. The D-sight technique provided both a photograph of the part that emphasized the surface peaks and valleys and an unbiased index number related to the surface quality that was larger for poorer quality surfaces and zero for an ideal, perfectly smooth, level, glossy surfaces.

The panels were used as they were molded, and no highlighting of the samples (application of a fluid to make the surface glossy) was necessary. The center regions of the parts were consistently analyzed by placing each part on the same location of the sample table. The algorithm “surf” was used to analyze the parts, and the light source was adjusted to be between 100 and 110. Figure 84 is a summary of the D-sight photographs obtained for the 45.7 cm panels molded. Figure 84(a) through Figure 84(g) summarize the LPA series with increasing LPA concentration. Figure 84(h) is the thickened sample, and Figure 84(i) is the sample cured at a higher temperature. When looking at the photographic output from D-sight, the lighter the color in a region, the higher the peak. That is, white represented a peak, and black represented a valley. Also, the box in the photographs shows the region in which the analysis was performed to determine the index number. Index number was found by analyzing several vertical lines within the box region, and vertical line shown in the box highlights the worst line measured.

(a)

(b)

Figure 84. D-sight output, (a) no LPA, (b) 2.5% LPA, (c) 6% LPA, (d) 10% LPA, (e) 15% LPA, (f) 20% LPA, (g) 25% LPA, (h) 15% LPA thickened and (i) 15% LPA cured at 150°C

Figure 84. Continued.

(c)

(d)

Figure 84. Continued

(e)

(f)

Figure 84. Continued

(g)

(h)

Figure 84. Continued.

(i)

The no LPA and 2.5% LPA panels were, by far, the worst. By visual inspection, the surface waviness was evident, and when placed on a flat surface, warpage was very apparent. From the output, the D-sight index (shown above the analysis box) was very high for flat panels, 569.0 for the no LPA sample and 478.7 for the 2.5% LPA sample. The D-sight index numbers for this series is summarized in Table 9. Finally, these two panels were different in color when compared to the other panels molded. They were almost tan and fibers could easily be seen in the panel molded without LPA. All the other panels were white in color, and fiber readout was not observed.

Continuing through Figure 84, the 6% and 10% LPA data showed continued improvement with addition of more LPA. The 15% LPA sample was slightly worst (with a slightly higher index), and again the 20% LPA sample showed more improvement still. Finally, at the 25% LPA panel surface quality decreased markedly with increasing concentration. With molding, several variables are important to surface quality, including the ability for the molding compound to evenly distribute and carry fibers. As the LPA content increased, the viscosity of the resin increased and the shrinkage control increased to a point. When viscosity is too high, the fibers are not as easily distributed into the resin when compounding the charge and mold filling becomes more difficult. Thus, the glitch at 15% LPA could be due to either several groups of fiber that did not distribute well or a random molding error.

According to Figure 66, the LPA concentration should eventually reach an optimum for best shrinkage control, and with the addition of more LPA, shrinkage control should lessen. However, the data in Figure 66 was for material cured at up to 16°C/minute and 0.69 MPa, and as heating rate increased, the minimum in shrinkage control broadened. Since the molding was performed at 120°C, an approximate heating

rate of 80°C/minute would be an appropriate estimate. Extrapolating from Figure 66, one might guess that shrinkage at that rate should show a relatively wide minimum and a higher LPA concentration requirement. This is in agreement with the surface quality trends represented in Figure 84 and the D-sight index data given in Table 9.

Table 9. D-sight index of molded panels.

Panel Description	Index Value
No LPA	569.0
2.5% LPA	478.7
6% LPA	268.2
10% LPA	82.7
15% LPA	84.6
20% LPA	41.3*
25% LPA	111.9*
15% LPA, thickened	471.9
15% LPA, 150°C cure	375.4

* This data based on the average value from two panels

Figure 84(h) and Figure 84(i) are the D-sight photographs for the thickened and 150°C cured panels respectively. These panels were molded to confirm briefly the effect of thickening and to better understand the effect of molding temperature. Both of these panels were molded from charges containing 15% LPA and should be compared to the 15% LPA panel in Figure 84(e). Clearly, thickening markedly decreased the part surface quality, and the index value of the thickened part was nearly as poor as the

2.5% LPA panel. This is in agreement with the thickened dilatometry work described in Chapter 4. The thickened samples should show a reduced surface quality because of polymerization shrinkage for that material should be higher than a part without thickener. Increasing the molding temperature also produced a part of less quality, but not as poor as the thickened sample. An explanation for this behavior is postponed until the morphology data for the panels are presented.

5.3 Molding Shrinkage

Molding shrinkage is a comparison between the cold part dimensions and the cold mold dimensions around the part perimeter. If the part dimensions are small compared to the mold, a shrinkage (negative number) is reported, and if the part is dimensionally larger, an expansion is reported (positive number). Molding shrinkage is often used to describe the LPA effect in molding assuming that the better the LPA performance, the less molding shrinkage one should measure. However, when considering molding shrinkage data, the coefficients of thermal expansion of both the part and the mold play a very important role in molding shrinkage, and, therefore, fiber content and orientation is an important variable to consider. Fiber is normally randomly oriented in the plane in which molding shrinkage is measured and has a very low thermal coefficient of thermal expansion. Fiber orientation will change the overall composite coefficient of thermal expansion in that plane. Care must be taken to compare molding shrinkage of panels with the same fiber content and orientation. Also, if the fiber content is kept low (as was the case in this study), the resin effects are dominant and will be more prominent in the data.

Dimensions for molding shrinkage are unit length over unit length, such as inch/inch, cm/cm or mil/inch (meaning inch shrinkage or difference per inch part dimensions). A description of the molding shrinkage technique and calculation was provided in Chapter 1. Table 10 provides a summary of the molding shrinkage measured for both series of molded panels. From Table 10, the molding shrinkages from the two molding series were in good agreement with each other.

Table 10. Molding shrinkage data, based on perimeter measurements.

Panel Description	Molding shrinkage 45.7 cm mold (cm/cm)	Molding shrinkage 30.5 cm mold (cm/cm)
No LPA	-1.526×10^{-3}	-2.872×10^{-3}
2.5% LPA	-1.596×10^{-3}	-1.665×10^{-3}
6% LPA	-0.791×10^{-3}	-0.811×10^{-3}
10% LPA	-0.055×10^{-3}	-0.042×10^{-3}
15% LPA	$+0.097 \times 10^{-3}$	$+0.146 \times 10^{-3}$
20% LPA	$+0.215 \times 10^{-3*}$	---
25% LPA	$+0.200 \times 10^{-3*}$	---
15% LPA, thickened	-0.721×10^{-3}	$-0.499 \times 10^{-3**}$
15% LPA, 150°C	-0.249×10^{-3}	0.000×10^{-3}

* Based on an average from two panels

** Molded at 2.07 MPa (300 psi)

As was the case with surface quality, the best molding shrinkage value was observed to be at an LPA concentration of 20%. Figure 85 is a plot comparing the D-sight index and molding shrinkage (times -1) measured for these panels as a function of LPA content. Molding shrinkage and D-sight index correlated nicely, as shown in Figure 85, implying that molding shrinkage and surface quality were related. Comparing this plot to Figure 66, the trend seems to agree with the polymerization shrinkage measurement trends reported in Chapter 4. From Table 10, the molding shrinkage was much higher for the thickened and high cure temperature panels, again, agreeing nicely with the surface quality data measured.

5.4 Morphology of Molded Panels

From Chapter 4, it was determined that shrinkage control was the product of a two stage process, first, micro-structure formation, and then fissure formation. The sample morphology was determined to be important because it provided a weak phase for fissures to form and propagate, and optimum morphology was found to have the largest particle size for each particular series. Therefore, SEM micro-graphs were prepared for all the 45.7 cm panels for comparison. All samples were obtained from the center of the molded part, etched with dichloromethane for 20 minutes and coated with 60% palladium/40% gold. Figure 86 summarizes all of the molded panel SEM micro-graphs.

Figure 85. Comparison of D-sight index and molding shrinkage as a function of LPA concentration.

(a)

(b)

Figure 86. SEM micro-graphs of panel morphologies, (a) no LPA, (b) 2.5% LPA, (c) 6% LPA, (d) 10% LPA, (e) 15% LPA, (f) 20% LPA, (g) 25% LPA, (h) 15% LPA thickened and (i) 15% LPA cured at 150°C.

Figure 86. Continued.

(c)

(d)

Figure 86. Continued.

(e)

(f)

Figure 86. Continued.

(g)

(h)

Figure 86. Continued.

(i)

From Figure 86(a) and Figure 86(b), the particulate morphology was not observed for the no LPA and 2.5% LPA panels. From the 6% LPA to the 15% LPA panel morphologies shown in Figure 86(c) to Figure 86(e), particulate formations were observed. With increasing LPA content, they increased in regularity of shape and clarity and decreased in particle size. At 20% LPA and 25% LPA content, panel morphologies, as shown in Figure 86(f) and Figure 86(g), were much smaller and more irregularly shaped. Packing for the 15% LPA and 20% LPA samples seemed to be the loosest providing the most interface between the particles formed and the weak LPA phase. The 25% LPA morphology was not as clear or loosely packed and the 6% LPA, and 10% LPA samples showed regions of particle aggregates where no weak phase developed. From the dilatometry results in Chapter 4, one might think that 15% LPA would provide the best shrinkage control based solely on the morphology, because the large clear particles formed. However, the 20% LPA sample provided the best molding shrinkage control and surface quality.

The morphological correlation found in Chapter 4 was correct only for those reaction conditions. In a fast process such as compression molding, the internal polymerization stresses would develop much more quickly and would reach a higher level than those reached in the dilatometer at the cure conditions investigated. Therefore, the particle surface area exposed to the weak LPA phase may be more important to the amount of fissure formation than the actual particle size and shape. In other words, the stress was high enough to form the fissures no matter what the morphology; therefore, the more weak phase distributed through the sample morphology, the more shrinkage control. Since a loosely packed, small morphology would best fit the description, the 20% LPA sample provided the best shrinkage control shown by having the best surface quality and lowest molding shrinkage.

Figure 86(h) is the thickened sample morphology. The thickened sample morphology looks similar to that of the thickened sample morphologies reported in Chapter 4; a clear particulate formation was not developed. Thickening changed the thermodynamics of the phase separation and prevented the particle formation from occurring. This, in turn, would not permit the formation and propagation of fissures, and, therefore, shrinkage control was lost. Similarly, Figure 86(i) is the morphology of the panel cured at 150°C. During the fast cure, morphology did not have time to develop as shown by the lack of clearly defined particles. Therefore, fissure formation was restricted.

5.5 Surface Area of Molded Panels

The surface areas of the no LPA, 10% LPA, 20% LPA and 25% LPA panels were measured using the BET technique as described in Chapter 4. Samples were prepared from material removed from the center of the molded panels and were broken and ground with a mortar and pestle. An effort was made to assure that the particle size distribution of the ground panel was about the same for each sample. The no LPA sample was included as a reference because the inclusion of filler and fiber had an effect on the surface area of a sample without low profile activity, and the data discussed in Chapter 4 was for a material without filler and fiber. The other samples were chosen to provide an idea of the trend of surface area as a function of LPA content and how that trend was related to the surface quality measured. Figure 87 is a plot comparing surface quality and surface area measured as a function of LPA content, and Table 11 summarizes the surface area data as a function of LPA content.

Figure 87. Comparison of D-sight index and BET surface area as a function of LPA concentration.

Table 11. Surface area data of molded parts.

Panel LPA Content	Surface Area (m ² /gram)
No LPA	0.398
10% LPA	0.532
20% LPA	0.727
25% LPA	0.558

From Figure 87, panel surface area correlated nicely with surface quality. As shown in Chapter 4, as fissures form, surface area should increase. A sample that would not form fissures, that is, a sample without LPA, should have a lower surface area, and a material with fissures should have more surface area. However, the magnitude of the surface area should not be directly correlated to level of shrinkage control because the pore size distribution of the material would also be an important factor in the magnitude of surface area. A sample could have several very small fissures (pores) throughout the sample (because of a smaller particulate morphology) which could provide a large surface area but little shrinkage control because the volume compensated by the fissures would be small. Likewise, a sample could have fewer fissures but be very large in effective diameter (due to a larger particulate morphology) thus providing better shrinkage control and less surface area. Nonetheless, the surface area data measured for this study did correlate nicely with the panel surface quality implying that a correlation between surface area, fissure formation, and shrinkage

control does exist, and that the pore size distribution (fissure size) of the panel materials were at least similar.

Summarizing the molding observations, the surface quality, dimensional control, morphology, and surface area seemed to agree with each other and with the explanation of LPA mechanism provided in Chapter 4. The sample morphologies followed a similar trend as a function of LPA content, but the optimum morphology rule was found not to be absolute when compared to the molding shrinkage and surface quality. Surface area correlated nicely with molded panel surface quality implying that LPA mechanism, fissure formation, and surface quality are all related. The thickened sample provided the same morphology and shrinkage control reported in Chapter 4, and the fast cure material demonstrated some of the problems with trying to enhance molding output by increasing reaction rate.

Chapter VI

Conclusions and Recommendations

In Chapter 1 of this work, some of the key material aspects of low shrink unsaturated polyester compounding were covered including a brief overview of the currently accepted low profile additive mechanism. From the discussion of low profile additive mechanism, it was apparent that the mechanism is still not well understood, and that most optimization of material formulation occurred by trial and error molding. The problem with trial and error molding is that it is costly in terms of equipment, time (labor) and material and is somewhat wasteful. Furthermore, molding does not add to the understanding of low profile additive shrinkage control mechanism. Other methods to study the low profile additive mechanism in the literature (including SEM, T_g studies, dipole moment, etc.) all provided insight into the mechanism; however, none could be used to study the polymerization shrinkage and overall performance directly. This discussion of LPA mechanism studies led to the flow diagram for this study in Figure 22.

To better design or optimize compound formulation and to study the low profile additive mechanism, first a method of measuring the polymerization shrinkage during cure was required as shown in Figure 22. To that end, a literature review of dilatometry was conducted in Chapter 2, and a dilatometer was designed and built as described in Chapter 3. Included in Chapter 3 were the dilatometer calibration runs for

both isothermal and ramping mode which proved the equipment accuracy and demonstrated the methodology used in operation. A discussion of the design limitations and design history was also provided.

With this dilatometer, several experiments with low profile unsaturated polyester resin were performed, and an understanding of the low profile additive mechanism was developed as described in Chapter 4 and outlined in Figure 53. Three different series of experiments were performed varying the heating conditions: one at isothermal conditions (80°C), one at approximately 8°C/minute ramp, and one at approximately a 16°C/minute ramp. For each series, the low profile additive concentration was varied. In addition, SEM micro-graphs of the dilatometer sample morphologies were prepared to compare directly shrinkage control and sample morphology trends. The findings of this study are summarized below:

- Increasing heating rate improved the ability to control polymerization shrinkage regardless of the low profile additive concentration. This effect was more dramatic for the 6% LPA to 15% LPA range but was observed in the 2.5% LPA concentration as well.
- The optimum low profile additive concentration as defined by a minimum percent final shrinkage, shifted to higher low profile additive concentrations, and the minimum trend broadened with increasing heating rate.
- When comparing the percent volume change as a function of time data for the three series, several features tended to correlate to good shrinkage performance. Isothermally, a plateau region was found to indicate low profile activity. Plateau length and expansion during the plateau region correlated to better shrinkage

performance. In temperature ramping studies, the existence of a secondary peak correlated with optimum shrinkage control; however, the secondary peak was not required for the existence of low profile activity.

- Optimum shrinkage control correlated with a more loosely packed particulate network. Optimal isothermal morphology showed very irregularly shaped particles whereas optimal shrinkage control in the ramping mode showed slightly less irregularity in the particle shape. Particle size correlating to optimum shrinkage control decreased with increasing heating (or reaction) rate; however, within a series, larger particle size correlated to better shrinkage control. Furthermore, it was found that a clear particulate structure was not required for shrinkage control to occur as was the case with the 2.5% LPA sample in the ramping studies and in Figure 69, and particle formation does not necessarily indicate the existence of shrinkage control as shown by the 10% LPA and 15% LPA samples which were cured isothermally.
- Shrinkage control and an opaque sample correlated nicely, and a translucent or cloudy sample provided poor shrinkage control.
- Morphology was not observed to change much once gelation occurred, and gelation occurred early in the reaction. However, the sample opacity was found to correlate with shrinkage control as indicated by the plateau region.
- Cure and shrinkage were observed to correlate linearly outside the plateau region. Inside the plateau region, cure continued but shrinkage was not observed macroscopically.

In addition to developing an understanding of the basic shrinkage trends as a function of heating rate and LPA concentration, several key polymerization shrinkage related issues were confirmed, including the effect of pressure, filler, and thickening. Pressure was found to have a negative effect on shrinkage control, but it was not found to change morphology much. Filler was not found to drastically change shrinkage control in ramp cure conditions but had a slightly negative effect on shrinkage control in isothermal mode. Thickening was found to greatly affect shrinkage control and morphology. As was mentioned in Chapter 1, the low profile additive and unsaturated polyester resin participated in the thickening reaction forming complex ionic bonds and orientations [7] which changed the phase separation thermodynamics, and, therefore, the particle formation. Consequently, the thickened sample morphology was observed to be of a reduced particulate nature; particles were observed, but they were markedly smaller and in aggregates. Shrinkage control was not observed for thickened samples cured isothermally and was greatly reduced for ramp cured samples.

Based on the dilatometric, morphological and opacity observations presented in Chapter 4, a two step LPA mechanism was presented and tested. It was proposed that the LPA first caused the particulate structure to form and then internal stresses, which develop because of polymerization shrinkage, caused the formation and propagation of fissures within the weaker LPA phase. The morphology provided the weak phase, and the optimum morphology provided the best weak phase geometry for the fissures to form and grow. Fissure formation was also used to explain why the samples became opaque which correlated to shrinkage control. To test for fissures, the surface areas of samples which did and did not demonstrate shrinkage control were measured using the BET technique. Samples which exhibited shrinkage control were found to have a

markedly larger surface area than samples that did not demonstrate shrinkage control which confirmed that the development of fissures provided the shrinkage control.

With an understanding of the LPA mechanism and the key variables related to it, several BMC compression molding experiments were performed to investigate the relationship between molding shrinkage, surface quality, morphology, and surface area. The molding experiments seemed to be in agreement with the proposed LPA mechanism and confirmed the trends found with dilatometry.

Based on the work presented in Chapters 3, 4 and 5, the key goals as outlined in Figure 22 were covered. With the understanding of the LPA mechanism developed in this study, material design could be conducted with a more informed and clear methodology. However, the work presented in this study is not exhaustive by any means; the window of study was just opened. The effects of thickening, filler and pressure require further investigation. There are several reactive systems which need to be better understood, including the various types of LPAs, unsaturated polyester resins and even some other reactive systems such as low profile vinyl ester resins which have not been as technologically developed as the unsaturated polyester resins. Furthermore, some of the variables which were not thought to be significant when designing this study were found to be important during this study and should be further studied, such as the effect of inhibitor. From Figure 69, inhibitor was found to strongly effect the morphological development which, in turn, affected the shrinkage control markedly.

The application of surface area measurement was developed in this study to prove a proposed theory. As this methodology has never been applied to the study of low profile unsaturated polyester resins, further work in this area should be performed

to better understand the relationships of surface area, pore size distribution, and shrinkage control as a possible method of better characterizing shrinkage control. Pore size distribution can be measured using either the BET technique (adsorption/desorption isotherms) or by the mercury penetration technique [135] for larger pore structures. Combined with a knowledge of the shrinkage control, surface area and particle size distribution, a better understanding of the fissure formation and growth may be developed. This may be very important to the prediction and modeling of polymerization shrinkage for these materials.

Finally, more molding work should be performed at different reaction conditions to better understand the role of shrinkage control and molding conditions. For example, RTM molding could be performed for various LPA concentrations at both reduced temperatures and at normal operating temperatures (both of which could be modeled with the dilatometer) to help develop a better understanding of the relationship between molding and dilatometry. The goal of this work and any future work that stems from it should be to provide a more sophisticated method of understanding the role and mechanism of shrinkage control in molding and to develop a better method of determining optimum compound formulation to industry by both methodology and understanding of the key principles of shrinkage control.

References

- [1] Handbook of Composites, Van Nostrand Reinhold : New York, 1982
- [2] Encyclopedia of Polymer Science and Engineering, John Wiley and Sons : New York, 1988.
- [3] Whelan, A. and Craft, J. (Eds.), Developments in Plastics Technology, Vol. 3, 1986.
- [4] Mallick, P. and Newman, S. (Eds.), Composite Materials Technology Processes and Properties, Hanser Publishers : New York, 1990.
- [5] Penn, W., GRP Technology, MacLaren and Sons : London, 1966.
- [6] Kamal, M., and Ryan, M., Advances in Polymer Technology, Vol. 4, No. 3/4, 1984.
- [7] Melby, E.G. and Castro, J. M., "Glass-reinforced Thermosetting Polyester Molding: Materials and Processing", Ch. 3, Comprehensive Polymer Science, Vol. 7, Pergamon Press : Oxford, U.K., 1989.
- [8] Kubel, E., Advanced Material and Processes, April, pp. 17 - 31, 1989.
- [9] Burns, R., Polyester Molding Compound, Marcel Dekkar, Inc : New York, 1982.
- [10] Atkins, K., "Low Profile Additives: Shrinkage Control Mechanisms and Applications", Sheet Molding Compound Materials: Science and Technology, H., Kia ed., Hanser Publishers (book to be published in 1993).
- [11] Wood, S., Modern Plastics, pp. 50 - 57, Oct. 1990.
- [12] Newman, S. and Fesko, D., Polymer Composites, Vol. 5, No. 1, pp. 88 - 96, 1984.
- [13] Landsettle, G., and Jensen, J., Modern Plastics, pp. 80 - 84, May 1986.
- [14] Wood, S., Modern Plastics, pp. 46 -54, October 1988.
- [15] Wigotsky, V., Plastics Engineering, pp. 19 - 24, Sept. 1990.

- [16] Kia, H., Polym.-Plast. Technol. Eng., Vol. 28, No. 4, pp. 43 - 53, 1989.
- [17] Kia, H., Journal of Composite Materials, Vol. 22, pp. 794 - 811, Sept. 1988.
- [18] Bartkus, E. and Kroekel, C., Applied Polymer Symposium, No. 15, pp. 113 - 135, 1970.
- [19] Mohan, R. and Grentzer, T., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 1-B, 1993.
- [20] Osswald, T., Matyssek, J. and Specker, O., Proceedings: SPI Composite Institute's 45th Annual Conference, Session 11-A, 1990.
- [21] Lo, C., Lamb, D., Gibson, A., and Quinn, J., Composite Polymer, Vol. 3, No. 4, pp. 290-305, 1990.
- [22] Tsia, S., Composite Design, 4th edition, Think Composites: Dayton, Ohio, 1988.
- [23] Kia, H., Proceedings: SPI Composite Institute's 45th Annual Conference, Session 1-B, 1990.
- [24] Personal communication, GenCorp representative.
- [25] Personal communication, Navistar representative.
- [26] Kim, Junil, Computer Modeling and Analysis of Anisotropic Material Flow in Compression Molding of Short-Fiber-Reinforced Composite Material, Ph.D. Dissertation, The Ohio State University, 1990.
- [27] Dziatwatkoski, Nick, Optimization of Surface Quality of SMC Compression Molded Parts by Automation of Two Stage Pressure Molding, Master's Thesis, The Ohio State University, 1992.
- [28] Personal communication, Union Carbide representative.
- [29] Akiyama, K., Shibata, T., Yuuzou, H., and Kenichi, N., Proceedings: SPI Composite Institute's 46th Annual Conference, Session 5-C, 1991.
- [30] Jensen, J., Proceedings: SPI Composite Institute's 45th Annual Conference, Composites Forum, Session 2-A, 1990.
- [31] "Processing Unsaturated Polyesters Based on Amoco Isophthalic Acid", Amoco Chemical Co., Bulletin IP 43b.
- [32] Kircher, K., Chemical Reactions in Plastics Processing, Hanser Publishing Co. : New York, 1987.
- [33] Colley, B., Chang, K., and Tufts, T., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 18-D, 1993.

- [34] Chang, K., and Tufts, T., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 18-E, 1993.
- [35] Atkins, K., Gandy, R., and Gentry, R., European Patent, Application # 82108379, 1982.
- [36] Atkins, K., United States Patent No. 4673706, 1987.
- [37] Atkins, K., United States Patent No. 4374215, 1983.
- [38] Comstock, L. and Smith, P., United States Patent No. 4284736, 1981.
- [39] Atkins, K., United States Patent No. 4555534, 1985.
- [40] Callais, P., Kamath, V., Stromberg, S., Sanchez, J., and Gravelle, J., Plastics Compounding, Vol. 15, No. 1, pp. 49 - 52, 1992.
- [41] Pryor, W., Free Radicals, McGraw Hill : New York, 1966.
- [42] Personal Communication, Witco representative.
- [43] Han, C. and Lem, K., Journal of Applied Polymer Science, Vol. 28, pp. 743-762, 1983.
- [44] Lem, K. and Han, C., Journal of Applied Polymer Science, Vol. 28, pp. 779-793, 1983.
- [45] Lee, D. and Han, C. Polymer Engineering and Science, Vol. 27, No. 13, pp. 964 - 975, 1987.
- [46] Atkins, K., United States Patent No.4491642, 1985.
- [47] Suspene, L., Fourquier, D. and Yang, Y., Polymer, Vol. 32, No. 9, pp. 1593-1604, 1991.
- [48] Atkins, K., Koleske, J., Smith, P., Walter, E. and Matthews, V., Proceedings: SPI Composite Institute's 31th Annual Conference, Session 2-E, 1976.
- [49] Kroekel, C., SAE Automotive Engineering Congress, 1968.
- [50] Pattison, V., Hindersinn, R. and Schwartz, W., Journal of Applied Polymer Science, Vol. 18, pp. 2763-2771, 1974.
- [51] Atkins, K., Gandy, R. and Gentry R., Journal of Elastomers and Plastics, Vol. 14, pp. 117-135, April 1982.
- [52] Bucknall, C., Davies, P. and Partridge, I., Polymer, Vol. 26, pp. 109 - 112, Jan. 1985.

- [53] Yasuda, M., Kawakami, H., Sasaki, S. and Shibata, N., Proceedings: SPI Composite Institute's 47th Annual Conference, Session 1-D, 1992.
- [54] Pattison, V., Hindersinn, R. and Schwartz, W., Journal of Applied Polymer Science, Vol. 19, pp. 3045 - 3051, 1975.
- [55] Taylor, E., Polym. - Plast. Technol. Eng., Vol. 22, No. 1, pp. 1 - 13, 1984.
- [56] Hsu, C. and Lee, J., three part series in publication, submitted to Polymer, 1992.
- [57] Hsu, C. P., An Integrated Analysis of Styrene/Unsaturated Polyester Free Radical Cross-Linking Polymerizations, Ph.D. Dissertation, The Ohio State University, 1992.
- [58] Kiaee, L., Yang, Y. and Lee, J., AIChE Symposium Series, No. 260, Vol. 84, pp. 52 - 73, 1988.
- [59] Vaccarella, P., Williams, P. and Tsia, J., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 3-C, 1993.
- [60] Atkins, K. and Rex, G., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 6-D, 1993.
- [61] Chan-Park, M. and McGarry, F., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 10-B, 1993.
- [62] Harada, K., Yasuhisa, O., Iwama, E. and Nomaguchi, K., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 17-A, 1993.
- [63] Dettre, M., Esswein, G. and Fukuda, Y., Proceedings: SPI Composite Institute's 48th Annual Conference, Session 17-D, 1993.
- [64] Mitani, T., Shiraishi, H., Honda, K. and Owens, G., Proceedings: SPI Composite Institute's 44th Annual Conference, Session 3-C, 1989.
- [65] Aktins, K., Gandy, R., Reid, C., Seats, R., and Rex, G., Proceedings: SPI Composite Institute's 43th Annual Conference, Session 17-D, 1988.
- [66] Ross, L., Hardebeck, S., and Bachmann, M., Proceedings: SPI Composite Institute's 43th Annual Conference, Session 17-C, 1988.
- [67] Wilson, E. and Isham, A., Proceedings: SPI Composite Institute's 45th Annual Conference, Session 1-A, 1990.
- [68] Pastorius, W., Proceedings: SPI Composite Institute's 45th Annual Conference, Session 16-A, 1990.
- [69] Cheever, D., Journal of Coatings Technology, Vol. 50, No. 645, pp. 36 - 49, October 1978.

- [70] Rodriguez, E., Journal of Applied Polymer Science, Vol. 40, pp. 1847-1855, 1990.
- [71] Han, C. and Lem, K., Journal of Applied Polymer Science, Vol. 28, pp. 763-778, 1983.
- [72] Sawallisch, K., Polym.-Plast Technol. Eng., Vol. 23, No. 1, pp. 1 - 36, 1984.
- [73] Languna, O. and Collar, E., J. Polym. Mater., Vol. 3, No. 4, pp. 217 - 224, 1986.
- [74] Bush, S., Methven, J. and Blackburn, D., "Networks as the Basis of Pro-Thickening SMC", Biological and Synthetic Polymer Networks, S. O'Kremer editor, Elsevier Applied Science Publishers : New York, 1988.
- [75] Grentzer, T., Gill, R., Sichina, W. and Sauerbrunn, S., Proceedings of the 4th Japan-US Conference on Composites, pp. 458-466, 1988.
- [76] Krolkowski, W. and Nowaczek, W., Polymer Process Engineering, Vol. 4, No. 2-4, pp. 295-302, 1986.
- [77] Iseler, K., Guha, P., and Yen, R., United States Patent No. 4535110, 1985.
- [78] Graham, W., Jutte, R., and Shipp, D., "Recyclability of Glass Fiber Reinforcements in Thermoset and Thermoplastic Applications", Technical Paper, Owens-Corning Fiberglas Corp., 1993.
- [79] "Recycling of SMC -- The Energy/Environment Picture", SMC Automotive Alliance Report No. AF-184, 1992.
- [80] Ramsteiner, F. and Theysohn, R., Composites, Vol. 15, No. 2, pp. 121-128, 1984.
- [81] Nicolais, L. and Mashelkar, R., Journal of Applied Polymer Science, Vol. 20, pp. 561 - 563, 1976.
- [82] Nielsen, L., Mechanical Properties of Polymers and Composites, Vol. 1 and 2, Marcel Dekkar, Inc: New York, 1974.
- [83] Carslaw, H. and Jaeger, J., Conduction of Heat in Solids, 2nd ed., Oxford Press: Oxford, 1959.
- [84] Vinson, J. and Sierakowski, R., The Behavior of Structures Composed of Composite Materials, Martinus Nijhoff Publishers : Boston, 1987.
- [85] Steg, L., Rosen, B. and Sutton, W., Israel Journal of Technology, Vol. 5, No. 1-2, pp. 71-98, 1971.
- [86] Bert, C. and Kline, R., Polymer Composites, Vol. 6, No. 3, pp. 133-141, 1985.
- [87] Cohen, L., Israel Journal of Technology, Vol. 5, No. 4, pp. 267-273, 1967.

- [88] "Quality Improvement of UP-Resin Laminates with BYK-Chemie Additives" BYK-Chemie USA.
- [89] "Air Release Agents For Thermosetting Plastics Such As Unsaturated Polyester and Epoxy", BYK-Chemie USA.
- [90] "Additive for Reducing Styrene Monomer Emission in Unsaturated Polyester and Vinyl Ester Resins", BYK-Chemie USA.
- [91] Kallaur, M., Proceedings: SPI Composite Institute's 45th Annual Conference, Session 4-F, 1990.
- [92] Collins, E. A., Billmeyer, W., Experiments in Polymer Science, Wiley Publishing Co : New York, 1973.
- [93] "Dilatometry", Encyclopedia of Polymer Science and Technology, Vol. 5, pp. 83 - 90, 1972.
- [94] Bekkedahl, N., Journal of Research of the National Bureau of Standards, Vol. 13, pp. 411-431, 1934.
- [95] Clash, R. and Rynkiewicz, L., Industrial and Engineering Chemistry, Vol. 36, No. 3, pp. 279 - 282, 1944.
- [96] Starkweather, H. and Taylor, G., Journal of American Chem. Soc., Vol. 52, pp. 4708 - 4714, 1930.
- [97] Braun, D. and Disselhoff, G., Polymer, Vol. 18, pp. 963-66, 1977.
- [98] Hunter, G., Proceedings: SPI Composite Institute's 43th Annual Conference, Section. 6-C, 1988.
- [99] Rees, J. and Jacobsen, P., Dental Materials, Vol. 5, pp. 41-44, 1989.
- [100] Bell, C., J. Scientific Instruments, Vol. 38, pp. 27-28, 1961.
- [101] Burnett, G. M., Trans Farad Soc, Vol. 46, pp. 772, 1950.
- [102] Naumann, M., Underhill, R. and Duran, R., Makromol. Chem., Rapid Commun., Vol. 13, pp. 243 - 253, 1992.
- [103] Kiaee, L., "Low Profile Additives on the Morphology and Kinetics of Unsaturated Polyester Resins", Master's Thesis, Ohio State University, 1987.
- [104] Bernatchez, P. and Goutier, D., Rev. Sci Instrum, Vol. 44, No. 12, pp. 1790-1791, 1973.
- [105] Niezette, J. and Desreux, V., Journal of Applied Polymer Science, Vol. 15, pp. 1981 - 1983, 1971.

- [106] Rubens, L. and Skochdopole, R., Journal of Applied Polymer Science, Vol. 9, pp. 1487 - 1497, 1965.
- [107] Cundall, R., Dandiker, Y., Davies, A., and Salim, M., Polymers, Paint and Colour Journal, Vol. 177, No. 4188, pp. 215 - 218, 1987.
- [108] Tung, L., Journal of Polymer Science, A-2 , Vol. 5, pp. 391 - 392, 1967.
- [109] Voeks, J. and Crane, R., Analytical Chemistry, Vol. 31, No. 11, pp. 1906 - 1908, 1959.
- [110] Hojfors, R. and Flodin, P., Journal of Applied Polymer Science, Vol. 16, pp. 1859 - 1860, 1972.
- [111] Sudol, E., El-Aasser, M., Micale, F. and Wanderhoff, J., Review of Scientific Instruments, Vol. 57, No. 9, pp. 2332-2338, 1986.
- [112] Curliss, D. and Russell, J., 37th International SAMPE Symposium, pp. 620 - 632, 1992.
- [113] Bridgman, P., The Physics of High Pressure, Bell : London, 1949.
- [114] Barlow, J., Polymer Engineering and Science, Vol. 18, No. 3, pp 238 - 245, 1978.
- [115] "Dilatometry", Encyclopedia of Polymer Science and Engineering, Vol. 5, pp. 69 - 78, 1986.
- [116] Taki, S., Takemura, T. and Matsushige, K., Japanese Journal of Applied Physics, Vol. 30, No. 4, pp. 888 - 889, 1991.
- [117] Oels, H. and Rehage, G., Macromolecules, Vol. 10, No. 5, pp. 1036 - 1043, 1977.
- [118] Quarch, A. and Simha, R., Journal of Applied Physics, Vol. 42, No. 12, pp. 4592-4606, 1971.
- [119] Walsh, D. and Zoller, P., Makromol Chem, Vol. 188, pp. 2193 - 2201, 1987.
- [120] He, J., and Zoller, P., Review of Scientific Instruments, Vol. 62, No. 5, pp. 1304 - 1308, 1991.
- [121] He, J., Fakhreddine, Y. and Zoller, P., Journal of Applied Polymer Science, Vol. 45, pp. 745 - 747, 1992.
- [122] Gnomix Research, 3809 Birchwood Drive, Boulder CO, 80304.
- [123] Dupont Thermal Analysis Manual, Dupont Chemical Co.
- [124] Miller, G., Materials Research and Standards, Vol. 12, No. 10, pp. 8 - 21, 1972.

- [125] Miller, G., Journal of Applied Polymer Science, Vol. 15, pp. 2335 - 2248, 1971.
- [126] Toyoseiki sales brochure, No. 633.
- [127] Hsiao, M., Shaw, M. and Samulski, E., Review of Scientific Instruments, Vol. 58, No. 6, pp. 1009-1013, 1987.
- [128] Kinkelaar, M., Dilatometry of Low Shrink Unsaturated Polyester Resins and It's Relation to Reaction, Rheological Change and Microstructure, Master's Thesis, The Ohio State University, 1990.
- [129] Kinkelaar, M. and Lee, L. J., Journal of Applied Polymer Science, Vol. 45, pp. 37 - 50, 1992.
- [130] Muzumdar, S., Rheological and Kinetic Changes of Unsaturated Polyester Resins: Mechanistic and Statistical Analysis, Master's Thesis, The Ohio State University, 1990.
- [131] Personal communication, Cook Composites representative.
- [132] Fan, J. D., Ph.D. Dissertation, The Ohio State University, 1988.
- [133] Brunauer, S., Emmett, P., and Teller, E., J. Am Chem Soc. Vol. 60, pp. 309, 1938.
- [134] Satterfield, C., Heterogeneous Catalysis - In Practice, McGraw Hill:New York, 1990.
- [135] Adkins, B., Heink, J. and Davis, B., Adsorption Science and Technology, Vol. 4, No. 1 and 2, pp. 87-104, 1987.

Appendix A

Dilatometer Operating Procedure

The purpose of this appendix is to cover a step-by-step procedure for assembling and operating the dilatometer developed in this study. The discussion here is intended for individuals who either wish to use the equipment developed in this study or wish to design, build, and operate their own system. This section assumes that the reader is familiar with the equipment as described in Chapter 3 of this document. First, preparation and filling of the sample pouch will be considered. Secondly, dilatometry assembly will be discussed followed by an overview of the actual operation and data analysis. By far, sample pouch preparation and dilatometer assembly are the most challenging and critical steps.

Before the day of the experiment, several tasks should be taken care of. First, the silicon oil used as the encapsulating fluid should be outgassed. To do this, place the oil in a large (4000 ml) vacuum safe flask. Using a magnetic stirring system assure that the oil is stirred continuously. Apply a vacuum over the oil until no bubbles are formed (generally overnight). Unless there is a good reason (such as fast cure at room temperature), the sample should also be formulated the day before the experiment; however, the pouch can be made the day of the experiment as well. This allows some of the oxygen and small air bubbles blended into the sample during formulation to rise.

Sample Pouch Preparation:

- Place a double layer of the plastic film used to make the pouch on a table and draw a circle about 10 cm in diameter on it.
- Using the heat sealer (warmed up at the 4 mil setting), seal along the edges of the circle leaving two gaps (one for the thermocouple the other to fill the pouch) approximately 1 cm in length. Cut the sealed circle out.
- Make a thermocouple using extra fine thermocouple wire leaving the leads bare and approximately 7 cm in length. The wire should be 30 gauge or less; thinner is better. Place the tip of the thermocouple inside the sample pouch (through one of the two remaining gaps in the seal) somewhere near the center. Assuring that the wire leads are not crossed anywhere, heat seal the thermocouple into place. Weigh the empty pouch.
- Through the last gap in the pouch seal, thread a smooth glass rod into the pouch and go along the edges. The purpose here is to test the seal strength and to open the pouch. This will help to prevent trapped air in the sample during filling.
- The final step is to pour (or transfer by pipette if viscosity is low enough) the sample into the pouch via the last gap in the pouch seal. Care must be taken to avoid air bubbles. Perhaps the easiest way to do this is to place more sample in the pouch than you need. In that way, the extra sample and air bubbles can be removed

together. Once the desired sample size is bubble free in the pouch, squeeze all the extra material from the last breach in the sample pouch and seal it. Weigh the pouch. The difference between empty and full pouch weight is the sample weight.

Dilatometer Assembly:

- Connect the sample thermocouple to the thermocouple leads which run through the upper disc of the dilatometer. A good mechanical connection is required so twist the sample pouch wire around the leads and fasten them with the inner spring of a wire nut. Test the connection by measuring temperature. Assure that the wires are connected correctly by squeezing the thermocouple between your fingers. If the temperature increases, the appropriate connection was made.
- Assure that the sealing edge of the upper disk is clean. Place the lower disc on a stand. Assure that the O-ring groove is clean, and that the lower valve is closed. Fill the lower half of the sample chamber with the degassed silicon oil and put the O-ring in place. Place one of the screens in the lower half of the sample chamber on the lower disc, and place the other one behind the sample connected to the upper disc (wedge it behind the thermocouple leads). Carefully place the upper disc and sample on to the lower disc assuring the correct alignment of the sample (in the center and clear of the sealing edge) and the discs (for proper bolt alignment). Thread in all eight bolts preferably in a star pattern and tighten.

- The next step is to fill the dilatometer. This is done using a bellows pump system. Place the draw tube of the pump into the degassed silicon oil and turn on the pump to fill the pump and the draw and exhaust tubes. Continue the flow until the tubes and pump are filled. Turn off the pump and connect the pump output line to the valve on the lower half of the dilatometer and connect a return line from the top dilatometer valve to the degassed silicon oil flask (completing the loop). Open both of the valves and turn on the pump. The oil will circulate through the dilatometer and out the top, removing air bubbles in the process. To aid in air removal, rock the dilatometer and work the cylinder. Once no more air bubbles are observed flowing out of the dilatometer, fill the upper half of the hydraulic cylinder by pulling the rod all the way up and simultaneously injecting (with a needle-free syringe) the oil into the flexible steel tube and pushing the rod down. This procedure may need to be repeated several times to assure a bubble free system. Position the rod such that it is approximately 2 cm from the bottom most position and turn off the bellows pump. Close both valves and press on the cylinder rod. If the rod deflects under pressure, more air is trapped in the lower half of the dilatometer and oil flow should be resumed until all the air is removed. If no deflection is detected, the dilatometer is air-free and ready.

Experimental Procedure:

- Mount the dilatometer cell into the stand. Attach the pressure system and LVDT. Pressurize the system to the desired operating pressure by increasing nitrogen

pressure on the cylinder regulator until the desired pressure is obtained. Once the desired pressure is obtained, the valve between the regulator and the pressure system the valve on the cylinder head is closed. This provides the most steady pressure level during the dilatometer operation. Place the dilatometer into the cooling bath, place a mixer into the cooling bath and turn it on. Place a thermocouple into the temperature bath and connect it to a two channel hand-held temperature reader. Connect the sample thermocouple to the second channel of the temperature reader and monitor sample and bath temperature.

- Monitor sample temperature, cooling bath temperature and position data until a steady state condition is reached (on the order of 30 to 60 minutes). At steady-state, connect the sample thermocouple to the data acquisition system and record the initial temperature and position data both by computer and into a notebook for later use.
- Remove the cooling system, clean the oil from the outside of the dilatometer, and install the heating system and insulation. Depending on the desired temperature profile, connect either the controllers or the Variac. At the same time, turn on the data acquisition system and the heating system.
- Take data throughout the experiment. When either cure is complete (isothermal mode) or the maximum temperature is reached (ramp mode), turn off the power to the heaters. In ramping mode or high temperature isothermal cures (over 80°C), air cooling to about 80°C is required before the cooling bath can be used. Otherwise, apply the cooling bath immediately. This is done to avoid warpage to the discs and possible leakage due to quench cooling.

- Using a copper coil and water flow in the cooling bath, lower the temperature to the initial temperature and hold it constant until the sample temperature and position data stabilize. This is the final position data for the cure and the initial data for the baseline.
- Repeat the heating cycle to get the baseline. Note that the heating time for a baseline in isothermal mode does not have to be as long as the cure time as once the baseline levels off it can be extended. On cooling the baseline, the final position should be the same as the initial (or within experimental error) or either more polymerization or a leak occurred.

Data Analysis:

- Import the data into a spreadsheet program. Columns of time, temperature (cure), position (cure), temperature (baseline), and position (baseline) should be formed, extending the baseline if necessary.
- Next, shift the cure and baselines (by constant addition or subtraction) so that the initial position data for both the cure and baseline is zero.
- Subtract the baseline from the cure data and get ΔL , or the difference in position.

To get the percent volume change from ΔL use:

$$\text{Percent Volume Change} = \left(\frac{\Delta L \pi R^2}{V} \right) \times 100\%$$

where:

R is the cylinder radius, and

V is the sample volume calculated by dividing the sample weight by the sample density.

Appendix B

Results from a Different Dilatometer

For comparative purposes, the dilatometer described in Figure 33 was used to measure polymerization of the 2.5%, 6%, 10% and 15% LPA formulations described in Table 3. From Chapter 2, the sample geometry for this dilatometric technique was an approximately 5 cm (2 in.) long, 1.25 cm (0.5 in.) diameter cylinder. Due to the heat produced during cure (approximately 450 J/gm), one cannot expect isothermal cure with this sample geometry; however, the sample temperature was measured and rough comparisons were possible with the isothermal and ramp cure trends described in Chapter 4. Errors in some of the shrinkage data were detected for some samples as the diameter of some of the samples were markedly less than the chamber dimensions implying that the sample pulled away from the chamber wall during cure. This would cause the polymerization shrinkage measured to be less than the true polymerization shrinkage. Samples most susceptible to this type of problem were ones with lower LPA concentration.

The operating procedure included preheating the sample chamber, opening the system, injecting the resin, closing the system, and measuring sample temperature and rod position. Operating conditions were 80°C with a sample pressure of 1.24 MPa (180 psi). Due to limitations of the system, a sample pressure of 0.69 MPa (100 psi, same as used in the studies described in Chapter 4) was not possible as the rod would not move to follow the polymerization shrinkage at that low of a pressure.

Figure 88 is a plot of the sample temperature measured versus time. The temperature profile here was neither ramp, isothermal, or adiabatic. Note that the height and timing of the temperature peak was somewhat dependent on the LPA concentration. With more LPA, reactive constituent concentrations decreased, and,

therefore, heat of reaction decreased. Furthermore, the filler effect of the low profile additive decreased the reactivity of the resin thereby affecting the reaction rate.

Figure 89 is a plot of the percent volume change measured. Percent volume change was calculated by first shifting the position data measured such that the position reached once temperature had risen to operating temperature (but before cure) was zero. By dividing the shifted position data by the effective sample length and multiplying by 100, percent volume change was found. The effective sample length was the measured sample length minus the calculated effective length of the thermocouple in the sample accounting for the sample volume lost to the thermocouple volume.

Figure 90 is a plot of the final shrinkage measured as a function of the LPA concentration. The minima observed with the dilatometric technique developed for this study was measured with this system as well. However, compared to the final shrinkage summary in Figure 66, the data lies somewhere between the isothermal and 8°C/minute ramp data. Furthermore, the increase in pressure had disabled the polymerization shrinkage control in the 2.5% LPA sample as shrinkage measured for that sample was on the order of pure resin without a low profile additive.

Figure 88. Comparison of measured temperature profiles using the dilatometric technique described in Figure 33.

Figure 89. Comparison of the percent volume change data obtained using the dilatometric technique described in Figure 33.

Figure 90. Plot of percent final shrinkage versus low profile additive concentration, as measured by the dilatometer described in Figure 33.

Appendix C

Dilatometry of Other Polymeric Systems

Two other polymeric systems were briefly investigated by the dilatometric technique developed for this study: an epoxy modified bismaleimide (BMI, 5250-4-RTM, BASF) and a vinyl ester system with and without low profile additive (Derakane 780 and Derakane 790).

Dilatometry of epoxy modified BMI

The only modification of the dilatometric technique required was the sample pouch preparation. The BMI material was a solid at room temperature; therefore, sample preparation had to be carried out at elevated temperatures. Sample degassing was required due to large amounts of air bubbles trapped in the solid resin; therefore, a vacuum was pulled on the sample while the sample was heated in an oven at approximately 100°C for one hour. The sample was quickly removed from the oven, and the pouch was filled before the sample cooled and hardened.

The BMI system was cured using a four stage heating profile comparable to that used in resin transfer molding of the material. Figure 91 is a plot of the temperature profile used in studying this material. From room temperature, the material was ramp heated to approximately 140°C, held at 140°C for 1 hour, ramped to 190°C, held at 190°C for 6 hours, and cooled to the initial temperature.

Figure 92 is a plot of the corresponding polymerization shrinkage measured for the system. The second expansion was due to the second heating ramp in the temperature profile. Note that polymerization shrinkage was observed for both holding temperatures, and that the polymerization shrinkage at elevated temperatures was much

higher than the final polymerization shrinkage which was based on room temperature comparison of density. This was due to the change in coefficient of thermal expansion during the cure of the material. In molding applications, the polymerization shrinkage of importance during molding would be the elevated temperature shrinkage, not the final shrinkage. A very slow ramp heating profile may be better to avoid the large initial expansion as cure would gradually occur to counteract the thermal expansion.

Low Profile Vinyl Ester Resin

A vinyl ester resin with (Derakane 790) and without (Derakane 780) a low profile additive was briefly studied with both the dilatometric technique developed in this study and the dilatometer described in Figure 33 and Appendix B. Unfortunately, the resin with a low profile additive had markedly more styrene than the resin without the LPA (46% as opposed to 33% by weight) so solid comparisons could not be made. Figure 93 is a plot comparing the two resin systems which were cured using the dilatometer developed in this study and the heating profile shown in Figure 55. Interestingly, the resin with low profile additive demonstrated a higher polymerization shrinkage than the resin without the LPA. This was due to the higher styrene content (which had a higher polymerization shrinkage) coupled with a low profile system which did not control cure shrinkage at these reactive conditions. The dilatometric unit described in Figure 33 using a similar temperature profile to Figure 88, provided exactly the opposite trend. The resin without LPA had a final shrinkage of approximately 10.9% while the resin with LPA had a final shrinkage of only 9.0%.

Figure 91. Plot of temperature profile used for BMI study.

Figure 92. Percent volume change data for BMI resin.

Figure 93. Plot of percent volume change as a function of time for a vinyl ester resin with (Derakane 790) and without (Derakane 780) LPA, cured isothermally at 80°C.